

# Dispex<sup>®</sup> CX 4340

## General

- Highly effective, low-viscosity dispersing agent for water-based coating systems
- Especially suitable for the dispersion of inorganic pigments
- Allows formulations of high-gloss/low-pigment-volume-concentration coatings in addition to standard matt formulations

## Chemical nature

Solution of a sodium salt of an acrylic polymer in water

---

## Properties

### Physical form

Hazy, viscous, colourless to pale straw

### Technical data

(not supply specification)

Dry Weight	BASF method	38.0 – 42.0 %
pH value	BASF method (25 °C, 100 % (m))	6.5 - 8.0
Viscosity, kinematic	BASF method (25 °C)	3.0 – 5.0 mm <sup>2</sup> /s
Density	Pyknometer (20 °C)	~ 1.13 g/cm <sup>3</sup>
Active content		~ 40 %
Solvent		Water

---

## Application

Dispex® CX 4340 is an ideal dispersing agent for a wide range of water-based coatings. The special copolymer backbone is designed for complete compatibility with polypropylene and hexylene glycols used in high proportions in water-based high-gloss coatings to promote wet-edge time.

The use of Dispex® CX 4340 is especially recommended when high-gloss/low-pigment-volume-concentration coatings are formulated.

Dispex® CX 4340 is effective over a pH range of 5 – 12 and up to temperatures in excess of 100 °C.

Dispex® CX 4340 is based on an organic polymer and provides improved storage stability of both pigment dispersion and formulated paint when compared with inorganic dispersing agents, e.g., polyphosphate products. There is little or no adverse reaction to high temperatures or pH changes.

## Incorporation

As opposed to adding the dispersing agent to a pigment slurry, the pigment should be added to heavily stirred water to which the dispersing agent had been added. In general, the pH of the final preparation should be in the region of 8.5 to obtain optimum dispersing efficiency.

## Recommended concentrations

Recommended dosages of Dispex® CX 4340 depend on the nature of the solids to be dispersed. In general, the dosage is between 0.2 – 1.0 %, calculated on the total formulation. In critical formulations it is possible to increase the dosage up to 2%.

---

## Storage

Although Dispex® CX 4340 is freeze-stable it should be stored at temperatures above 5 °C to allow easy handling.

### Contacts worldwide

Asia  
BASF East Asia Regional Headquarters Limited  
36/F, Two Taikoo Place,  
Taikoo Place,  
979 King's Road,  
Quarry Bay, Hong Kong  
[formulation-additives-asia@basf.com](mailto:formulation-additives-asia@basf.com)

North America  
BASF Corporation  
11501 Steele Creek Road  
Charlotte, NC 28273  
USA  
[formulation-additives-nafta@basf.com](mailto:formulation-additives-nafta@basf.com)

Europe  
BASF SE  
Formulation Additives  
67056 Ludwigshafen  
Germany  
[formulation-additives-europe@basf.com](mailto:formulation-additives-europe@basf.com)

South America  
BASF S.A  
Rochaverá - Crystal Tower  
Av. das Nações Unidas, 14.171  
Morumbi - São Paulo-SP  
Brazil  
[formulation-additives-south-america@basf.com](mailto:formulation-additives-south-america@basf.com)

### Validity

This Technical Data Sheet is valid for all versions of the Dispex® CX 4340.

### Safety

When handling this product, please comply with the advice and information given in the safety data sheet and observe protective and workplace hygiene measures adequate for handling chemicals.

### Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. The agreed contractual quality of the product results exclusively from the statements made in the product specification. It is the responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed.

® = Registered trademark

™ = Trademark of the BASF Group, unless otherwise noted

[www.basf.com/formulation-additives](http://www.basf.com/formulation-additives)