

FoamStar® ED 2521

Product description

Emulsion defoamer

FoamStar® ED 2521 is an excellent universal emulsion defoamer for all flat to semi-gloss aqueous coatings:

- Excellent foam suppression during grinding as well as application
- Retains antifoam efficiency during extended storage of paint
- Easy to incorporate without requiring strong shear forces
- No loss of gloss, no fogging

The eco-friendly polymer technology makes FoamStar® ED 2521 VOC free according to EU Directive 2002/42/EC and EPA Method 24 (USA) and best in class with an ultra-low semi-volatile organic compound content.

Chemical nature

Polymer emulsion

Properties

Physical form

White emulsion

Technical data

(not supply specification)

Solid content	DIN ISO 1625	15.0 – 18.0 %
Density	(20 °C)	~ 1.00 g/cm ³
Viscosity, dynamic	ISO 2555 (Brookfield 25 °C)	1,700 – 3,000 mPa.s

Application

FoamStar® ED 2521 is suitable for manufacturing of all kinds of water-based architectural paints. It is especially recommended for high-PVC systems based on styrene-acrylic, vinyl/VeoVa™1 and vinyl-acrylic emulsions.

Recommended concentrations

0.2 - 0.6 % on total formulation.

FoamStar® ED 2521 should be added during grinding in order to achieve perfect incorporation of the defoamer into the system.

Storage

FoamStar® ED 2521 should be stored in a cool dry place.

Contacts worldwide

Asia
BASF East Asia Regional Headquarters Limited
36/F, Two Taikoo Place,
Taikoo Place,
979 King's Road,
Quarry Bay, Hong Kong
formulation-additives-asia@basf.com

Europe
BASF SE
Formulation Additives
67056 Ludwigshafen
Germany
formulation-additives-europe@basf.com

North America BASF Corporation 11501 Steele Creek Road Charlotte, NC 28273 USA formulation-additives-nafta@basf.com

South America BASF S.A Rochaverá - Crystal Tower Av. das Naçoes Unidas, 14.171 Morumbi - São Paulo-SP Brazil

formulation-additives-south-america@basf.com

Validity

This Technical Data Sheet is valid for all versions of the FoamStar® ED 2521.

Safety

When handling this product, please comply with the advice and information given in the safety data sheet and observe protective and workplace hygiene measures adequate for handling chemicals.

Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. The agreed contractual quality of the product results exclusively from the statements made in the product specification. It is the responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed.

® = Registered trademark

www.basf.com\formulation-additives