

Acronal® 4000

Chemical Nature

APEO Free Aqueous styrene-acrylate copolymer dispersion for modifying hydraulic binders

Properties

Typical Properties

Solids content	%	~ 57.0
pH		~ 8.0
Apparent viscosity at 23 °C (Brookfield RVT, Spindle #3, at 100 rpm)	mPa s	~ 200 – 750

Other properties of the dispersion

Viscosity at 23 °C (shear rate, 250 s ⁻¹)	mPa s	140 – 200
Density	lbs/gal g/cm ³	ca 8.58 ca. 1.03
Average particle size	µm	ca. 0.2
Film forming temperature	°F °C	<33 min. <1 min.
Dispersion type		anionic
Plasticizer content		free from plasticizer
Sensitivity to frost	°F °C	below 32 below 0

Properties of the film

Density	g/cm ³	ca. 1.08
Glass transition temperature T _g (DSC)	°C	ca. -6
Water absorption (After 24 hour immersion in water)	%	ca. 5 -10
Mechanical strength*		
Tensile strength	psi	130
Elongation at break	%	>1200
Appearance		clear, transparent
Surface		tacky
Resistance to aging		good

* The above values should not be taken as specification.

Compatible with

Polymer dispersions

Thickeners

Plasticizers

Antifoams

Pigments and fillers

Acronal 296 D and with most other nonionic and anionic dispersions

Rheovis® AS 1420, Rheovis® AS 1125, and cellulose ether

Plastilit® 3060, Palatino® types, Palamol® types, and chlorinated paraffin waxes

Lumiten® E-L

Silica flour, fine-grained sand, microdolomite, amorphous calcium carbonates. The compatibility with pigments is improved by the addition of sodium polyphosphate and Pigment Disperser N. The formulation can be tinted with mineral colors, Pigmosol® or Luconyl® pigments.

Hydraulic binders

Acronal S 4000 is compatible with hydraulic binders.

Application

Features

Acronal 4000 is used mainly for producing flexible mortars, adhesives and coatings. It blends readily with hydraulic binders and can be used to produce ceramic tile adhesives as well as flexible, water-resistant two-component mortars.

A particular application of Acronal 4000 is the production of crack-filling systems and flexible cementitious coatings for flat roofs and walls. It can also be used in combination with asphalt emulsions to produce waterproofing membranes.

Processing

It is advisable to add small amounts of a suitable preservative to products containing Acronal 4000 in order to ensure adequate shelf life. The suitability of the preservative must be tested and monitored.

A sample two-component, cementitious, flexible waterproofing mixture based on Acronal 4000 is highlighted as follows (guiding formulation):

Dry Premix	% by Weight	% by Volume
F-110 ¹ - Silica sand	30.0	22.5
F-95 ¹ - Silica sand	27.3	20.4
Portland cement ² (Type I/II)	19.6	12.3
Dispex® AA 4935³	0.2	0.7
Lumiten® E-P 3108³ (Antifoam)	1.6	3.1
Latex mixture	20.66	Polymer 16.0
Acronal 4000³	0.2	0.5
Antifoam	0.5	Total 24.5 +
Water = Adjust to desired flow characteristics		

Formulation Parameters

Polymer / cement ratio	0.60
Water / cement ratio	0.48 *
Sand / cement ratio	2.92

Suppliers:

¹ U. S. Silica, Ottawa, IL

² Lehigh Portland Cement Company, Allentown, PA

³ BASF Corporation, Charlotte, NC

Flexible cementitious waterproofing slurries contain sand, cement, water and a high proportion, 11 - 18% by volume (16% shown above), of a polymer dispersed in the water. To apply, firstly, blend the dry premix (1) and latex mixtures together. Slurries are applied to wetted concrete in two to four coats with a total thickness of 1/8 inch (2 - 4 mm or 80 - 150 mils). The polymer particles coalesce to form a compact film. The coating remains somewhat flexible and because of its thickness, it seals most pores in the surface of the concrete. Access to moisture and water through the diurnal cycle allows hydration of the cement to continue with the result that the coat becomes somewhat denser and firmer yet still at least two magnitudes more flexible than concrete without the polymer modification. The coating is permeable to water vapor but almost impermeable to water itself. Chloride ion penetration and carbonation of concrete can also be considerably reduced or even entirely prevented under flexible cementitious membranes. The suitability of formulations for field use must be thoroughly evaluated and optimized prior to launch.

* These typical values should not be interpreted as specifications.

Safety

General

The usual safety precautions when handling chemicals must be observed. These include the measures described in Federal, State and Local health and safety regulations, thorough ventilation of the workplace, good skin care and wearing of protective goggles.

Safety Data Sheet

All safety information is provided in the Safety Data Sheet for Acronal 4000.

Storage

Please refer to the "Handling and Storage of Polymer Dispersions" brochure.

Important

WHILE THE DESCRIPTIONS, DESIGNS, DATA AND INFORMATION CONTAINED HEREIN ARE PRESENTED IN GOOD FAITH AND BELIEVED TO BE ACCURATE, THEY ARE PROVIDED FOR GUIDANCE ONLY. BECAUSE MANY FACTORS MAY AFFECT PROCESSING OR APPLICATION/USE, BASF RECOMMENDS THAT THE READER MAKE TESTS TO DETERMINE THE SUITABILITY OF A PRODUCT FOR A PARTICULAR PURPOSE PRIOR TO USE. NO WARRANTIES OF ANY KIND, EITHER EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESCRIPTIONS, DESIGNS, DATA OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, INFORMATION, DATA OR DESIGNS PROVIDED BE CONSIDERED A PART OF BASF'S TERMS AND CONDITIONS OF SALE. FURTHER, THE DESCRIPTIONS, DESIGNS, DATA, AND INFORMATION FURNISHED BY BASF HEREUNDER ARE GIVEN GRATIS AND BASF ASSUMES NO OBLIGATION OR LIABILITY FOR THE DESCRIPTIONS, DESIGNS, DATA OR INFORMATION GIVEN OR RESULTS OBTAINED, ALL SUCH BEING GIVEN AND ACCEPTED AT THE READER'S RISK.

Acronal is a registered trademark of BASF Group.

© BASF Corporation, 2023



BASF Corporation is fully committed to the Responsible Care® initiative in the USA, Canada, and Mexico.

For more information on Responsible Care® go to:

U.S.: www.basf.us/responsiblecare_usa

Canada: www.basf.us/responsiblecare_canada

México: www.basf.us/responsiblecare_mexico

BASF Corporation

Dispersions and Resins

11501 Steele Creek Road

Charlotte, North Carolina 28273

Phone: (800) 251 – 0612

Email: CustCare-Charlotte@basf.com

www.basf.us/dpsolutions