



Joncryl® 2660

Product Description	Joncryl 2660 is a Rheology Controlled (RC) acrylic emulsion for high gloss, transparent polyethylene film and foil ink applications.
Key Features & Benefits	- High gloss - Excellent transparency
Chemical Composition	RC acrylic emulsion

Properties		
Typical Properties	Appearance	semi-translucent emulsion
	Non-volatile	% 49.0
	pH at 25°C	8.6
	Viscosity at 25°C	cps 1,100
	Acid number (NV)	45
	Density at 25°C	g/cm³ 1.04
	MFFT	°C < 5
	Tg	°C 13
	Freeze-thaw stable	No
	Total VOC	% wt 0.9

These typical values should not be interpreted as specifications.

Application

Joncryl 2660 is a film forming; RC acrylic emulsion that exhibits superior gloss, transparency, and printability on high density polyethylene (HDPE) and aluminum foil substrates. In addition, this emulsion provides excellent rub, water, and grease resistance, low foaming, excellent press transfer, high solids, near Newtonian viscosity, and good press resolubility.

Joncryl 2660 is recommended for applications such as:

- Printing inks for flexographic or gravure applications
- Film/foil applications

Alcohol Compatibility

Joncryl® 2660	95.0	95.0	95.0
Water	5.0	-	-
Isopropyl alcohol	-	5.0	-
Normal propyl alcohol	-	-	5.0
TOTAL	100.0	100.0	100.0
Physical Characteristics			
pH	8.2	8.2	8.2
Initial viscosity, cps*	45	325	400
24-hour viscosity, cps*	45	340	400
One-week viscosity, cps*	50	385	425

*Brookfield #2 LVF spindle, 30 rpm, 25°C

Safety

General

The usual safety precautions when handling chemicals must be observed. These include the measures described in Federal, State and Local health and safety regulations, thorough ventilation of the workplace, good skin care and wearing of protective goggles.

Safety Data Sheet

All safety information is provided in the Safety Data Sheet for Joncryl 2660.

Storage

Please refer to the "Handling and Storage of Polymer Dispersions" brochure.

Important

The descriptions, designs, and data contained herein are presented for your guidance only. Because there are many factors under your control which may affect processing or application/use it is necessary for you to make appropriate tests to determine whether the product is suitable for your particular purpose prior to use. **NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESIGNS, OR DATA MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, DATA OR DESIGNS PROVIDED BE PRESUMED TO BE A PART OF OUR TERMS AND CONDITIONS OF SALE.** Further, you expressly understand and agree that the descriptions, designs, and data furnished by BASF hereunder are given gratis and BASF assumes no obligation or liability for same or results obtained from use thereof, all such being given to you and accepted by you at your risk.

Joncryl® is a registered trademark of BASF Group.

© BASF Corporation, 2024



BASF Corporation is fully committed to the Responsible Care® initiative in the USA, Canada, and Mexico.

For more information on Responsible Care® go to:

U.S.: www.basf.us/responsiblecare_usa

Canada: www.basf.us/responsiblecare_canada

México: www.basf.us/responsiblecare_mexico

BASF Corporation

Dispersions and Resins

11501 Steele Creek Road

Charlotte, North Carolina 28273

Phone: (800) 251 – 0612

Email: CustCare-Charlotte@basf.com

Email: edtech_info@basf.com

www.basf.us/dpsolutions