

Irganox® 1076

Chemical Nature

Irganox 1076 is a highly efficient, non-discoloring, sterically hindered phenolic, primary antioxidant stabilizer that protects organic substrates against thermo-oxidative degradation.

Key Features & Benefits

- Good compatibility with most substrates
- High resistance to extraction
- Low volatility
- Odorless
- Stable to light and excellent color retention
- Manufactured using a tin-free process

Chemical Composition

Octadecyl-[3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate]

Properties

Typical Properties

| Appearance | | white, fine granules |
|--------------------------|-------|----------------------|
| CAS number | | 2082-79-3 |
| Molecular weight | g/mol | 531 |
| Melting range | °C | 50 – 55 |
| Flash point | °C | 273 |
| Vapor pressure at 20°C | Pa | 2.5 E-7 |
| Specific gravity at 20°C | g/ml | 1.02 |
| Density (bulk) | g/l | 360 – 400 |

Solubility at 20°C (g/100 g solution)

| Acetone | 19 |
|---------------|--------|
| Benzene | 57 |
| Chloroform | 57 |
| Cyclohexane | 40 |
| Ethanol | 1.5 |
| Ethyl acetate | 38 |
| n-Hexane | 32 |
| Methanol | 0.6 |
| Toluene | 50 |
| Water | < 0.01 |

Volatility TGA, air at 20°C/min)

Temperature at 1% weight loss °C 230 Temperature at 10% weight loss °C 288

These typical values should not be interpreted as specifications.

October 2022 Rev 4 page 1 of 3

Applications

Irganox 1076 is used in polyolefins such as polyethylene, polypropylene, polybutene, as well as, in other polymers, such as engineering plastics, styrene homo- and co-polymers, polyurethanes, elastomers, adhesives, and other organic substrates. In addition, Irganox 1076 can be used to thermally stabilize polymers used in construction applications.

It can be used in combination with other additives such as co-stabilizers (thioethers, phosphites, phosphonites), light stabilizers, and other functional stabilizers.

Irganox 1076 is recommended for applications such as:

- · Hot-melt adhesives
- · Solvent-based coating applications
- Tackifier resins
- · Sealant systems
- · Wood flooring adhesives
- · Roof coatings

Recommended Concentrations

The amount of Irganox 1076 required for optimum performance should be determined in laboratory trials covering a concentration range. Concentrations up to several percent may be used depending on the substrate, processing conditions, requirements of the end application, and long term thermal stability requirements.

0.05 - 0.2% of Irganox 1076 provides long term thermal stability to the polymer.

| <u>Application</u> <u>C</u> | <u>oncentration</u> |
|----------------------------------|---------------------|
| Polyolefins 0. | 1 – 0.4% |
| Styrene homo- and co-polymers 0. | 1 – 0.3% |
| Hot melt adhesives 0. | 2 – 1% |
| Synthetic tackifiers resins 0. | 1 – 0.5% |
| Solvent-based coatings 0. | 2 – 1.0% |

Safety

General

The usual safety precautions when handling chemicals must be observed. These include the measure described in Federal, State and Local health and safety regulations, thorough ventilation of the workplace, good skin care, and wearing of protective goggles.

Safety Data Sheet

All safety information is provided in the Safety Data Sheet for Irganox 1076.

Storage

Please refer to the "Handling and Storage of Polymer Dispersions" brochure.

October 2022 Rev 4 page 2 of 3

Important

WHILE THE DESCRIPTIONS, DESIGNS, DATA AND INFORMATION CONTAINED HEREIN ARE PRESENTED IN GOOD FAITH AND BELIEVED TO BE ACCURATE, THEY ARE PROVIDED FOR GUIDANCE ONLY. BECAUSE MANY FACTORS MAY AFFECT PROCESSING OR APPLICATION/USE, BASF RECOMMENDS THAT THE READER MAKE TESTS TO DETERMINE THE SUITABILITY OF A PRODUCT FOR A PARTICULAR PURPOSE PRIOR TO USE. NO WARRANTIES OF ANY KIND, EITHER EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESCRIPTIONS, DESIGNS, DATA OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, INFORMATION, DATA OR DESIGNS PROVIDED BE CONSIDERED A PART OF BASF'S TERMS AND CONDITIONS OF SALE. FURTHER, THE DESCRIPTIONS, DESIGNS, DATA, AND INFORMATION FURNISHED BY BASF HEREUNDER ARE GIVEN GRATIS AND BASF ASSUMES NO OBLIGATION OR LIABILITY FOR THE DESCRIPTIONS, DESIGNS, DATA OR INFORMATION GIVEN OR RESULTS OBTAINED, ALL SUCH BEING GIVEN AND ACCEPTED AT THE READER'S RISK.

Irganox is a registered trademark of BASF Group.

© BASF Corporation, 2022



BASF Corporation is fully committed to the Responsible Care® initiative in the USA, Canada, and Mexico.
For more information on Responsible Care® go to:
U.S.: www.basf.us/responsiblecare_usa
Canada: www.basf.us/responsiblecare_canada
México: www.basf.us/responsiblecare_mexico

BASF Corporation

Dispersions and Resins
11501 Steele Creek Road
Charlotte, North Carolina 28273
Phone: (800) 251 – 0612
Email: CustCare-Charlotte@basf.com
www.basf.us/dpsolutions

October 2022 Rev 4 page 3 of 3