Technical Information





general

slip and leveling agent for aqueous coating systems

- improves leveling
- prevents cratering and orange peel
- · supports substrate wetting
- acts as a defoamer
- improves adhesion

chemical nature

fluorocarbon-modified polyacrylate

Properties

physical form clear, colorless liquid

storage Efka® FL 3772 should be stored in a cool dry place.

typical properties (no supply specification)

active ingredients	~ 60%
solvent	secondary butanol
density at 20 °C (68 °F)	~ 0.95 g/cm ³
acid value	~ 72 mg KOH/g
flash point	24 °C (75°F)
color	≤1

Application

Efka® FL 3772 can be used in water-based air-drying and baking

enamels as well as in solvent-based industrial paints. Efka® FL 3772 needs to be neutralized with ammonia or triethanolamine. Complete water solubility is achieved with 9%

triethanolamine or 12% of a 25% ammonia solution.

recommended concentrations 0.5–2.0% on total formulation

Efka® FL 3772 should be added at the end of the batch preparation.

December 2016 page 2 of 2 Efka® FL 3772

Contacts worldwide

Asia

BASF East Asia Regional Headquarters Ltd

45/F, Jardine House No. 1 Connaught Place Central Hong Kong

China

formulation-additives-asia@basf.com

Europe BASF SE

Formulation Additives 67056 Ludwigshafen

Germany

formulation-additives-europe@basf.com

North America BASF Corporation 11501 Steele Creek Road Charlotte, NC 28273

USA

formulation-additives-nafta@basf.com

South America BASF S.A

Rochaverá - Crystal Tower Av. das Naçoes Unidas, 14.171 Morumbi - São Paulo-SP

Brazil

formulation-additives-south-america@basf.com

Validity

This Technical Data Sheet is valid for all versions of the Efka® FL 3772.

Safety

When handling these products, please comply with the advice and information given in the safety data sheet and observe protective and workplace hygiene measures adequate for handling chemicals.

Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. The agreed contractual quality of the product results exclusively from the statements made in the product specification. It is the responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed.

^{® =} registered trademark, TM = trademark of BASF Group, unless otherwise noted