

0.1% Pd/AS R5279

R5279 is used for DeOxo (O₂ removal e.g. with H₂) and CatOx (catalytic oxidation of hydrocarbon)

General

R5279 is a catalyst in the form of spheres with a nominal diameter of 4 – 8 mm and with Palladium as active component. While showing high activity, the larger sphere shows low pressure drop. The material was formerly referred to as “DEDUX 0.1”.

Product Application


R5279 is used for the conversion of hydrogen in the presence of oxygen to form water (DeOxo reaction) according to the following chemical formula



This reaction can be applied in the production of pure hydrogen or in the production of inert gases like N₂ or He, when adding H₂ to remove oxygen. Alternative materials for this application can be

0.3% Pd/AS R4578 or 0.5% Pd/AS R4577

Alternatively, the material can also be used for the conversion of CO or hydrocarbons with oxygen according to the following chemical formulae.



Due to the high exotherm of these reactions, proper instrumentation and safety measures always need to be put in place to assure full control of the reaction.

Typical reaction temperatures are in the range of 50 – 100°C / 120 – 210°F for reaction (1). For other reactions higher temperatures will be required. The

maximum recommended temperature is 500°C / 930°F.

Special Operations

R5279 might gain maximum activity via a short activation procedure when used in reduced state. Before unloading, the material should be oxidized.

Poisons

As every Pd containing catalyst R5279 is sensitive against Sulfur and its components. Heavy metals like AsH₃ can also have a detrimental effect on its performance. CO will have an impact on activity but might be compensated e.g. via higher temperature.

Storage

R5279 does not deteriorate or constitute any hazard when stored in sealed containers. The containers should not be allowed to become damp or wet and should not be stored in contact with organic or easily oxidizing vapors.

Target Properties

Chemical Composition (dry basis)	0.1 % wt./wt. Pd on high surface Alumina
--	---

Typical Physical Properties

Packed Bulk Density, g/ml	0.75
Total Surface Area (BET), m ² /g	300

Packaging

- 210 l steel drum with up to 120 kg net

Point of Shipment

- Rome, Italy

About Us

BASF is a leading global manufacturer of catalysts for the chemical industry, with solutions across the chemical value chain. The business comprises chemical catalysts, adsorbents and custom catalysts. Priority is given to developing new and improved products that enable the chemical industry transformation to net-zero emissions.

BASF's chemical catalysts and adsorbents business is part of the company's Performance Chemicals division. The division's portfolio also includes refinery catalysts, fuel and lubricant solutions, as well as oilfield chemicals and mining solutions. Customers from a variety of industries including Chemicals, Plastics, Consumer Goods, Energy & Resources and Automotive & Transportation benefit from our innovative solutions.

BASF - We create chemistry



chemical-catalysts-and-adsorbents.basf.com/

Americas

BASF Corporation
Phone: +1-732-205-5000
Email: catalysts-america@basf.com

Asia Pacific

BASF (China) Company Limited
Phone: +86-21-2039 2549
Email: catalysts-asia@basf.com

Europe, Middle East, Africa

BASF Services GmbH
Phone: +49-30-2005 5000
Email: catalysts-europe@basf.com

Although all statements and information in this publication are believed to be accurate and reliable, they are presented gratis and for guidance only, and risks and liability for results obtained by use of the products or application of the suggestions described are assumed by the user. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH. Statements or suggestions concerning possible use of the products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that toxicity data and safety measures are indicated or that other measures may not be required. © 2015 BASF

BASF-10636 04/25