

Acronal® 4250

Chemical Nature

Aqueous acrylate copolymer dispersion with room temperature crosslinking for use in flexible roof coatings

Properties

Typical Properties

Solids content	%	~ 55.0
pH		~ 8.0
Viscosity at 73 °F (Brookfield RV viscometer, Spindle #4, at 100 rpm)	mPa s	~ 100 – 500

Other properties of the dispersion

Density	lbs/gal g/cm ³	ca. 8.63 ca. 1.04
Film-forming temperature	°F °C	ca. >32 ca. >0
Dispersion type		Anionic
Plasticizer content		Free from plasticizer
Sensitivity to freezing	°F °C	below 32 below 0

Properties of the film

Density	g/cm ³	ca. 1.06
Appearance	clear, transparent	
Surface		tacky

* These typical values should not be interpreted as specifications.

Application

Fields of application

Acronal 4250 may be used for the production of flexible coating compounds. Such coatings may be used for the sealing of concrete roofs and the protection of polyurethane insulation foam, rolled roofing felts or asphalt roof systems against the effects of weathering. For areas where permanent water loading is anticipated or the slope is <2°, Acronal 4250 is not recommended.

Processing

Acronal 4250 is a pure acrylic polymer dispersion designed for high flexibility at low temperatures. The glass transition temperature of minus 28 °C (DSC midpoint) makes it ideally suitable for designing mixtures that need to meet ASTM D 6083 - 05 requirements.

Acronal 4250 was developed to give excellent adhesion to polyurethane roofing foam and many other substrates. In addition, it contains internal crosslinking agents that crosslink the polymer film after the water has evaporated. This crosslinking occurs both on the surface and through the coating to give good elastic film properties with only a slightly tacky surface. This aids in the resistance of the film to pick up dirt and retain good reflectivity.

Acronal 4250 does not require Zinc Oxide for additional crosslinking of the polymer. However if one chooses to use Zinc Oxide for this purpose or for fungal protection, precaution should be taken to stabilize the Acronal 4250 in the presence of the zinc oxide.

Acronal 4250 is a mechanically stable anionic dispersion that can be pigmented and formulated into flexible coatings as shown in Table 1. This includes mixtures prepared with the dispersion in the grind (#1 through 3) or as an addition to pigment dispersion (#4).

Table 1

Formulation Number:	1.	2.	3.	4.
Raw Materials -	Weight %			
Water	6.88	6.81	6.81	14.79
Propylene glycol	2.23	2.24	2.24	2.08
30% Pigment Disperser® NL ¹	0.45	0.45	0.45	0.42
Acronal® 4250 ¹	28.45	28.53	28.52	0.00
BYK 035 ²	0.45	0.45	0.45	0.45
Iconol NP-40 ³	0.00	0.00	0.00	0.13
Natrosol 250 MXR ⁴	0.00	0.00	0.00	0.06
Kronos 2101 ⁵	11.17	11.20	7.83	10.18
Kadox 915 ⁶ (Zinc oxide)	0.00	0.00	3.41	0.00
Duramite ⁷	26.36	21.92	21.91	24.31
Atomite ⁷	1.34	5.94	5.94	1.25
Omyacarb UFT ⁸	0.00	7.94	7.93	0.00
Microtalc MP 10-52 ⁹	8.27	0.00	0.00	7.48
Proxel GXL ¹⁰	0.22	0.22	0.22	0.21
Acronal® 4250	12.78	12.81	12.81	37.78
Natrosol 250 MXR	0.34	0.34	0.34	0.34
Ammonia	0.23	0.23	0.23	0.23
BYK 035	0.91	0.92	0.92	0.91
Totals	100.0	100.0	100.0	100.0
~ Weight (% solids)	72	72	72	66

Mix ingredients in the above order until smooth.

Mixture Properties:	PVC (%)	~ 42
	Viscosity (Krebs)	~ 105
	Volume % solids	~ 59

Suppliers for ingredients shown in Table 1.

- ¹ BASF Corporation, Charlotte, NC
- ² BYK-Chemie USA, Wallingford, CT
- ³ BASF Corporation, Performance Chemicals, Mount Olive, NJ
- ⁴ Aqualon, A Div. of Hercules Inc., Wilmington, DE
- ⁵ Kronos, Inc., Houston, TX
- ⁶ Zinc Corporation of America, Monaca, PA
- ⁷ Imerys; or Distributor Fitz Chem Corporation, Itasca, IL
- ⁸ Omya, Inc., Alpharetta, GA
- ⁹ Barretts Minerals, Easton, PA
- ¹⁰ Zeneca Biocides, Wilmington, DE

Safety

General

The usual safety precautions when handling chemicals must be observed. These include the measures described in Federal, State and Local health and safety regulations, thorough ventilation of the workplace, good skin care and wearing of protective goggles.

Safety Data Sheet

All safety information is provided in the Safety Data Sheet for Acronal 4250.

Storage

Please refer to the “Handling and Storage of Polymer Dispersions brochure”.

Important

WHILE THE DESCRIPTIONS, DESIGNS, DATA AND INFORMATION CONTAINED HEREIN ARE PRESENTED IN GOOD FAITH AND BELIEVED TO BE ACCURATE, THEY ARE PROVIDED FOR GUIDANCE ONLY. BECAUSE MANY FACTORS MAY AFFECT PROCESSING OR APPLICATION/USE, BASF RECOMMENDS THAT THE READER MAKE TESTS TO DETERMINE THE SUITABILITY OF A PRODUCT FOR A PARTICULAR PURPOSE PRIOR TO USE. NO WARRANTIES OF ANY KIND, EITHER EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESCRIPTIONS, DESIGNS, DATA OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, INFORMATION, DATA OR DESIGNS PROVIDED BE CONSIDERED A PART OF BASF'S TERMS AND CONDITIONS OF SALE. FURTHER, THE DESCRIPTIONS, DESIGNS, DATA, AND INFORMATION FURNISHED BY BASF HEREUNDER ARE GIVEN GRATIS AND BASF ASSUMES NO OBLIGATION OR LIABILITY FOR THE DESCRIPTIONS, DESIGNS, DATA OR INFORMATION GIVEN OR RESULTS OBTAINED, ALL SUCH BEING GIVEN AND ACCEPTED AT THE READER'S RISK.

Acronal is a registered trademark of BASF Group.

© BASF Corporation, 2025



BASF Corporation is fully committed to the Responsible Care® initiative in the USA, Canada, and Mexico.

For more information on Responsible Care® go to:

U.S.: www.basf.us/responsiblecare_usa

Canada: www.basf.us/responsiblecare_canada

México: www.basf.us/responsiblecare_mexico

BASF Corporation

Dispersions and Resins

11501 Steele Creek Road

Charlotte, North Carolina 28273

Phone: (800) 251 – 0612

Email: CustCare-Charlotte@basf.com

www.basf.us/dpsolutions