

Acronal[®] TC 1015 na

Product Description	Acronal TC 1015 na is a self-condensing emulsion under baking conditions for formaldehyde free systems.
Key Features & Benefits	<ul style="list-style-type: none">- Formaldehyde free- Adhesion to metals and glass- Outstanding chemical resistance- Low VOC enabler- Overcoatability
Chemical Composition	Acid and hydroxyl functional emulsion polymer

Properties

Typical Properties

Appearance		white emulsion
Solids	% by wt	49-51
pH		~ 3.5
Viscosity at 23°C	cps	~ 500
Density	g/ml	1.06
Acid value (calculated on solids)	mg KOH/g	300
Hydroxyl value (calculated on solids)	mg KOH/g	120
MFFT	°C	< 0
Freeze-thaw stable		No

These typical values should not be interpreted as specifications.

Applications

Acronal TC 1015 na is a self-condensing emulsion for formaldehyde-free stoving coatings with high chemical resistance and strong adhesion properties to metal and glass. Baking of the system is required for performance.

Coatings formulated with Acronal TC 1015 na are hard and offer scratch and chemical resistance.

Acronal TC 1015 na is recommended for applications such as:

- General industrial topcoats for chemical resistance on metal and glass
- Rigid packaging coatings

Formulation Guidelines

Since Acronal TC 1015 na is a shear-stable product, pigments can be dispersed into it. Dispersing agents are recommended in most formulations.

Although the film formation temperature is very low for Acronal TC 1015 na, cosolvent for maximizing gloss and further supporting film formation during baking is recommended.

Acronal TC 1015 na is a low pH emulsion, therefore use of low pH stable additives are required. This includes use of surfactants, dispersants, thickeners, defoamers and performance additives (such as antioxidants or light stabilizers). To avoid disruption of the curing mechanism, a pH of <5 should be adhered to and avoidance of highly basic additives and fillers should be avoided.

Recommendations for an antioxidant include Irganox® 1010-DW and a light stabilizer package includes a combination of Tinuvin® 400-DW ECO and Tinuvin 123-DW ECO.

For modification of properties of finished films, Acronal TC 1015 na may be combined with other reactive resins including epoxies, melamine-formaldehyde resins, urea-formaldehyde, or isocyanates to enable cure at lower temperatures. Testing must be completed by formulators to ensure adequate performance.

Application

For maximal performance, a recommended baking schedule of at least 160°C is required. Higher temperatures can influence cure speed and response. Temperatures up to 300°C are suitable for fast curing (1 minute or less).

Safety

General

The usual safety precautions when handling chemicals must be observed. These include the measures described in Federal, State and Local health and safety regulations, thorough ventilation of the workplace, good skin care and wearing of protective goggles.

Safety Data Sheet

All safety information is provided in the Safety Data Sheet for Acronal TC 1015 na.

Storage

Please refer to the "Handling and Storage of polymer dispersions" brochure.

Important

The descriptions, designs, and data contained herein are presented for your guidance only. Because there are many factors under your control which may affect processing or application/use it is necessary for you to make appropriate tests to determine whether the product is suitable for your particular purpose prior to use. **NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESIGNS, OR DATA MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, DATA OR DESIGNS PROVIDED BE PRESUMED TO BE A PART OF OUR TERMS AND CONDITIONS OF SALE.** Further, you expressly understand and agree that the descriptions, designs, and data furnished by BASF hereunder are given gratis and BASF assumes no obligation or liability for same or results obtained from use thereof, all such being given to you and accepted by you at your risk.

Acronal, Irganox, Tinuvin are registered trademarks of BASF Group.

© BASF Corporation, 2025



BASF Corporation is fully committed to the Responsible Care®

Initiative in the USA, Canada, and Mexico.

For more information on Responsible Care® go to:

U.S.: www.basf.us/responsiblecare_usa

Canada: www.basf.us/responsiblecare_canada

México: www.basf.us/responsiblecare_mexico

BASF Corporation

Dispersions and Resins

11501 Steele Creek Road

Charlotte, North Carolina 28273

Phone: (800) 251 – 0612

Email: CustCare-Charlotte@basf.com

Email: edtech_info@basf.com

www.basf.us/dpsolutions