

Acronal® NX 4846 X

Polymer dispersion used to bond nonwoven fabrics

Chemical nature

Aqueous dispersion of a heat-crosslinking copolymer of acrylic esters and styrene, manufactured by a process incorporating acrylonitrile.

Properties

Typical Properties Solids content % ~ 49.0 ~ 7.0 pH value

Viscosity at 23 °C <1,000 cps

(Brookfield RV, Spindle #2, at 20 rpm)

Further properties of

Properties of the film

the dispersion Freeze/thaw stability Dispersion type

> Appearance clear

g/cm3

approx. 1.0

not stable

anionic

Surface tack-free

Crosslinking The films that Acronal NX 4846 X forms by the evaporation of water are already partially crosslinked on drying. The degree of crosslinking can be increased by heating to a temperature of 130 – 170 °C.

Resistance to solvents The films formed by Acronal NX 4846 X are insoluble in water and most organic solvents once they

have been completely crosslinked.

Compatible with Acronal NX 4846 X is compatible with other substances commonly used in nonwovens and

saturation applications.

Applications

Features Acronal NX 4846 X is a sturdy, resilient binder for a variety of applications.

Acronal NX 4846 X provides excellent thermal dimensional stability at elevated temperatures.

Acronal NX 4846 X has good strength in the presence of oil or water.

Processing The pH value of compounding formulations should be in the neutral-to-alkaline range before

Acronal NX 4846 X is added.

^{*} These values should not be taken as specification

Safety

General

The usual safety precautions when handling chemicals must be observed. These include the measures described in Federal, State and Local health and safety regulations, thorough ventilation of the workplace, good skin care and wearing of protective goggles.

Safety Data Sheet

All safety information is provided in the Safety Data Sheet for Acronal NX 4846.

Storage

Please refer to the "Handling and Storage of Polymer Dispersions" brochure.

Important

WHILE THE DESCRIPTIONS, DESIGNS, DATA AND INFORMATION CONTAINED HEREIN ARE PRESENTED IN GOOD FAITH AND BELIEVED TO BE ACCURATE, THEY ARE PROVIDED FOR GUIDANCE ONLY. BECAUSE MANY FACTORS MAY AFFECT PROCESSING OR APPLICATION/USE, BASF RECOMMENDS THAT THE READER MAKE TESTS TO DETERMINE THE SUITABILITY OF A PRODUCT FOR A PARTICULAR PURPOSE PRIOR TO USE. NO WARRANTIES OF ANY KIND, EITHER EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESCRIPTIONS, DESIGNS, DATA OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, INFORMATION, DATA OR DESIGNS PROVIDED BE CONSIDERED A PART OF BASF'S TERMS AND CONDITIONS OF SALE. FURTHER, THE DESCRIPTIONS, DESIGNS, DATA, AND INFORMATION FURNISHED BY BASF HEREUNDER ARE GIVEN GRATIS AND BASF ASSUMES NO OBLIGATION OR LIABILITY FOR THE DESCRIPTIONS, DESIGNS, DATA OR INFORMATION GIVEN OR RESULTS OBTAINED, ALL SUCH BEING GIVEN AND ACCEPTED AT THE READER'S RISK.

Acronal is a registered trademark of BASF Group.

© BASF Corporation, 2025



BASF Corporation is fully committed to the Responsible Care® initiative in the USA, Canada, and Mexico.
For more information on Responsible Care® go to:
U.S.: www.basf.us/responsiblecare_usa
Canada: www.basf.us/responsiblecare_canada
México: www.basf.us/responsiblecare_mexico

BASF Corporation

Dispersions and Resins 11501 Steele Creek Road Charlotte, North Carolina 28273 Phone: (800) 251 – 0612 Email: CustCare-Charlotte@basf.com www.basf.us/dpsolutions