

# Joncryl® HPD 71

<b>Product Description</b>	Joncryl HPD 71 is a cost-effective, high molecular weight resin solution for pigment dispersion applications.
<b>Key Features &amp; Benefits</b>	<ul style="list-style-type: none"><li>- <b>High color development</b></li><li>- <b>Heat resistant</b></li><li>- <b>Economical</b></li></ul>
<b>Chemical Composition</b>	Styrene acrylic resin solution

## Properties

<b>Typical Properties</b>	Appearance		clear liquid
	Non-volatile	%	27.5
	pH at 25°C		8.5
	Viscosity at 25°C	cps	4,000
	Molecular weight (Mw)		17,250
	Acid number (NV)		214
	Density at 25°C	g/cm <sup>3</sup>	1.05
	Tg	°C	128
	Freeze-thaw stable		Yes
	Total VOC	% wt	0.2

\* These typical values should not be interpreted as specifications.

## Application

Joncryl HPD 71 is a ~27.5% solids solution of Joncryl HPD 671, a cost-effective, high molecular weight acrylic resin designed for high quality pigment dispersions with very good viscosity stability.

Joncryl HPD 71 provides superior wetting properties for the formulation of stable high solids, low viscosity pigment dispersions.

Joncryl HPD 71 is recommended for applications such as:

- Pigment dispersions

## Safety

### General

The usual safety precautions when handling chemicals must be observed. These include the measures described in Federal, State and Local health and safety regulations, thorough ventilation of the workplace, good skin care and wearing of protective goggles.

### Safety Data Sheet

All safety information is provided in the Safety Data Sheet for Joncryl HPD 71.

## Storage

Please refer to the "Handling and Storage of Polymer Dispersions" brochure.

## Important

WHILE THE DESCRIPTIONS, DESIGNS, DATA AND INFORMATION CONTAINED HEREIN ARE PRESENTED IN GOOD FAITH AND BELIEVED TO BE ACCURATE, THEY ARE PROVIDED FOR GUIDANCE ONLY. BECAUSE MANY FACTORS MAY AFFECT PROCESSING OR APPLICATION/USE, BASF RECOMMENDS THAT THE READER MAKE TESTS TO DETERMINE THE SUITABILITY OF A PRODUCT FOR A PARTICULAR PURPOSE PRIOR TO USE. NO WARRANTIES OF ANY KIND, EITHER EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESCRIPTIONS, DESIGNS, DATA OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, INFORMATION, DATA OR DESIGNS PROVIDED BE CONSIDERED A PART OF BASF'S TERMS AND CONDITIONS OF SALE. FURTHER, THE DESCRIPTIONS, DESIGNS, DATA, AND INFORMATION FURNISHED BY BASF HEREUNDER ARE GIVEN GRATIS AND BASF ASSUMES NO OBLIGATION OR LIABILITY FOR THE DESCRIPTIONS, DESIGNS, DATA OR INFORMATION GIVEN OR RESULTS OBTAINED, ALL SUCH BEING GIVEN AND ACCEPTED AT THE READER'S RISK.

*Joncryn* is a registered trademark of BASF Group.

© BASF Corporation, 2023



BASF Corporation is fully committed to the Responsible Care® Initiative in the USA, Canada, and Mexico.  
For more information on Responsible Care® go to:  
U.S.: [www.basf.us/responsiblecare\\_usa](http://www.basf.us/responsiblecare_usa)  
Canada: [www.basf.us/responsiblecare\\_canada](http://www.basf.us/responsiblecare_canada)  
México: [www.basf.us/responsiblecare\\_mexico](http://www.basf.us/responsiblecare_mexico)

**BASF Corporation**  
Dispersions and Resins  
11501 Steele Creek Road  
Charlotte, North Carolina 28273  
Phone: (800) 251 – 0612  
Email: [CustCare-Charlotte@basf.com](mailto:CustCare-Charlotte@basf.com)  
[www.basf.us/dpsolutions](http://www.basf.us/dpsolutions)