

# Specification data sheet

Page: 1/2

BASF Specification data sheet

Date / Revised: 2020/12/04

Product: **Acronal® MB ECO 6716 E**

Version: 1.1

(30860568/SPE\_GEN\_P/EN)

Date of print 20.10.2025

## 1. Substance/preparation and company identification

### Acronal® MB ECO 6716 E

BASF SE

Regional Business Unit Dispersions Europe

67056 Ludwigshafen, Germany

E-mail address: ede-qm@basf.com

## 2. Characterization

Aqueous dispersion of a polymer based on: acrylic ester, Styrene

Colour: white  
Form: liquid, dispersion  
Odour: almost odourless

## 3. Specified tests

Property	Test method (parameter)	Value
Solid content	DIN EN ISO 3251	49.0 - 51.0 %
pH value	DIN ISO 976	6.5 - 8.5
Viscosity, dynamic	DIN EN ISO 3219 (23 °C, 100 1/s)	300 - 1,000 mPa.s

## 4. Handling and Storage

BASF Specification data sheet  
Date / Revised: 2020/12/04  
Product: **Acronal® MB ECO 6716 E**

Version: 1.1

(30860568/SPE\_GEN\_P/EN)

Date of print 20.10.2025

Further information on storage conditions:

Store protected against freezing.

To avoid problems during storage (impact of microorganisms) we recommend the stabilization with biocides.

The product should not come into contact with exposed iron or non-ferrous metal during storage or processing.

Keep container tightly sealed.

The headspace of bulk storage tanks must be kept saturated with water vapour.

---

Vertical lines in the left hand margin indicate an amendment from the previous version.

The Specified Parameters listed in section 3 represent the contractual quality at the time of the transfer of risk. The previous mentioned data are controlled at regular intervals as part of our quality assurance program. Neither these data nor the properties of product specimens shall imply any legally binding guarantee of certain properties or of fitness for a specific purpose. No liability of ours can be derived therefrom.

This product specification was issued automatically and is not signed.