

Efka® PU 4010

Product description

high-molecular-weight dispersing agent

Key benefits

Efka® PU 4010 is a polymeric dispersant for stabilizing inorganic pigments including carbon blacks. It also has an excellent performance with many organic pigments. This results in:

- reduced grinding time
- improved gloss
- prevention of flooding and floating
- higher color strength

Due to its particularly good combination of price and performance, Efka® PU 4010 is a very attractive substitute for conventional wetting and dispersing agents.

It is possible to mix combinations of inorganic pigments stabilized with Efka® PU 4010 and organic pigments stabilized with other Efka® high-molecular-weight polymeric dispersants.

Chemical nature

modified polyurethane

Properties

Physical form

clear, slightly yellowish liquid

Technical data

(not supply specification)

solvent	butyl acetate / methoxypropyl acetate / solvent naphtha
density at 20 °C	~ 0.983 g/cm3
active ingredients	~ 50 %
flash point	34.5 °C
acid value	~ 13 mg KOH/g
amine value	~ 6 mg KOH/g
color	≤ 6

February 2023

Supersedes: December 2016 page 1 of 2

Application

Efka® PU 4010 was developed as a general dispersing agent for all solvent-based paints from high-performance industrial coatings to decorative paints. It can also be used in universal solvent-based pigment concentrates.

Recommended concentrations

titanium dioxide	2-4 % as supplied
inorganic pigments	5–10 % as supplied
organic pigments	20–40 % as supplied
carbon blacks	30–60 % as supplied

Efka® PU 4010 should be incorporated in the mill base before adding the pigments.

Storage

Efka® PU 4010 may partially solidify when stored below 10 °C (50 °F). Heat to 35–40 °C (95–104 °F) to reliquify.

Contacts worldwide

Asia BASF East Asia Regional Headquarters Ltd 45/F, Jardine House No. 1 Connaught Place Central Hong Kong China

formulation-additives-asia@basf.com

Europe BASF SE Formulation Additives 67056 Ludwigshafen

formulation-additives-europe@basf.com

North America BASF Corporation 11501 Steele Creek Road Charlotte, NC 28273

formulation-additives-nafta@basf.com

South America BASF S.A Rochaverá - Crystal Tower Av. das Naçoes Unidas, 14.171 Morumbi - São Paulo-SP

Brazil

formulation-additives-south-america@basf.com

Validity

This Technical Data Sheet is valid for all versions of the Efka® PU 4010.

Safety

When handling this product, please comply with the advice and information given in the safety data sheet and observe protective and workplace hygiene measures adequate for handling chemicals.

Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. The agreed contractual quality of the product results exclusively from the statements made in the product specification. It is the responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed.

® = Registered trademark

www.basf.com\formulation-additives