

Specification data sheet

Page: 1/2

BASF Specification data sheet

Date / Revised: 2025/08/18

Product: **Laromer® TPGDA CN**

Version: 1.0

(30858971/SPE_GEN_P/EN)

Date of print 16.10.2025

1. Substance/preparation and company identification

Laromer® TPGDA CN

BASF SE

Global Business Unit Resins and Additives

67056 Ludwigshafen, Germany

E-mail address: ede-qm@basf.com

2. Characterization

Resin based on: polyetherpolyol, acrylic ester, unsaturated, (1-Methyl-1,2-ethanediyl)bis[oxy(methyl-2,1-ethanediyl)] diacrylate

3. Specified tests

Property	Test method (parameter)	Value
Viscosity, dynamic	DIN EN ISO 2555 (LV) (25 °C)	10 - 17 mPa.s
Color number	DIN EN ISO 6271	<= 70
Acid number (KOH)	DIN EN ISO 660	<= 0.5 mg/g
Water content	ISO 4317	<= 0.2 %

4. Handling and Storage

Advice on safe handling:

See SDS section 7 - Handling and storage.

BASF Specification data sheet
Date / Revised: 2025/08/18
Product: **Laromer® TPGDA CN**

Version: 1.0

(30858971/SPE_GEN_P/EN)

Date of print 16.10.2025

The Specified Parameters listed in section 3 represent the contractual quality at the time of the transfer of risk. The data are controlled at regular intervals as part of our quality assurance program. BASF MAKES NO WARRANTY OF ANY KIND, EITHER EXPRESS OR IMPLIED, BY FACT OR LAW, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.

This product specification was issued automatically and is not signed.