Product Information
Acronal® MB 6400

Biomass Balance Dispersion Polymer for near Odorless, near zero Emission architectural coatings with excellent Stain Resistance

Acronal® MB 6400 contains finely dispersed particles and has a low viscosity. It is near odorless and contains no ammonia, solvents or plasticizers. It exhibits excellent compatibility with commonly used pigments and extenders. Films obtained from it are clear, flexible and glossy, and very resistant to water and hydrolysis.
A biomass balance product certified by TÜV Nord according to REDcert² certification scheme for the chemical industry; certification number: REDcert²-929-35244206. This product entails a 100 % substitution of fossil with renewable raw materials in the value chain.

Chemical Nature:

Acronal MB* 6400 is a dispersion polymer of acrylic ester and styrene

* MB = Mass Balance

Benefits

- Earlier reoccupation of painted space
- Environmentally friendly formulated standard interior paint
- Excellent stain resistance
- Good scrub resistance

Features

- Near odorless dispersion polymer for near Zero Emission Paints
- Can be formulated at various PVC levels
- Excellent water and alkali resistance

Properties

Product specification*	Solids content	%	48 ± 1
	pH value	pH	7.0 – 9.0
	Viscosity at 23 °C, Brookfield, RVT 20 rpm, 1#	mPa s	2000 – 3000
Other properties of dispersions	Minimum film-forming temperature (ISO 2115)	°C	< 5
	Density (ISO 2811-1)	g/cm³	approx. 1.04
	Resistance to frost	ºC	≤ 0
	Type of dispersion		anionic

*The aforementioned data shall constitute the agreed contractual quality of the product at the time of passing of risk. The data are controlled at regular intervals as part of our quality assurance program. Neither these data nor the properties of product specimens shall imply any legally binding guarantee of certain properties or of fitness for a specific purpose. No liability of ours can be derived therefrom.

Note
The information submitted in this publication is based on our current knowledge and experience. In view of the many factors that may affect processing and application, these data do not relieve processors of the responsibility of carrying out their own tests and experiments; neither do they imply any legally binding assurance of certain properties or of suitability for a specific purpose. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and legislation are observed.

Acronal® MB 6400

Applications

Areas of application

Acronal® MB 6400 is ideal for odorless paints. It is suitable for use in emulsion paints for interior or exterior.

Processing

It is advisable to disperse the pigments and extenders with wetting and dispersing agents such as sodium polyacrylates or sodium polyphosphates, which are particularly appropriate for use as dispersing agents in low-odor coatings. It is only when products with very high viscosity are being mixed in low-speed mixers that Acronal® MB 6400 should be added together with the wetting and dispersing agents.

The nature and quantity of the pigments and fillers can be varied within wide limits. This primarily depends on the application for which the coating is intended, i. e. interior or exterior, factors such as the required gloss, flexibility and wet abrasion resistance, the type of substrate and the amount of binder required to disperse the pigments and fillers (i.e. their oil absorption).

Various thickeners can be added to emulsion paints in order to adjust their viscosity and workability. Cellulose ethers, polyacrylates, diurethane thickener (such as Rheovis® AS 1125) and bentonite can be used. The choice of thickener depends on whether the coating is expected to be free-flowing or more thixotropic.

Like all finely divided dispersion polymers, Acronal® MB 6400 has a tendency to foam. It is therefore necessary to add a commercial defoamer at the level recommended by the manufacturer. Trials should be carried out to test the effectiveness of the defoamer.

Although Acronal® MB 6400 itself is resistant to microorganisms in the form in which it is supplied, preservatives need to be added to products formulated with Acronal® MB 6400 to protect them from attack by microorganisms over long periods in storage. Trials should always be carried out to test the compatibility and efficacy of the preservatives.

Customers have to carry out their own trials when developing and processing products based on Acronal® MB 6400. The compatibility of Acronal® MB 6400 with other ingredients of formulations, its effect on mixing processes and its adhesion on different substrates etc., are affected by a variety of factors which are too numerous for us to take into account in our own trials. This includes testing its stability by storing it at ca. 50 °C to confirm that its viscosity remains stable.

Note
The information submitted in this publication is based on our current knowledge and experience. In view of the many factors that may affect processing and plication, these data do not relieve processors of the responsibility of carrying out their own tests and experiments; neither do they imply any legally binding assurance of certain properties or of suitability for a specific purpose. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and legislation are observed.

Acronal® MB 6400

Safety

General
The usual precautions for handling chemicals must be observed. These include the measures set out in the guidelines of the organizations responsible for safety at work, in particular, good ventilation and fume extraction at the workplace, care of the skin and the wearing of eye protection.

Safety Data Sheet
When using this product, the information and advice given in our **Safety Data Sheet** should be observed. Due attention should also be given to the **precautions** necessary for handling chemicals.

Labelling
According to all the data at our disposal, Acronal® MB 6400 does not need to be labelled as a dangerous substance or preparation as defined in the relevant local directives according to their current status.

Storage

Acronal® MB 6400 must not be allowed to come into contact during storage with metals or alloys that are susceptible to corrosion. It is important to ensure that containers are kept tightly sealed, and the headspace of bulk storage tanks must be kept saturated with water vapor. This product must not be exposed to high temperatures, and it must be protected from frost.

Acronal® MB 6400 has a shelf life of nine months at 10 – 30 °C, provided due attention is paid to the hygiene of tanks and storage facilities..

We would recommend treating this product with a biocide in order to prevent problems with micro organisms from occurring during storage and processing.

Note
The information submitted in this publication is based on our current knowledge and experience. In view of the many factors that may affect processing and application, these data do not relieve processors of the responsibility of carrying out their own tests and experiments; neither do they imply any legally binding assurance of certain properties or of suitability for a specific purpose. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and legislation are observed.

Contact Us

BASF East Asia Regional Headquarters Ltd
Dispersions & Pigments Asia Pacific
45th Floor, Jardine House, No. 1,
Connaught Place Central,
Hong Kong

Phone: +852 2731 0111
Fax: +852 2731 5670
E-mail: Dispersions-Pigments-Asia@basf.com
www.dispersions.asiapacific.basf.com