Product Information
AQACell® HIDE 6299

Opacifying Polymer Dispersion for Paints

AQACell® HIDE 6299 ap is an APEO free, ammonia free anionic opacifying pigment dispersion for paints. It is designed to provide opacity and whiteness to paints in architectural coatings by extending and/or improving the efficiency of TiO_2 without sacrificing interior or exterior coating properties.

Chemical Nature:
State of the art Organic Opacifying Pigment

Benefits

- Highly scattering organic pigment
- Pigment spacing effect which leads to increased TiO2 efficiency
- Improved economics of paint while maintaining equal hiding power
- Broad formulation latitude: Low to high PVC paints

Features

- APEO free
- Ammonia free
- Low odor
- Spherical, low relative surface area leads to very low binder demand

Properties

Product specification*	Solids content	%	30 ± 1
	pH value		8.1 – 9.5
	Viscosity at 23 °C, 2/50 rpm mPas		1 - 350
Other properties of the dispersion	Density g/cm³ (ISO 2811-1)		approx. 1.05
	Resistance to frost ºC		≤ 0
	Type of emulsion		anionic

*The aforementioned data shall constitute the agreed contractual quality of the product at the time of passing of risk. The data are controlled at regular intervals as part of our quality assurance program. Neither these data nor the properties of product specimens shall imply any legally binding guarantee of certain properties or of fitness for a specific purpose. No liability of ours can be derived therefrom.

Note
The information submitted in this publication is based on our current knowledge and experience. In view of the many factors that may affect processing and application, these data do not relieve processors of the responsibility of carrying out their own tests and experiments; neither do they imply any legally binding assurance of certain properties or of suitability for a specific purpose. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and legislation are observed.

AQACell® HIDE 6299

Applications

Areas of application

The main field of application for Acronal HIDE 6299 ap is as an organic opacifiying pigment for interior and exterior paints over a broad PVC range.

Processing

Acronal HIDE 6299 ap is recommended to be added in the let down stage. Dispex® CX 4320 is recommended for dispersing titanium dioxide pigments in propylene glycol or propylene glycol/water. Dispex® AA polyacrylate types can be used as a codispersant or the sole dispersant, particularly if high levels of calcium carbonate are used.

Associative thickeners, e. g. Rheovis PE 1332, PU 1280 and PU 1191, are particularly suitable for adjusting the viscosity and flow, because they do not give rise to a yield point in the rheological characteristic. These thickeners may be combined with hydroxyethyl cellulose or modified cellulose thickeners in order to reduce any tendency of sagging and to prevent pigment flocculation, although cellulose based thickeners may reduce the stain and wash resistance of the paint.

Like all dispersions Acronal HIDE 6299 ap tends to foam, with the consequence that it generally necessitates the addition of a defoamer like FoamStar® ST2410 in proportions of 0.2 - 1%.

A coalescent is typically required to ensure satisfactory film formation for paints. Water miscible glycol ethers are particularly suitable for this purpose. Examples of other suitable coalescents are Texanol® (Eastman Chemical Company), and Loxanol® CA 5310 (BASF). AQACell HIDE 6299 ap will show wet good stability in paints using these coalescents. As with all polymer dispersions care should be taken when adding solvents so as to not cause coagulation. If a low odor or low VOC paint is to be formulated then care should also be taken in the selection of the coalescent solvent.

Propylene glycol is suitable for increasing the wet edge time but temporarily impairs the resistance to blocking and increases the sensitivity to water.
Preservatives should be added to products made up with Acronal HIDE 6299 ap, in order to ensure adequate protection against microbial attack during long storage periods. Their compatibility and effectiveness however should be tested also.

Note
The information submitted in this publication is based on our current knowledge and experience. In view of the many factors that may affect processing and plication, these data do not relieve processors of the responsibility of carrying out their own tests and experiments; neither do they imply any legally binding assurance of certain properties or of suitability for a specific purpose. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and legislation are observed.

AQACell® HIDE 6299

Safety

General
The usual precautions for handling chemicals must be observed. These include the measures set out in the guidelines of the organizations responsible for safety at work, in particular, good ventilation and fume extraction at the workplace, care of the skin and the wearing of eye protection.

Safety Data Sheet
When using this product, the information and advice given in our **Safety Data Sheet** should be observed. Due attention should also be given to the **precautions** necessary for handling chemicals.

Labeling
According to all the data at our disposal, AQACell® HIDE 6299 does not need to be labelled as a dangerous substance or preparation as defined in the relevant local directives according to their current status.

Storage

AQACell® HIDE 6299 must not be allowed to come into contact during storage with metals or alloys that are susceptible to corrosion. It is important to ensure that containers are kept tightly sealed, and the headspace of bulk storage tanks must be kept saturated with water vapour. This product must not be exposed to high temperatures, and it must be protected from frost.

AQACell® HIDE 6299 has a shelf life of nine months at 10 – 30 °C, provided due attention is paid to the hygiene of tanks and storage facilities.

We would recommend treating this product with a biocide in order to prevent problems with microorganisms from occurring during storage and processing. Further details are given in our leaflet on “The handling and storage of polymer dispersions”.

Note
The information submitted in this publication is based on our current knowledge and experience. In view of the many factors that may affect processing and application, these data do not relieve processors of the responsibility of carrying out their own tests and experiments; neither do they imply any legally binding assurance of certain properties or of suitability for a specific purpose. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and legislation are observed.

Contact Us

BASF East Asia Regional Headquarters Ltd
Dispersions & Pigments Asia Pacific
45th Floor, Jardine House, No. 1,
Connaught Place Central,
Hong Kong

Phone: +852 2731 0111
Fax: +852 2731 5670
E-mail: Dispersions-Pigments-Asia@basf.com
www.dispersions.asiapacific.basf.com