Product Information
Acronal® 7066

Aqueous polymer dispersion for use in exterior coating, stone finishes and textured coatings

Acronal® 7066 is a finely divided polymer dispersion with a medium viscosity. It forms films that are tough, flexible and tack-free at temperatures in the region of 20-22°C. Films formed by Acronal® 7066 have high water resistance and high light fastness, and they are very resistant to saponification and weathering. They have very little tendency to blush, even if they are exposed to water for long periods.

Chemical Nature:
Dispersion polymer of acrylic ester and styrene

Benefits
- Designed for stone/textured finishes
- Excellent exterior durability
- Excellent yellowing resistance
- Outstanding blushing resistance
- Tough, flexible and tack-free

Features
- Excellent weatherability
- Very good water whitening resistance
- Resistant to saponification
- APEO free

Properties

Product specification*	Solids content	%	45 ± 1
	pH value	pH	7.0 – 9.5
	Viscosity at 23 °C, RVT Sp3/20 rpm (DIN EN ISO 2555)	mPa s	1000 – 4000
Other properties of dispersions	Minimum film-forming temperature (ISO 2115)	°C	approx. 22
	Density (ISO 2811-1)	g/cm³	approx. 1.05
	Average particle size	µm	approx. 0.1
	Type of dispersion		anionic

*The aforementioned data shall constitute the agreed contractual quality of the product at the time of passing of risk. The data are controlled at regular intervals as part of our quality assurance program. Neither these data nor the properties of product specimens shall imply any legally binding guarantee of certain properties or of fitness for a specific purpose. No liability of ours can be derived therefrom.

Note
The information submitted in this publication is based on our current knowledge and experience. In view of the many factors that may affect processing and application, these data do not relieve processors of the responsibility of carrying out their own tests and experiments; neither do they imply any legally binding assurance of certain properties or of suitability for a specific purpose. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and legislation are observed.

Acronal® 7066

Applications

Areas of application

Acronal® 7066 is mainly used as a binder for stone finishes/textured coatings with excellent blushing resistance. It can also be used for wood stains, wood paints, emulsion paints with a gloss or satin gloss finish, and plastic paints.

Processing

It is advisable to disperse the pigments and extenders with wetting and dispersing agents such as Pigment Disperser® MD 20 and water-soluble polyphosphates in an alkaline medium in advance before the polymer dispersion is added. It is only when products with very high viscosity are being mixed in low-speed mixers that Acronal® 7066 should be added together with the wetting and dispersing agents.

Acronal® 7066 has very good compatibility with pigments and fillers. Various thickeners can be added to emulsion paints in order to adjust their viscosity and workability. Diurethane thickeners (such as, Collacral® PU 80 and DSX® 3100) and bentonite can be used. The choice of thickener depends on whether the coating is expected to be free-flowing or more thixotropic.

Solvents need to be added in order to enable the polymer to form a uniform film at temperatures below ambient temperature. e.g. Loxanol® EFC 300 Lusolvon® FBH. It is usually sufficient to add these solvents at a level of 2%, expressed as a proportion of the total dispersion. Short-chain alcohol and glycols improve the freeze-thaw resistance of paints, but they can not be used to lower the film-forming temperature. If possible, solvents should not be added direct to the polymer dispersion, they should be mixed with the pigment paste and then added.

Acronal® 7066, like all fine dispersions, has a tendency to foam. It is therefore necessary to add a commercial defoamer at the level of 0.3~1%. e.g. Dehydran® SE2. Trials should be carried out to test the effectiveness of the defoamer.

Acronal® 7066 is protected against attack by microorganisms, preservatives must still be added to the formulated products so as to ensure uniform quality even with prolonged storage. Compatibility and effectiveness must be determined by preliminary trials.

Customers have to carry out their own trials when developing and processing products based on Acronal® 7066. The compatibility of Acronal® 7066 with other ingredients of formulations, its effect on mixing process and its adhesion on different substrates etc., are affected by a variety of factors which are too numerous for us to take into account in our own trials. This includes testing its stability by storing it at ca.50°C to confirm that its viscosity remains stable.

Note
The information submitted in this publication is based on our current knowledge and experience. In view of the many factors that may affect processing and plication, these data do not relieve processors of the responsibility of carrying out their own tests and experiments; neither do they imply any legally binding assurance of certain properties or of suitability for a specific purpose. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and legislation are observed.

Acronal® 7066

Safety

General
The usual precautions for handling chemicals must be observed. These include the measures set out in the guidelines of the organizations responsible for safety at work, in particular, good ventilation and fume extraction at the workplace, care of the skin and the wearing of eye protection.

Safety Data Sheet
When using this product, the information and advice given in our **Safety Data Sheet** should be observed. Due attention should also be given to the **precautions** necessary for handling chemicals.

Labeling
According to all the data at our disposal, Acronal® 7066 does not need to be labeled as a dangerous substance or preparation as defined in the relevant local directives according to their current status.

Storage

Acronal® 7066 must not come with metals or alloys that are susceptible to corrosion. During storage it is particularly important to ensure that containers are closed tightly; in storage tanks the air must always be saturated with water vapor. Undue heating must be avoided, as much exposure to frost.

Given adequate tank and storage hygiene Acronal® 7066 can be kept for about nine months at 10-30ºC.

To prevent problems with microorganisms we recommend post-stabilizing the product with biocides for storage.

Note
The information submitted in this publication is based on our current knowledge and experience. In view of the many factors that may affect processing and application, these data do not relieve processors of the responsibility of carrying out their own tests and experiments; neither do they imply any legally binding assurance of certain properties or of suitability for a specific purpose. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and legislation are observed.

Contact Us

BASF East Asia Regional Headquarters Ltd
Dispersions & Pigments Asia Pacific
45th Floor, Jardine House, No. 1,
Connaught Place Central,
Hong Kong

Phone: +852 2731 0111
Fax: +852 2731 5670
E-mail: Dispersions-Pigments-Asia@basf.com
www.dispersions.asiapacific.basf.com