Product Information
Acronal® 7629

Polymer dispersion for use in formulations for robust colored gels formation in multicolor coatings

Acronal® 7629 is an anionic polymer dispersion with a medium viscosity. Its compatibility with most conventional colorants facilitate full freedom in formulating multicolor patterns. With Acronal® 7630 as the clear carrier for colored gel particles, complete water-based system of multicolor coatings could be achieved. This complete system exhibits excellent stability, good scrub and alkali resistance.

Chemical Nature:

Polymer dispersion of acrylic and methacrylic acid esters

Benefits

- Compatible with wide range of conventional colorants in multicolor formulations
- Good color gel storage stability in multicolor formulations
- Good scrub resistance
- Robust and flexible formulation

Features

- Excellent weatherability
- Outstanding stability
- High water & alkali resistance
- Good dirt pick-up resistance
- Coverage of hairline cracks

Properties

Product specification*	Solids content	%	48 ± 1
	pH value	pH	7.5 – 8.5
	Viscosity at 23 °C, RVT 5/20	mPa s	2000 – 6000
Other properties of dispersions	Minimum film-forming temperature (ISO 2115)	°C	approx. 13
	Density (ISO 2811-1)	g/cm^3	approx. 1.04
	Resistance to frost	ºC	≤ 0
	Type of dispersion		anionic

*The aforementioned data shall constitute the agreed contractual quality of the product at the time of passing of risk. The data are controlled at regular intervals as part of our quality assurance program. Neither these data nor the properties of product specimens shall imply any legally binding guarantee of certain properties or of fitness for a specific purpose. No liability of ours can be derived therefrom.

Note
The information submitted in this publication is based on our current knowledge and experience. In view of the many factors that may affect processing and application, these data do not relieve processors of the responsibility of carrying out their own tests and experiments; neither do they imply any legally binding assurance of certain properties or of suitability for a specific purpose. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and legislation are observed.

Acronal® 7629

Applications

Areas of application

Acronal® 7629 is specially designed for paint formulations to form colored gel particles for multicolor finish in both interior and exterior coatings, which are based on formulations with hectorite. Together with Acronal® 7630 as the clear carrier for these colored gel particles. It offers green solution of complete water-based multicolor coatings.

Processing

Dispersants:

It is advisable to disperse pigments and extenders with wetting and dispersing agents such as Dispex® CX 4320 in alkaline medium in advance before the polymer dispersion is added. It is only when products with very high viscosity are being mixed in low speed mixtures that Acronal® 7629 should be added together with wetting and dispersing agents. Acronal® 7629 has high pigment binding power and very good compatibility with pigments and fillers.

Thickeners:

Various thickeners can be added to emulsion paints in order to adjust their viscosity and workability. Cellulose ethers, polyacrylate thickeners like Rheovis® HS 1152 or PU thickeners like Rheovis® PU series and bentonite can be used. The choice of thickeners depends on whether the coating is expected to be more thixotropic or application dependent. It is advisable to adjust the viscosity to at least 120 KU for stable colored gels formation.

Solvents:

Short chain alcohols and glycols improve freeze thaw resistance of paints, but they cannot be used to lower the film forming temperature. If possible solvents should not be added to the polymer dispersion, they should be mixed with the pigment paste and then added.

Defoamers:

Like all finely divided polymer dispersions, Acronal® 7629 has a tendency to foam. It is therefore, necessary to add a commercial defoamer like Foamaster® MO NXZ or Foamaster® MO 2150 at levels of 0.4 to 0.8%. Trials should be carried out to test the effectiveness of the defoamer.

Preservatives:

Although Acronal® 7629 itself is resistant to microorganisms in the form in which it is supplied, preservatives need to be added to products formulated with Acronal® 7629 to protect them from attack by microorganisms over a long periods in storage. Trials should always be carried out to test the compatibility and efficacy of the preservatives.

Customers have to carry out their own trials when developing and processing products based on Acronal® 7629. The compatibility of Acronal® 7629 with other ingredients of formulations, its effect on mixing processes and its adhesion on different substrates etc., are affected by a variety of factors which are too numerous for us to take into account in our own trials. This includes testing its stability by storing it at ca. 50°C to conform that its viscosity remains stable.

Note
The information submitted in this publication is based on our current knowledge and experience. In view of the many factors that may affect processing and plication, these data do not relieve processors of the responsibility of carrying out their own tests and experiments; neither do they imply any legally binding assurance of certain properties or of suitability for a specific purpose. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and legislation are observed.

Acronal® 7629

Safety

General
The usual precautions for handling chemicals must be observed. These include the measures set out in the guidelines of the organizations responsible for safety at work, in particular, good ventilation and fume extraction at the workplace, care of the skin and the wearing of eye protection.

Safety Data Sheet
When using this product, the information and advice given in our **Safety Data Sheet** should be observed. Due attention should also be given to the **precautions** necessary for handling chemicals.

Labeling
According to all the data at our disposal, Acronal® 7629 does not need to be labelled as a dangerous substance or preparation as defined in the relevant local directives according to their current status.

Storage

Acronal® 7629 must not be allowed to come into contact during storage with metals or alloys that are susceptible to corrosion. It is important to ensure that containers are kept tightly sealed, and the headspace of bulk storage tanks must be kept saturated with water vapor. This product must not be exposed to high temperatures, and it must be protected from frost.

Acronal® 7629 has a shelf life of nine months at 10 – 30 °C, provided due attention is paid to the hygiene of tanks and storage facilities.

We would recommend treating this product with a biocide in order to prevent problems with microorganisms from occurring during storage and processing.

Note
The information submitted in this publication is based on our current knowledge and experience. In view of the many factors that may affect processing and application, these data do not relieve processors of the responsibility of carrying out their own tests and experiments; neither do they imply any legally binding assurance of certain properties or of suitability for a specific purpose. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and legislation are observed.

Contact Us

BASF East Asia Regional Headquarters Ltd
Dispersions & Pigments Asia Pacific
45th Floor, Jardine House, No. 1,
Connaught Place Central,
Hong Kong

Phone: +852 2731 0111
Fax: +852 2731 5670
E-mail: Dispersions-Pigments-Asia@basf.com
www.dispersions.asiapacific.basf.com