BASF
We create chemistry

Dispex® CX 4389

Product description Dispersing agent

Key benefits

- Good dispersant efficiency
- Stabilizes systems with high inorganic filler content
- Suited for dispersion of inorganic pigments

Chemical nature Polycarboxylate, sodium salt in water

Properties

Physical form liquid

Technical data
(no supply specification)

Solid content	~ 10 %
pH value	~ 6.5

Application

Dispex® CX 4389 is an effective polymeric sodium salt of a carboxylic acid copolymer in water. It is particularly effective for dispersing inorganic fillers and pigments.

Formulation guideline 0.5 – 1.0 %, calculated on total formulation

Recommended dosages of Dispex® CX 4389 depend on the nature of the solids to be dispersed. In critical formulations it is possible to increase the dosage up to 2 %. The amount of Dispex® CX 4389 required for optimal performance should be determined in trials covering a concentration range. Dispex® CX 4389 is most efficient in systems that have been adjusted to a pH of 7 to 9 prior to the grinding process.

Storage

Dispex® CX 4389 should always be stored in tightly closed containers and in a cool dry place.

Contacts worldwide

Asia
BASF East Asia Regional Headquarters Ltd
45/F, Jardine House
No. 1 Connaught Place
Central Hong Kong
China
formulation-additives-asia@basf.com

Europe
BASF SE
Formulation Additives
67056 Ludwigshafen
Germany
formulation-additives-europe@basf.com

North America
BASF Corporation
11501 Steele Creek Road
Charlotte, NC 28273
USA
formulation-additives-nafta@basf.com

South America
BASF S.A
Rochaverá - Crystal Tower
Av. das Naçoes Unidas, 14.171
Morumbi - São Paulo-SP
Brazil
formulation-additives-south-america@basf.com

Validity

This Technical Data Sheet is valid for all versions of the Dispex® CX 4389.

Safety

When handling this product, please comply with the advice and information given in the safety data sheet and observe protective and workplace hygiene measures adequate for handling chemicals.

Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. The agreed contractual quality of the product results exclusively from the statements made in the product specification. It is the responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed.

® = Registered trademark
™ = Trademark of the BASF Group, unless otherwise noted