

Individual protection measures, such as personal protective equipment

Eye/face protection	Wear safety glasses with side shields (or goggles).
Skin protection	
Hand protection	Suitable chemical protective gloves should be worn when the potential exists for skin exposure. The choice of an appropriate glove does not only depend on its material but also on other quality features and is different from one producer to the other. Nitrile, butyl rubber or neoprene gloves are recommended.
Other	Wear appropriate chemical resistant clothing if applicable.
Respiratory protection	If engineering controls do not maintain airborne concentrations to a level which is adequate to protect worker health, an approved respirator must be worn. Respirator selection, use and maintenance should be in accordance with the requirements of OSHA Respiratory Protection Standard 29 CFR 1910.134 and/or Canadian Standard CSA Z94.4.
Thermal hazards	Wear appropriate thermal protective clothing, when necessary.
General hygiene considerations	Always observe good personal hygiene measures, such as washing after handling the material and before eating, drinking, and/or smoking. Routinely wash work clothing and protective equipment to remove contaminants. Contaminated work clothing should not be allowed out of the workplace.

9. Physical and chemical properties**Appearance**

Physical state	Solid.
Form	Paste.
Color	Black
Odor	Mild.
Odor threshold	Not available.
pH	Not available.
Melting point/freezing point	Not available.
Initial boiling point and boiling range	253.4 °F (123 °C)
Flash point	>201.0 °F (>93.9 °C) Setflash
Evaporation rate	<1 (BuAc=1)
Flammability (solid, gas)	Not available.
Upper/lower flammability or explosive limits	
Explosive limit - lower (%)	Not available.
Explosive limit - upper (%)	Not available.
Vapor pressure	Not available.
Vapor density	>1 (Air=1)
Relative density	1.42 (Water=1)
Solubility(ies)	
Solubility (water)	Insoluble
Partition coefficient (n-octanol/water)	Not available.
Auto-ignition temperature	Not available.
Decomposition temperature	Not available.
Viscosity	Not available.
Other information	
Density	1.42 g/cm ³
VOC	28 g/l

10. Stability and reactivity

Reactivity	The product is stable and non-reactive under normal conditions of use, storage and transport.
Chemical stability	Material is stable under normal conditions.
Possibility of hazardous reactions	No dangerous reaction known under conditions of normal use.