## FIR No. 199695



Revision Date: 17 Mar 2015

Page 6 of 11



Lag Pay /n Ostana (Mater Partition Coefficient) > 2.5. [Estimated]

Log Pow (n-Octanol/Water Partition Coefficient): > 3.5 [Estimated]

Solubility in Water: Negligible

**Viscosity:** [N/D at 40 °C] | 15 cSt (15 mm2/sec) at 100°C **Oxidizing Properties:** See Hazards Identification Section.

**OTHER INFORMATION** 

Freezing Point: N/D Melting Point: N/A

Pour Point:  $-45^{\circ}$ C  $(-49^{\circ}$ F)

## SECTION 10 STABILITY AND REACTIVITY

**REACTIVITY:** See sub-sections below.

**STABILITY:** Material is stable under normal conditions.

**CONDITIONS TO AVOID:** Excessive heat. High energy sources of ignition.

MATERIALS TO AVOID: Strong oxidizers

HAZARDOUS DECOMPOSITION PRODUCTS: Material does not decompose at ambient temperatures.

POSSIBILITY OF HAZARDOUS REACTIONS: Hazardous polymerization will not occur.

## SECTION 11 TOXICOLOGICAL INFORMATION

## INFORMATION ON TOXICOLOGICAL EFFECTS

Hazard Class	Conclusion / Remarks
Inhalation	
Acute Toxicity: No end point data for	Minimally Toxic. Based on assessment of the components.
material.	·
Irritation: No end point data for material.	Negligible hazard at ambient/normal handling temperatures.
Ingestion	
Acute Toxicity: No end point data for	Minimally Toxic. Based on assessment of the components.
material.	
Skin	
Acute Toxicity: No end point data for	Minimally Toxic. Based on assessment of the components.
material.	
Skin Corrosion/Irritation: No end point data	Negligible irritation to skin at ambient temperatures. Based on
for material.	assessment of the components.
Eye	
Serious Eye Damage/Irritation: No end point	May cause mild, short-lasting discomfort to eyes. Based on
data for material.	assessment of the components.
Sensitization	
Respiratory Sensitization: No end point data	Not expected to be a respiratory sensitizer.
for material.	
Skin Sensitization: No end point data for	Not expected to be a skin sensitizer. Based on assessment of the
material.	components.
Aspiration: Data available.	Not expected to be an aspiration hazard. Based on
	physico-chemical properties of the material.
Germ Cell Mutagenicity: No end point data	Not expected to be a germ cell mutagen. Based on assessment of