WPS-AKE-057 - Non-Asbestos Friction Material NS516, NS516H, AS522, AS522H

Revision Date 13-Feb-2018

Flammability Limits in Air

upper flammability limit No data available lower flammability limit No data available **Vapor Pressure** No data available

None known **Vapor Density** No data available None known **Specific Gravity** 2.0-3.0 None known **Water Solubility** None None known Solubility in other solvents None. None known Partition coefficient: n-octanol/waterNo data available None known **Autoignition Temperature** No data available None known **Decomposition Temperature** No data available None known No data available **Viscosity** None known

Flammable Properties Not flammable

Explosive Properties No data available **Oxidizing Properties** No data available

Other information

VOC Content (%) No data available

10. STABILITY AND REACTIVITY

Reactivity

Not reactive under normal conditions.

Chemical stability

Stable under recommended storage conditions.

Possibility of hazardous reactions

None under normal processing.

Hazardous Polymerization

Hazardous polymerization does not occur.

Conditions to avoid

None known.

Incompatible materials

None known.

Hazardous decomposition products

None known.

11. TOXICOLOGICAL INFORMATION

Information on likely routes of exposure