

Material Safety Data Sheet

Issue No.: SMC-11.07

Date: September 16, 2011

1.1 PRODUCT INFORMATION:

This MSDS covers the following Special Metals Corporation alloy families and individual products identified as:

INCONEL®, INCOLOY®, INCOCLAD®, MONEL®, UDIMET®, UDIMAR®, NILO®, NILOMAG®, NIMONIC®, NIMOLOY, NI-SPAN-C®, BRIGHTRAY®, KOTHERM® & NOTHERM® alloys; Nitinol, Nickel, DEPOLARIZED & DURVANIC nickel, Electroformed nickel foil, Cupro 107; Miscellaneous designations, Mixed nickel alloy revert.

These are corrosion or heat resisting alloys, or alloys with special physical properties, which are primarily used in process, industrial, aerospace, automotive, marine, electrical or electronic equipment. Alloys not described in this document may be proprietary; contact one of the SMC locations below for more information.

1.2 COMPANY INFORMATION

The products are supplied by the main manufacturing companies in the Special Metals Corporation Group and/or their subsidiaries*:

USA

Special Metals Corporation
3200 Riverside Drive
Huntington, WV, USA 25705
EMERGENCY TELEPHONE NUMBER: +1(304) 526-5780
GENERAL INFORMATION: +1(304) 526-5100

EUROPE

Special Metals Wiggin Ltd.
Holmer Road
Hereford, HR4 9SL, UK
EMERGENCY TELEPHONE NUMBER: +44 (0) 1432 382200
GENERAL INFORMATION: +44 (0) 1432 382200
FAX: +44 (0) 1432 264030

Special Metals Corporation
4317 Middle Settlement Road
New Hartford, NY, USA 13413-5392
EMERGENCY TELEPHONE NUMBER: +1(315) 798-2900
GENERAL INFORMATION: +1(314) 798-2900

This document does not cover Welding Products.

For Welding Products MSDS, contact:
Special Metals Welding Products Company
1401 Burris Road
Newton, NC, USA 28658
Tel: +1(828) 465-0352
www.specialmetalswelding.com

*For a full list of subsidiary companies, please refer to our website www.specialmetals.com or call +1(304) 526-5100 or toll-free in the USA +1(800) 334-4626.

2. COMPONENT INFORMATION:

The compositions of individual products in the alloy families or categories listed under 1.1 are given in the product composition tables in APPENDIX 1. Please refer to the appropriate alloy name or designation.

3. HAZARDS IDENTIFICATION:

Description of hazards:

As shipped, these complex alloys in massive form have no known toxicological properties other than causing allergic reactions in individuals sensitive to the metals contained in the alloys. Nickel, Cobalt, and some forms of Chromium are known skin sensitizers. Nickel and Cobalt also are classified as suspected carcinogens (EU Category 3). Absent specific test data for the alloy, mixtures (including alloys) that contain more than 1% of a substance are classified in the same manner as that substance.

Hazardous fume or dust emissions may be released during remelting, grinding, cutting or welding. In addition to Nickel and Cobalt, Hexavalent Chromium (a known human inhalation carcinogen – EU Category 2) may be generated during processing activities. If airborne emissions are excessive, inhalation may affect worker health. Further information is given in Section 8 – Exposure Controls / Personal Protection.

In addition, individual products in the above alloy families may contain one or more of the following ingredients, which may be considered hazardous under the legislation indicated:

Special Metals Corporation Material Safety Data Sheet

USA: SARA SECTION 313 SUPPLIER NOTIFICATION: Emergency Planning and Community Right-To-Know Act of 1986 and of 40 CFR 372.

Aluminum	CAS No. 7429-90-5
Chromium	CAS No. 7440-47-3
Cobalt	CAS No. 7440-48-4
Copper	CAS No. 7440-50-8
Iron	CAS No. 7439-89-6
Manganese	CAS No. 7439-96-5
Molybdenum	CAS No. 7439-98-7
Nickel	CAS No. 7440-02-0
Niobium	CAS No. 7440-03-1
Tantalum	CAS No. 7440-25-7
Titanium	CAS No. 7440-32-6
Tungsten	CAS No. 7440-33-7
Yttrium Oxide	CAS No. 1314-36-9

EUROPE

Nickel EC Label No. 231-111-4
Index No. 028-002-00-7
Designation: Xn Harmful
Risk Phrases: R40 Possible risk of irreversible effects.
R43 May cause sensitization by skin contact.

Cobalt EC Label No. 231-158-0
Index No. 027-001-00-9
Designation: Xn Harmful
Risk Phrases: R42/43 May cause sensitization by inhalation and skin contact.
R53 May cause long-term adverse effects in the aquatic environment.

Refer to APPENDIX 1 of this MSDS for the individual alloy name and the percent by weight of the various ingredients in each alloy.
Refer to APPENDIX 2 for detailed information on the toxicological properties of these ingredients.

4. FIRST AID MEASURES:

Eye contact: Flush particles from the eyes with clean water for at least 15 minutes. If irritation persists, seek medical help.
Skin contact: Wash skin with soap and water to remove any metallic particles. If a rash develops, seek medical attention.
Inhalation: Remove from exposure. If respiratory irritation persists, seek medical help.
Ingestion: If symptoms of ingestion arise, seek medical help.

5. FIRE or EXPLOSION HAZARD: Nonflammable, however sparks from welding or grinding in user operations could ignite flammable or combustible liquids, vapors and solids.

6. ACCIDENTAL RELEASE MEASURES:

Vacuum or shovel any spilled material into a suitable container. Alloy wastes are normally collected to recover metal values.

7. HANDLING AND STORAGE:

Under normal circumstances the materials do not produce any hazardous products and as such do not require any special precautions. However, see Section 10, "STABILITY AND REACTIVITY". The transient handling of the materials would not be expected to produce any sensitization but it is good practice to use gloves for handling. The normal precautions for handling heavy objects with possible sharp edges should also be observed.

8. EXPOSURE CONTROLS/PERSONAL PROTECTION:

Respiratory Protection: Respiratory protection is necessary when exposure limits for airborne contaminants are exceeded during cutting, grinding or welding on these alloys. Use air-supplied respirator in confined spaces. In the USA, use only NIOSH-approved respirators in accordance with 29 CFR 1910.134, or other nationally approved respirators. In the EU if required use protection to EN136 (full face respirators), EN140 (half mask respirators), EN149 (filtered half masks (disposable)) or other appropriate EN standard. In the rest of the world use respiratory protection to the appropriate national standard.

Ventilation: Use local exhaust ventilation when cutting, grinding or welding. Maintain exposures below published exposure limits. Confined spaces require special attention to provision of adequate ventilation and/or air-supplied respirators.

Special Metals Corporation Material Safety Data Sheet

Eye Protection and Protective Clothing: Eye protection is recommended when cutting, grinding and welding. Wear gloves, face protection and flame retardant clothing. Do not expose skin or eyes to the heat and radiation from welding operations.

IMPORTANT

Maintain exposures below the published exposure levels. Use industrial hygiene air monitoring to ensure that your use of this material does not create exposures that exceed the recommended exposure limits. Always use exhaust ventilation in user operations such as high temperature cutting, welding and grinding. Refer to the following sources for important additional information:

In U.S.A.: 29 CFR 1910, ANSI Z49.1, American Welding Society, OSHA, U.S. Dept of Labor
In Canada: Canadian Standards Association, CAN/CSA - W17.2-M87
In UK: Current exposure limits under Health & Safety Executive EH40 are given in Appendix 2.

9. PHYSICAL AND CHEMICAL PROPERTIES:

Physical State: Solid Specific Gravity: 8.9 gm/cc Melting Point: >1260° C Odor: Odorless
Appearance: Silver-colored metal shaped as plate, bar, wire, tube, rod, strip, sheet or some intermediate form.

Other physical and chemical properties, e.g. as described in 91/155/EEC and in the Approved Code of Practice, ref. 11 (viscosity, flash point, auto flammability, vapor pressure, solubility and partition coefficient), have no safety implications in relation to these materials.

10. STABILITY AND REACTIVITY:

These alloys are very stable and no hazardous decomposition products are formed upon exposure to water or the atmosphere. Nickel can react with carbon monoxide in reducing atmospheres to form nickel carbonyl, an extremely toxic gas.

11. TOXICOLOGICAL PROPERTIES:

Nickel and cobalt are classified as Category 3 carcinogens. The exposure route of concern is inhalation. Hexavalent Chromium (a known human inhalation carcinogen - EU Category 2) may be generated during processing activities.

As shipped, these complex alloys in massive form have no known toxicological properties other than causing allergic reactions in individuals sensitive to the metal(s) contained in the alloys. However, user-generated dusts and fumes may on contact with the skin or eyes produce mechanical irritation. Chronic exposures coupled with sweat could cause dermatitis (skin) or conjunctivitis (eyes). Excessive inhalation of user-generated fumes from high temperature cutting, remelting or welding of these alloys may, depending on the specific features of the process used, pose a long-term health hazard. The International Agency for Research on Cancer (IARC) has concluded that welding fumes are possibly carcinogenic to humans.

The ingredients of fumes and gases generated in user welding, grind and high temperature cutting operations will depend on the base metal, electrode, flux and the specific process being used. Ingredients may include metals, metal oxides, chromates, fluorides, carbon monoxide, ozone, and oxides of nitrogen. Phosgene can be produced if chlorinated solvent vapors are present in user operations.

More detailed toxicological information is given in APPENDIX 2.

12. ECOLOGICAL EFFECTS:

These alloys are not soluble in water and react only very slowly with natural environments. No special precautions are necessary.

13. DISPOSAL:

Alloy wastes are normally collected to recover metal values. However, if disposal is necessary, dispose of in accordance with national, federal, state or local regulations. In the UK, most alloy material would be classified as special waste.

14. TRANSPORTATION:

No special precautions are necessary for the transport of these materials.

15. REGULATORY INFORMATION:

Classification and labeling requirements

Alloys containing less than 1% of nickel or cobalt are not classified as "dangerous for supply". Alloys containing more than 1% of either metal are classified as the metals themselves (see Section 3). However, in recognition of their essentially non-hazardous nature, these alloys in the massive form are not required to be labeled as hazardous.

16. OTHER INFORMATION:

Bibliography:

1. U.S. National Toxicology Program – 10th Report On carcinogens
 2. Health and Safety Executive UK – EH40 – Occupational exposure limits; EH42 – Monitoring Strategies for toxic substances; EH44 – Dust the Workplace – general principles of protection; EH54 – Assessment of Exposure to Fume from Welding and Allied Processes; EH55 – The Control of Exposure to Fume from Welding, Brazing and Similar Processes; EH60 – Nickel and its inorganic compounds.
 3. EH Health and Safety Executive's publications (www.hse.gov.uk)
 4. HSC. Information approved for the classification, packaging and labeling of dangerous substances for supply and conveyance by road
 5. European Commission Directive 5/3/91 – 91/155/EEC
 6. European Commission Directive 10/12/93 – 93/112/EEC
 7. Twelfth adaptation of Council Directive 67/548/EEC – 91/325/EEC
 8. Sixth amendment of Council Directive 67/548/EEC – 79/831/EEC
 9. The Chemicals (Hazard Information and Packaging for Supply) Regulations 2002 No. 1689
 10. International Agency for Research on Cancer. Monographs on the evaluation of carcinogenic risks to humans. Vol. 49 Chromium Nickel and Welding, 1990.
 11. Approved Code of Practice ISBN 0 7176 0859X
 12. European Norm – EN 1811
-

- 17. PREPARATION INFORMATION:** Prepared By: Health & Environmental Safety Department
Special Metals Corporation
Huntington, WV USA 25705
+1 304 526-5100

It is Special Metals' belief that information set forth in this Material Safety Data Sheet is accurate. Special Metals makes no warranty, expressed or implied, with respect thereto and disclaims any liability from reliance thereon. Users should make their own assessment of workplace risks as required by other health and safety legislation.

APPENDIX 1 – HAZARDOUS INGREDIENTS

The nominal compositions of individual alloys are given in the tables below. The MSDS covers all products thus identified.

Table 1. INCONEL® alloys
Tradename and Nominal Composition (% weight)

Alloy Designation	Aluminum	Chromium	Cobalt	Copper	Iron	Manganese	Molybdenum	Nickel	Niobium	Silicon	Tantalum	Titanium	Tungsten	Yttrium Oxide
INCONEL® alloy 050		20	3		18		9	50	1					
INCONEL® alloy 22	0.2	22			2.5		14	58					3	
INCONEL® alloy 600 & 600T		16			8			76						
INCONEL® alloy 600SP		15			8			77						
INCONEL® alloy 601	1	24			14			61						
INCONEL® alloy 601GC	1	24			14			61						
INCONEL® alloy 603XL		22					3	73		2				
INCONEL® alloy 604		16			8			72	2					
INCONEL® alloy 606		20			1	3		73	3					
INCONEL® alloy 613	1	16			6	1		76						
INCONEL® alloy 617	1	22	13		1		10	53						
INCONEL® alloy 618		23			16			55					6	
INCONEL® alloy 622	0.2	22			2.5		14	58					3	
INCONEL® alloy 625		22			4		9	61	4					
INCONEL® alloy 625LCF		22			4		9	61	4					
INCONEL® alloy 672		45						54			1			
INCONEL® alloy 673	1	37	1		1			58	1			0.5		
INCONEL® alloy 686		21			1		16	58					4	
INCONEL® alloy 690 & 690T		29			9			62						
INCONEL® alloy 691	1	30			9			59			1			
INCONEL® alloy 692	1	30			9	1		57				1		
INCONEL® alloy 693	3	30			5			60	2					
INCONEL® alloy 702	3	16			1			79				1		
INCONEL® alloy 708		16			37			42	3			2		
INCONEL® alloy 718	1	18			18		3	54	5			1		
INCONEL® alloy 718SPF	1	18			18		3	54	5			1		
INCONEL® alloy 721		16			7	2		71				3		
INCONEL® alloy 722	1	16			7			74				3		
INCONEL® alloy 725		21			9		8	58	3			1		
INCONEL® alloy 725HS		21			9		8	58	3			1		
INCONEL® alloy 740	1	25	20		1			49	2			2		
INCONEL® alloy 740H	1.5	25	20		1			49	1.5			1.5		
INCONEL® alloy X-750	1	16			7			72	1			3		
INCONEL® alloy 751	1	15			7			73	1			3		
INCONEL® alloy 783	6	3	35		25			28	3					
INCONEL® alloy C-276		16			6	1	16	57					4	
INCONEL® alloy G		22	1	2	20	1	7	44	2					
INCONEL® alloy G-3		22	3	2	20	1	7	44					1	
INCONEL® alloy HX		22	2		18		9	48					1	
INCONEL® alloy MA754		20						78				1		1
INCONEL® alloy MA758		30						68				1		1
INCONEL® alloy MA6000	5	15					2	69			2	3	4	1
INCONEL® alloy N06230	0.3	22	1		1	0.5	2	60					14	
INCOTERM® alloy TD		22					3	73			2			

® Registered trademarks of the Special Metals Corporation group of companies

Special Metals Corporation Material Safety Data Sheet

**Table 2. INCOLOY®, NILO® and NI-SPAN-C® alloys
Tradename and Nominal Composition (% weight)**

Alloy Designation	Aluminum	Chromium	Cobalt	Copper	Iron	Manganese	Molybdenum	Nickel	Niobium	Silicon	Titanium	Yttrium Oxide	Nitrogen
INCOLOY® alloy 20		20		4	38		3	34	1				
INCOLOY® alloy 28		27			37		4	32					
INCOLOY® alloy 25-6HN		20		0.3	45	0.5	6	25					0.2
INCOLOY® alloy 25-6MO		20		1	45	0.5	6	25					
INCOLOY® alloy 27-7MO		22		1	41	1	7	27					0.35
INCOLOY® alloy 330		19			44			36		1			
INCOLOY® alloy 330Cb		19			42			36	1	1			
INCOLOY® alloy 330HC		19			48			34		1			
INCOLOY® alloy 800		20			45	1		33		1			
INCOLOY® alloy 800H		20			45			33			1		
INCOLOY® alloy 800HT		20			45			33			1		
INCOLOY® alloy 801		20			46	1		32			1		
INCOLOY® alloy 802		21			44	1		33			1		
INCOLOY® alloy 803		27			36	1		35			1		
INCOLOY® alloy 805		8			55	1	1	36			1		
INCOLOY® alloy 825		22		2	29	1	3	42			1		
INCOLOY® alloy 832		20			65			14		1			
INCOLOY® alloy 840		20			59			20		1			
INCOLOY® alloy 864		21			40		4	34		1			
INCOLOY® alloy 865		24			52	0.8	2	21		1.2			0.2
INCOLOY® alloy 890		25			27	1	2	43		2			
INCOLOY® alloy 901		13			36		6	42			3		
INCOLOY® alloy 903	1		15		42			38	3		1		
INCOLOY® alloy 904			15		51			33			2		
INCOLOY® alloy 907			13		42			38	5		2		
INCOLOY® alloy 908	1	4			41			49	3		2		
INCOLOY® alloy 909			13		42			38	5		2		
INCOLOY® alloy 925		21		2	28		3	44			2		
INCOLOY® alloy 945	0.5	21		2	18	0.5	3	50	3		1.5		
INCOLOY® alloy 945X	0.5	21		2	14	0.5	3	53	4		1.5		
INCOLOY® alloy A-286		14			58		1	25			2		
INCOLOY® alloy DS		18			42	1		37		2			
INCOLOY® alloy MA956	5	20			74							1	
INCOLOY® alloy MA957		14			85						1		
NI-SPAN-C® alloy 902		5			49			43		1	2		
NILO® alloy 36					64			36					
NILO® alloy 42					58			42					
NILO® alloy 45					55			45					
NILO® alloy 475		5			48			47					
NILO® alloy 48					52			51					
NILO® alloy 51					49			51					
NILO® alloy 55					44			5					
NILO® alloy K			17		53			30					
NILO® alloy 365					50			44	3.5		1.5		
NILOMAG® alloy 77				5	14		4	77					

® Registered trademarks of the Special Metals Corporation group of companies

Special Metals Corporation Material Safety Data Sheet

Table 3. NIMONIC® and NIMOLOY alloys
Tradename and Nominal Composition (% weight)

Alloy Designation	Aluminum	Chromium	Cobalt	Iron	Manganese	Molybdenum	Nickel	Niobium	Titanium
NIMONIC® alloy 70	1	20		25			51	2	1
NIMONIC® alloy 75		20		4	1		75		
NIMONIC® alloy 80a	1	20					76		2
NIMONIC® alloy 81	1	30		1			66		2
NIMONIC® alloy 86		25				10	65		
NIMONIC® alloy 90	2	20	16	1			58		3
NIMONIC® alloy 91	1	29	20				48		2
NIMONIC® alloy 101	1	24	20			2	49	1	3
NIMONIC® alloy 105		15	20			5	54		1
NIMONIC® alloy 108	5	15	20			5	53		1
NIMONIC® alloy 115	5	15	13			4	59		4
NIMONIC® alloy 263	1	20	20			6	51		2
NIMONIC® alloy 901		13		35		6	43		3
NIMONIC® alloy PE11	1	18		35		5	38		2
NIMONIC® alloy PE16	1	17		34		3	44		1
NIMONIC® alloy PK31		20	14			5	53	5	2
NIMONIC® alloy PK33	2	19	14	1		7	55		2
NIMOLOY alloy PK37	1	19	17				60		2

® Registered trademarks of the Special Metals Corporation group of companies

Table 4. BRIGHTRAY®, KOTHERM® and NIOOTHERM® alloys
Tradename and Nominal Composition (% weight)

Alloy Designation	Chromium	Iron	Nickel	Silicon	Manganese	Copper
BRIGHTRAY® alloy B	16	24	59	1		
BRIGHTRAY® alloy C	20		78	2		
BRIGHTRAY® alloy F	18	42	37	2	1	
BRIGHTRAY® alloy S	20		78	1	1	
BRIGHTRAY® alloy 35	20	42	36	2		
KOTHERM® Positive	10		90			
KOTHERM® Negative			94	3		2
NIOOTHERM® Positive	14		85	1		
NIOOTHERM® Negative			96	4		

® Registered trademarks of the Special Metals Corporation group of companies

Special Metals Corporation Material Safety Data Sheet

Table 5A. Miscellaneous Designations
Tradename and Nominal Composition (% weight)

Alloy Designation	Aluminum	Chromium	Cobalt	Iron	Manganese	Molybdenum	Nickel	Niobium	Rhenium	Tantalum	Titanium	Tungsten	Calcium	Silicon
JBK		15		52		1	30				2			
Nickel 200							99							
Nickel 201							99							
Nickel 205							99							
Nickel 208							96				3			
Nickel 209							95				4			
Nickel 211					4.7		95							
Nickel 212					2		97							
Nickel 213					1		97							
Nickel 222							99							
Nickel 229							99							
Nickel 240		2			2		96							
Nickel 243		2			2		96							
Nickel 270							99							
Nickel-Iron 258	0.3			40	0.5		60				0.3			0.3
Electroformed nickel							99							
DEPOLARIZED nickel							99							
DURVANIC nickel							99							
Mixed nickel alloy revert	0-3	0-20	0-5	20-40	0-1	0-5	30-60	0-1		0-0.5	1-4	0-1	1-4	

© Registered trademarks of the Special Metals Corporation group of companies

Table 5B. Miscellaneous Designations
Tradename and Nominal Composition (% weight)

Alloy Designation	Aluminum	Chromium	Cobalt	Iron	Manganese	Molybdenum	Nickel	Niobium	Tantalum	Titanium	Tungsten	Copper	Nitrogen
13-8	1	13		76		2	8						
304SS		19		71	1		9						
713C	6	14				5	73	2		1			
B300			9	67		5	19						
C1023	4	15	10			8	60			4			
Crutonite	2	16		45			32	2		2			
G255		24		13		7	52				2	1	
GMR235	4	15		4		5	70			3			
GTD222	1	23	19				51		1	2	2		
IN738LC	4	16	8			2	62		2	3	3		
IN738	3	16	9			2	61	1	2	4	3		
M252	1	19	10			10	57			3			
MERC76	5	13	19			3	55	1		4			
NICOCRALY	13	22	23				43						
NiTiFe				2			54			45			
Rene 220		19	12			3	56	5	3				
Rene 77	4	15	15			4	58	5	3				
SR50A		22		50		6	21						0.25
Waspaloy	2	19	13			4	59			3			
X40		26	54				11			8			

© Registered trademarks of the Special Metals Corporation group of companies

Special Metals Corporation Material Safety Data Sheet

Table 6. MONEL® alloys, FERRY® alloy and Cupro 107
Tradename and Nominal Composition (% weight)

Alloy Designation	Aluminum	Copper	Iron	Manganese	Nickel	Silicon	Titanium
MONEL® alloy 400		32	1	1	66		
MONEL® alloy 401		55	1	2	43		
MONEL® alloy 404		46			54		
MONEL® alloy R-405		32	1	1	66		
MONEL® alloy 413		67	1	1	31		
MONEL® alloy 418	1	30		1		2	
MONEL® alloy 418		27		4	66	1	2
MONEL® alloy 450		67	1	1	31		
MONEL® alloy K-500	3	30	1	1	65		1
FERRY® alloy		54			44		
Cupro 107		67	1	1	31		

® Registered trademarks of the Special Metals Corporation group of companies

Table 7. UDIMET® and UDIMAR® alloys
Tradename and Nominal Composition (% weight)

Alloy Designation	Aluminum	Chromium	Cobalt	Iron	Manganese	Molybdenum	Nickel	Niobium	Titanium	Tungsten
UDIMET® alloy R41	2	19	11			10	55		3	
UDIMET® alloy 188		22	40		1		23			14
UDIMET® alloy 500	3	19	18			4	53		3	
UDIMET® alloy 520	2	19	12			6	57		3	1
UDIMET® alloy 700	5	15	19			5	53		4	
UDIMET® alloy 713	6	14				5	73	2		
UDIMET® alloy 718		18		19		3	54	5	1	
UDIMET® alloy 720	3	18	15			3	56		5	1
UDIMET® alloy 706		16		37			42	3	2	
UDIMET® alloy L-605		20	53		2		10			15
UDIMET® alloy D301	5						95			
UDIMET® alloy D979	1	15		28		4	45		3	4
UDIMAR® alloy 250	0.1		8	Bal		5	18		0.5	
UDIMAR® alloy 300	0.1		9	Bal		5	18		0.7	

® Registered trademarks of the Special Metals Corporation group of companies

Table 8. Nitinol alloys
Tradename and Nominal Composition (% weight)

Alloy Designation	Chromium	Cobalt	Copper	Iron	Nickel	Niobium	Titanium
Nickel-Titanium					54-57		43-46
Ni-Ti-Fe				1-7	48-50		43-51
Ni-Ti-Cu			5-10		43-45		46-52
Ni-Ti-Cr	0.2-0.3				54-57		43-46
Ni-Ti-Nb					45-51	13-15	34-42
Ni-Ti-Co		1-2			54-57		41-45

® Registered trademarks of the Special Metals Corporation group of companies

Special Metals Corporation Material Safety Data Sheet

Table 9. INCOCLAD® products

(N.B. these are products containing more than one alloy or component. Nominal compositions are given for each component.)

Tradename and Nominal Composition (% weight)

Alloy Designation	Chromium	Cobalt	Copper	Iron	Molybdenum	Nickel	Niobium	Titanium
INCOCLAD® 625/steel	22			4 95	9	61	4	
INCOCLAD® 671/800H/HT	49 20			45		51 33		

® Registered trademarks of the Special Metals Corporation group of companies

APPENDIX 2

TOXICOLOGICAL AND EXPOSURE LIMIT INFORMATION

The following information is primarily directed to the ingredients of the complex alloys listed in APPENDIX 1. Although it is the user's responsibility to assess end products, intermediates or fugitive emissions arising out of the use of these alloys, information is also provided for common fume ingredients. *UK EH40 limits for the ingredients are shown in italics at the end of each section.*

Aluminum (Al)**Exposure Limits⁽¹⁾:**TVL: 10 mg/m³ (Metal dust); 5 mg/m³ (Welding fumes)PEL: 15 mg/m³ (Total metal dust); 5 mg/m³ (Metal dust – respirable fraction)CAS No.⁽²⁾: 7429-90-5LD₅₀: Not Available

Aluminum is not readily absorbed through the skin or the GI tract and only poorly through the lungs. Foreign literature between 1958 and 1962 reported cases of severe and sometimes fatal pulmonary fibrosis in workers exposed to aluminum dust. In one of the fatal cases, the worker developed fibrosis and encephalopathy after 13.5 years of exposure to aluminum dust.

In rodent studies and currently in US industry, no fibrosis or encephalopathy have been reported from the inhalation of aluminum powder. Acute exposure to alumina fume may cause bronchial irritation, however reports of pulmonary fibrosis and emphysema in alumina abrasive workers are no longer seen, owing to improved environmental control.

EH40- Aluminum metal:

Total inhalable dust OES 10 mg/m³ (8 hours TWA)Total respirable dust OES 4 mg/m³ (8 hours TWA)**Chromium (Cr)****Exposure Limits⁽¹⁾:**TLV: 0.5 mg/m³PEL: 1.0 mg/m³ (Metal as CR); 5 µg/m³ (8 hours TWA) (Chromium VI compounds)CAS No.⁽²⁾: 7440-47-3LD₅₀: Not Available

Chromium metal is relatively nontoxic. Chromium metal and insoluble salts are said to be involved in fibrosis of the lungs. When the metal is heated to a high temperature, fumes produced may be damaging to the lungs if inhaled. The International Agency for Research on Cancer has concluded that the evidence for carcinogenicity in humans and animals is inadequate for chromium metal and trivalent chromium compounds, but sufficient for hexavalent chromium compounds. Fumes from welding chromium-containing stainless steel or certain chromium-containing rods can trigger eczematous eruptions on the palms of the hands of chromium-sensitized individuals.

EH40 – Chromium:

Chromium VI compounds (as Chrome) MEL 0.05 mg/m³ (8 hours TWA)Chromium II compounds (as Chrome) OES 0.5 mg/m³ (8 hours TWA)Chromium III compounds (as Chrome) OES 0.5 mg/m³ (8 hours TWA)Chromium OES 0.5 mg/m³ (8 hours TWA)**Cobalt (Co)****Exposure Limits:**TVL: 0.02 mg/m³ (Dust & fume as Co)PEL: 0.1 mg/m³ (As Co metal)CAS No.⁽²⁾: 7440-48-4LD₅₀: 6,170 mg/kg, rat, oral

Asthmatic symptoms and pulmonary fibrosis occurring in the tungsten carbide industry may be related to the inhalation of metallic cobalt dust. Evidence of polycythemia (an increase in the total red cell mass of the blood in the body) and altered thyroid, kidney and liver function have also been found. Excessive inhalation of metallic cobalt have produced cardiac changes in miniature swine. Eye contact may cause conjunctivitis. Symptoms of excessive ingestion may be a sensation of hotness with vomiting, diarrhea and nausea along with the potential for causing damage to blood, heart, thyroid and pancreas. Repeated skin contact can cause sensitivity and allergic skin rashes. Cobalt powders have caused tumors at the site of injection in rodents. However, studies of cobalt-containing prostheses do not suggest a significant risk for humans.

EH40 – MEL 0.1 mg/m³ (8 hours TWA)

Copper (Cu)**Exposure Limits⁽¹⁾:**TLV: 1 mg/m³ (Dusts & mists, as Cu), 0.2 mg/m³ (Fume)PEL: 1 mg/m³ (Dusts & mists, as Cu); 0.1 mg/m³ (Fume as Cu)CAS No.⁽²⁾: 7440-50-8LD₅₀: 35 mg/kg, mouse, intraperitoneal

Copper metal dust and fume may be irritating to the respiratory tract. In user operations where copper fume is generated, inhalation of the fume can result in symptoms of "Metal Fume Fever" such as chills, fever and sweating. A few instances of allergic skin rashes have been reported in workers with skin exposure to metallic copper. In the eyes, copper metal as foreign body can provoke an inflammatory reaction resulting in pus formation in the conjunctiva, cornea or sclera. Ingestion of copper metal may cause gastrointestinal upset. Wilson's disease can occur in certain individuals with a rare, inherited metabolic disorder characterized by retention of excessive amounts of copper in the liver, brain, kidneys and corneas. These deposits eventually lead to tissue necrosis and fibrosis, causing a variety of clinical effects, especially liver disease and neurological changes. Wilson's disease is progressive and, if untreated, leads to fatal liver failure.

EH40: Fume OES 0.2 mg/m³ (8 hours TWA)Dusts & mists (as Cu) 1.0 mg/m³ (8 hours TWA), 2.0 mg/m³ (15 minute reference period)**Iron (Fe)****Exposure Limits⁽¹⁾:**TLV: No limit set (For Fe₂O₃ fume the TLV is 5 mg/m³ as Fe)PEL: No limit set (For Fe₂O₃ dust & fume the PEL is 10 mg/m³ as Fe)CAS No.⁽²⁾: 7439-89-6LD₅₀: Not Available

Inhalation of the excessive oxide fumes or dusts can lead to irritation of the respiratory tract. Prolonged inhalation of iron oxide for periods of 6 to 10 years is known to cause siderosis which appears to be a benign pneumonconiosis. Prolonged eye contact with the metal dust could cause rust brown colored spots forming around the particles and if left for several years, permanent damage could result.

EH40 – Iron Oxide, fume (as Fe) OES 5.0 mg/m³ (8 hours TWA), 10 mg/m³ (15 minute reference period)**Manganese (Mn)****Exposure Limits⁽¹⁾:**TLV: 0.2 mg/m³ elemental and inorganic compounds, as MnPEL: 5 mg/m³ (Ceiling, as Mn compounds); 5 mg/m³ (Fume, as Mn)CAS No.⁽²⁾: 7439-96-5LD₅₀: 9,000 mg/kg, rat, oral

Excessive inhalation or ingestion of manganese can produce manganese poisoning. Chronic exposures can lead to neurological problems such as apathy, drowsiness, weakness, spastic gait, paralysis, and other neurological problems resembling Parkinsonism. These symptoms can become progressive and permanent if not treated. Excessive inhalation of fumes may cause "Metal Fume Fever" with its flu-like symptoms, such as chills, fever, body aches, vomiting, sweating, etc.

EH40 – Fume (as Mn) OES 1.0 mg/m³ (8 hours TWA), 3.0 mg/m³ (15 minute reference period)Manganese and compounds (as Mn) OES 5.0 mg/m³ (8 hours TWA)**Molybdenum (Mo)****Exposure Limits⁽¹⁾:**TLV: 10 mg/m³ (Insoluble and metal compounds, as Mo)PEL: 15 mg/m³ (Insoluble compounds, total dust as Mo)CAS No.⁽²⁾: 7439-98-7LD₅₀: Not Available

Molybdenum and its insoluble compounds are reported to have low toxicity. High dietary intake may produce a gout-like disease and high blood uric acid. Inhalation of fumes has caused kidney damage, respiratory irritation and liver damage in animals. Skin and eye contact may cause irritation.

EH40 – Molybdenum compounds (as Mo):

Soluble – OES 5.0 mg/m³ (8 hours TWA), 10 mg/m³ (15 minute reference period)Insoluble – OES 10 mg/m³ (8 hours TWA), 20 mg/m³ (15 minute reference period)**Nickel (Ni)****Exposure Limits⁽¹⁾:**TLV: 1.5 mg/m³ as metal (Inhalable Fraction)PEL: 1 mg/m³ for metal and insoluble compounds as Ni

Special Metals Corporation Material Safety Data Sheet

CAS No. ⁽²⁾: 7440-02-0

LD₅₀: >9,000 mg/kg, rat, oral

The U.S. National Toxicology Program (NTP) 10th Report on Carcinogens has listed "metallic nickel" as "reasonably anticipated to be a human carcinogen" and "nickel compounds" as "known human carcinogens". "Nickel Alloys" were reviewed but not listed. The International Agency for Research on Cancer (IARC) concluded that nickel compounds were carcinogenic to humans and that metallic nickel is possibly carcinogenic to humans. Epidemiological studies of workers exposed to nickel powder and to dust and fume generated in the production of nickel alloys and of stainless steel have not indicated the presence of a significant respiratory cancer hazard.

The inhalation of nickel powder has not resulted in an increased incidence of malignant tumors in rodents. Repeated intratracheal instillation of nickel powder produced an increased incidence of malignant lung tumors in rats, but did not produce an increased incidence in hamsters when administered at the maximum tolerated dose. However, single intratracheal instillations of nickel powder in hamsters at doses near the LD₅₀ have produced an increased incidence of fibrosarcomas, mesotheliomas and rhabdomyosarcomas. Inhalation of nickel powder at concentrations 15 times the PEL irritated the respiratory tract in rodents. Nickel is a known sensitizer and may produce allergic reactions.

EH40 – Nickel and its inorganic compounds (except nickel carbonyl)

Water soluble nickel compounds (as nickel) MEL 0.1 mg/m³ (8 hours TWA)

Niobium (Nb)

Exposure Limits⁽¹⁾:

TLV: No limit set

PEL: No limit set

CAS No. ⁽²⁾: 7440-03-1

LD₅₀: Not Available

Also known as Columbium (Cb), there is almost no information on the toxicity of this metal or its fumes. Russian medical literature has described early chest x-ray changes in welders and chemical workers handling niobium and tantalum, but no specific data has been found. It is expected that the metal dust and fumes could cause irritation to the skin, eyes and respiratory tract upon acute exposure.

EH40-40: No limit set.

Tantalum (Ta)

Exposure Limits⁽¹⁾:

TLV: 5 mg/m³ (Metal & oxide dusts)

PEL: 5 mg/m³ (Metal & oxide dusts)

CAS No. ⁽²⁾: 7440-25-7

LD₅₀: Not Available

There are no reports of adverse health effects in industrially exposed workers. Massive doses of tantalum given by the intratracheal route to rats have produced respiratory tract lesions. In contact with tissue, metallic tantalum is inert. Tantalum pentoxide has an LD₅₀ of >8 g/kg, orally in rats.

EH40 – OES 0.5 mg/m³ (8 hours TWA, 10 mg/m³ (15 minute reference period)

Titanium (Ti)

Exposure Limits⁽¹⁾:

TLV: No limit set; 10 mg/m³ (8 hours TWA) (titanium dioxide)

PEL: No limit set; 15 mg/m³ (8 hours TWA) (titanium dioxide)

CAS No. ⁽²⁾: 7440-32-6

LD₅₀: Not Available

Inhalation of titanium could cause mild irritation to the respiratory tract. Inhalation of titanium dioxide dust or fume could produce lung fibrosis and chronic bronchitis.

EH40 – As Titanium dioxide:

Total inhalable dust OES 10 mg/m³ (8 hours TWA), Total respirable dust OES 4 mg/m³ (8 hours TWA)

Tungsten (W)

Exposure Limits⁽¹⁾:

TLV: 5 mg/m³ insoluble compounds, as W

STEL: 10 mg/m³ for insoluble compounds, as W

PEL: No limit set

CAS No. ⁽²⁾: 7440-33-7

LD₅₀: 2,000 mg/kg, rat, unreported route

Inhalation of tungsten dust may cause irritation of the respiratory tract. Skin or eye contact could cause abrasion or irritation of the respective surfaces. No hazards have been identified for tungsten fume except that it may aggravate an existing chronic respiratory disease.

Special Metals Corporation Material Safety Data Sheet

EH40 – No limit set.

Yttrium Oxide (Y_2O_3)

Exposure Limits⁽¹⁾:

TLV: 1 mg/m³ (as Y)

PEL: 1 mg/m³

CAS No. ⁽²⁾: 1314-36-9

LD₅₀: 230 mg/kg, rat, intraperitoneal

Short term inhalation in large amounts could cause discomfort, coughing and nasal discharge similar to the symptoms of a bad cold. Drying of the mucous membranes might be experienced. After intratracheal administration in rats, emphysema and diffused modular fibrosis in the lungs have been reported. The oral toxicity of this material is low as it is poorly absorbed from the gastrointestinal tract. Skin and eye contact should produce no problems other than mechanical irritation.

EH40 – No limit set.

Silicon (Si)

Exposure Limits⁽¹⁾:

PEL: 15 mg/m³ (Total inhalable dust); 5 mg/m³ (Total respirable dust)

EH40 – Total inhalable dust OES 10 mg/m³ (8 hours TWA). Total respirable dust OES 4 mg/m³ (8 hours TWA).

Rhenium (Rh)

EH4 – No limit set.

Calcium (Ca)

EH40 – As oxide OES 2 mg/m³ (8 hours TWA).

- Notes: (1) TLV = Threshold Limit Values – American Conference of Governmental Industrial Hygienists
PEL = Permissible Exposure Limit – OSHA 29 CFR 1910.1000
C = Ceiling value
STEL = Short Term Exposure Limit – a time-weighted 15-minute exposure limit, not to be exceeded at any time during a workday
(2) CAS No. = Chemical Abstracts Services Number



U.S.A.

Special Metals Corp.

3200 Riverside Drive
Huntington, WV 25705
Phone +1 (304) 526-5100
+1 (800) 334-4626
Fax +1 (304) 526-5643

Special Metals Corp.

4317 Middle Settlement Road,
New Hartford, NY 13413
Phone +1 (315) 798-2900
(800) 334-8351
Fax +1 (315) 798-2016

United Kingdom

Special Metals Wiggins Ltd.

Holmer Road
Hereford HR4 9SL
Phone +44 (0) 1432 382200
Fax +44 (0) 1432 264030

Special Metals Wire Prod.

Holmer Road
Hereford HR4 9SL
Phone +44 (0) 1432 382518
Fax +44 (0) 1432 353995

Germany

Special Metals Deutschland Ltd.

Postfach 20 04 09
40102 Düsseldorf
Phone +49 (0) 211 38 63 40
Fax +49 (0) 211 37 00 81

Hong Kong

Special Metals Pacific Pte

Unit A, 17th Floor, On Hing
Bldg
1 On Hing Terrace
Central, Hong Kong
Phone +852 2439 9336
Fax +852 2530 4511

Singapore

Special Metals Pacific Pte Ltd.

24 Raffles Place
#27-04 Clifford Centre
Singapore 048621
Phone +65 6532 3823
Fax +65 6532 3621

China

Special Metals Pacific Pte. Ltd.

Room 2001, Long Tai
International Building
No. 198 Zhongshan East Road
Nanjing 210002, Jiangsu Province
Phone +86 25 8440 1722
Fax +86 25 8451 1822

Special Metals Pacific Pte. Ltd.

Room 16B, Yuntian Plaza
#12 Fengcheng Er Road
Xi'an Economic & Industrial
Development Zone
Xi'an 7100016 P.R. China
Phone +86 29 8210 6151
Fax +86 29 8652 4031

India

Special Metals Services, Ltd.

No. 60, First Main Road,
First Block
Vasanth Vallabha Nagar
Subramanyapura Post
Bangalore 560 061
Phone +91 (0) 80 2666 9159
Fax +91 (0) 80 2666 8918

Affiliated Companies

Special Metals Welding Prod

1401 Burris Road
Newton, NC 28658, U.S.A.
Phone +1 (828) 465-0352
+1 (800) 624-3411
Fax +1 (828) 464-8993

Western Australian Specialty Alloys Pty. Ltd. (WASA)

2-4 Hopewell Street,
Canning Vale;
Western Australia 6155 Australia
Phone 61.8.9455.4111
Fax 61.8.9456.0011

Controlled Products Group

590 Seaman Street
Stoney Creek
Ontario L8E 4H1, Canada
Phone +1 (905) 643-6555
Fax +1 (905) 643-6614

A-1 Wire Tech, Inc.

A Special Metals Company

4550 Kishwaukee Street
Rockford, IL 61109
Phone +1 (815) 226-0477
+1 (800) 426-6380
Fax +1 (815) 226-0537

Daido-Special Metals Ltd

A Joint Venture Company

Daido Shinagawa Building
6-35, Kohnan 1-chome
Minato-ku, Tokyo 108-0075,
Japan
Phone +81 (0) 3 5495 7237
Fax +81 (0) 3 5495 1853

Wyman Gordon

10825 Telge Rd
Houston, TX 77095
Phone +1 (281) 856-9900
Fax +1 (281) 856-3222

Wyman Gordon

400 East Willow
Enid, OK 73701
Phone +1 (580) 237-4212
Fax +1 (281) 856-3222

Wyman Gordon Beijing

Rm 1703, Office Tower 1,
China Central Place
No. 81 Jian'guo Road
Chaoyang District, Beijing
P.R. China 100025
Phone (8610) 5969505
Fax (8610) 59695906

Wyman Gordon

Houston Road
Livingston, West Lothian
EH54 5BZ, Scotland
Phone +44 (0) 1506 446200
Fax +44 (0) 1506 446300

Wyman Gordon

708 South Elmira
Russellville, AR 72802
Phone +1 (479) 968-7555
Fax +1 (281) 856-3222