B125193
R.C. Sheheen

MSDS DIC 7
January 1, 2003

DuPont Performance Coatings
MATERIAL SAFETY DATA SHEET
EPOXY PRIMERS, ENAMELS, AND ACTIVATORS

SECTION 1 - Product and Company Identification

Manufacturer: E.I. du Pont de Nemours & Co.
du Pont Performance Coatings
Wilmington, DE, 19898

Telephone:
Product Information: (800) 441-7515
Medical Emergency: (800) 441-3637
Transportation Emergency: (800) 424-9300 (CHEMTREC)

Product: **EPOXY PRIMERS, ENAMELS, AND ACTIVATORS**

DOT Shipping Name: See DOT addendum.

Hazardous Materials Information: See Section 10.

SECTION 2 - Composition, Information on Ingredients

INGREDIENTS	CAS #	VAPOR PRESSURE	EXPOSURE LIMITS
ACRYLIC POLYMER-A	26010-51-5	None	A None O None
ACRYLIC POLYMER-B	42767-92-0	None	A None O None
ACRYLIC POLYMER-C	148969-95-3	None	A None O None
ALUMINUM	7429-90-5	None	A 10.0 mg/m³ O 15.0 mg/m³ Total Dust O 5.0 mg/m³ Respirable Dust
ALUMINUN HYDRATE	21645-51-2	None	A None O None
AMIDOAMINE RESIN-A	Not Avail	None	A None O None
AMIDOAMINE RESIN-B	64754-99-0	None	A None O None
AMIDOAMINE RESIN-C	68443-08-3	None	A None O None
AMINE SALT OF POLYCARBONIC ACID	Not Avail	None	A None O None
AMORPHOUS SILICA-A	7631-86-9	None	D 3.0 mg/m³ 8 hr PEL O 20.0 mppcf2 A 10.0 mg/m³ Total Dust
AMORPHOUS SILICA-B	92797-60-9	None	O 1.0 mg/m³ 15 min STEL D 1.0 mg/m³ Respirable Dust A 2.0 mg/m³ Respirable Dust

MSDS DIC 7
January 1, 2003

AMORPHOUS SILICA-FUMED			
	68611-44-9	None	D 1.0 mg/m³ Respirable Dust A 2.0 mg/m³ Respirable Dust O None
AROMATIC HYDROCARBON-A	64742-94-5	10.0	D 100.0 ppm A None O None
AROMATIC HYDROCARBON-B	64742-95-6	10.0 @ 25.0°C	D 50.0 ppm A None O None
BARIUM SULFATE	7727-43-7	None	A 10.0 mg/m³ Total Dust D 10.0 mg/m³ Total Dust O 15.0 mg/m³ Total Dust O 15.0 mg/m³ Respirable Dust
BENZYL ALCOHOL	100-51-6	0.1 @ 30.0°C	D 10.0 ppm A None O None
BISPHENOL A/EPICHLOROHYDRIN POLYMER	25036-25-3	2.7 @ 23.9°C	A None O None
BISPHENOL-EPICHLOROHYDRIN TYPE POLYMER	25068-38-6	0.0 @ 77.0°C	A None O None
BLACK IRON OXIDE	1317-61-9	None	A None O None
BUTYL ACETATE	123-86-4	10.0	A 200.0 ppm 15 min STEL A 150.0 ppm O 150.0 ppm
CALCIUM CARBONATE	471-34-1	None	A 10.0 mg/m³ O 15.0 mg/m³ A 5.0 mg/m³ Respirable Dust
CALCIUM PHOSPHOSILICATE	Not Avail	None	A None O None
CARBON BLACK	1333-86-4	None	A 3.5 mg/m³ O 3.5 mg/m³

			D 0.5 mg/m³ 8 & 12 hour TWA
CUMENE			
	98-82-8	3.7	A 50.0 ppm O 50.0 ppm Skin
DIACETONE ALCOHOL			
	123-42-2	1.1 @ 200.0°C	A 50.0 ppm TLV O 50.0 ppm TWA
DIATOMACEOUS EARTH			
	7631-86-9	None	A 1.0 mg/m³ 15 min STEL O 15.0 mg/m³ A 0.2 mg/m³ Respirable Dust O 5.0 mg/m³ Respirable Dust
DIISOBUTYL KETONE			
	108-83-8	1.7	A 25.0 ppm O 50.0 ppm
DIOCTYL PHTHALATE			
	117-81-7	1.2	A 5.0 mg/m³ D 1.0 mg/m³ 8 & 12 hour TWA O None
Epoxy hardener			
	1477-55-0	None	A 0.1 mg/m³ TWA Skin O 0.1 mg/m³ TWA Skin
ETHYL ACETATE			
	141-78-6	76.0	A 400.0 ppm O 400.0 ppm
ETHYLBENZENE			
	100-41-4	7.0	A 125.0 ppm 15 min STEL A 100.0 ppm O 100.0 ppm D 25.0 ppm 8 & 12 hour TWA
ETHYLENE GLYCOL MONOBUTYLETHER			
	111-76-2	0.6	A 20.0 ppm D 5.0 ppm Skin O 50.0 ppm Skin
GLYCIDYL ESTER OF TERT CARBOXYLIC ACID			
	26761-45-5	2.5 @ 212.0°F	A None O None
GLYCIDYL ETHER OF ALKYL PHENOL			
	171263-24-1	None	A None O None

							A 2.0 mg/m³ Respirable Dust
HYDROUS MAGNESIUM SILICATE	14807-96-6	None	A 2.0 mg/m³ Respirable Dust D 0.5 mg/m³ 8 & 12 hour TWA Respirable Dust O None	LIGHT YELLOW LEMON YELLOW OXIDE PIGMENT	51274-00-1	None	A None O None
IRON OXIDE	1309-37-1	None	A 5.0 mg/m³ O 10.0 mg/m³	MEDIUM MINERAL SPIRITS	64742-88-7	2.0 @ 68.0°F	D 50.0 ppm 8 & 12 hour TWA A None O None
ISOINDOLINONE PIGMENT	36888-99-0	None	A None O None	METHYL AMYL KETONE	110-43-0	2.8	A 50.0 ppm O 100.0 ppm
ISOPROPYL ALCOHOL	67-63-0	33.0	A 500.0 ppm 15 min STEL A 400.0 ppm O 400.0 ppm D 400.0 ppm 8 & 12 hour TWA	METHYL ETHYL KETONE	78-93-3	71.0 @ 0.0	A 300.0 ppm 15 min STEL D 300.0 ppm 15 min TWA A 200.0 ppm O 200.0 ppm D 200.0 ppm 8 & 12 hour TWA
KAOLIN	1332-58-7	None	O 10.0 mg/m³ TWA Total Dust O 5.0 mg/m³ TWA Respirable Dust	METHYL ISOBUTYL KETONE	108-10-1	15.0	A 75.0 ppm 15 min STEL A 50.0 ppm O 100.0 ppm

					Not Avail	None	A None
MICA							O None
	12001-26-2	None	A 3.0 mg/m³				
			Respirable Dust	PARA-NONYLPHENOL			
			O None		84852-15-3	None	A None
							O None
MONOAZO PIGMENT							
	12236-62-3	None	A 10.0 mg/m³	PHENOLIC POLYMER			
			Inhalable dust		9003-35-4	None	A None
			Particulate				O None
			O None				
				PHTHALOCYANINE BLUE PIGMENT			
					147-14-8	None	O 15.0 mg/m³
N-BUTYL ALCOHOL							Total Dust
	71-36-3	4.2 @ 68.0°F	D 50.0 ppm				PNOR
			15 min TWA				O 5.0 mg/m³
			A 20.0 ppm				TWA
			D 25.0 ppm				Respirable Dust
			O 50.0 ppm				PNOR
			CEIL				A 10.0 mg/m³
			Skin				Inhalable dust
							PNOC
NAPHTHALENE							A 3.0 mg/m³
	91-20-3	1.0 @ 52.6°C	A 10.0 ppm				Respirable
			O 10.0 ppm				Particulate
			D 0.1 ppm				PNOC
			8 & 12 hour				
			TWA	POLYAMIDE RESIN			
ORGANOCLAY					68410-23-1	None	A None
	68911-87-5	None	A None				O None
			O None				
				PROPYLENE CARBONATE			
ORGANOPHILIC CLAY					108-32-7	0.0	A None

			O None
PROPYLENE GLYCOL MONOMETHYL ETHER ACETATE			
	108-65-6	3.7	D 10.0 ppm 8 & 12 hour TWA A None O None
QUARTZ-CRYSTALLINE SILICA			
	14808-60-7	None	O 0.1 mg/m³ Respirable Dust D 0.1 mg/m³ Respirable Dust A 50.0 ug/m³ Respirable Dust
QUINACRIDONE PIGMENT			
	1047-16-1	None	O 15.0 mg/m³ Total Dust PNOR A 10.0 mg/m³ Inhalable dust A 3.0 mg/m³ Respirable Particulate
TETRAETHYLENEPENTAMINE			
	112-57-2	None	A None O None
TETRAHYDROFURAN			
	109-99-9	160.0@25.0°C	D 75.0 ppm 15 min TWA A 250.0 ppm 15 min STEL A 200.0 ppm D 50.0 ppm 8 & 12 hour TWA O None
TITANIUM DIOXIDE			
	13463-67-7	None	A 10.0 mg/m³ D 10.0 mg/m³ Total Dust O 15.0 mg/m³ Total Dust D 5.0 mg/m³ Respirable Dust
TITANIUM DIOXIDE/ALUMINUM HYDRATE/AMORPHOUS SILICA			
	Not Avail	None	A None O None
TOFA, REACTION PRODUCTS W/TEPA			
	68953-36-6	20.6 @ 21.0°C	A None O None
TOLUENE			
	108-88-3	22.0	O 300.0 ppm CEIL O 500.0 ppm 10 min TWA O 200.0 ppm D 50.0 ppm 8 & 12 hour TWA A 50.0 ppm

			Skin	1,2,4-TRIMETHYL BENZENE			
					95-63-6	7.0 @ 44.4°C	A 25.0 ppm
TRADE SECRET							O 25.0 ppm
	Not Avail	7.5 @ 21.0°F	A None				
			O None	2-ETHYLHEXYL GLYCIDYL ETHER			
					Not Avail	None	A None
							O None
UREA FORMALDEHYDE RESIN							
	68002-19-7	5.5	A None				
			O None				
				2,4,6- TRI((DIMETHYLAMINO)METHYL) PHENOL			
					90-72-2	0.0 @ 21.0°C	A None
XYLENE							O None
	1330-20-7	9.0 @ 25.0°C	A 150.0 ppm				
			15 min STEL	4,6-DIMETHYL-2-HEPTANONE			
					19549-80-5	None	A None
			D 150.0 ppm				
							O None
			15 min STEL				
			A 100.0 ppm				
			O 100.0 ppm				
			D 100.0 ppm				
			8 & 12 hour TWA				
YELLOW IRON OXIDE							
	51274-00-1	None	A 5.0 mg/m³				
			O 10.0 ppm				
ZINC OXIDE							
	1314-13-2	None	A 10.0 mg/m³				
			Total Dust				
			O 15.0 mg/m³				
			Total Dust				
			O 5.0 mg/m³				
			Respirable Dust				

*A=ACGIH, O=OSHA, D=DuPont, S=Suppliers. Limits are 8 hour TWA unless otherwise specified. Vapor pressure @25°C unless otherwise noted.

SECTION 3 - Hazards Information

Potential Health Effects:

Inhalation:

May cause nose and throat irritation. May cause nervous system depression characterized by the following progressive steps: headache, dizziness, nausea, staggering gait, confusion, unconsciousness. Reports have associated repeated and prolonged overexposure to solvents with permanent brain and nervous system damage.

Ingestion:

May result in gastrointestinal distress.

Skin or eye contact:

May cause irritation or burning of the eyes. Repeated or prolonged liquid contact may cause skin irritation with discomfort and dermatitis.

Other Potential Health Effects in addition to those listed above:

ACRYLIC POLYMER-A

May cause temporary upper respiratory and/or lung irritation with cough, difficult breathing, or shortness of breath.
Contact may cause skin irritation with discomfort or rash.
May cause eye irritation with discomfort, tearing, or blurred vision.

ACRYLIC POLYMER-B

Skin contact may cause any of the following: mild irritation

AMIDOAMINE RESIN-B

Contact may cause skin irritation with discomfort or rash.
Causes eye corrosion and permanent injury.

AMIDOAMINE RESIN-C
Contact may cause skin irritation with discomfort or rash.
Contact may cause skin burns.
Causes eye corrosion and permanent injury.
Causes severe eye irritation.

AROMATIC HYDROCARBON-A
Laboratory studies with rats have shown that petroleum distillates can cause kidney damage and kidney or liver tumors. These effects were not seen in similar studies with guinea pigs, dogs, or monkeys. Several studies evaluating petroleum workers have not shown a significant increase of kidney damage or an increase in kidney or liver tumors.

AROMATIC HYDROCARBON-B
Laboratory studies with rats have shown that petroleum distillates can cause kidney damage and kidney or liver tumors. These effects were not seen in similar studies with guinea pigs, dogs, or monkeys. Several studies evaluating petroleum workers have not shown a significant increase of kidney damage or an increase in kidney or liver tumors.

BENZYL ALCOHOL
Material is irritating to mucous membranes and upper respiratory tract. May cause central nervous system effects such as dizziness, headache, nausea, and loss of consciousness. Contact may cause skin irritation with discomfort or rash. May cause eye irritation with discomfort, tearing, or blurred vision. May be a weak skin sensitizer. Skin permeation can occur in amounts capable of producing the effects of systemic toxicity.

BISPHENOL A/EPICHLOROHYDRIN POLYMER
Has shown mutagenic activity in laboratory cell culture tests.
Repeated exposure may cause allergic skin rash, itching, swelling.

BISPHENOL-EPICHLOROHYDRIN TYPE POLYMER
The following medical conditions may be aggravated by exposure: skin disorders
Vapor may be irritating at elevated temperatures. Repeated or prolonged skin contact may cause any of the following: allergic skin rash

BUTYL ACETATE
May cause abnormal liver function. The following medical conditions may be aggravated by exposure: respiratory system
Tests for embryotoxic activity in animals has been inconclusive. Rats exposed to very high airborne levels have exhibited high frequency hearing deficits. The significance of this to man is unknown. Has been toxic to the fetus in laboratory animals at doses that are toxic to the mother.

CALCIUM PHOSPHOSILICATE
Ingestion may cause any of the following: nausea vomiting gastrointestinal irritation diarrhea
Repeated or prolonged eye contact may cause any of the following: corneal injury
The following medical conditions may be aggravated by overexposure: lung disease pulmonary condition

CARBON BLACK
Is an IARC, NTP or OSHA carcinogen. Has shown carcinogenic activity in laboratory animals at high doses. Significance to man is unknown. The following medical conditions may be aggravated by exposure: asthma respiratory disease

CUMENE
Skin contact may cause any of the following: irritation discomfort rash
Eye contact may cause any of the following: blurred vision irritation discomfort tearing

DIACETONE ALCOHOL
Recurrent overexposure may result in liver and kidney injury.

DIATOMACEOUS EARTH
Repeated and prolonged overexposure may lead to chronic lung disease.

DIISOBUTYL KETONE
The following medical conditions may be aggravated by exposure: asthma blood dermatitis
Contact may cause skin irritation with discomfort or rash.
Repeated exposure may cause allergic skin rash, itching, swelling.
This substance may cause damage to any of the following organs/systems: eyes kidneys liver
Extremely high oral and inhalation doses in laboratory animals have shown weight changes in various organs such as the liver, kidney, brain, heart and adrenal gland. In addition liver and kidney injury were observed at the extremely high inhalation level. In another inhalation study there was a slight depression in the white blood cell count. Liquid or vapor causes irritation, experienced as stinging, excess blinking and tear production, with excess redness and swelling of the conjunctiva.

DIOCTYL PHTHALATE
Cancer hazard based on tests with laboratory animals.
Overexposure may create cancer risk. Tests in animals demonstrate reproductive toxicity.

EPOXY HARDENER
If ingested, may be: moderately toxic
Skin or eye contact may cause any of the following: severe irritation

ETHYL ACETATE
Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: eyes respiratory system skin
Tests in laboratory animals have shown effects on any of the following organs/systems: blood kidneys liver

ETHYLBENZENE
Is an IARC, NTP or OSHA carcinogen. Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: central nervous system kidneys liver lungs
Recurrent overexposure may result in liver and kidney injury.
Studies in laboratory animals have shown reproductive, embryotoxic and developmental effects.

ETHYLENE GLYCOL MONOBUTYLETHER
Increased susceptibility to the effects of this material may be

observed in people with preexisting disease of any of the following: bone marrow central nervous system eyes gastrointestinal system kidneys liver respiratory system skin
May cause injury to the kidneys, liver, blood and/or bone marrow. Repeated overexposure may result in damage to the blood. Eye contact may cause corneal injury. Has been toxic to the fetus in laboratory animals at doses that are toxic to the mother.
If absorbed through the skin, may be: harmful
DuPont has classified this as: not likely to be a human carcinogen

GLYCIDYL ESTER OF TERT CARBOXYLIC ACID

May cause eye irritation with discomfort, tearing, or blurred vision. High doses in laboratory animals have shown non-specific effects such as irritation, weight loss, moderate blood changes.

GLYCIDYL ETHER OF ALKYL PHENOL

Contact may cause skin irritation with discomfort or rash.
May cause eye irritation with discomfort, tearing, or blurred vision.

ISOPROPYL ALCOHOL

The following medical conditions may be aggravated by exposure: dermatitis respiratory disease
Developmental toxicity was seen in rat's offspring at doses that were maternally toxic. Contact will cause moderate to severe redness and swelling, itching, tingling sensation, painful burning. May cause injury to the cornea of the eyes. Prolonged or repeated exposure may cause damage to any of the following organs/systems: liver
Ingestion studies on laboratory animals showed that very high oral doses caused increased liver and kidney weights.

KAOLIN

The following medical conditions may be aggravated by exposure: asthma dermatitis
Repeated or prolonged inhalation may cause any of the following: lung injury

LIGHT YELLOW LEMON YELLOW OXIDE PIGMENT

Contact may cause skin irritation with discomfort or rash.
May cause eye irritation with discomfort, tearing, or blurred vision.

MEDIUM MINERAL SPIRITS

Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: central nervous system kidneys liver respiratory system skin
This substance may cause damage to any of the following organs/systems: blood central nervous system eyes kidneys liver lungs reproductive system skin
Laboratory studies with rats have shown that petroleum distillates can cause kidney damage and kidney or liver tumors. These effects were not seen in similar studies with guinea pigs, dogs, or monkeys. Several studies evaluating petroleum workers have not shown a significant increase of kidney damage or an increase in kidney or liver tumors.

METHYL ETHYL KETONE

Material is irritating to mucous membranes and upper respiratory tract. Persons with certain types of neurological disease such as multiple sclerosis should consult a physician prior to exposure. Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: central nervous system eyes respiratory system skin
Contact may cause skin irritation with discomfort or rash. Can irritate or burn eyes. Prolonged or repeated overexposure may cause any of the following: conjunctivitis dermatitis
High concentrations have caused embryotoxic effects in laboratory Animals. Methyl ethyl ketone has been demonstrated to potentiate (i.e., shorten the time of onset) the peripheral neuropathy caused by either n-hexane or methyl n-butyl ketone. MEK by itself has not been demonstrated to cause peripheral neuropathy. Mice that were force fed (gavage) showed teratogenic effects embryofetotoxicity and maternal toxicity. The no observed effect level was estimated to be 25g/50 kg (110 lb.) woman. Laboratory animals exposed to high airborne levels showed tissue changes in the nasal passages. Aspiration may occur during swallowing or vomiting, resulting in lung damage. May cause central nervous system depression with headache, stupor, uncoordinated or strange behavior, or unconsciousness.

METHYL ISOBUTYL KETONE

The following medical conditions may be aggravated by exposure: asthma respiratory disease eye disorders pulmonary condition skin disorders
Repeated or prolonged skin contact may cause any of the following: dryness cracking of the skin defatting
Inhalation may cause any of the following: dizziness stupor (central nervous system depression) drowsiness respiratory tract irritation

MICA

Repeated and prolonged overexposure may lead to chronic lung disease.

N-BUTYL ALCOHOL

May cause abnormal blood forming function with anemia.
Liquid splashes in the eye may result in chemical burns.

NAPHTHALENE

Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: kidneys liver
Recurrent overexposure may result in liver and kidney injury.
WARNING: This chemical is known to the State of California to cause cancer.

PROPYLENE GLYCOL MONOMETHYL ETHER ACETATE

May cause eye irritation with discomfort, tearing, or blurred vision. May cause moderate eye burning. Recurrent overexposure may result in liver and kidney injury. May cause irritation of the upper respiratory passages.

QUARTZ-CRYSTALLINE SILICA

Is an IARC, NTP or OSHA carcinogen. Repeated overexposure to crystalline silica may lead to x-ray changes and chronic lung disease.
WARNING: This chemical is known to the State of California to cause cancer.

TETRAETHYLENEPENTAMINE

Causes eye corrosion and permanent injury. Contact will cause moderate to severe redness and swelling, itching, tingling sensation, painful burning. Inhalation overexposure may cause lung injury, fluid in the lung, and difficulty in breathing.
Inhalation of vapor may cause any of the following:

TETRAHYDROFURAN

Tests in some laboratory animals demonstrate carcinogenic activity. May cause temporary upper respiratory and/or lung irritation with cough, difficult breathing, or shortness of breath. May cause abnormal liver function. Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: liver lungs
Contact may cause skin irritation with discomfort or rash. May cause eye irritation with discomfort, tearing, or blurred vision. Can be absorbed through the skin in harmful amounts. Liquid splashes in the eye may result in chemical burns. Has been toxic to the fetus in laboratory animals at doses that are toxic to the mother. May cause central nervous system depression with headache, stupor, uncoordinated or strange behavior, or unconsciousness. Inhalation may cause headache and drowsiness.

TITANIUM DIOXIDE

In a lifetime inhalation test, lung cancers were found in some rats exposed to 250 mg/m^3 respirable titanium dust. Analysis of the titanium dioxide concentrations in the rat's lungs showed that the lung clearance mechanism was overwhelmed and that the results at the massive 250 mg/m^3 level are not relevant to the workplace.

TOFA, REACTION PRODUCTS W/TEPA

Contact may cause skin irritation with discomfort or rash.
May cause eye irritation with discomfort, tearing, or blurred vision.

TOLUENE

Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: central nervous system kidneys liver respiratory system skin
Can be absorbed through the skin in harmful amounts.
Recurrent overexposure may result in liver and kidney injury.
High airborne levels have produced irregular heartbeats in animals and occasional palpitations in humans. Rats exposed to very high airborne levels have exhibited high frequency hearing deficits. The significance of this to man is unknown.
WARNING: This chemical is known to the State of California to cause birth defects or other reproductive harm.

UREA FORMALDEHYDE RESIN

This chemical is a formaldehyde donor. Formaldehyde is an IARC, NTP or OSHA carcinogen and has shown mutagenic activity in laboratory cell culture tests. Formaldehyde has produced tumors in the nasal passages of laboratory animals when exposed to high concentrations for a two year period. Epidemiology studies conducted to date have not found evidence of formaldehyde related tumor induction in humans.
WARNING: This chemical is known to the State of California to cause cancer.

XYLENE

Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: bone marrow cardiovascular system central nervous system kidneys liver lungs
Recurrent overexposure may result in liver and kidney injury.
High exposures may produce irregular heartbeats. Canada classifies Xylene as a developmental toxin as high exposures to xylenes in some animal studies have been reported to cause health effects on the developing fetus/embryo. These effects were often at levels toxic to the adult animal. The significance of these effects to humans is not known. Repeated or prolonged skin contact may cause any of the following: irritation dryness cracking of the skin

YELLOW IRON OXIDE

Eye contact may cause any of the following: mechanical irritation

2,4,6- TRI((DIMETHYLAMINO)METHYL) PHENOL

The following medical conditions may be aggravated by exposure: asthma respiratory disease eye disorders skin disorders
Skin contact may cause any of the following: severe irritation burns
Eye contact may cause any of the following: severe irritation burns blindness
Repeated or prolonged exposure may cause effects on any of the following organs/systems: nervous system respiratory system skin and eyes

SECTION 4 - First Aid Measures

First Aid Procedures:

Inhalation:

If affected by inhalation of vapor or spray mist, move to fresh air. If not breathing, give artificial respiration, preferably mouth-to-mouth. If breathing difficulty persists, or occurs later, consult a physician.

Ingestion:

In the unlikely event of ingestion, DO NOT INDUCE VOMITING. Call a physician immediately and have names of ingredients available.

Skin or eye:

In case of eye contact, immediately flush with plenty of water for at least 15 minutes; call a physician. In case of skin contact, wash thoroughly with soap and water. If irritation occurs, contact a physician.

SECTION 5 - Firefighting Measures

Flash Point (Closed Cup) See Section 11 for exact values.
Flammable limits LFL 0.0 % UFL 13.1 %

Extinguishing media:

Universal aqueous film-forming foam, carbon dioxide, dry chemical.

Fire fighting procedures:

Full protective equipment, including self-contained breathing apparatus, is recommended. Water from fog nozzles may be used to prevent pressure build-up.

Fire & explosion hazards:

For flammable liquids, vapor/air will ignite when an ignition source is present. In other cases, when heated above the flash point, emits flammable vapors which, when mixed with air, can burn or be explosive. Fine mists or sprays may be flammable at temperatures below the flash point.

SECTION 6 - Accidental Release Measures

Steps to be taken in case material is released or spilled:

Ventilate area. Remove sources of ignition. Prevent skin and eye contact and breathing of vapor. Wear a properly fitted air-purifying respirator with organic vapor cartridges (NIOSH approved TC-23C), eye protection, gloves and protective clothing. Confine, remove with inert absorbent, and dispose of properly.

SECTION 7 - Handling and Storage

Precautions to be taken in handling and storing:
Observe label precautions. If combustible (flashpoint between 100 - 200°F), keep away from heat, sparks and flame. If flammable (flashpoint less than 100°F), also keep away from static discharges and other sources of ignition. If material is extremely flammable (flashpoint less than 20°F) or flammable, VAPORS MAY IGNITE EXPLOSIVELY OR CAUSE FLASH FIRE, respectively. Vapors may spread long distances. Prevent buildup of vapors. Close container after each use. Ground containers when pouring. Wash thoroughly after handling and before eating or smoking. Do not store above 120°F. If product is waterbased, do not freeze.

Other precautions:
If material is a coating: do not sand, flame cut, braze or weld dry coating without a NIOSH approved respirator or appropriate ventilation, and gloves.

SECTION 8 - Exposure Controls or Personal Protection

Engineering controls and work practices:
Ventilation:
Provide sufficient ventilation in volume and pattern to keep contaminants below applicable exposure limits.

Respiratory:
Do not breathe vapors or mists. Wear a properly fitted air-purifying respirator with organic vapor cartridges (NIOSH approved TC-23C) and particulate filter (NIOSH TC-84A) during application and until all vapors and spray mists are exhausted. In confined spaces, or in situations where continuous spray operations are typical, or if proper air-purifying respirator fit is not possible, wear a positive pressure, supplied-air respirator (NIOSH TC-19C). In all cases, follow respirator manufacturer s directions for respirator use. Do not permit anyone without protection in the painting area.

Protective clothing:
Neoprene gloves and coveralls are recommended.

Eye protection:
Desirable in all industrial situations. Goggles are preferred to prevent eye irritation. If safety glasses are substituted, include splash guard or side shields.

SECTION 9 - Physical and Chemical Properties

Evaporation Rate	Slower than Ether
Solubility in water	NIL
Vapor Density	Heavier than air
Approx. boiling range (°C)	No Data Available
Approx. freezing range (°C)	-92 - -88°(C)
Gallon weight (lbs./gal)	7.69 - 13.96
Specific gravity	0.92 - 1.67
Percent volatile by volume	1.79 - 52.43
Percent volatile by weight	0.96 - 43.55
Percent solids by volume	47.57 - 98.21
Percent solids by weight	56.46 - 99.05

SECTION 10 - Stability and Reactivity

Stability:
Stable

Incompatibility (materials to avoid):
None reasonably foreseeable

Hazardous decomposition products:
CO, CO_2, smoke, and oxides of any heavy metals that are reported in "Composition, Information on Ingredients" section.

Hazardous polymerization:
Will not occur.

Sensitivity to static discharge:
For flammable materials (flashpoint less than 100°F) and combustibles (flashpoint between 100-200°F) if heated above the flashpoint, solvent vapors in air may explode if static grounding and bonding is not used during transfer of this product.

Sensitivity to mechanical impact:
Not Applicable

SECTION 11 - Additional Information

PRODUCT CODE **INGREDIENTS (Product Specific)**

1LB25P™ Amidoamine Resin-B (14.8%), Amorphous Silica-A (1.6%), Aromatic Hydrocarbon-B (9.9%), Calcium Phosphosilicate (5.1%), Glycidyl Ether Of Alkyl Phenol (11.4%), Hydrous Magnesium Silicate (2.8%), Mica (18.6%), Quartz-Crystalline Silica (1.0%), Titanium Dioxide (25.3%), 1,2,4-Trimethyl Benzene (2-7%*), 2,4,6- Tri((Dimethylamino)Methyl) Phenol (1.5%)
GAL WT: 12.87 WT PCT SOLIDS: 83.97 VOL PCT SOLIDS: 71.43
SOLVENT DENSITY: 7.22 VOC LE: 2.1 VOC AP: 2.1
FLASH POINT: 100°F - 141°F H: 3 F: 2 R: 1 OSHA STORAGE: II
TSCA STATUS: In compliance PHOTOCHEMICALLY REACTIVE: YES

2MB25P™ Amidoamine Resin-B (16.9%), Amorphous Silica-A (1.0%), Aromatic Hydrocarbon-B (11.0%), Calcium Phosphosilicate (6.1%), Cumene (0-1%*@), Glycidyl Ether Of Alkyl Phenol (13.0%), Hydrous Magnesium Silicate (3.3%), Mica (23.1%), Quartz-Crystalline Silica (1.2%), Titanium Dioxide (14.2%), 1,2,4-Trimethyl Benzene (2-8%*), 2,4,6- Tri((Dimethylamino)Methyl) Phenol (1.8%)
GAL WT: 11.87 WT PCT SOLIDS: 82.16 VOL PCT SOLIDS: 70.66
SOLVENT DENSITY: 7.22 VOC LE: 2.1 VOC AP: 2.1
FLASH POINT: 100°F - 141°F H: 3 F: 2 R: 1 OSHA STORAGE: II
TSCA STATUS: In compliance PHOTOCHEMICALLY REACTIVE: YES

3DB25P™ Amidoamine Resin-B (18.9%), Aromatic Hydrocarbon-B (10.4%), Calcium Phosphosilicate (6.6%), Glycidyl Ether Of Alkyl Phenol (14.5%), Hydrous Magnesium Silicate (3.6%), Mica (26.6%), Quartz-Crystalline Silica (1.4%), Titanium Dioxide (7.5%), 1,2,4-Trimethyl Benzene (2-7%*), 2,4,6- Tri((Dimethylamino)Methyl) Phenol (2.0%)
GAL WT: 11.44 WT PCT SOLIDS: 83.02 VOL PCT SOLIDS: 73.08
SOLVENT DENSITY: 7.22 VOC LE: 1.9 VOC AP: 1.9
FLASH POINT: 100°F - 141°F H: 3 F: 2 R: 1 OSHA STORAGE: II
TSCA STATUS: In compliance PHOTOCHEMICALLY REACTIVE: YES

4NB25P™ Amidoamine Resin-B (19.9%), Aromatic Hydrocarbon-B (12.6%), Calcium Phosphosilicate (6.9%), Cumene (0-1%*@), Glycidyl Ether Of Alkyl Phenol (15.3%), Hydrous Magnesium Silicate (3.8%), Mica (28.7%), Quartz-Crystalline Silica (1.5%), 1,2,4-Trimethyl Benzene (2-9%*), 2,4,6 Tri((Dimethylamino)Methyl) Phenol (2.1%)
GAL WT: 10.73 WT PCT SOLIDS: 79.61 VOL PCT SOLIDS: 69.69
SOLVENT DENSITY: 7.22 VOC LE: 2.2 VOC AP: 2.2
FLASH POINT: 100°F - 141°F H: 3 F: 2 R: 1 OSHA STORAGE: II
TSCA STATUS: In compliance PHOTOCHEMICALLY REACTIVE: YES

MSDS DIC 7
EPOXY PRIMERS, ENAMELS, AND ACTIVATORS
January 1, 2003

LF-6AL25P™ Aluminum (24.3%*), Amidoamine Resin-B (19.0%), Amorphous Silica-A (2.4%), Aromatic Hydrocarbon-B (8.7%), Calcium Phosphosilicate (6.6%), Glycidyl Ether Of Alkyl Phenol (14.4%), Hydrous Magnesium Silicate (3.6%), Medium Mineral Spirits (13.1%), 1,2,4-Trimethyl Benzene (1-6%*), 2,4,6- Tri((Dimethylamino)Methyl) Phenol (1.9%)
GAL WT: 9.86 WT PCT SOLIDS: 72.97 VOL PCT SOLIDS: 60.82
SOLVENT DENSITY: 6.81 VOC LE: 2.7 VOC AP: 2.7
FLASH POINT: 100°F - 141°F H: 3 F: 2 R: 1 OSHA STORAGE: II
TSCA STATUS: In compliance PHOTOCHEMICALLY REACTIVE: YES

LF-63225P™ Amidoamine Resin-B (13.6%), Amorphous Silica-A (1.5%), Aromatic Hydrocarbon-B (9.1%), Glycidyl Ether Of Alkyl Phenol (10.5%), Mica (17.2%), Quartz-Crystalline Silica (0.9%), Titanium Dioxide (23.4%), Zinc Oxide (15.2%*), 1,2,4-Trimethyl Benzene (1-7%*), 2,4,6- Tri((Dimethylamino)Methyl) Phenol (1.4%)
GAL WT: 13.96 WT PCT SOLIDS: 85.24 VOL PCT SOLIDS: 71.45
SOLVENT DENSITY: 7.22 VOC LE: 2.1 VOC AP: 2.1
FLASH POINT: 100°F - 141°F H: 3 F: 2 R: 1 OSHA STORAGE: II
TSCA STATUS: In compliance PHOTOCHEMICALLY REACTIVE: YES

LF-63325P™ Amidoamine Resin-B (16.6%), Aromatic Hydrocarbon-B (10.8%), Calcium Phosphosilicate (6.0%), Carbon Black (0.2%), Cumene (0-1%*@), Glycidyl Ether Of Alkyl Phenol (12.8%), Hydrous Magnesium Silicate (3.3%), Mica (22.6%), Quartz-Crystalline Silica (1.2%), Titanium Dioxide (13.9%), 1,2,4-Trimethyl Benzene (2-8%*), 2,4,6- Tri((Dimethylamino)Methyl) Phenol (1.7%)
GAL WT: 11.88 WT PCT SOLIDS: 81.94 VOL PCT SOLIDS: 70.35
SOLVENT DENSITY: 7.24 VOC LE: 2.1 VOC AP: 2.1
FLASH POINT: 100°F - 141°F H: 3 F: 2 R: 1 OSHA STORAGE: II
TSCA STATUS: In compliance PHOTOCHEMICALLY REACTIVE: YES

LF-63525P™ Amidoamine Resin-B (14.6%), Amorphous Silica-A (1.6%), Aromatic Hydrocarbon-B (9.8%), Calcium Phosphosilicate (5.1%), Glycidyl Ether of Alkyl Phenol (11.3%), Hydrous Magnesium Silicate (2.8%), Mica (18.5%), Quartz-Crystalline Silica (1.0%), Titanium Dioxide (25.1%), 1,2,4-Trimethyl Benzene (2-7%*), 2,4,6- Tri((Dimethylamino)Methyl) Phenol (1.5%)
GAL WT: 12.88 WT PCT SOLIDS: 83.90 VOL PCT SOLIDS: 71.30
SOLVENT DENSITY: 7.23 VOC LE: 2.1 VOC AP: 2.1
FLASH POINT: 100°F - 141°F H: 3 F: 2 R: 1 OSHA STORAGE: II
TSCA STATUS: In compliance PHOTOCHEMICALLY REACTIVE: YES

LF-63725P™ Amidoamine Resin-B (14.7%), Amorphous Silica-A (1.6%), Aromatic Hydrocarbon-B (9.8%), Calcium Phosphosilicate (5.1%), Glycidyl Ether Of Alkyl Phenol (11.3%), Hydrous Magnesium Silicate (2.8%), Mica (18.6%), Quartz-Crystalline Silica (1.0%), Titanium Dioxide (25.2%), 1,2,4-Trimethyl Benzene (2-7%*), 2,4,6- Tri((Dimethylamino)Methyl) Phenol (1.5%)
GAL WT: 12.87 WT PCT SOLIDS: 83.92 VOL PCT SOLIDS: 71.35
SOLVENT DENSITY: 7.23 VOC LE: 2.1 VOC AP: 2.1
FLASH POINT: 100°F - 141°F H: 3 F: 2 R: 1 OSHA STORAGE: II
TSCA STATUS: In compliance PHOTOCHEMICALLY REACTIVE: YES

LF-71125P™ Amidoamine Resin-B (13.1%), Aromatic Hydrocarbon-B (8.9%), Barium Sulfate (26.8%), Calcium Phosphosilicate (5.6%), Glycidyl Ether Of Alkyl Phenol (10.1%), Hydrous Magnesium Silicate (3.1%), Iron Oxide (8.9%), Mica (13.8%), Quartz-Crystalline Silica (1.3%), 1,2,4-Trimethylbenzene (1-6%*), 2,4,6- Tri((Dimethylamino)Methyl) Phenol (1.4%)
GAL WT: 13.93 WT PCT SOLIDS: 85.31 VOL PCT SOLIDS: 71.72
SOLVENT DENSITY: 7.24 VOC LE: 2.0 VOC AP: 2.0
FLASH POINT: 100°F - 141°F H: 3 F: 2 R: 1 OSHA STORAGE: II
TSCA STATUS: In compliance PHOTOCHEMICALLY REACTIVE: YES

525-333™ Amidoamine Resin-B (8.5%), Barium Sulfate (24.7%), Calcium Phosphosilicate (6.1%), Diisobutyl Ketone (6.0%), Ethylene Glycol Monobutylether (8.3%*@), Glycidyl Ether Of Alkyl Phenol (6.5%), Hydrous Magnesium Silicate (12.9%), Kaolin (10.8%), Methyl Amyl Ketone (5.2%), Methyl Ethyl Ketone (5.8%*@), 2,4,6- Tri((Dimethylamino)Methyl) Phenol (1.2%), 4,6-Dimethyl-2-Heptanone (1.5%)
GAL WT: 12.33 WT PCT SOLIDS: 72.66 VOL PCT SOLIDS: 51.35
SOLVENT DENSITY: 6.83 VOC LE: 3.4 VOC AP: 3.4
FLASH POINT: 20°F to below 73°F H: 3 F: 3 R: 1 OSHA STORAGE: IB
TSCA STATUS: In compliance PHOTOCHEMICALLY REACTIVE: YES

1LB26P™ Aluminum Hydrate (1.3%), Amorphous Silica-A (2.1%), Aromatic Hydrocarbon-B (5.6%), Barium Sulfate (6.8%), Bisphenol-Epichlorohydrin Type Polymer (30.4%), Diacetone Alcohol (7.0%), Ethylbenzene (0.2%*@), Hydrous Magnesium Silicate (4.1%), Titanium Dioxide (34.0%), Xylene (1-1%*@), 1,2,4-Trimethyl Benzene (1-4%*)
GAL WT: 13.50 WT PCT SOLIDS: 80.85 VOL PCT SOLIDS: 65.18
SOLVENT DENSITY: 7.25 VOC LE: 2.6 VOC AP: 2.6
FLASH POINT: 100°F - 141°F H: 2 F: 2 R: 0 OSHA STORAGE: II
TSCA STATUS: In compliance PHOTOCHEMICALLY REACTIVE: YES

2MB26P™ Amorphous Silica-A (1.1%), Aromatic Hydrocarbon-B (5.1%), Barium Sulfate (15.4%), Bisphenol-Epichlorohydrin Type Polymer (33.3%), Diacetone Alcohol (7.9%), Ethylbenzene (0.2%*@), Ethylene Glycol Monobutylether (1.4%*@), Hydrous Magnesium Silicate (9.4%), Titanium Dioxide (17.8%), Xylene (1-2%*@), 1,2,4-Trimethyl Benzene (1-4%*)
GAL WT: 12.92 WT PCT SOLIDS: 79.96 VOL PCT SOLIDS: 65.22
SOLVENT DENSITY: 7.29 VOC LE: 2.6 VOC AP: 2.6
FLASH POINT: 100°F - 141°F H: 2 F: 2 R: 0 OSHA STORAGE: II
TSCA STATUS: In compliance PHOTOCHEMICALLY REACTIVE: YES

3DB26P™ Aromatic Hydrocarbon-B (4.3%), Barium Sulfate (20.7%), Bisphenol-Epichlorohydrin Type Polymer (34.2%), Diacetone Alcohol (8.6%), Ethylbenzene (0.2%*@), Ethylene Glycol Monobutylether (1.8%*@), Hydrous Magnesium Silicate (12.6%), Titanium Dioxide (9.2%), Xylene (1-2%*@), 1,2,4-Trimethyl Benzene (1-3%*)
GAL WT: 12.80 WT PCT SOLIDS: 80.02 VOL PCT SOLIDS: 65.78
SOLVENT DENSITY: 7.32 VOC LE: 2.6 VOC AP: 2.6
FLASH POINT: 100°F - 141°F H: 2 F: 2 R: 0 OSHA STORAGE: II
TSCA STATUS: In compliance PHOTOCHEMICALLY REACTIVE: YES

4NB26P™ Aromatic Hydrocarbon-B (2.8%), Barium Sulfate (25.9%), Bisphenol-Epichlorohydrin Type Polymer (36.8%), Diacetone Alcohol (9.3%), Ethylbenzene (0.2%*@), Ethylene Glycol Monobutylether (2.3%*@), Hydrous Magnesium Silicate (15.8%), Xylene (1-2%*@), 1,2,4-Trimethyl Benzene (0-2%*)
GAL WT: 12.67 WT PCT SOLIDS: 81.17 VOL PCT SOLIDS: 68.25
SOLVENT DENSITY: 7.34 VOC LE: 2.4 VOC AP: 2.4

FLASH POINT: 100°F - 141°F H: 2 F: 2 R: 0 OSHA STORAGE: II
TSCA STATUS: In compliance PHOTOCHEMICALLY REACTIVE: YES

LF-63226P™ Aluminum Hydrate (1.3%), Amorphous Silica-A (2.1%), Aromatic Hydrocarbon-B (5.9%), Barium Sulfate (6.8%), Bisphenol-Epichlorohydrin Type Polymer (30.0%), Diacetone Alcohol (7.0%), Ethylbenzene (0.2%*@), Hydrous Magnesium Silicate (4.1%), Titanium Dioxide (33.9%), Xylene (1-1%*@), 1,2,4-Trimethyl Benzene (1-4%*)
GAL WT: 13.45 WT PCT SOLIDS: 80.35 VOL PCT SOLIDS: 64.37
SOLVENT DENSITY: 7.25 VOC LE: 2.6 VOC AP: 2.6
FLASH POINT: 100°F - 141°F H: 2 F: 2 R: 0 OSHA STORAGE: II
TSCA STATUS: In compliance PHOTOCHEMICALLY REACTIVE: YES

LF-63326P™ Aluminum Hydrate (1.3%), Amorphous Silica-A (2.0%), Aromatic Hydrocarbon-B (5.4%), Barium Sulfate (7.2%), Bisphenol-Epichlorohydrin Type Polymer (29.4%), Carbon Black (0.2%), Diacetone Alcohol (6.8%), Ethylbenzene (0.2%*@), Hydrous Magnesium Silicate (4.0%), Titanium Dioxide (33.0%), Xylene (1-1%*@), 1,2,4-Trimethyl Benzene (1-4%*)
GAL WT: 13.48 WT PCT SOLIDS: 80.56 VOL PCT SOLIDS: 64.80
SOLVENT DENSITY: 7.28 VOC LE: 2.6 VOC AP: 2.6
FLASH POINT: 100°F - 141°F H: 2 F: 2 R: 0 OSHA STORAGE: II
TSCA STATUS: In compliance PHOTOCHEMICALLY REACTIVE: YES

LF-63526P™ Aluminum Hydrate (1.3%), Amorphous Silica-A (2.1%), Aromatic Hydrocarbon-B (5.8%), Barium Sulfate (6.7%), Bisphenol-Epichlorohydrin Type Polymer (30.8%), Diacetone Alcohol (6.9%), Ethylbenzene (0.2%*@), Hydrous Magnesium Silicate (4.1%), Titanium Dioxide (33.3%), Xylene (1-1%*@), 1,2,4-Trimethyl Benzene (1-4%*)
GAL WT: 13.39 WT PCT SOLIDS: 80.63 VOL PCT SOLIDS: 65.04
SOLVENT DENSITY: 7.26 VOC LE: 2.6 VOC AP: 2.6
FLASH POINT: 100°F - 141°F H: 2 F: 2 R: 0 OSHA STORAGE: II
TSCA STATUS: In compliance PHOTOCHEMICALLY REACTIVE: YES

LF-63726P™ Aluminum Hydrate (1.3%), Amorphous Silica-A (2.0%), Aromatic Hydrocarbon-B (5.7%), Barium Sulfate (6.7%), Bisphenol-Epichlorohydrin Type Polymer (31.2%), Diacetone Alcohol (6.8%), Ethylbenzene (0.2%*@), Hydrous Magnesium Silicate (4.0%), Titanium Dioxide (33.0%), Xylene (1-1%*@), 1,2,4-Trimethyl Benzene (1-4%*)
GAL WT: 13.35 WT PCT SOLIDS: 80.71 VOL PCT SOLIDS: 65.31
SOLVENT DENSITY: 7.26 VOC LE: 2.6 VOC AP: 2.6
FLASH POINT: 100°F - 141°F H: 2 F: 2 R: 0 OSHA STORAGE: II
TSCA STATUS: In compliance PHOTOCHEMICALLY REACTIVE: YES

LF-64026P™ Aromatic Hydrocarbon-B (6.0%), Barium Sulfate (34.1%), Bisphenol-Epichlorohydrin Type Polymer (28.6%), Carbon Black (1.0%), Diacetone Alcohol (7.2%), Ethylbenzene (0.2%*@), Hydrous Magnesium Silicate (2.7%), Kaolin (13.2%), Xylene (1-1%*@), 1,2,4-Trimethyl Benzene (1-4%*)
GAL WT: 13.56 WT PCT SOLIDS: 80.91 VOL PCT SOLIDS: 65.00
SOLVENT DENSITY: 7.21 VOC LE: 2.6 VOC AP: 2.6
FLASH POINT: 100°F - 141°F H: 2 F: 2 R: 0 OSHA STORAGE: II
TSCA STATUS: In compliance PHOTOCHEMICALLY REACTIVE: YES

LF-66226P™ Acrylic Polymer-C(1.3%), Aromatic Hydrocarbon-B (6.7%), Barium Sulfate (10.5%), Bisphenol-Epichlorohydrin Type Polymer (37.7%), Diacetone Alcohol (8.4%), Ethylbenzene (0.2%*@), Hydrous Magnesium Silicate (6.4%), Isoindolinone Pigment (10.1%), Monoazo Pigment (4.2%), Titanium Dioxide (4.7%), Xylene (1-2%*@), 1,2,4-Trimethyl Benzene (1-5%*)
GAL WT: 11.19 WT PCT SOLIDS: 76.65 VOL PCT SOLIDS: 64.73
SOLVENT DENSITY: 7.19 VOC LE: 2.6 VOC AP: 2.6
FLASH POINT: 100°F - 141°F H: 2 F: 2 R: 0 OSHA STORAGE: II
TSCA STATUS: In compliance PHOTOCHEMICALLY REACTIVE: YES

LF-66326P™ Acrylic Polymer-C(3.5%), Aromatic Hydrocarbon-B (7.3%), Barium Sulfate (2.6%), Bisphenol-Epichlorohydrin Type Polymer (39.3%), Butyl Acetate (1.8%), Diacetone Alcohol (8.4%), Ethylbenzene (0.2%*@), Hydrous Magnesium Silicate (1.5%), Light Yellow Lemon Yellow Oxide Pigment (1.2%), Monoazo Pigment (11.0%), Propylene Carbonate (1.8%), Tetrahydrofuran (1.2%), Titanium Dioxide (12.0%), Xylene (1-1%*@), 1,2,4-Trimethyl Benzene (1-5%*)
GAL WT: 10.58 WT PCT SOLIDS: 73.31 VOL PCT SOLIDS: 62.61
SOLVENT DENSITY: 7.51 VOC LE: 2.8 VOC AP: 2.8
FLASH POINT: 100°F - 141°F H: 2 F: 2 R: 0 OSHA STORAGE: II
TSCA STATUS: In compliance PHOTOCHEMICALLY REACTIVE: YES

LF-66426P™ Acrylic Polymer-C(1.5%), Aromatic Hydrocarbon-B (6.6%), Barium Sulfate (10.4%), Bisphenol-Epichlorohydrin Type Polymer (41.2%), Diacetone Alcohol (9.4%), Ethylbenzene (0.2%*@), Hydrous Magnesium Silicate (6.3%), Monoazo Pigment (5.3%), Quinacridone Pigment (8.1%), Titanium Dioxide (1.3%), Xylene (1-2%*@), 1,2,4-Trimethyl Benzene (1-5%*)
GAL WT: 10.59 WT PCT SOLIDS: 75.43 VOL PCT SOLIDS: 65.05
SOLVENT DENSITY: 7.27 VOC LE: 2.6 VOC AP: 2.6
FLASH POINT: 100°F - 141°F H: 2 F: 2 R: 0 OSHA STORAGE: II
TSCA STATUS: In compliance PHOTOCHEMICALLY REACTIVE: YES

LF-66526P™ Aromatic Hydrocarbon-B (3.1%), Barium Sulfate (19.3%), Bisphenol A/Epichlorohydrin Polymer (3.1%), Bisphenol Epichlorohydrin Type Polymer (29.3%), Diacetone Alcohol (8.1%), Ethyl Acetate (2.2%), Ethylbenzene (0.2%*@), Ethylene Glycol Monobutylether (1.7%*@), Hydrous Magnesium Silicate (11.8%), Isopropyl Alcohol (2.2%), Phthalocyanine Blue Pigment (1.3%), Titanium Dioxide (8.6%), Xylene (1-1%*@), 1,2,4-Trimethyl Benzene (0-2%*)
GAL WT: 12.35 WT PCT SOLIDS: 76.71 VOL PCT SOLIDS: 61.07
SOLVENT DENSITY: 7.26 VOC LE: 2.9 VOC AP: 2.9
FLASH POINT: 100°F - 141°F H: 2 F: 2 R: 0 OSHA STORAGE: II
TSCA STATUS: In compliance PHOTOCHEMICALLY REACTIVE: YES

LF-6AL90P™ Aluminum (4.6%*), Amorphous Silica-A (1.5%), Bisphenol Epichlorohydrin Type Polymer (48.4%), Dioctyl Phthalate (7.7%*), Ethylbenzene (1.0%*@), Medium Mineral Spirits (2.5%), Organophillic Clay (3.8%), Quartz-Crystalline Silica (24.9%), Xylene (4-5%*@)
GAL WT: 11.12 WT PCT SOLIDS: 90.83 VOL PCT SOLIDS: 85.26
SOLVENT DENSITY: 6.92 VOC LE: 1.0 VOC AP: 1.0
FLASH POINT: 100°F - 141°F H: 2 F: 2 R: 1 OSHA STORAGE: II
TSCA STATUS: In compliance PHOTOCHEMICALLY REACTIVE: YES

MSDS DIC 7
EPOXY PRIMERS, ENAMELS, AND ACTIVATORS
January 1, 2003

LF-64090P™ Bisphenol-Epichlorohydrin Type Polymer (44.1%), Black Iron Oxide (6.9%), Dioctyl Phthalate (7.0%*), Ethylbenzene (0.8%*@), Organophilic Clay (3.8%), Quartz-Crystalline Silica (32.2%), Xylene (3-4%*@)
GAL WT: 12.21 WT PCT SOLIDS: 93.97 VOL PCT SOLIDS: 89.63
SOLVENT DENSITY: 7.10 VOC LE: 0.7 VOC AP: 0.7
FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 1 OSHA STORAGE: IB
TSCA STATUS: In compliance PHOTOCHEMICALLY REACTIVE: YES

LF-63290P™ Bisphenol-Epichlorohydrin Type Polymer (43.3%), Dioctyl Phthalate (6.9%*), Ethylbenzene (0.8%*@), Organophilic Clay (3.8%), Quartz-Crystalline Silica (19.3%), Titanium Dioxide (19.5%), Xylene (3-4%*@)
GAL WT: 12.57 WT PCT SOLIDS: 93.95 VOL PCT SOLIDS: 89.30
SOLVENT DENSITY: 7.11 VOC LE: 0.8 VOC AP: 0.8
FLASH POINT: 100°F - 141°F H: 2 F: 2 R: 0 OSHA STORAGE: II
TSCA STATUS: In compliance PHOTOCHEMICALLY REACTIVE: YES

LF-63790P™ Bisphenol-Epichlorohydrin Type Polymer (43.1%), Dioctyl Phthalate (6.9%*), Ethylbenzene (0.8%*@), Organophilic Clay (3.8%), Quartz-Crystalline Silica (19.2%), Titanium Dioxide (19.5%), Xylene (3-4%*@)
GAL WT: 12.56 WT PCT SOLIDS: 93.97 VOL PCT SOLIDS: 89.34
SOLVENT DENSITY: 7.11 VOC LE: 0.8 VOC AP: 0.8
FLASH POINT: 100°F - 141°F H: 2 F: 2 R: 0 OSHA STORAGE: II
TSCA STATUS: In compliance PHOTOCHEMICALLY REACTIVE: YES

LF-71190P™ Bisphenol-Epichlorohydrin Type Polymer (43.6%), Dioctyl Phthalate (7.0%*), Ethylbenzene (0.8%*@), Iron Oxide (10.3%), Organophilic Clay (3.7%), Quartz-Crystalline Silica (29.3%), Xylene (4-4%*@)
GAL WT: 12.37 WT PCT SOLIDS: 93.90 VOL PCT SOLIDS: 89.39
SOLVENT DENSITY: 7.11 VOC LE: 0.8 VOC AP: 0.7
FLASH POINT: 100°F - 141°F H: 2 F: 2 R: 0 OSHA STORAGE: II
TSCA STATUS: In compliance PHOTOCHEMICALLY REACTIVE: YES

LF-63590P™ Bisphenol-Epichlorohydrin Type Polymer (43.0%), Dioctyl Phthalate (6.9%*), Ethylbenzene (0.8%*@), Organophilic Clay (3.8%), Quartz-Crystalline Silica (19.2%), Titanium Dioxide (19.4%), Xylene (3-4%*@)
GAL WT: 12.58 WT PCT SOLIDS: 93.99 VOL PCT SOLIDS: 89.36
SOLVENT DENSITY: 7.11 VOC LE: 0.8 VOC AP: 0.8
FLASH POINT: 100°F - 141°F H: 2 F: 2 R: 0 OSHA STORAGE: II
TSCA STATUS: In compliance PHOTOCHEMICALLY REACTIVE: YES

823Y67632™ Barium Sulfate (9.7%), Bisphenol A/Epichlorohydrin Polymer (25.3%), Ethyl Acetate (6.6%), Hydrous Magnesium Silicate (13.3%), Isopropyl Alcohol (3.5%), N-Butyl Alcohol (5.6%*), Propylene Glycol Monomethyl Ether Acetate (10.3%), Titanium Dioxide (17.0%), Toluene (4.9%*@)
GAL WT: 11.97 WT PCT SOLIDS: 68.01 VOL PCT SOLIDS: 47.89
SOLVENT DENSITY: 7.35 VOC LE: 3.8 VOC AP: 3.8
FLASH POINT: 20°F to below 73°F H: 3 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In compliance PHOTOCHEMICALLY REACTIVE: NO

823Y67633™ Barium Sulfate (9.3%), Bisphenol A/Epichlorohydrin Polymer (25.9%), Carbon Black (0.2%), Ethyl Acetate (6.9%), Hydrous Magnesium Silicate (12.7%), Isopropyl Alcohol (3.7%), N-Butyl Alcohol (5.7%*), Propylene Glycol Monomethyl Ether Acetate (10.0%), Titanium Dioxide (16.1%), Toluene (5.1%*@)
GAL WT: 11.81 WT PCT SOLIDS: 67.44 VOL PCT SOLIDS: 47.57
SOLVENT DENSITY: 7.33 VOC LE: 3.8 VOC AP: 3.8
FLASH POINT: 20°F to below 73°F H: 3 F: 3 R: 0 OSHA STORAGE: IB

TSCA STATUS: In compliance PHOTOCHEMICALLY REACTIVE: NO

823Y67635™ Barium Sulfate (9.6%), Bisphenol A/Epichlorohydrin Polymer (25.3%), Ethyl Acetate (6.8%), Hydrous Magnesium Silicate (13.2%), Isopropyl Alcohol (3.5%), N-Butyl Alcohol (5.6%*), Propylene Glycol Monomethyl Ether Acetate (10.2%), Titanium Dioxide (16.8%), Toluene (4.9%*@)
GAL WT: 11.95 WT PCT SOLIDS: 67.85 VOL PCT SOLIDS: 47.68
SOLVENT DENSITY: 7.34 VOC LE: 3.8 VOC AP: 3.8
FLASH POINT: 20°F to below 73°F H: 3 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In compliance PHOTOCHEMICALLY REACTIVE: NO

823Y67637™ Barium Sulfate (9.7%), Bisphenol A/Epichlorohydrin Polymer (25.3%), Ethyl Acetate (6.9%), Hydrous Magnesium Silicate (13.2%), Isopropyl Alcohol (3.5%), N-Butyl Alcohol (5.6%*), Propylene Glycol Monomethyl Ether Acetate (10.2%), Titanium Dioxide (16.8%), Toluene (4.9%*@)
GAL WT: 11.93 WT PCT SOLIDS: 67.74 VOL PCT SOLIDS: 47.60
SOLVENT DENSITY: 7.34 VOC LE: 3.8 VOC AP: 3.8
FLASH POINT: 20°F to below 73°F H: 3 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In compliance PHOTOCHEMICALLY REACTIVE: NO

VF-333™ Barium Sulfate (12.0%), Bisphenol-Epichlorohydrin Type Polymer (19.4%), Diisobutyl Ketone (4.3%), Ethyl Acetate (3.4%), Ethylene Glycol Monobutylether (12.2%*@), Hydrous Magnesium Silicate (10.4%), Kaolin (11.7%), Methyl Ethyl Ketone (2.8%*@), Phenolic Polymer (7.6%), Titanium Dioxide (8.6%), Urea Formaldehyde Resin (1.1%), 4,6-Dimethyl-2-Heptanone (1.1%)
GAL WT: 12.05 WT PCT SOLIDS: 74.54 VOL PCT SOLIDS: 57.24
SOLVENT DENSITY: 7.02 VOC LE: 3.1 VOC AP: 3.0
FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB

TSCA STATUS: In compliance PHOTOCHEMICALLY REACTIVE: NO

VF-455™ Barium Sulfate (11.7%), Bisphenol-Epichlorohydrin Type Polymer (19.1%), Ethyl Acetate (3.2%), Hydrous Magnesium Silicate (9.5%), Kaolin (11.5%), Methyl Ethyl Ketone (11.0%*@), Phenolic Polymer (7.1%), Titanium Dioxide (8.4%), Toluene (11.8%*@), Urea Formaldehyde Resin (1.1%)
GAL WT: 11.64 WT PCT SOLIDS: 72.23 VOL PCT SOLIDS: 53.72
SOLVENT DENSITY: 6.87 VOC LE: 3.2 VOC AP: 3.2
FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In compliance PHOTOCHEMICALLY REACTIVE: YES

VF-525™ Bisphenol-Epichlorohydrin Type Polymer (36.0%), Ethyl Acetate (6.4%), Hydrous Magnesium Silicate (27.9%), N-Butyl Alcohol (2.4%*), Phenolic Polymer (14.1%), Toluene (10.0%*@)
GAL WT: 10.74 WT PCT SOLIDS: 80.88 VOL PCT SOLIDS: 71.74
SOLVENT DENSITY: 7.26 VOC LE: 2.1 VOC AP: 2.1

FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In compliance PHOTOCHEMICALLY REACTIVE: YES

VF-026™ Acrylic Polymer-A (10.2%), Amidoamine Resin-C(20.9%), Amine Salt Of Polycarbonic Acid(1.0%), Amorphous Silica-Fumed(2.0%), Aromatic Hydrocarbon-A (1.0%), Aromatic Hydrocarbon-B (10.4%), Calcium Phosphosilicate (3.7%), Glycidyl Ester Of Tert Carboxylic Acid(10.7%), Hydrous Magnesium Silicate (5.6%), Kaolin (3.8%), Methyl Ethyl Ketone (9.0%*@), Mica (9.4%), N-Butyl Alcohol (3.1%*), Quartz-Crystalline Silica (0.5%), 1,2,4-Trimethyl Benzene (2-7%*), 2,4,6-Tri((Dimethylamino)Methyl) Phenol (2.1%)
GAL WT: 9.26 WT PCT SOLIDS: 70.42 VOL PCT SOLIDS: 60.90
SOLVENT DENSITY: 7.00 VOC LE: 2.7 VOC AP: 2.7
FLASH POINT: 20°F to below 73°F H: 3 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In compliance PHOTOCHEMICALLY REACTIVE: YES

VG-026™ Acrylic Polymer-A (25.6%), Amidoamine Resin-C (23.0%), Aromatic Hydrocarbon-B (11.3%), Cumene (0-1%*@), Glycidyl Ester Of Tert Carboxylic Acid(11.8%), Methyl Ethyl Ketone (11.6%*@), N-Butyl Alcohol (7.7%*), 1,2,4-Trimethyl Benzene (2-8%*), 2,4,6- Tri((Dimethylamino) Methyl) Phenol (2.3%)
GAL WT: 7.86 WT PCT SOLIDS: 62.79 VOL PCT SOLIDS: 58.04
SOLVENT DENSITY: 6.94 VOC LE: 2.9 VOC AP: 2.9
FLASH POINT: 20°F to below 73°F H: 3 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In compliance PHOTOCHEMICALLY REACTIVE: YES

525-450™ Amorphous Silica-B (1.1%), Bisphenol-Epichlorohydrin Type Polymer (24.7%), Calcium Carbonate (6.3%), Hydrous Magnesium Silicate (26.0%), Methyl Isobutyl Ketone (9.9%*@), Organoclay (2.1%), Quartz-Crystalline Silica (2.7%), Titanium Dioxide (8.2%), Toluene (9.2%*@), Xylene (8.2%*@)
GAL WT: 11.91 WT PCT SOLIDS: 72.49 VOL PCT SOLIDS: 53.25
SOLVENT DENSITY: 7.00 VOC LE: 3.3 VOC AP: 3.3
FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In compliance PHOTOCHEMICALLY REACTIVE: YES

525-451™ Amorphous Silica-B (1.1%), Bisphenol-Epichlorohydrin Type Polymer (24.7%), Calcium Carbonate (6.3%), Hydrous Magnesium Silicate (26.0%), Methyl Isobutyl Ketone (9.9%*@), Organoclay (2.1%), Quartz-Crystalline Silica (2.7%), Titanium Dioxide (8.2%), Toluene (9.2%*@), Xylene (8.2%*@)
GAL WT: 11.91 WT PCT SOLIDS: 72.49 VOL PCT SOLIDS: 53.25
SOLVENT DENSITY: 7.00 VOC LE: 3.3 VOC AP: 3.3
FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In compliance PHOTOCHEMICALLY REACTIVE: YES

VG-400™ Polyamide Resin (56.5%), Toluene (19.3%*@), Xylene (24.2%*@)
GAL WT: 7.69 WT PCT SOLIDS: 56.46 VOL PCT SOLIDS: 53.64
SOLVENT DENSITY: 7.22 VOC LE: 3.3 VOC AP: 3.3
FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 1 OSHA STORAGE: IB
TSCA STATUS: In compliance PHOTOCHEMICALLY REACTIVE: YES

525-2420™ Bisphenol-Epichlorohydrin Type Polymer (48.6%), Hydrous Magnesium Silicate (39.6%), Para-Nonylphenol (4.9%), 2-Ethylhexyl Glycidyl Ether (4.7%)
GAL WT: 12.30 WT PCT SOLIDS: 99.05 VOL PCT SOLIDS: 98.21
SOLVENT DENSITY: 6.59 VOC LE: 0.1 VOC AP: 0.1
FLASH POINT: Above 200°F H: 2 F: 1 R: 0 OSHA STORAGE: IIIB
TSCA STATUS: In compliance PHOTOCHEMICALLY REACTIVE: NO

FG-090™ Benzyl Alcohol (4.4%), Epoxy Hardener (2.0%), Ethylbenzene (0.2%*@), Organophillic Clay (4.0%), Quartz-Crystalline Silica (44.5%), Tetraethylenepentamine (5.7%), Tofa, Reaction Products W/Tepa (32.6%), Trade Secret (3.4%), 2,4,6- Tri((Dimethylamino)Methyl) Phenol (2.3%)
GAL WT: 11.51 WT PCT SOLIDS: 94.67 VOL PCT SOLIDS: 92.67
SOLVENT DENSITY: 8.39 VOC LE: 0.6 VOC AP: 0.6
FLASH POINT: 100°F - 141°F H: 3 F: 2 R: 1 OSHA STORAGE: II
TSCA STATUS: In compliance PHOTOCHEMICALLY REACTIVE: YES

VF-335™ Barium Sulfate (11.8%), Bisphenol-Epichlorohydrin Type Polymer (19.1%), Carbon Black (0.2%), Ethyl Acetate (3.1%), Hydrous Magnesium Silicate (10.2%), Kaolin (11.6%), Methyl Amyl Ketone (1.4%), Methyl Ethyl Ketone (8.1%*@), Phenolic Polymer (7.5%), Titanium Dioxide (8.4%), Toluene (11.7%*@), Urea Formaldehyde Resin (1.1%)
GAL WT: 11.85 WT PCT SOLIDS: 74.30 VOL PCT SOLIDS: 56.50
SOLVENT DENSITY: 6.89 VOC LE: 3.0 VOC AP: 3.0
FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In compliance PHOTOCHEMICALLY REACTIVE: YES

FG-334™ Acrylic Polymer-B (1.0%), Barium Sulfate (11.5%), Bisphenol-Epichlorohydrin Type Polymer (18.6%), Diisobutyl Ketone (4.2%), Ethyl Acetate (3.3%), Ethylene Glycol Monobutylether (11.9%*@), Hydrous Magnesium Silicate (9.9%), Kaolin (11.3%), Methyl Amyl Ketone (1.6%), Methyl Ethyl Ketone (2.7%*@), Monoazo Pigment (1.4%), Phenolic Polymer (7.7%), Titanium Dioxide/Aluminum Hydrate/Amorphous Silica (9.0%), Urea Formaldehyde Resin (1.1%), 4,6-Dimethyl-2-Heptanone (1.0%)
GAL WT: 11.85 WT PCT SOLIDS: 74.05 VOL PCT SOLIDS: 56.99
SOLVENT DENSITY: 7.15 VOC LE: 3.1 VOC AP: 3.1
FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IA

TSCA STATUS: In compliance PHOTOCHEMICALLY REACTIVE: NO

525-A8603™ Aromatic Hydrocarbon-A (22.5%), Bisphenol-Epichlorohydrin Type Polymer (48.8%), Diatomaceous Earth (5.7%), Ethylbenzene (0.8%*@), Hydrous Magnesium Silicate (9.2%), Naphthalene (1-3%*@), Quartz-Crystalline Silica (8.6%), 1,2,4-Trimethyl Benzene (0-3%*)
GAL WT: 10.12 WT PCT SOLIDS: 73.12 VOL PCT SOLIDS: 63.19
SOLVENT DENSITY: 7.38 VOC LE: 2.7 VOC AP: 2.7
FLASH POINT: 100°F - 141°F H: 3 F: 2 R: 0 OSHA STORAGE: II
TSCA STATUS: In compliance PHOTOCHEMICALLY REACTIVE: YES

525-B8603™ Amidoamine Resin-A (1.7%*), Ethylbenzene (0.7%*@), Hydrous Magnesium Silicate (33.8%), N-Butyl Alcohol (24.9%*), Polyamide Resin (16.4%), Quartz-Crystalline Silica (10.4%), Titanium Dioxide (7.4%), Yellow Iron Oxide (1.6%)
GAL WT: 11.95 WT PCT SOLIDS: 73.65 VOL PCT SOLIDS: 53.48
SOLVENT DENSITY: 6.74 VOC LE: 3.1 VOC AP: 3.1
FLASH POINT: 73°F to below 100°F H: 2 F: 3 R: 0

MSDS DIC 7
EPOXY PRIMERS, ENAMELS, AND ACTIVATORS
January 1, 2003

OSHA STORAGE: IC
TSCA STATUS: In compliance PHOTOCHEMICALLY REACTIVE: NO

525-A8601™ Aromatic Hydrocarbon-A (19.3%), Bisphenol-Epichlorohydrin Type Polymer (51.0%), Ethylbenzene (0.8%*@), Hydrous Magnesium Silicate (24.5%), Naphthalene (1-2%*@),1,2,4-Trimethyl Benzene (0-2%*)
GAL WT: 10.47 WT PCT SOLIDS: 76.83 VOL PCT SOLIDS: 67.15
SOLVENT DENSITY: 7.38 VOC LE: 2.4 VOC AP: 2.4
FLASH POINT: 100°F - 141°F H: 2 F: 2 R: 0 OSHA STORAGE: II
TSCA STATUS: In compliance PHOTOCHEMICALLY REACTIVE: YES

525-B8601™ Aluminum Hydrate (1.8%), Amidoamine Resin-A (1.8%*), Ethylbenzene (0.6%*@), Hydrous Magnesium Silicate (8.1%), N-Butyl Alcohol (25.8%*), Polyamide Resin (16.4%), Quartz-Crystalline Silica (5.7%), Titanium Dioxide (37.5%)
GAL WT: 12.47 WT PCT SOLIDS: 72.83 VOL PCT SOLIDS: 49.98
SOLVENT DENSITY: 6.74 VOC LE: 3.4 VOC AP: 3.4
FLASH POINT: 73°F to below 100°F H: 2 F: 3 R: 0
OSHA STORAGE: IC
TSCA STATUS: In compliance PHOTOCHEMICALLY REACTIVE: NO

6AL90P™ Aluminum (4.6%*), Amorphous Silica-A (1.5%), Bisphenol Epichlorohydrin Type Polymer (48.4%), Dioctyl Phthalate (7.7%*), Ethylbenzene (1.0%*@), Medium Mineral Spirits (2.5%), Organophilic Clay (3.8%), Quartz-Crystalline Silica (24.9%), Xylene (4-5%*@)
GAL WT: 11.12 WT PCT SOLIDS: 90.83 VOL PCT SOLIDS: 85.26
SOLVENT DENSITY: 6.92 VOC LE: 1.0 VOC AP: 1.0
FLASH POINT: 100°F – 141°F H: 2 F: 2 R: 1 OSHA STORAGE: II
TSCA STATUS: In compliance PHOTOCHEMICALLY REACTIVE: YES

Footnotes:
TSCA: In compliance = In compliance with TSCA Inventory requirements for commercial purposes.
ACGIH = American Conference of Government Industrial Hygienists.
IARC = International agency for Research on Cancer.
NTP = National Toxicology Program.
OSHA = Occupational Safety and Health Administration.
PNOR = Particles Not Otherwise Regulated.
PNOC = Particles Not Otherwise Classified.
STEL = Short Term Exposure Limit.
TWA = Time Weighted Average.
TM = Is a Trademark of E.I. DuPont de Nemours & Co.
* = Section 313 Supplier Notification: These chemicals are subject to the reporting requirements of Section 313 of the Emergency planning and Right-to-Know act of 1986 and of 40 CFR 372.
@ = Clean Air Act Hazardous Air Pollutant.
# = EPCRA Section 302 - Extremely Hazardous Substance.

NOTICE:
The information on this Material Safety Data Sheet relates only to the specific material designated herein and does not relate to use in combination with any other material or in any process.

Product Manager - Refinish Sales
Prepared by: E. L. Taylor