

(12) **Patent Application Publication**
MA et al.

(43) **Pub. Date:** **Aug. 14, 2025**

Publication Classification

(51) **Int. Cl.**
H10D 89/60 (2025.01)


(52) **U.S. Cl.**
CPC *H10D 89/713* (2025.01)

(57) **ABSTRACT**

Substrate-less silicon controlled rectifier (SCR) integrated circuit structures, and methods of fabricating substrate-less silicon controlled rectifier (SCR) integrated circuit structures, are described. For example, a substrate-less integrated circuit structure includes a first fin portion and a second fin portion that meet at a junction. A plurality of gate structures is over the first fin portion and a second fin portion. A plurality of P-type epitaxial structures and N-type epitaxial structures is between corresponding adjacent ones of the plurality of gate structures. Pairs of the P-type epitaxial structures alternate with pairs of the N-type epitaxial structures.

Related U.S. Application Data

(63) Continuation of application No. 17/357,754, filed on Jun. 24, 2021, now Pat. No. 12,328,947.






FIG. 1A





FIG. 1B



U
L




FIG. 2




FIG. 3




FIG. 4A




FIG. 5A




FIG. 4B

FIG. 5B




FIG. 4C




FIG. 5C




FIG. 4D




FIG. 5D




FIG. 4E




FIG. 5E




FIG. 4F




FIG. 5F




FIG. 4G




FIG. 5G




FIG. 4H






FIG. 5H



6
6
6
6



76E




FIG. 8A




FIG. 8B




FIG. 8C




FIG. 9




FIG. 10

SUBSTRATE-LESS SILICON CONTROLLED RECTIFIER (SCR) INTEGRATED CIRCUIT STRUCTURES

CROSS-REFERENCE TO RELATED APPLICATIONS

[0001] This application is a continuation of U.S. patent application Ser. No. 17/357,754 filed Jun. 24, 2021, the entire contents of which is hereby incorporated by reference herein.

TECHNICAL FIELD

[0002] Embodiments of the disclosure are in the field of integrated circuit structures and processing and, in particular, substrate-less silicon controlled rectifier (SCR) integrated circuit structures, and methods of fabricating substrate-less silicon controlled rectifier (SCR) integrated circuit structures.

BACKGROUND

[0003] For the past several decades, the scaling of features in integrated circuits has been a driving force behind an ever-growing semiconductor industry. Scaling to smaller and smaller features enables increased densities of functional units on the limited real estate of semiconductor chips. For example, shrinking transistor size allows for the incorporation of an increased number of memory or logic devices on a chip, leading to the fabrication of products with increased capacity. The drive for ever-more capacity, however, is not without issue. The necessity to optimize the performance of each device becomes increasingly significant.

[0004] In the manufacture of integrated circuit devices, multi-gate transistors, such as tri-gate transistors, have become more prevalent as device dimensions continue to scale down. In conventional processes, tri-gate transistors are generally fabricated on either bulk silicon substrates or silicon-on-insulator substrates. In some instances, bulk silicon substrates are preferred due to their lower cost and because they enable a less complicated tri-gate fabrication process. In another aspect, maintaining mobility improvement and short channel control as microelectronic device dimensions scale below the 10 nanometer (nm) node provides a challenge in device fabrication.

[0005] Scaling multi-gate and nanowire transistors has not been without consequence, however. As the dimensions of these fundamental building blocks of microelectronic circuitry are reduced and as the sheer number of fundamental building blocks fabricated in a given region is increased, the constraints on the lithographic processes used to pattern these building blocks have become overwhelming. In particular, there may be a trade-off between the smallest dimension of a feature patterned in a semiconductor stack (the critical dimension) and the spacing between such features.

BRIEF DESCRIPTION OF THE DRAWINGS

[0006] FIG. 1A illustrates a cross-sectional view of a silicon controlled rectifier (SCR) architecture, in accordance with an embodiment of the present disclosure.

[0007] FIG. 1B illustrates a cross-sectional view of another silicon controlled rectifier (SCR) architecture, in accordance with another embodiment of the present disclosure.

[0008] FIG. 1C illustrates a cross-sectional view of another silicon controlled rectifier (SCR) architecture, in accordance with another embodiment of the present disclosure.

[0009] FIG. 2 illustrates a cross-sectional view of another silicon controlled rectifier (SCR) architecture, in accordance with another embodiment of the present disclosure.

[0010] FIG. 3 illustrates a cross-sectional view of a non-planar integrated circuit structure as taken along a gate line, in accordance with an embodiment of the present disclosure.

[0011] FIGS. 4A-4H illustrate plan views of a substrate processed with double-sided device processing methods, in accordance with some embodiments.

[0012] FIGS. 5A-5H illustrate cross-sectional views of a substrate processed with double-sided device processing methods, in accordance with some embodiments.

[0013] FIG. 6 illustrates a cross-sectional view taken through nanowires and fins for a non-endcap architecture, in accordance with an embodiment of the present disclosure.

[0014] FIG. 7 illustrates a cross-sectional view taken through nanowires and fins for a self-aligned gate endcap (SAGE) architecture, in accordance with an embodiment of the present disclosure.

[0015] FIG. 8A illustrates a three-dimensional cross-sectional view of a nanowire-based integrated circuit structure, in accordance with an embodiment of the present disclosure.

[0016] FIG. 8B illustrates a cross-sectional source or drain view of the nanowire-based integrated circuit structure of FIG. 8A, as taken along an a-a' axis, in accordance with an embodiment of the present disclosure.

[0017] FIG. 8C illustrates a cross-sectional channel view of the nanowire-based integrated circuit structure of FIG. 8A, as taken along the b-b' axis, in accordance with an embodiment of the present disclosure.

[0018] FIG. 9 illustrates a computing device in accordance with one implementation of an embodiment of the disclosure.

[0019] FIG. 10 illustrates an interposer that includes one or more embodiments of the disclosure.

DESCRIPTION OF THE EMBODIMENTS

[0020] Substrate-less silicon controlled rectifier (SCR) integrated circuit structures, and methods of fabricating substrate-less silicon controlled rectifier (SCR) integrated circuit structures, are described. In the following description, numerous specific details are set forth, such as specific integration and material regimes, in order to provide a thorough understanding of embodiments of the present disclosure. It will be apparent to one skilled in the art that embodiments of the present disclosure may be practiced without these specific details. In other instances, well-known features, such as integrated circuit design layouts, are not described in detail in order to not unnecessarily obscure embodiments of the present disclosure. Furthermore, it is to be appreciated that the various embodiments shown in the Figures are illustrative representations and are not necessarily drawn to scale.

[0021] Certain terminology may also be used in the following description for the purpose of reference only, and thus are not intended to be limiting. For example, terms such as "upper", "lower", "above", and "below" refer to directions in the drawings to which reference is made. Terms such as "front", "back", "rear", and "side" describe the orientation and/or location of portions of the component within a

consistent but arbitrary frame of reference which is made clear by reference to the text and the associated drawings describing the component under discussion. Such terminology may include the words specifically mentioned above, derivatives thereof, and words of similar import.

[0022] Embodiments described herein may be directed to front-end-of-line (FEOL) semiconductor processing and structures. FEOL is the first portion of integrated circuit (IC) fabrication where the individual devices (e.g., transistors, capacitors, resistors, etc.) are patterned in the semiconductor substrate or layer. FEOL generally covers everything up to (but not including) the deposition of metal interconnect layers. Following the last FEOL operation, the result is typically a wafer with isolated transistors (e.g., without any wires).

[0023] Embodiments described herein may be directed to back-end-of-line (BEOL) semiconductor processing and structures. BEOL is the second portion of IC fabrication where the individual devices (e.g., transistors, capacitors, resistors, etc.) are interconnected with wiring on the wafer, e.g., the metallization layer or layers. BEOL includes contacts, insulating layers (dielectrics), metal levels, and bonding sites for chip-to-package connections. In the BEOL part of the fabrication stage contacts (pads), interconnect wires, vias and dielectric structures are formed. For modern IC processes, more than 10 metal layers may be added in the BEOL.

[0024] Embodiments described below may be applicable to FEOL processing and structures, BEOL processing and structures, or both FEOL and BEOL processing and structures. In particular, although an exemplary processing scheme may be illustrated using a FEOL processing scenario, such approaches may also be applicable to BEOL processing. Likewise, although an exemplary processing scheme may be illustrated using a BEOL processing scenario, such approaches may also be applicable to FEOL processing.

[0025] One or more embodiments described herein are directed to approaches for fabricating silicon controlled rectifiers (SCRs) in substrate-less technology, such as a technology used to enable backside metal interconnects. Embodiments described herein can be implemented to fabricate SRC using fin or nanowire technologies. Unless stated explicitly otherwise, reference to a nanowire structure can include nanowire structure and/or nanoribbon structures.

[0026] To provide context, silicon controlled rectifiers (SCRs) are area efficient electrostatic discharge (ESD) devices characterized by deep snapback, large failure current and low on-resistance, and are commonly used in failsafe IOs. Traditional methods to form SCR devices rely on an inter-diffused well design in a thick silicon (Si) substrate. However, in substrate-less or nanowire technologies where the Si substrate is removed or the devices are isolated from the substrate, traditional approaches to SCR fabrication cannot be used.

[0027] In accordance with one or more embodiments of the present disclosure, approaches for fabricating SCRs in substrate-less/nanowire technologies are described. In one embodiment, a PNP junction is formed from P (epi) to Nwell, then Pwell/Psub to N (epi). In one embodiment, the Nwell and Pwell have their own taps as a trigger node. With different trigger circuitry, SCR performance such as trigger voltage, holding current and leakage current can be fine-tuned.

[0028] In an embodiment, as an added advantage over bulk Si SCR designs, a decreased electrical length of a current path can decrease the transient voltage overshoot often observed for bulk Si SCR designs. SCR design in thick Si substrate normally has a large overshoot issue due to deep STI isolation in between. Ballasting resistance and secondary protection is often needed to pair with SCR to safely clamp a victim voltage when large overshoots are present. Addressing one or more of the above issue, embodiments described herein can be implemented to enable SCR in a substrate-less or nanowire technology. Embodiments can include a lateral Fin-based SCR, a vertical fin-based SCR, and a lateral nanowire or ribbon-based SCR.

[0029] In a first aspect, lateral SCRs with shallow epitaxial undercut for leakage suppression are described. In a traditional STI SCR, a current path goes under the STI, but such a path no longer exists in substrate-less processes due to the backside polish. To create a new current path through a subfin region, a lateral SCR solution is described. An epitaxial undercut process on a Si island can be introduced to reduce the leakage. In one embodiment, epi is skipped between the junctions to push the current under the EUC and avoid a majority of leakage path influenced by gate electrostatics. In one embodiment, compared with STI depth, epi undercut depth is usually less which can remedy large overshoot issues.

[0030] As an example, FIG. 1A illustrates a cross-sectional view of a silicon controlled rectifier (SCR) architecture, in accordance with an embodiment of the present disclosure.

[0031] Referring to FIG. 1A, an integrated circuit structure **100** includes portions **102** coupled to ground, a portion **104** coupled to a pad, and a portion **106** coupled to a trigger. The integrated circuit structure **100** includes a first fin portion **108A** and a second fin portion **108B**, such as first and second silicon fin portions. In one embodiment, the first fin portion **108A** includes P-well doping, and the second fin portion **108B** includes N-well doping. The first fin portion **108A** and the second fin portion **108B** meet at a junction **109**. A plurality of gate structures **112** is over the first fin portion **108A** and the second fin portion **108B**. In one embodiment, each of the plurality of gate structures **112** includes a gate cap **112A** on a corresponding gate portion **112B**, as is depicted. P-type epitaxial (Epi) structures **116**, such as boron-doped silicon or boron-doped silicon germanium structures, are between adjacent ones of some of the plurality of gate structures **112**. N-type epitaxial (Epi) structures **118**, such as phosphorous-doped silicon structures, are between adjacent ones of others of the plurality of gate structures **112**. Open locations **120** are between adjacent ones of yet others of the plurality of gate structures **112**. Each open location **120** can represent a region where a P-type epitaxial (Epi) structure **116** or an N-type epitaxial (Epi) structure **118** is removed or is blocked from being formed. In an embodiment, pairs of P-type epitaxial (Epi) structures **116** alternate with pairs of N-type epitaxial (Epi) structures **118**, and a corresponding single open location **120** is between neighboring pairs of P-type epitaxial (Epi) structures **116** and pairs of N-type epitaxial (Epi) structures **118**, as is depicted.

[0032] It is to be appreciated that, in an embodiment, the epi undercut depth and number of epi structures skipped can be changed to balance leakage and overshoot concerns. Also, special SCR specific dopant underneath a junction can

be used to reduce the leakage. As an example, FIG. 1B illustrates a cross-sectional view of another silicon controlled rectifier (SCR) architecture, in accordance with another embodiment of the present disclosure.

[0033] Referring to FIG. 1B, an integrated circuit structure 130 includes portions 132 coupled to ground, a portion 134 coupled to a pad, and a portion 136 coupled to a trigger. The integrated circuit structure 130 includes a first fin portion 138A and a second fin portion 138B, such as first and second silicon fin portions. In one embodiment, the first fin portion 138A includes P-well doping, and the second fin portion 138B includes N-well doping. The first fin portion 108A and the second fin portion 108B meet at a junction 139. In an embodiment, an N-dopant region 152 can be formed in the first fin portion 138A, and an N-dopant region 154 can be formed in the second fin portion 138B in locations proximate the junction 139, as is depicted, e.g., for leakage reduction. A plurality of gate structures 142 is over the first fin portion 138A and the second fin portion 138B. In one embodiment, each of the plurality of gate structures 142 includes a gate cap 142A on a corresponding gate portion 142B, as is depicted. P-type epitaxial (Epi) structures 146, such as boron-doped silicon or boron-doped silicon germanium structures, are between adjacent ones of some of the plurality of gate structures 142. N-type epitaxial (Epi) structures 148, such as phosphorous-doped silicon structures, are between adjacent ones of others of the plurality of gate structures 142. Open locations 150 are between adjacent ones of yet others of the plurality of gate structures 142. Each open location 150 can represent a region where a P-type epitaxial (Epi) structure 146 or an N-type epitaxial (Epi) structure 148 is removed or is blocked from being formed. In an embodiment, pairs of P-type epitaxial (Epi) structures 146 alternate with pairs of N-type epitaxial (Epi) structures 148, and a corresponding pair of open locations 150 is between neighboring pairs of P-type epitaxial (Epi) structures 146 and pairs of N-type epitaxial (Epi) structures 148, as is depicted.

[0034] In a second aspect, area efficient vertical SCRs for substrate-less technology are described. In an embodiment, a vertical PN junction in an SCR structure is achieved using a source-drain (S/D) epi and a semiconductor (SC)-Fin and a buried high doped SC of opposite polarity than the S/D epi. The PN junction along with the capability to contact the buried-doped layer from backside metal layer can enable a vertical diode for substrate-less technologies. By implementing DJN and DJP vertical diode next to each other a vertical area-efficient SCR could be formed. Also, SCR pad and vss signal is more exposed to each other without a trigger node in between, potentially remedying overshoot issues.

[0035] As an example, FIG. 1C illustrates a cross-sectional view of another silicon controlled rectifier (SCR) architecture, in accordance with another embodiment of the present disclosure.

[0036] Referring to FIG. 1C, an integrated circuit structure 160 includes a portion 162 coupled to ground and a portion 164 coupled to a pad. The integrated circuit structure 160 includes a first fin portion 168A and a second fin portion 168B, such as first and second silicon fin portions. In one embodiment, the first fin portion 168A includes P-well doping, and the second fin portion 168B includes N-well doping. The first fin portion 168A and the second fin portion 168B meet at a junction 169. A plurality of gate structures

172 is over the first fin portion 168A and the second fin portion 168B. In one embodiment, each of the plurality of gate structures 172 includes a gate cap 172A on a corresponding gate portion 172B, as is depicted. P-type epitaxial (Epi) structures 176, such as boron-doped silicon or boron-doped silicon germanium structures, are between adjacent ones of some of the plurality of gate structures 172. N-type epitaxial (Epi) structures 178, such as phosphorous-doped silicon structures, are between adjacent ones of others of the plurality of gate structures 172. An open location 180 is between adjacent ones of yet others of the plurality of gate structures 172. The open location 180 can represent a region where a P-type epitaxial (Epi) structure 176 or an N-type epitaxial (Epi) structure 178 is removed or is blocked from being formed. In an embodiment, a pair of P-type epitaxial (Epi) structures 176 is separated from a pair of N-type epitaxial (Epi) structures 178, and a corresponding single open location 180 is between the pair of P-type epitaxial (Epi) structures 176 and the pair of N-type epitaxial (Epi) structures 178, as is depicted. In an embodiment, a backside metallization structure 190 is coupled to a bottom of the first fin portion 168A, and a backside metallization structure 192 is coupled to a bottom of the second fin portion 168B, as is depicted. In one such embodiment, the backside metallization structure 190 is coupled to ground, and the backside metallization structure 192 is coupled to or is a trigger for an SCR. It is to be appreciated that, in an embodiment, the epi undercut depth and number of epi structures skipped can be changed to balance leakage and overshoot concerns. Also, special SCR specific dopant underneath a junction can be used to reduce the leakage.

[0037] In a third aspect, ribbon SCRs are used in nanowire technology. To support SCRs in ribbon-based technologies where a device is isolated from a substrate, PNPJ junctions can be implemented inside ribbon wires. Alternating P and N epi together with special SCR Ntype/Ptype doping inside ribbon wires can form a PNPJ junction. Inside ribbon wires, PN junction location and performance can be adjusted by implant mask locations.

[0038] As an example, FIG. 2 illustrates a cross-sectional view of another silicon controlled rectifier (SCR) architecture, in accordance with another embodiment of the present disclosure.

[0039] Referring to FIG. 2, an integrated circuit structure 200 includes portions 202 coupled to ground, a portion 204 coupled to a pad, and a portion 206 coupled to a trigger. The integrated circuit structure 200 includes stacks of nanowires 208, such as stacks of silicon nanowires. A plurality of gate structures 212, such as polysilicon gate structures is over the stacks of nanowires 208 and between vertically adjacent nanowires within a stack. P-type epitaxial (Epi) structures 216, such as boron-doped silicon or boron-doped silicon germanium structures, are adjacent to ones of some of the plurality of gate structures 212. N-type epitaxial (Epi) structures 218, such as phosphorous-doped silicon structures, are adjacent to others of the plurality of gate structures 212. In an embodiment, individual P-type epitaxial (Epi) structures 216 alternate with individual N-type epitaxial (Epi) structures 218, as is depicted. In one embodiment, the plurality of gate structures 212, the P-type epitaxial (Epi) structures 216 and the N-type epitaxial (Epi) structures 218 are formed over an isolation layer 220, such as a silicon nitride layer, which may be further formed over a back polish layer 222, as is depicted.

[0040] It is to be appreciated that, as used throughout the disclosure, a fin portion, a nanowire, a nanoribbon, or a fin described herein may be a silicon fin portion, a silicon nanowire, a silicon nanoribbon, or a silicon fin. As used throughout, a silicon layer or structure may be used to describe a silicon material composed of a very substantial amount of, if not all, silicon. However, it is to be appreciated that, practically, 100% pure Si may be difficult to form and, hence, could include a tiny percentage of carbon, germanium or tin. Such impurities may be included as an unavoidable impurity or component during deposition of Si or may “contaminate” the Si upon diffusion during post deposition processing. As such, embodiments described herein directed to a silicon layer or structure may include a silicon layer or structure that contains a relatively small amount, e.g., “impurity” level, non-Si atoms or species, such as Ge, C or Sn. It is to be appreciated that a silicon layer or structure as described herein may be undoped or may be doped with dopant atoms such as boron, phosphorous or arsenic.

[0041] It is to be appreciated that, as used throughout the disclosure, a fin portion, a nanowire, a nanoribbon, or a fin described herein may be a silicon germanium fin portion, a silicon germanium nanowire, a silicon germanium nanoribbon, or a silicon germanium fin. As used throughout, a silicon germanium layer or structure may be used to describe a silicon germanium material composed of substantial portions of both silicon and germanium, such as at least 5% of both. In some embodiments, the amount of germanium is greater than the amount of silicon. In particular embodiments, a silicon germanium layer or structure includes approximately 60% germanium and approximately 40% silicon ($\text{Si}_{40}\text{Ge}_{60}$). In other embodiments, the amount of silicon is greater than the amount of germanium. In particular embodiments, a silicon germanium layer or structure includes approximately 30% germanium and approximately 70% silicon ($\text{Si}_{70}\text{Ge}_{30}$). It is to be appreciated that, practically, 100% pure silicon germanium (referred to generally as SiGe) may be difficult to form and, hence, could include a tiny percentage of carbon or tin. Such impurities may be included as an unavoidable impurity or component during deposition of SiGe or may “contaminate” the SiGe upon diffusion during post deposition processing. As such, embodiments described herein directed to a silicon germanium layer or structure may include a silicon germanium layer or structure that contains a relatively small amount, e.g., “impurity” level, non-Ge and non-Si atoms or species, such as carbon or tin. It is to be appreciated that a silicon germanium layer or structure as described herein may be undoped or may be doped with dopant atoms such as boron, phosphorous or arsenic.

[0042] It is to be appreciated that the SCR structures described above in association with FIGS. 1A, 1B, 1C and/or 2 can be co-integrated with other substrate-less integrated circuits structures. As an example of a substrate-less device, FIG. 3 illustrate a cross-sectional view of a non-planar integrated circuit structure as taken along a gate line, in accordance with an embodiment of the present disclosure.

[0043] Referring to FIG. 3, a semiconductor structure or device 300 includes a non-planar active region (e.g., a fin structure including protruding fin portion 304 and sub-fin region 305) within a trench isolation region 306. In an embodiment, instead of a solid fin, the non-planar active region is separated into nanowires (such as nanowires 304A

and 304B) above sub-fin region 305, as is represented by the dashed lines. In either case, for ease of description for non-planar integrated circuit structure 300, a non-planar active region 304 is referenced below as a protruding fin portion. It is to be appreciated that, in one embodiment, there is no bulk substrate coupled to the sub-fin region 305.

[0044] A gate line 308 is disposed over the protruding portions 304 of the non-planar active region (including, if applicable, surrounding nanowires 304A and 304B), as well as over a portion of the trench isolation region 306. As shown, gate line 308 includes a gate electrode 350 and a gate dielectric layer 352. In one embodiment, gate line 308 may also include a dielectric cap layer 354. A gate contact 314, and overlying gate contact via 316 are also seen from this perspective, along with an overlying metal interconnect 360, all of which are disposed in inter-layer dielectric stacks or layers 370. Also seen from the perspective of FIG. 3, the gate contact 314 is, in one embodiment, disposed over trench isolation region 306, but not over the non-planar active regions.

[0045] In an embodiment, the semiconductor structure or device 300 is a non-planar device such as, but not limited to, a fin-FET device, a tri-gate device, a nano-ribbon device, or a nano-wire device. In such an embodiment, a corresponding semiconducting channel region is composed of or is formed in a three-dimensional body. In one such embodiment, the gate electrode stacks of gate lines 308 surround at least a top surface and a pair of sidewalls of the three-dimensional body.

[0046] As is also depicted in FIG. 3, in an embodiment, an interface 380 exists between a protruding fin portion 304 and sub-fin region 305. The interface 380 can be a transition region between a doped sub-fin region 305 and a lightly or undoped upper fin portion 304. In one such embodiment, each fin is approximately 10 nanometers wide or less, and sub-fin dopants are supplied from an adjacent solid state doping layer at the sub-fin location. In a particular such embodiment, each fin is less than 10 nanometers wide. In another embodiment, the subfin region is a dielectric material, formed by recessing the fin through a wet or dry etch, and filling the recessed cavity with a conformal or flowable dielectric.

[0047] Although not depicted in FIG. 3, it is to be appreciated that source or drain regions of or adjacent to the protruding fin portions 304 are on either side of the gate line 308, i.e., into and out of the page. In one embodiment, the source or drain regions are doped portions of original material of the protruding fin portions 304. In another embodiment, the material of the protruding fin portions 304 is removed and replaced with another semiconductor material, e.g., by epitaxial deposition to form discrete epitaxial nubs or non-discrete epitaxial structures. In either embodiment, the source or drain regions may extend below the height of dielectric layer of trench isolation region 306, i.e., into the sub-fin region 305. In accordance with an embodiment of the present disclosure, the more heavily doped sub-fin regions, i.e., the doped portions of the fins below interface 380, inhibits source to drain leakage through this portion of the bulk semiconductor fins.

[0048] With reference again to FIG. 3, in an embodiment, fins 304/305 (and, possibly nanowires 304A and 304B) are composed of a crystalline silicon, silicon/germanium or germanium layer doped with a charge carrier, such as but not limited to phosphorus, arsenic, boron or a combination

thereof. In one embodiment, the concentration of silicon atoms is greater than 93%. In another embodiment, fins **304/305** are composed of a group III-V material, such as, but not limited to, gallium nitride, gallium phosphide, gallium arsenide, indium phosphide, indium antimonide, indium gallium arsenide, aluminum gallium arsenide, indium gallium phosphide, or a combination thereof. Trench isolation region **306** may be composed of a dielectric material such as, but not limited to, silicon dioxide, silicon oxy-nitride, silicon nitride, or carbon-doped silicon nitride.

[0049] Gate line **308** may be composed of a gate electrode stack which includes a gate dielectric layer **352** and a gate electrode layer **350**. In an embodiment, the gate electrode of the gate electrode stack is composed of a metal gate and the gate dielectric layer is composed of a high-k material. For example, in one embodiment, the gate dielectric layer is composed of a material such as, but not limited to, hafnium oxide, hafnium oxy-nitride, hafnium silicate, lanthanum oxide, zirconium oxide, zirconium silicate, tantalum oxide, barium strontium titanate, barium titanate, strontium titanate, yttrium oxide, aluminum oxide, lead scandium tantalum oxide, lead zinc niobate, or a combination thereof. Furthermore, a portion of gate dielectric layer may include a layer of native oxide formed from the top few layers of the substrate fin **304**. In an embodiment, the gate dielectric layer is composed of a top high-k portion and a lower portion composed of an oxide of a semiconductor material. In one embodiment, the gate dielectric layer is composed of a top portion of hafnium oxide and a bottom portion of silicon dioxide or silicon oxy-nitride. In some implementations, a portion of the gate dielectric is a “U”-shaped structure that includes a bottom portion substantially parallel to the surface of the substrate and two sidewall portions that are substantially perpendicular to the top surface of the substrate.

[0050] In one embodiment, the gate electrode is composed of a metal layer such as, but not limited to, metal nitrides, metal carbides, metal silicides, metal aluminides, hafnium, zirconium, titanium, tantalum, aluminum, ruthenium, palladium, platinum, cobalt, nickel or conductive metal oxides. In a specific embodiment, the gate electrode is composed of a non-workfunction-setting fill material formed above a metal workfunction-setting layer. The gate electrode layer may consist of a P-type workfunction metal or an N-type workfunction metal, depending on whether the transistor is to be a PMOS or an NMOS transistor. In some implementations, the gate electrode layer may consist of a stack of two or more metal layers, where one or more metal layers are workfunction metal layers and at least one metal layer is a conductive fill layer. For a PMOS transistor, metals that may be used for the gate electrode include, but are not limited to, ruthenium, palladium, platinum, cobalt, nickel, and conductive metal oxides, e.g., ruthenium oxide. A P-type metal layer will enable the formation of a PMOS gate electrode with a workfunction that is between about 4.9 eV and about 5.2 eV. For an NMOS transistor, metals that may be used for the gate electrode include, but are not limited to, hafnium, zirconium, titanium, tantalum, aluminum, alloys of these metals, and carbides of these metals such as hafnium carbide, zirconium carbide, titanium carbide, tantalum carbide, and aluminum carbide. An N-type metal layer will enable the formation of an NMOS gate electrode with a workfunction that is between about 3.9 eV and about 4.2 eV. In some implementations, the gate electrode may consist of a “U”-

shaped structure that includes a bottom portion substantially parallel to the surface of the substrate and two sidewall portions that are substantially perpendicular to the top surface of the substrate. In another implementation, at least one of the metal layers that form the gate electrode may simply be a planar layer that is substantially parallel to the top surface of the substrate and does not include sidewall portions substantially perpendicular to the top surface of the substrate. In further implementations of the disclosure, the gate electrode may consist of a combination of U-shaped structures and planar, non-U-shaped structures. For example, the gate electrode may consist of one or more U-shaped metal layers formed atop one or more planar, non-U-shaped layers.

[0051] Spacers associated with the gate electrode stacks may be composed of a material suitable to ultimately electrically isolate, or contribute to the isolation of, a permanent gate structure from adjacent conductive contacts, such as self-aligned contacts. For example, in one embodiment, the spacers are composed of a dielectric material such as, but not limited to, silicon dioxide, silicon oxy-nitride, silicon nitride, or carbon-doped silicon nitride.

[0052] Gate contact **314** and overlying gate contact via **316** may be composed of a conductive material. In an embodiment, one or more of the contacts or vias are composed of a metal species. The metal species may be a pure metal, such as tungsten, nickel, or cobalt, or may be an alloy such as a metal-metal alloy or a metal-semiconductor alloy (e.g., such as a silicide material).

[0053] In an embodiment (although not shown), a contact pattern which is essentially perfectly aligned to an existing gate pattern **308** is formed while eliminating the use of a lithographic step with exceedingly tight registration budget. In one such embodiment, the self-aligned approach enables the use of intrinsically highly selective wet etching (e.g., versus conventionally implemented dry or plasma etching) to generate contact openings. In an embodiment, a contact pattern is formed by utilizing an existing gate pattern in combination with a contact plug lithography operation. In one such embodiment, the approach enables elimination of the need for an otherwise critical lithography operation to generate a contact pattern, as used in conventional approaches. In an embodiment, a trench contact grid is not separately patterned, but is rather formed between poly (gate) lines. For example, in one such embodiment, a trench contact grid is formed subsequent to gate grating patterning but prior to gate grating cuts.

[0054] In an embodiment, providing structure **300** involves fabrication of the gate stack structure **308** by a replacement gate process. In such a scheme, dummy gate material such as polysilicon or silicon nitride pillar material, may be removed and replaced with permanent gate electrode material. In one such embodiment, a permanent gate dielectric layer is also formed in this process, as opposed to being carried through from earlier processing. In an embodiment, dummy gates are removed by a dry etch or wet etch process. In one embodiment, dummy gates are composed of polycrystalline silicon or amorphous silicon and are removed with a dry etch process including use of SF_6 . In another embodiment, dummy gates are composed of polycrystalline silicon or amorphous silicon and are removed with a wet etch process including use of aqueous NH_4OH or tetramethylammonium hydroxide. In one

embodiment, dummy gates are composed of silicon nitride and are removed with a wet etch including aqueous phosphoric acid.

[0055] Referring again to FIG. 3, the arrangement of semiconductor structure or device **300** places the gate contact over isolation regions. Such an arrangement may be viewed as inefficient use of layout space. In another embodiment, however, a semiconductor device has contact structures that contact portions of a gate electrode formed over an active region, e.g., over a sub-fin **305**, and in a same layer as a trench contact via.

[0056] It is to be appreciated that not all aspects of the processes described above need be practiced to fall within the spirit and scope of embodiments of the present disclosure. For example, in one embodiment, dummy gates need not ever be formed prior to fabricating gate contacts over active portions of the gate stacks. The gate stacks described above may actually be permanent gate stacks as initially formed. Also, the processes described herein may be used to fabricate one or a plurality of semiconductor devices. The semiconductor devices may be transistors or like devices. For example, in an embodiment, the semiconductor devices are a metal-oxide semiconductor (MOS) transistors for logic or memory, or are bipolar transistors. Also, in an embodiment, the semiconductor devices have a three-dimensional architecture, such as a trigate device, an independently accessed double gate device, or a FIN-FET. One or more embodiments may be particularly useful for fabricating semiconductor devices at a sub-10 nanometer (10 nm) technology node.

[0057] In an embodiment, as used throughout the present description, interlayer dielectric (ILD) material is composed of or includes a layer of a dielectric or insulating material. Examples of suitable dielectric materials include, but are not limited to, oxides of silicon (e.g., silicon dioxide (SiO_2)), doped oxides of silicon, fluorinated oxides of silicon, carbon doped oxides of silicon, various low-k dielectric materials known in the arts, and combinations thereof. The interlayer dielectric material may be formed by conventional techniques, such as, for example, chemical vapor deposition (CVD), physical vapor deposition (PVD), or by other deposition methods.

[0058] In an embodiment, as is also used throughout the present description, metal lines or interconnect line material (and via material) is composed of one or more metal or other conductive structures. A common example is the use of copper lines and structures that may or may not include barrier layers between the copper and surrounding ILD material. As used herein, the term metal includes alloys, stacks, and other combinations of multiple metals. For example, the metal interconnect lines may include barrier layers (e.g., layers including one or more of Ta, TaN, Ti or TiN), stacks of different metals or alloys, etc. Thus, the interconnect lines may be a single material layer, or may be formed from several layers, including conductive liner layers and fill layers. Any suitable deposition process, such as electroplating, chemical vapor deposition or physical vapor deposition, may be used to form interconnect lines. In an embodiment, the interconnect lines are composed of a conductive material such as, but not limited to, Cu, Al, Ti, Zr, Hf, V, Ru, Co, Ni, Pd, Pt, W, Ag, Au or alloys thereof. The interconnect lines are also sometimes referred to in the art as traces, wires, lines, metal, or simply interconnect.

[0059] In an embodiment, as is also used throughout the present description, hardmask materials, capping layers, or plugs are composed of dielectric materials different from the interlayer dielectric material. In one embodiment, different hardmask, capping or plug materials may be used in different regions so as to provide different growth or etch selectivity to each other and to the underlying dielectric and metal layers. In some embodiments, a hardmask layer, capping or plug layer includes a layer of a nitride of silicon (e.g., silicon nitride) or a layer of an oxide of silicon, or both, or a combination thereof. Other suitable materials may include carbon-based materials. Other hardmask, capping or plug layers known in the arts may be used depending upon the particular implementation. The hardmask, capping or plug layers may be formed by CVD, PVD, or by other deposition methods.

[0060] In an embodiment, as is also used throughout the present description, lithographic operations are performed using 193 nm immersion litho (i193), EUV and/or EBDW lithography, or the like. A positive tone or a negative tone resist may be used. In one embodiment, a lithographic mask is a trilayer mask composed of a topographic masking portion, an anti-reflective coating (ARC) layer, and a photoresist layer. In a particular such embodiment, the topographic masking portion is a carbon hardmask (CHM) layer and the anti-reflective coating layer is a silicon ARC layer.

[0061] In another aspect, integrated circuit structures described herein may be fabricated using a back-side reveal of front-side structures fabrication approach. In some exemplary embodiments, reveal of the back-side of a transistor or other device structure entails wafer-level back-side processing. In contrast to a conventional TSV-type technology, a reveal of the back-side of a transistor as described herein may be performed at the density of the device cells, and even within sub-regions of a device. Furthermore, such a reveal of the back-side of a transistor may be performed to remove substantially all of a donor substrate upon which a device layer was disposed during front-side device processing. As such, a microns-deep TSV becomes unnecessary with the thickness of semiconductor in the device cells following a reveal of the back-side of a transistor potentially being only tens or hundreds of nanometers.

[0062] Reveal techniques described herein may enable a paradigm shift from “bottom-up” device fabrication to “center-out” fabrication, where the “center” is any layer that is employed in front-side fabrication, revealed from the back side, and again employed in back-side fabrication. Processing of both a front side and revealed back side of a device structure may address many of the challenges associated with fabricating 3D ICs when primarily relying on front-side processing.

[0063] A reveal of the back-side of a transistor approach may be employed for example to remove at least a portion of a carrier layer and intervening layer of a donor-host substrate assembly, for example as illustrated in FIGS. 4A-4H and 5A-5H, described below. The process flow begins with an input of a donor-host substrate assembly. A thickness of a carrier layer in the donor-host substrate is polished (e.g., CMP) and/or etched with a wet or dry (e.g., plasma) etch process. Any grind, polish, and/or wet/dry etch process known to be suitable for the composition of the carrier layer may be employed. For example, where the carrier layer is a group IV semiconductor (e.g., silicon) a CMP slurry known to be suitable for thinning the semicon-

ductor may be employed. Likewise, any wet etchant or plasma etch process known to be suitable for thinning the group IV semiconductor may also be employed.

[0064] In some embodiments, the above is preceded by cleaving the carrier layer along a fracture plane substantially parallel to the intervening layer. The cleaving or fracture process may be utilized to remove a substantial portion of the carrier layer as a bulk mass, reducing the polish or etch time needed to remove the carrier layer. For example, where a carrier layer is 400-900 μm in thickness, 100-700 μm may be cleaved off by practicing any blanket implant known to promote a wafer-level fracture. In some exemplary embodiments, a light element (e.g., H, He, or Li) is implanted to a uniform target depth within the carrier layer where the fracture plane is desired. Following such a cleaving process, the thickness of the carrier layer remaining in the donor-host substrate assembly may then be polished or etched to complete removal. Alternatively, where the carrier layer is not fractured, the grind, polish and/or etch operation may be employed to remove a greater thickness of the carrier layer.

[0065] Next, exposure of an intervening layer is detected. Detection is used to identify a point when the back-side surface of the donor substrate has advanced to nearly the device layer. Any endpoint detection technique known to be suitable for detecting a transition between the materials employed for the carrier layer and the intervening layer may be practiced. In some embodiments, one or more endpoint criteria are based on detecting a change in optical absorbance or emission of the back-side surface of the donor substrate during the polishing or etching performed. In some other embodiments, the endpoint criteria are associated with a change in optical absorbance or emission of byproducts during the polishing or etching of the donor substrate back-side surface. For example, absorbance or emission wavelengths associated with the carrier layer etch byproducts may change as a function of the different compositions of the carrier layer and intervening layer. In other embodiments, the endpoint criteria are associated with a change in mass of species in byproducts of polishing or etching the back-side surface of the donor substrate. For example, the byproducts of processing may be sampled through a quadrupole mass analyzer and a change in the species mass may be correlated to the different compositions of the carrier layer and intervening layer. In another exemplary embodiment, the endpoint criteria is associated with a change in friction between a back-side surface of the donor substrate and a polishing surface in contact with the back-side surface of the donor substrate.

[0066] Detection of the intervening layer may be enhanced where the removal process is selective to the carrier layer relative to the intervening layer as non-uniformity in the carrier removal process may be mitigated by an etch rate delta between the carrier layer and intervening layer. Detection may even be skipped if the grind, polish and/or etch operation removes the intervening layer at a rate sufficiently below the rate at which the carrier layer is removed. If an endpoint criteria is not employed, a grind, polish and/or etch operation of a predetermined fixed duration may stop on the intervening layer material if the thickness of the intervening layer is sufficient for the selectivity of the etch. In some examples, the carrier etch rate:intervening layer etch rate is 3:1-10:1, or more.

[0067] Upon exposing the intervening layer, at least a portion of the intervening layer may be removed. For

example, one or more component layers of the intervening layer may be removed. A thickness of the intervening layer may be removed uniformly by a polish, for example. Alternatively, a thickness of the intervening layer may be removed with a masked or blanket etch process. The process may employ the same polish or etch process as that employed to thin the carrier, or may be a distinct process with distinct process parameters. For example, where the intervening layer provides an etch stop for the carrier removal process, the latter operation may employ a different polish or etch process that favors removal of the intervening layer over removal of the device layer. Where less than a few hundred nanometers of intervening layer thickness is to be removed, the removal process may be relatively slow, optimized for across-wafer uniformity, and more precisely controlled than that employed for removal of the carrier layer. A CMP process employed may, for example employ a slurry that offers very high selectivity (e.g., 100:1-300:1, or more) between semiconductor (e.g., silicon) and dielectric material (e.g., SiO) surrounding the device layer and embedded within the intervening layer, for example, as electrical isolation between adjacent device regions.

[0068] For embodiments where the device layer is revealed through complete removal of the intervening layer, backside processing may commence on an exposed backside of the device layer or specific device regions there in. In some embodiments, the backside device layer processing includes a further polish or wet/dry etch through a thickness of the device layer disposed between the intervening layer and a device region previously fabricated in the device layer, such as a source or drain region.

[0069] In some embodiments where the carrier layer, intervening layer, or device layer backside is recessed with a wet and/or plasma etch, such an etch may be a patterned etch or a materially selective etch that imparts significant non-planarity or topography into the device layer back-side surface. As described further below, the patterning may be within a device cell (i.e., "intra-cell" patterning) or may be across device cells (i.e., "inter-cell" patterning). In some patterned etch embodiments, at least a partial thickness of the intervening layer is employed as a hard mask for back-side device layer patterning. Hence, a masked etch process may preface a correspondingly masked device layer etch.

[0070] The above described processing scheme may result in a donor-host substrate assembly that includes IC devices that have a back side of an intervening layer, a back side of the device layer, and/or back side of one or more semiconductor regions within the device layer, and/or front-side metallization revealed. Additional backside processing of any of these revealed regions may then be performed during downstream processing.

[0071] In accordance with one or more embodiments of the present disclosure, in order to enable backside access to a partitioned source or drain contact structure, a double-sided device processing scheme may be practiced at the wafer-level. In some exemplary embodiments, a large formal substrate (e.g., 300 or 450 mm diameter) wafer may be processed. In an exemplary processing scheme, a donor substrate including a device layer is provided. In some embodiments, the device layer is a semiconductor material that is employed by an IC device. As one example, in a transistor device, such as a field effect transistor (FET), the channel semiconductor is formed from the semiconductor

device layer. As another example, for an optical device, such as a photodiode, the drift and/or gain semiconductor is formed from the device layer. The device layer may also be employed in a passive structure with an IC device. For example, an optical waveguide may employ semiconductor patterned from the device layer.

[0072] In some embodiments, the donor substrate includes a stack of material layers. Such a material stack may facilitate subsequent formation of an IC device stratum that includes the device layer but lacks other layers of the donor substrate. In an exemplary embodiment, the donor substrate includes a carrier layer separated from the device layer by one or more intervening material layers. The carrier layer is to provide mechanical support during front-side processing of the device layer. The carrier may also provide the basis for crystallinity in the semiconductor device layer. The intervening layer(s) may facilitate removal of the carrier layer and/or the reveal of the device layer backside.

[0073] Front-side fabrication operations are then performed to form a device structure that includes one or more regions in the device layer. Any known front-side processing techniques may be employed to form any known IC device and exemplary embodiments are further described elsewhere herein. A front side of the donor substrate is then joined to a host substrate to form a device-host assembly. The host substrate is to provide front-side mechanical support during back-side processing of the device layer. The host substrate may also entail integrated circuitry with which the IC devices fabricated on the donor substrate are interconnected. For such embodiments, joining of the host and donor substrate may further entail formation of 3D interconnect structures through hybrid (dielectric/metal) bonding. Any known host substrate and wafer-level joining techniques may be employed.

[0074] The process flow continues where the back side of the device stratum is revealed by removing at least a portion of the carrier layer. In some further embodiments, portions of any intervening layer and/or front-side materials deposited over the device layer may also be removed during the reveal operation. As described elsewhere herein in the context of some exemplary embodiments, an intervening layer(s) may facilitate a highly-uniform exposure of the device stratum back-side, for example serving as one or more of an etch marker or etch stop employed in the wafer-level backside reveal process. Device stratum surfaces exposed from the back side are processed to form a double-side device stratum. Native materials, such as any of those of the donor substrate, which interfaced with the device regions may then be replaced with one or more non-native materials. For example, a portion of a semiconductor device layer or intervening layer may be replaced with one or more other semiconductor, metal, or dielectric materials. In some further embodiments, portions of the front-side materials removed during the reveal operation may also be replaced. For example, a portion of a dielectric spacer, gate stack, or contact metallization formed during front-side device fabrication may be replaced with one or more other semiconductor, metal, or dielectric materials during backside deprocessing/reprocessing of the front-side device. In still other embodiments, a second device stratum or metal interposer is bonded to the reveal back-side.

[0075] The above process flow provides a device stratum-host substrate assembly. The device stratum-host assembly may then be further processed. For example, any known

technique may be employed to singulate and package the device stratum-host substrate assembly. Where the host substrate is entirely sacrificial, packaging of the device stratum-host substrate may entail separation of the host substrate from the device stratum. Where the host substrate is not entirely sacrificial (e.g., where the host substrate also includes a device stratum), the device stratum-host assembly output may be fed back as a host substrate input during a subsequent iteration of the above process flow. Iteration of the above approach may thus form a wafer-level assembly of any number of double-side device strata, each only tens or hundreds of nanometers in thickness, for example. In some embodiments, and as further described elsewhere herein, one or more device cells within a device stratum are electrically tested, for example as a yield control point in the fabrication of a wafer-level assembly of double-side device strata. In some embodiments, the electrical test entails back-side device probing.

[0076] FIGS. 4A-4H illustrate plan views of a substrate processed with double-sided device processing methods, in accordance with some embodiments. FIGS. 5A-5H illustrate cross-sectional views of a substrate processed with double-sided device processing methods, in accordance with some embodiments.

[0077] As shown in FIGS. 4A and 5A, donor substrate **401** includes a plurality of IC die **411** in an arbitrary spatial layout over a front-side wafer surface. Front-side processing of IC die **411** may have been performed following any techniques to form any device structures. In exemplary embodiments, die **411** include one or more semiconductor regions within device layer **415**. An intervening layer **410** separates device layer **415** from carrier layer **405**. In the exemplary embodiment, intervening layer **410** is in direct contact with both carrier layer **405** and device layer **415**. Alternatively, one or more spacer layers may be disposed between intervening layer **410** and device layer **415** and/or carrier layer **405**. Donor substrate **401** may further include other layers, for example disposed over device layer **415** and/or below carrier layer **405**.

[0078] Device layer **415** may include one or more layers of any device material composition known to be suitable for a particular IC device, such as, but not limited to, transistors, diodes, and resistors. In some exemplary embodiments, device layer **415** includes one or more group IV (i.e., IUPAC group 14) semiconductor material layers (e.g., Si, Ge, SiGe), group III-V semiconductor material layers (e.g., GaAs, InGaAs, InAs, InP), or group III-N semiconductor material layers (e.g., GaN, AlGaIn, InGaIn). Device layer **415** may also include one or more semiconductor transition metal dichalcogenide (TMD or TMDC) layers. In other embodiments, device layer **415** includes one or more graphene layer, or a graphenic material layer having semiconductor properties. In still other embodiments, device layer **415** includes one or more oxide semiconductor layers. Exemplary oxide semiconductors include oxides of a transition metal (e.g., IUPAC group 4-10) or post-transition metal (e.g., IUPAC groups 11-14). In advantageous embodiments, the oxide semiconductor includes at least one of Cu, Zn, Sn, Ti, Ni, Ga, In, Sr, Cr, Co, V, or Mo. The metal oxides may be suboxides (A₂O) monoxides (AO), binary oxides (AO₂), ternary oxides (ABO₃), and mixtures thereof. In other embodiments, device layer **415** includes one or more magnetic, ferromagnetic, ferroelectric material layer. For example device layer **415** may include one or more layers of

any material known to be suitable for an tunneling junction device, such as, but not limited to a magnetic tunneling junction (MTJ) device.

[0079] In some embodiments, device layer 415 is substantially monocrystalline. Although monocrystalline, a significant number of crystalline defects may nonetheless be present. In other embodiments, device layer 415 is amorphous or nanocrystalline. Device layer 415 may be any thickness (e.g., z-dimension in FIG. 5A). In some exemplary embodiments, device layer 415 has a thickness greater than a z-thickness of at least some of the semiconductor regions employed by die 411 as functional semiconductor regions of die 411 built on and/or embedded within device layer 415 need not extend through the entire thickness of device layer 415. In some embodiments, semiconductor regions of die 411 are disposed only within a top-side thickness of device layer 415 demarked in FIG. 5A by dashed line 412. For example, semiconductor regions of die 411 may have a z-thickness of 200-300 nm, or less, while device layer may have a z-thickness of 700-1000 nm, or more. As such, around 600 nm of device layer thickness may separate semiconductor regions of die 411 from intervening layer 410.

[0080] Carrier layer 405 may have the same material composition as device layer 415, or may have a material composition different than device layer 415. For embodiments where carrier layer 405 and device layer 415 have the same composition, the two layers may be identified by their position relative to intervening layer 410. In some embodiments where device layer 415 is a crystalline group IV, group III-V or group III-N semiconductor, carrier layer 405 is the same crystalline group IV, group III-V or group III-N semiconductor as device layer 415. In alternative embodiments, where device layer 415 is a crystalline group IV, group III-V or group III-N semiconductor, carrier layer 405 is a different crystalline group IV, group III-V or group III-N semiconductor than device layer 415. In still other embodiments, carrier layer 405 may include, or be, a material onto which device layer 415 transferred, or grown upon. For example, carrier layer may include one or more amorphous oxide layers (e.g., glass) or crystalline oxide layer (e.g., sapphire), polymer sheets, or any material(s) built up or laminated into a structural support known to be suitable as a carrier during IC device processing. Carrier layer 405 may be any thickness (e.g., z-dimension in FIG. 5A) as a function of the carrier material properties and the substrate diameter. For example, where the carrier layer 405 is a large format (e.g., 300-450 mm) semiconductor substrate, the carrier layer thickness may be 700-1000 μm , or more.

[0081] In some embodiments, one or more intervening layers 410 are disposed between carrier layer 405 and device layer 415. In some exemplary embodiments, an intervening layer 410 is compositionally distinct from carrier layer 405 such that it may serve as a marker detectable during subsequent removal of carrier layer 405. In some such embodiments, an intervening layer 410 has a composition that, when exposed to an etchant of carrier layer 405 will etch at a significantly slower rate than carrier layer 405 (i.e., intervening layer 410 functions as an etch stop for a carrier layer etch process). In further embodiments, intervening layer 410 has a composition distinct from that of device layer 415. Intervening layer 410 may be a metal, semiconductor, or dielectric material, for example.

[0082] In some exemplary embodiments where at least one of carrier layer 405 and device layer 415 are crystalline semiconductors, intervening layer 410 is also a crystalline semiconductor layer. Intervening layer 410 may further have the same crystallinity and crystallographic orientation as carrier layer 405 and/or device layer 415. Such embodiments may have the advantage of reduced donor substrate cost relative to alternative embodiments where intervening layer 410 is a material that necessitates bonding (e.g., thermal-compression bonding) of intervening layer 410 to intervening layer 410 and/or to carrier layer 405.

[0083] For embodiments where intervening layer 410 is a semiconductor, one or more of the primary semiconductor lattice elements, alloy constituents, or impurity concentrations may vary between at least carrier layer 405 and intervening layer 410. In some embodiments where at least carrier layer 405 is a group IV semiconductor, intervening layer 410 may also be a group IV semiconductor, but of a different group IV element or alloy and/or doped with an impurity species to an impurity level different than that of carrier layer 405. For example, intervening layer 410 may be a silicon-germanium alloy epitaxially grown on a silicon carrier. For such embodiments, a pseudomorphic intervening layer may be grown heteroepitaxially to any thickness below the critical thickness. Alternatively, the intervening layer 410 may be a relaxed buffer layer having a thickness greater than the critical thickness.

[0084] In other embodiments, where at least carrier layer 405 is a group III-V semiconductor, intervening layer 410 may also be a group III-V semiconductor, but of a different group III—V alloy and/or doped with an impurity species to an impurity level different than that of carrier layer 405. For example, intervening layer 410 may be an AlGaAs alloy epitaxially grown on a GaAs carrier. In some other embodiments where both carrier layer 405 and device layer 415 are crystalline semiconductors, intervening layer 410 is also a crystalline semiconductor layer, which may further have the same crystallinity and crystallographic orientation as carrier layer 405 and/or device layer 415.

[0085] In embodiments where both carrier layer 405 and intervening layer 410 are of the same or different primary semiconductor lattice elements, impurity dopants may differentiate the carrier and intervening layer. For example, intervening layer 410 and carrier layer 405 may both be silicon crystals with intervening layer 410 lacking an impurity present in carrier layer 405, or doped with an impurity absent from carrier layer 405, or doped to a different level with an impurity present in carrier layer 405. The impurity differentiation may impart etch selectivity between the carrier and intervening layer, or merely introduce a detectable species.

[0086] Intervening layer 410 may be doped with impurities that are electrically active (i.e., rendering it an n-type or p-type semiconductor), or not, as the impurity may provide any basis for detection of the intervening layer 410 during subsequent carrier removal. Exemplary electrically active impurities for some semiconductor materials include group III elements (e.g., B), group IV elements (e.g., P). Any other element may be employed as a non-electrically active species. Impurity dopant concentration within intervening layer 410 need only vary from that of carrier layer 405 by an amount sufficient for detection, which may be predetermined as a function of the detection technique and detector sensitivity.

[0087] As described further elsewhere herein, intervening layer 410 may have a composition distinct from device layer 415. In some such embodiments, intervening layer 410 may have a different band gap than that of device layer 415. For example, intervening layer 410 may have a wider band-gap than device layer 415.

[0088] In embodiments where intervening layer 410 includes a dielectric material, the dielectric material may be an inorganic material (e.g., SiO, SiN, SiON, SiOC, hydrogen silsesquioxane, methyl silsesquioxane) or organic material (polyimide, polynorbornenes, benzocyclobutene). For some dielectric embodiments, intervening layer 410 may be formed as an embedded layer (e.g., SiO_x through implantation of oxygen into a silicon device and/or carrier layer). Other embodiments of a dielectric intervening layer may necessitate bonding (e.g., thermal-compression bonding) of carrier layer 405 to device layer 415. For example, where donor substrate 401 is a semiconductor-on-oxide (SOI) substrate, either or both of carrier layer 405 and device layer 415 may be oxidized and bonded together to form a SiO intervening layer 410. Similar bonding techniques may be employed for other inorganic or organic dielectric materials.

[0089] In some other embodiments, intervening layer 410 includes two or more materials laterally spaced apart within the layer. The two or more materials may include a dielectric and a semiconductor, a dielectric and a metal, a semiconductor and a metal, a dielectric and a metal, two different dielectric, two different semiconductors, or two different metals. Within such an intervening layer, a first material may surround islands of the second material that extend through the thickness of the intervening layer. For example, an intervening layer may include a field isolation dielectric that surrounds islands of semiconductor, which extend through the thickness of the intervening layer. The semiconductor may be epitaxially grown within openings of a patterned dielectric or the dielectric material may be deposited within openings of a patterned semiconductor.

[0090] In some exemplary embodiments, semiconductor features, such as fins or mesas, are etched into a front-side surface of a semiconductor device layer. Trenches surrounding these features may be subsequently backfilled with an isolation dielectric, for example following any known shallow trench isolation (STI) process. One or more of the semiconductor feature or isolation dielectric may be employed for terminating a back-side carrier removal process, for example as a back-side reveal etch stop. In some embodiments, a reveal of trench isolation dielectric may stop, significantly retard, or induce a detectable signal for terminating a back-side carrier polish. For example, a CMP polish of carrier semiconductor employing a slurry that has high selectivity favoring removal of carrier semiconductor (e.g., Si) over removal of isolation dielectric (e.g., SiO) may be significantly slowed upon exposure of a (bottom) surface of the trench isolation dielectric surrounding semiconductor features including the device layer. Because the device layer is disposed on a front side of intervening layer, the device layer need not be directly exposed to the back-side reveal process.

[0091] Notably, for embodiments where the intervening layer includes both semiconductor and dielectric, the intervening layer thickness may be considerably greater than the critical thickness associated with the lattice mismatch of the intervening layer and carrier. Whereas an intervening layer below critical thickness may be an insufficient thickness to

accommodate non-uniformity of a wafer-level back-side reveal process, embodiments with greater thickness may advantageously increase the back-side reveal process window. Embodiments with pin-holed dielectric may otherwise facilitate subsequent separation of carrier and device layers as well as improve crystal quality within the device layer.

[0092] Semiconductor material within intervening layers that include both semiconductor and dielectric may also be homoepitaxial. In some exemplary embodiments, a silicon epitaxial device layer is grown through a pin-holed dielectric disposed over a silicon carrier layer.

[0093] Continuing with description of FIGS. 4A and 5A, intervening layer 410 may also be a metal. For such embodiments, the metal may be of any composition known to be suitable for bonding to carrier layer 405 or device layer 415. For example, either or both of carrier layer 405 and device layer 415 may be finished with a metal, such as, but not limited to Au or Pt, and subsequently bonded together, for example to form an Au or Pt intervening layer 410. Such a metal may also be part of an intervening layer that further includes a patterned dielectric surrounding metal features.

[0094] Intervening layer 410 may be of any thickness (e.g., z-height in FIG. 5A). The intervening layer should be sufficiently thick to ensure the carrier removal operation can be reliably terminated before exposing device regions and/or device layer 415. Exemplary thicknesses for intervening layer 410 range from a few hundred nanometers to a few micrometers and may vary as a function of the amount of carrier material that is to be removed, the uniformity of the carrier removal process, and the selectivity of the carrier removal process, for example. For embodiments where the intervening layer has the same crystallinity and crystallographic orientation as carrier layer 405, the carrier layer thickness may be reduced by the thickness of intervening layer 410. In other words, intervening layer 410 may be a top portion of a 700-1000 μm thick group IV crystalline semiconductor substrate also employed as the carrier layer. In pseudomorphic heteroepitaxial embodiments, intervening layer thickness may be limited to the critical thickness. For heteroepitaxial intervening layer embodiments employing aspect ratio trapping (ART) or another fully relaxed buffer architecture, the intervening layer may have any thickness.

[0095] As further illustrated in FIGS. 4B and 5B, donor substrate 401 may be joined to a host substrate 402 to form a donor-host substrate assembly 403. In some exemplary embodiments, a front-side surface of donor substrate 401 is joined to a surface of host substrate 402 such that device layer 415 is proximal host substrate 402 and carrier layer 405 is distal from host substrate 402. Host substrate 402 may be any substrate known to be suitable for joining to device layer 415 and/or a front-side stack fabricated over device layer 415. In some embodiments, host substrate 402 includes one or more additional device strata. For example, host substrate 402 may further include one or more device layer (not depicted). Host substrate 402 may include integrated circuitry with which the IC devices fabricated in a device layer of host substrate 402 are interconnected, in which case joining of device layer 415 to host substrate 402 may further entail formation of 3D interconnect structures through the wafer-level bond.

[0096] Although not depicted in detail by FIG. 5B, any number of front-side layers, such as interconnect metallization levels and interlayer dielectric (ILD) layers, may be present between device layer 415 and host substrate 402.

Any technique may be employed to join host substrate **402** and donor substrate **401**. In some exemplary embodiments further described elsewhere herein, the joining of donor substrate **401** to host substrate **402** is through metal-metal, oxide-oxide, or hybrid (metal/oxide-metal/oxide) thermal compression bonding.

[0097] With host substrate **402** facing device layer **415** on a side opposite carrier layer **405**, at least a portion of carrier layer **405** may be removed as further illustrated in FIGS. **4C** and **5C**. Where the entire carrier layer **405** is removed, donor-host substrate assembly **403** maintains a highly uniform thickness with planar back side and front side surfaces. Alternatively, carrier layer **405** may be masked and intervening layer **410** exposed only in unmasked sub-regions to form a non-planar back side surface. In the exemplary embodiments illustrated by FIGS. **4C** and **5C**, carrier layer **405** is removed from the entire back-side surface of donor-host substrate assembly **403**. Carrier layer **405** may be removed, for example by cleaving, grinding, and/or polishing (e.g., chemical-mechanical polishing), and/or wet chemical etching, and/or plasma etching through a thickness of the carrier layer to expose intervening layer **410**. One or more operations may be employed to remove carrier layer **405**. Advantageously, the removal operation(s) may be terminated based on duration or an endpoint signal sensitive to exposure of intervening layer **410**.

[0098] In further embodiments, for example as illustrated by FIGS. **4D** and **5D**, intervening layer **410** is also at least partially etched to expose a back side of device layer **415**. At least a portion of intervening layer **410** may be removed subsequent to its use as a carrier layer etch stop and/or carrier layer etch endpoint trigger. Where the entire intervening layer **410** is removed, donor-host substrate assembly **403** maintains a highly uniform device layer thickness with planar back-side and front-side surfaces afforded by the intervening layer being much thinner than the carrier layer. Alternatively, intervening layer **410** may be masked and device layer **415** exposed only in unmasked sub-regions, thereby forming a non-planar back-side surface. In the exemplary embodiments illustrated by FIGS. **4D** and **5D**, intervening layer **410** is removed from the entire back-side surface of donor-host substrate assembly **403**. Intervening layer **410** may be so removed, for example, by polishing (e.g., chemical-mechanical polishing), and/or blanket wet chemical etching, and/or blanket plasma etching through a thickness of the intervening layer to expose device layer **415**. One or more operations may be employed to remove intervening layer **410**. Advantageously, the removal operation(s) may be terminated based on duration or an endpoint signal sensitive to exposure of device layer **415**.

[0099] In some further embodiments, for example as illustrated by FIGS. **4E** and **5E**, device layer **415** is partially etched to expose a back side of a device structure previously formed from during front-side processing. At least a portion of device layer **415** may be removed subsequent to its use in fabricating one or more of the device semiconductor regions, and/or its use as an intervening layer etch stop or endpoint trigger. Where device layer **415** is thinned over the entire substrate area, donor-host substrate assembly **403** maintains a highly uniform reduced thickness with planar back and front surfaces. Alternatively, device layer **415** may be masked and device structures (e.g., device semiconductor regions) selectively revealed only in unmasked sub-regions, thereby forming a non-planar back-side surface. In the

exemplary embodiments illustrated by FIGS. **4E** and **5E**, device layer **415** is thinned over the entire back-side surface of donor-host substrate assembly **403**. Device layer **415** may be thinned, for example by polishing (e.g., chemical-mechanical polishing), and/or wet chemical etching, and/or plasma etching through a thickness of the device layer to expose one or more device semiconductor regions, and/or one or more other device structures (e.g., front-side device terminal contact metallization, spacer dielectric, etc.) previously formed during front-side processing. One or more operations may be employed to thin device layer **415**. Advantageously, the device layer thinning may be terminated based on duration or an endpoint signal sensitive to exposure of patterned features within device layer **415**. For example, where front-side processing forms device isolation features (e.g., shallow trench isolation), back-side thinning of device layer **415** may be terminated upon exposing the isolation dielectric material.

[0100] A non-native material layer may be deposited over a back-side surface of an intervening layer, device layer, and/or specific device regions within device layer **415**, and/or over or more other device structures (e.g., front-side device terminal contact metallization, spacer dielectric, etc.). One or more materials exposed (revealed) from the backside may be covered with non-native material layer or replaced with such a material. In some embodiments, illustrated by FIGS. **4F** and **5F**, non-native material layer **420** is deposited on device layer **415**. Non-native material layer **420** may be any material having a composition and/or microstructure distinct from that of the material removed to reveal the backside of the device stratum. For example, where intervening layer **410** is removed to expose device layer **415**, non-native material layer **420** may be another semiconductor of different composition or microstructure than that of intervening layer **410**. In some such embodiments where device layer **415** is a group III-N semiconductor, non-native material layer **420** may also be a group III-N semiconductor of the same or different composition that is regrown upon a revealed backside surface of a group III-N device region. This material may be epitaxially regrown from the revealed group III-N device region, for example, to have better crystal quality than that of the material removed, and/or to induce strain within the device layer and/or device regions within the device layer, and/or to form a vertical (e.g., z-dimension) stack of device semiconductor regions suitable for a stacked device.

[0101] In some other embodiments where device layer **415** is a group III-V semiconductor, non-native material layer **420** may also be a group III-V semiconductor of the same or different composition that is regrown upon a revealed backside surface of a group III-V device region. This material may be epitaxially regrown from the revealed group III-V device region, for example, to have relatively better crystal quality than that of the material removed, and/or to induce strain within the device layer or a specific device region within the device layer, and/or to form a vertical stack of device semiconductor regions suitable for a stacked device.

[0102] In some other embodiments where device layer **415** is a group IV semiconductor, non-native material layer **420** may also be a group IV semiconductor of the same or different composition that is regrown upon a revealed backside surface of a group IV device region. This material may be epitaxially regrown from the revealed group IV device region, for example, to have relatively better crystal quality

than that of the material removed, and/or to induce strain within the device region, and/or to form a stack of device semiconductor regions suitable for a stacked device.

[0103] In some other embodiments, non-native material layer 420 is a dielectric material, such as, but not limited to SiO, SiON, SiOC, hydrogen silsesquioxane, methyl silsesquioxane, polyimide, polynorbornenes, benzocyclobutene, or the like. Deposition of such a dielectric may serve to electrically isolate various device structures, such as semiconductor device regions, that may have been previously formed during front-side processing of donor substrate 401.

[0104] In some other embodiments, non-native material layer 420 is a conductive material, such as any elemental metal or metal alloy known to be suitable for contacting one or more surfaces of device regions revealed from the back-side. In some embodiments, non-native material layer 420 is a metallization suitable for contacting a device region revealed from the backside, such as a transistor source or drain region. In embodiments, intermetallic contacts such as Ni₃Si₂, Ti₃Si₂, Ni₃Si₂:Pt, TiSi, CoSi, etc. may be formed. Additionally, implants may be used to enable robust contacts (e.g., P, Ge, B etc.).

[0105] In some embodiments, non-native material layer 420 is a stack of materials, such as a FET gate stack that includes both a gate dielectric layer and a gate electrode layer. As one example, non-native material layer 420 may be a gate dielectric stack suitable for contacting a semiconductor device region revealed from the backside, such as a transistor channel region. Any of the other materials described as options for device layer 415 may also be deposited over a backside of device layer 415 and/or over device regions formed within device layer 415. For example, non-native material layer 420 may be any of the oxide semiconductors, TMDC, or tunneling materials described above, which may be deposited on the back-side, for example, to incrementally fabricate vertically-stacked device strata.

[0106] Back-side wafer-level processing may continue in any manner known to be suitable for front-side processing. For example, non-native material layer 420 may be patterned into active device regions, device isolation regions, device contact metallization, or device interconnects using any known lithographic and etch techniques. Back-side wafer-level processing may further fabricate one or more interconnect metallization levels coupling terminals of different devices into an IC. In some embodiments further described elsewhere herein, back-side processing may be employed to interconnect a power bus to various device terminals within an IC.

[0107] In some embodiments, back-side processing includes bonding to a secondary host substrate. Such bonding may employ any layer transfer process to join the back-side (e.g., non-native) material layer to another substrate. Following such joining, the former host substrate may be removed as a sacrificial donor to re-expose the front-side stack and/or the front side of the device layer. Such embodiments may enable iterative side-to-side lamination of device strata with a first device layer serving as the core of the assembly. In some embodiments illustrated in FIGS. 4G and 5G, secondary host substrate 440 joined to non-native material layer 420 provides at least mechanical support while host substrate 402 is removed.

[0108] Any bonding, such as, but not limited to, thermal-compression bonding may be employed to join secondary

host substrate 440 to non-native material layer 420. In some embodiments, both a surface layer of secondary host substrate 440 and non-native material layer 420 are continuous dielectric layers (e.g., SiO), which are thermal-compression bonded. In some other embodiments, both a surface layer of secondary host substrate 440 and non-native material layer 420 include a metal layer (e.g., Au, Pt, etc.), which are thermal-compression bonded. In other embodiments, at least one of surface layer of secondary host substrate 440 and non-native material layer 420 are patterned, including both patterned metal surface (i.e., traces) and surrounding dielectric (e.g., isolation), which are thermal-compression bonded to form a hybrid (e.g., metal/oxide) joint. For such embodiments, structural features in the secondary host substrate 440 and the patterned non-native material layer 420 are aligned (e.g., optically) during the bonding process. In some embodiments, non-native material layer 420 includes one or more conductive back-side traces coupled to a terminal of a transistor fabricated in device layer 415. The conductive back-side trace may, for example, be bonded to metallization on secondary host substrate 440.

[0109] Bonding of device strata may proceed from the front-side and/or back-side of a device layer before or after front-side processing of the device layer has been completed. A back-side bonding process may be performed after front-side fabrication of a device (e.g., transistor) is substantially complete. Alternatively, back-side bonding process may be performed prior to completing front-side fabrication of a device (e.g., transistor), in which case the front side of the device layer may receive additional processing following the back-side bonding process. As further illustrated in FIGS. 4H and 5H, for example, front-side processing includes removal of host substrate 402 (as a second donor substrate) to re-expose the front side of device layer 415. At this point, donor-host substrate assembly 403 includes secondary host 440 joined to device layer 415 through non-native material layer 420.

[0110] In another aspect, the SCR structures described above in association with FIGS. 1A, 1B, 1C and/or 2 can be co-integrated with other substrate-less integrated circuits structures such as neighboring semiconductor structures or devices separated by self-aligned gate endcap (SAGE) structures. Particular embodiments may be directed to integration of multiple width (multi-Wsi) nanowires and nanoribbons in a SAGE architecture and separated by a SAGE wall. In an embodiment, nanowires/nanoribbons are integrated with multiple Wsi in a SAGE architecture portion of a front-end process flow. Such a process flow may involve integration of nanowires and nanoribbons of different Wsi to provide robust functionality of next generation transistors with low power and high performance. Associated epitaxial source or drain regions may be embedded (e.g., portions of nanowires removed and then source or drain (S/D) growth is performed).

[0111] To provide further context, advantages of a self-aligned gate endcap (SAGE) architecture may include the enabling of higher layout density and, in particular, scaling of diffusion to diffusion spacing. To provide illustrative comparison, FIG. 6 illustrates a cross-sectional view taken through nanowires and fins for a non-endcap architecture, in accordance with an embodiment of the present disclosure. FIG. 7 illustrates a cross-sectional view taken through

nanowires and fins for a self-aligned gate endcap (SAGE) architecture, in accordance with an embodiment of the present disclosure.

[0112] Referring to FIG. 6, an integrated circuit structure 600 includes a substrate 602 having fins 604 protruding therefrom by an amount 606 above an isolation structure 608 laterally surrounding lower portions of the fins 604. Upper portions of the fins may include a local isolation structure 622 and a growth enhancement layer 620, as is depicted. Corresponding nanowires 605 are over the fins 604. A gate structure may be formed over the integrated circuit structure 600 to fabricate a device. However, breaks in such a gate structure may be accommodated for by increasing the spacing between fin 604/nanowire 605 pairs.

[0113] Referring to FIG. 6, in an embodiment, following gate formation, the lower portions of the structure 600 can be planarized and/or etched to level 634 in order to leave a backside surface including exposed bottom surfaces of gate structures and epitaxial source or drain structures. It is to be appreciated that backside (bottom) contacts may be formed on the exposed bottom surfaces of the epitaxial source or drain structures. It is also to be appreciated that planarization and/or etching could be to other levels such as 630 or 632.

[0114] By contrast, referring to FIG. 7, an integrated circuit structure 750 includes a substrate 752 having fins 754 protruding therefrom by an amount 756 above an isolation structure 758 laterally surrounding lower portions of the fins 754. Upper portions of the fins may include a local isolation structure 772 and a growth enhancement layer 770, as is depicted. Corresponding nanowires 755 are over the fins 754. Isolating SAGE walls 760 (which may include a hardmask thereon, as depicted) are included within the isolation structure 758 and between adjacent fin 754/nanowire 755 pairs. The distance between an isolating SAGE wall 760 and a nearest fin 754/nanowire 755 pair defines the gate endcap spacing 762. A gate structure may be formed over the integrated circuit structure 750, between isolating SAGE walls to fabricate a device. Breaks in such a gate structure are imposed by the isolating SAGE walls. Since the isolating SAGE walls 760 are self-aligned, restrictions from conventional approaches can be minimized to enable more aggressive diffusion to diffusion spacing. Furthermore, since gate structures include breaks at all locations, individual gate structure portions may be layer connected by local interconnects formed over the isolating SAGE walls 760. In an embodiment, as depicted, the isolating SAGE walls 760 each include a lower dielectric portion and a dielectric cap on the lower dielectric portion.

[0115] Referring to FIG. 7, in an embodiment, following gate formation, the lower portions of the structure 700 can be planarized and/or etched to level 784 in order to leave a backside surface including exposed bottom surfaces of gate structures and epitaxial source or drain structures. It is to be appreciated that backside (bottom) contacts may be formed on the exposed bottom surfaces of the epitaxial source or drain structures. It is also to be appreciated that planarization and/or etching could be to other levels such as 780 or 782.

[0116] A self-aligned gate endcap (SAGE) processing scheme involves the formation of gate/trench contact endcaps self-aligned to fins without requiring an extra length to account for mask mis-registration. Thus, embodiments may be implemented to enable shrinking of transistor layout area. Embodiments described herein may involve the fabrication

of gate endcap isolation structures, which may also be referred to as gate walls, isolation gate walls or self-aligned gate endcap (SAGE) walls.

[0117] In an embodiment, as described throughout, self-aligned gate endcap (SAGE) isolation structures may be composed of a material or materials suitable to ultimately electrically isolate, or contribute to the isolation of, portions of permanent gate structures from one another. Exemplary materials or material combinations include a single material structure such as silicon dioxide, silicon oxy-nitride, silicon nitride, or carbon-doped silicon nitride. Other exemplary materials or material combinations include a multi-layer stack having lower portion silicon dioxide, silicon oxy-nitride, silicon nitride, or carbon-doped silicon nitride and an upper portion higher dielectric constant material such as hafnium oxide.

[0118] It is to be appreciated that the SCR structures described above in association with FIGS. 1A, 1B, 1C and/or 2 can be co-integrated with other substrate-less integrated circuits structures such as nanowire or nanoribbon based devices. To highlight an exemplary integrated circuit structure having three vertically arranged nanowires, FIG. 8A illustrates a three-dimensional cross-sectional view of a nanowire-based integrated circuit structure, in accordance with an embodiment of the present disclosure. FIG. 8B illustrates a cross-sectional source or drain view of the nanowire-based integrated circuit structure of FIG. 8A, as taken along an a-a' axis. FIG. 8C illustrates a cross-sectional channel view of the nanowire-based integrated circuit structure of FIG. 8A, as taken along the b-b' axis.

[0119] Referring to FIG. 8A, an integrated circuit structure 800 includes one or more vertically stacked nanowires (804 set) above a substrate 802. In an embodiment, as depicted, a local isolation structure 802C, a growth enhancement layer 802B, and a lower substrate portion 802A are included in substrate 802, as is depicted. An optional fin below the bottommost nanowire and formed from the substrate 802 is not depicted for the sake of emphasizing the nanowire portion for illustrative purposes. Embodiments herein are targeted at both single wire devices and multiple wire devices. As an example, a three nanowire-based devices having nanowires 804A, 804B and 804C is shown for illustrative purposes. For convenience of description, nanowire 804A is used as an example where description is focused on one of the nanowires. It is to be appreciated that where attributes of one nanowire are described, embodiments based on a plurality of nanowires may have the same or essentially the same attributes for each of the nanowires.

[0120] Each of the nanowires 804 includes a channel region 806 in the nanowire. The channel region 806 has a length (L). Referring to FIG. 8C, the channel region also has a perimeter (Pc) orthogonal to the length (L). Referring to both FIGS. 8A and 8C, a gate electrode stack 808 surrounds the entire perimeter (Pc) of each of the channel regions 806. The gate electrode stack 808 includes a gate electrode along with a gate dielectric layer between the channel region 806 and the gate electrode (not shown). In an embodiment, the channel region is discrete in that it is completely surrounded by the gate electrode stack 808 without any intervening material such as underlying substrate material or overlying channel fabrication materials. Accordingly, in embodiments having a plurality of nanowires 804, the channel regions 806 of the nanowires are also discrete relative to one another.

[0121] Referring to both FIGS. 8A and 8B, integrated circuit structure **800** includes a pair of non-discrete source or drain regions **810/812**. The pair of non-discrete source or drain regions **810/812** is on either side of the channel regions **806** of the plurality of vertically stacked nanowires **804**. Furthermore, the pair of non-discrete source or drain regions **810/812** is adjoining for the channel regions **806** of the plurality of vertically stacked nanowires **804**. In one such embodiment, not depicted, the pair of non-discrete source or drain regions **810/812** is directly vertically adjoining for the channel regions **806** in that epitaxial growth is on and between nanowire portions extending beyond the channel regions **806**, where nanowire ends are shown within the source or drain structures. In another embodiment, as depicted in FIG. 8A, the pair of non-discrete source or drain regions **810/812** is indirectly vertically adjoining for the channel regions **806** in that they are formed at the ends of the nanowires and not between the nanowires.

[0122] In an embodiment, as depicted, the source or drain regions **810/812** are non-discrete in that there are not individual and discrete source or drain regions for each channel region **806** of a nanowire **804**. Accordingly, in embodiments having a plurality of nanowires **804**, the source or drain regions **810/812** of the nanowires are global or unified source or drain regions as opposed to discrete for each nanowire. That is, the non-discrete source or drain regions **810/812** are global in the sense that a single unified feature is used as a source or drain region for a plurality (in this case, 3) of nanowires **804** and, more particularly, for more than one discrete channel region **806**. In one embodiment, from a cross-sectional perspective orthogonal to the length of the discrete channel regions **806**, each of the pair of non-discrete source or drain regions **810/812** is approximately rectangular in shape with a bottom tapered portion and a top vertex portion, as depicted in FIG. 8B. In other embodiments, however, the source or drain regions **810/812** of the nanowires are relatively larger yet discrete non-vertically merged epitaxial structures such as nubs.

[0123] In accordance with an embodiment of the present disclosure, and as depicted in FIGS. 8A and 8B, integrated circuit structure **800** further includes a pair of contacts **814**, each contact **814** on one of the pair of non-discrete source or drain regions **810/812**. In one such embodiment, in a vertical sense, each contact **814** completely surrounds the respective non-discrete source or drain region **810/812**. In another aspect, the entire perimeter of the non-discrete source or drain regions **810/812** may not be accessible for contact with contacts **814**, and the contact **814** thus only partially surrounds the non-discrete source or drain regions **810/812**, as depicted in FIG. 8B. In a contrasting embodiment, not depicted, the entire perimeter of the non-discrete source or drain regions **810/812**, as taken along the a-a' axis, is surrounded by the contacts **814**.

[0124] Referring again to FIG. 8A, in an embodiment, integrated circuit structure **800** further includes a pair of spacers **816**. As is depicted, outer portions of the pair of spacers **816** may overlap portions of the non-discrete source or drain regions **810/812**, providing for “embedded” portions of the non-discrete source or drain regions **810/812** beneath the pair of spacers **816**. As is also depicted, the embedded portions of the non-discrete source or drain regions **810/812** may not extend beneath the entirety of the pair of spacers **816**.

[0125] Substrate **802** may be composed of a material suitable for integrated circuit structure fabrication. In one embodiment, substrate **802** includes a lower bulk substrate composed of a single crystal of a material which may include, but is not limited to, silicon, germanium, silicon-germanium, germanium-tin, silicon-germanium-tin, or a group III-V compound semiconductor material. An upper insulator layer composed of a material which may include, but is not limited to, silicon dioxide, silicon nitride or silicon oxy-nitride is on the lower bulk substrate. Thus, the structure **800** may be fabricated from a starting semiconductor-on-insulator substrate. Alternatively, the structure **800** is formed directly from a bulk substrate and local oxidation is used to form electrically insulative portions in place of the above described upper insulator layer. In another alternative embodiment, the structure **800** is formed directly from a bulk substrate and doping is used to form electrically isolated active regions, such as nanowires, thereon. In one such embodiment, the first nanowire (i.e., proximate the substrate) is in the form of an omega-FET type structure.

[0126] In an embodiment, the nanowires **804** may be sized as wires or ribbons, as described below, and may have squared-off or rounder corners. In an embodiment, the nanowires **804** are composed of a material such as, but not limited to, silicon, germanium, or a combination thereof. In one such embodiment, the nanowires are single-crystalline. For example, for a silicon nanowire **804**, a single-crystalline nanowire may be based from a (100) global orientation, e.g., with a <100> plane in the z-direction. As described below, other orientations may also be considered. In an embodiment, the dimensions of the nanowires **804**, from a cross-sectional perspective, are on the nano-scale. For example, in a specific embodiment, the smallest dimension of the nanowires **804** is less than approximately 20 nanometers. In an embodiment, the nanowires **804** are composed of a strained material, particularly in the channel regions **806**.

[0127] Referring to FIGS. 8C, in an embodiment, each of the channel regions **806** has a width (Wc) and a height (Hc), the width (Wc) approximately the same as the height (Hc). That is, in both cases, the channel regions **806** are square-like or, if corner-rounded, circle-like in cross-section profile. In another aspect, the width and height of the channel region need not be the same, such as the case for nanoribbons as described throughout.

[0128] Referring again to FIGS. 8A, 8B and 8C, in an embodiment, the lower portions of the structure **800** can be planarized and/or etched to level **899** in order to leave a backside surface including exposed bottom surfaces of gate structures and epitaxial source or drain structures. It is to be appreciated that backside (bottom) contacts may be formed on the exposed bottom surfaces of the epitaxial source or drain structures.

[0129] In an embodiment, as described throughout, an integrated circuit structure includes non-planar devices such as, but not limited to, a finFET or a tri-gate structure with corresponding one or more overlying nanowire structures, and an isolation structure between the finFET or tri-gate structure and the corresponding one or more overlying nanowire structures. In some embodiments, the finFET or tri-gate structure is retained. In other embodiments, the finFET or tri-gate structure is may ultimately be removed in a substrate removal process.

[0130] Embodiments disclosed herein may be used to manufacture a wide variety of different types of integrated

circuits and/or microelectronic devices. Examples of such integrated circuits include, but are not limited to, processors, chipset components, graphics processors, digital signal processors, micro-controllers, and the like. In other embodiments, semiconductor memory may be manufactured. Moreover, the integrated circuits or other microelectronic devices may be used in a wide variety of electronic devices known in the arts. For example, in computer systems (e.g., desktop, laptop, server), cellular phones, personal electronics, etc. The integrated circuits may be coupled with a bus and other components in the systems. For example, a processor may be coupled by one or more buses to a memory, a chipset, etc. Each of the processor, the memory, and the chipset, may potentially be manufactured using the approaches disclosed herein.

[0131] FIG. 9 illustrates a computing device **900** in accordance with one implementation of an embodiment of the present disclosure. The computing device **900** houses a board **902**. The board **902** may include a number of components, including but not limited to a processor **904** and at least one communication chip **906**. The processor **904** is physically and electrically coupled to the board **902**. In some implementations the at least one communication chip **906** is also physically and electrically coupled to the board **902**. In further implementations, the communication chip **906** is part of the processor **904**.

[0132] Depending on its applications, computing device **900** may include other components that may or may not be physically and electrically coupled to the board **902**. These other components include, but are not limited to, volatile memory (e.g., DRAM), non-volatile memory (e.g., ROM), flash memory, a graphics processor, a digital signal processor, a crypto processor, a chipset, an antenna, a display, a touchscreen display, a touchscreen controller, a battery, an audio codec, a video codec, a power amplifier, a global positioning system (GPS) device, a compass, an accelerometer, a gyroscope, a speaker, a camera, and a mass storage device (such as hard disk drive, compact disk (CD), digital versatile disk (DVD), and so forth).

[0133] The communication chip **906** enables wireless communications for the transfer of data to and from the computing device **900**. The term “wireless” and its derivatives may be used to describe circuits, devices, systems, methods, techniques, communications channels, etc., that may communicate data through the use of modulated electromagnetic radiation through a non-solid medium. The term does not imply that the associated devices do not contain any wires, although in some embodiments they might not. The communication chip **906** may implement any of a number of wireless standards or protocols, including but not limited to Wi-Fi (IEEE 802.11 family), WiMAX (IEEE 802.16 family), IEEE 802.20, long term evolution (LTE), Ev-DO, HSPA+, HSDPA+, HSUPA+, EDGE, GSM, GPRS, CDMA, TDMA, DECT, Bluetooth, derivatives thereof, as well as any other wireless protocols that are designated as 3G, 4G, 5G, and beyond. The computing device **900** may include a plurality of communication chips **906**. For instance, a first communication chip **906** may be dedicated to shorter range wireless communications such as Wi-Fi and Bluetooth and a second communication chip **906** may be dedicated to longer range wireless communications such as GPS, EDGE, GPRS, CDMA, WiMAX, LTE, Ev-DO, and others.

[0134] The processor **904** of the computing device **900** includes an integrated circuit die packaged within the pro-

cessor **904**. The integrated circuit die of the processor **904** may include one or more structures, such as substrate-less integrated circuit structures, built in accordance with implementations of embodiments of the present disclosure. The term “processor” may refer to any device or portion of a device that processes electronic data from registers and/or memory to transform that electronic data into other electronic data that may be stored in registers and/or memory.

[0135] The communication chip **906** also includes an integrated circuit die packaged within the communication chip **906**. The integrated circuit die of the communication chip **906** may include one or more structures, such as substrate-less integrated circuit structures, built in accordance with implementations of embodiments of the present disclosure.

[0136] In further implementations, another component housed within the computing device **900** may contain an integrated circuit die that includes one or structures, such as substrate-less integrated circuit structures, built in accordance with implementations of embodiments of the present disclosure.

[0137] In various implementations, the computing device **900** may be a laptop, a netbook, a notebook, an ultrabook, a smartphone, a tablet, a personal digital assistant (PDA), an ultra mobile PC, a mobile phone, a desktop computer, a server, a printer, a scanner, a monitor, a set-top box, an entertainment control unit, a digital camera, a portable music player, or a digital video recorder. In further implementations, the computing device **900** may be any other electronic device that processes data.

[0138] FIG. 10 illustrates an interposer **1000** that includes one or more embodiments of the present disclosure. The interposer **1000** is an intervening substrate used to bridge a first substrate **1002** to a second substrate **1004**. The first substrate **1002** may be, for instance, an integrated circuit die. The second substrate **1004** may be, for instance, a memory module, a computer motherboard, or another integrated circuit die. Generally, the purpose of an interposer **1000** is to spread a connection to a wider pitch or to reroute a connection to a different connection. For example, an interposer **1000** may couple an integrated circuit die to a ball grid array (BGA) **1006** that can subsequently be coupled to the second substrate **1004**. In some embodiments, the first and second substrates **1002/1004** are attached to opposing sides of the interposer **1000**. In other embodiments, the first and second substrates **1002/1004** are attached to the same side of the interposer **1000**. And in further embodiments, three or more substrates are interconnected by way of the interposer **1000**.

[0139] The interposer **1000** may be formed of an epoxy resin, a fiberglass-reinforced epoxy resin, a ceramic material, or a polymer material such as polyimide. In further implementations, the interposer **1000** may be formed of alternate rigid or flexible materials that may include the same materials described above for use in a semiconductor substrate, such as silicon, germanium, and other group III-V and group IV materials.

[0140] The interposer **1000** may include metal interconnects **1008** and vias **1010**, including but not limited to through-silicon vias (TSVs) **1012**. The interposer **1000** may further include embedded devices **1014**, including both passive and active devices. Such devices include, but are not limited to, capacitors, decoupling capacitors, resistors, inductors, fuses, diodes, transformers, sensors, and electrostatic discharge (ESD) devices. More complex devices such

as radio-frequency (RF) devices, power amplifiers, power management devices, antennas, arrays, sensors, and MEMS devices may also be formed on the interposer **1000**. In accordance with embodiments of the disclosure, apparatuses or processes disclosed herein may be used in the fabrication of interposer **1000** or in the fabrication of components included in the interposer **1000**.

[0141] Thus, embodiments of the present disclosure include substrate-less silicon controlled rectifier (SCR) integrated circuit structures, and methods of fabricating substrate-less silicon controlled rectifier (SCR) integrated circuit structures.

[0142] The above description of illustrated implementations of embodiments of the disclosure, including what is described in the Abstract, is not intended to be exhaustive or to limit the disclosure to the precise forms disclosed. While specific implementations of, and examples for, the disclosure are described herein for illustrative purposes, various equivalent modifications are possible within the scope of the disclosure, as those skilled in the relevant art will recognize.

[0143] These modifications may be made to the disclosure in light of the above detailed description. The terms used in the following claims should not be construed to limit the disclosure to the specific implementations disclosed in the specification and the claims. Rather, the scope of the disclosure is to be determined entirely by the following claims, which are to be construed in accordance with established doctrines of claim interpretation.

[0144] Example embodiment 1: A substrate-less integrated circuit structure includes a first fin portion and a second fin portion that meet at a junction. A plurality of gate structures is over the first fin portion and a second fin portion. A plurality of P-type epitaxial structures and N-type epitaxial structures is between corresponding adjacent ones of the plurality of gate structures. Pairs of the P-type epitaxial structures alternate with pairs of the N-type epitaxial structures. A corresponding one or more open locations is between neighboring pairs of the P-type epitaxial structures and pairs of the N-type epitaxial structures.

[0145] Example embodiment 2: The substrate-less integrated circuit structure of example embodiment 1, wherein the first fin portion includes P-well doping, and the second fin portion includes N-well doping.

[0146] Example embodiment 3: The substrate-less integrated circuit structure of example embodiment 1 or 2, wherein the substrate-less integrated circuit structure is a silicon controlled rectifier (SCR).

[0147] Example embodiment 4: The substrate-less integrated circuit structure of example embodiment 1, 2 or 3, wherein the P-type epitaxial structures are boron-doped silicon or boron-doped silicon germanium structures.

[0148] Example embodiment 5: The substrate-less integrated circuit structure of example embodiment 1, 2, 3 or 4, wherein the N-type epitaxial structures are phosphorous-doped silicon structures.

[0149] Example embodiment 6: A computing device includes a board, and a component coupled to the board. The component includes a substrate-less integrated circuit structure. The substrate-less integrated circuit structure includes a first fin portion and a second fin portion that meet at a junction. A plurality of gate structures is over the first fin portion and a second fin portion. A plurality of P-type epitaxial structures and N-type epitaxial structures is between corresponding adjacent ones of the plurality of gate

structures. Pairs of the P-type epitaxial structures alternate with pairs of the N-type epitaxial structures. A corresponding one or more open locations is between neighboring pairs of the P-type epitaxial structures and pairs of the N-type epitaxial structures.

[0150] Example embodiment 7: The computing device of example embodiment 6, further including a memory coupled to the board.

[0151] Example embodiment 8: The computing device of example embodiment 6 or 7, further including a communication chip coupled to the board.

[0152] Example embodiment 9: The computing device of example embodiment 6, 7 or 8, wherein the component is a packaged integrated circuit die.

[0153] Example embodiment 10: The computing device of example embodiment 6, 7, 8 or 9, wherein the component is selected from the group consisting of a processor, a communications chip, and a digital signal processor.

[0154] Example embodiment 11: A substrate-less integrated circuit structure includes a first fin portion and a second fin portion that meet at a junction. A plurality of gate structures is over the first fin portion and a second fin portion. A plurality of P-type epitaxial structures and N-type epitaxial structures is between corresponding adjacent ones of the plurality of gate structures. A pair of the P-type epitaxial structures is over the second fin portion, and a pair of the N-type epitaxial structures is over the first fin portion. An open location is over the junction between the first fin portion and the second fin portion. A first backside metallization structure is coupled to a bottom of the first fin portion. A second backside metallization structure is coupled to a bottom of the second fin portion.

[0155] Example embodiment 12: The substrate-less integrated circuit structure of example embodiment 11, wherein the first fin portion includes P-well doping, and the second fin portion includes N-well doping.

[0156] Example embodiment 13: The substrate-less integrated circuit structure of example embodiment 11 or 12, wherein the substrate-less integrated circuit structure is a silicon controlled rectifier (SCR).

[0157] Example embodiment 14: The substrate-less integrated circuit structure of example embodiment 11, 12 or 13, wherein the P-type epitaxial structures are boron-doped silicon or boron-doped silicon germanium structures.

[0158] Example embodiment 15: The substrate-less integrated circuit structure of example embodiment 11, 12, 13 or 14, wherein the N-type epitaxial structures are phosphorous-doped silicon structures.

[0159] Example embodiment 16: A computing device includes a board, and a component coupled to the board. The component includes a substrate-less integrated circuit structure. The substrate-less integrated circuit structure includes a first fin portion and a second fin portion that meet at a junction. A plurality of gate structures is over the first fin portion and a second fin portion. A plurality of P-type epitaxial structures and N-type epitaxial structures is between corresponding adjacent ones of the plurality of gate structures. A pair of the P-type epitaxial structures is over the second fin portion, and a pair of the N-type epitaxial structures is over the first fin portion. An open location is over the junction between the first fin portion and the second fin portion. A first backside metallization structure is

coupled to a bottom of the first fin portion. A second backside metallization structure is coupled to a bottom of the second fin portion.

[0160] Example embodiment 17: The computing device of example embodiment 16, further including a memory coupled to the board.

[0161] Example embodiment 18: The computing device of example embodiment 16 or 17, further including a communication chip coupled to the board.

[0162] Example embodiment 19: The computing device of example embodiment 16, 17 or 18, wherein the component is a packaged integrated circuit die.

[0163] Example embodiment 20: The computing device of example embodiment 16, 17, 18 or 19, wherein the component is selected from the group consisting of a processor, a communications chip, and a digital signal processor.

What is claimed is:

1. A substrate-less integrated circuit structure, comprising:

- a first nanowire portion and a second nanowire portion that meet at a junction;
- a plurality of gate structures over the first nanowire portion and the second nanowire portion; and
- a plurality of P-type epitaxial structures and N-type epitaxial structures between corresponding adjacent ones of the plurality of gate structures, wherein pairs of the P-type epitaxial structures alternate with pairs of the N-type epitaxial structures, and a corresponding one or more open locations is between neighboring pairs of the P-type epitaxial structures and pairs of the N-type epitaxial structures, wherein each of the one or more open locations is directly between corresponding ones of the plurality of gate structures.

2. The substrate-less integrated circuit structure of claim 1, wherein the first nanowire portion includes P-well doping, and the second nanowire portion includes N-well doping.

3. The substrate-less integrated circuit structure of claim 1, wherein the substrate-less integrated circuit structure is a silicon controlled rectifier (SCR).

4. The substrate-less integrated circuit structure of claim 1, wherein the P-type epitaxial structures are boron-doped silicon or boron-doped silicon germanium structures.

5. The substrate-less integrated circuit structure of claim 1, wherein the N-type epitaxial structures are phosphorous-doped silicon structures.

6. A computing device, comprising:

a board; and

a component coupled to the board, the component including a substrate-less integrated circuit structure, comprising:

- a first nanowire portion and a second nanowire portion that meet at a junction;
- a plurality of gate structures over the first nanowire portion and the second nanowire portion; and
- a plurality of P-type epitaxial structures and N-type epitaxial structures between corresponding adjacent ones of the plurality of gate structures, wherein pairs of the P-type epitaxial structures alternate with pairs of the N-type epitaxial structures, and a corresponding one or more open locations is between neighboring pairs of the P-type epitaxial structures and pairs of the N-type epitaxial structures, wherein each

of the one or more open locations is directly between corresponding ones of the plurality of gate structures.

7. The computing device of claim 6, further comprising: a memory coupled to the board.

8. The computing device of claim 6, further comprising: a communication chip coupled to the board.

9. The computing device of claim 6, wherein the component is a packaged integrated circuit die.

10. The computing device of claim 6, wherein the component is selected from the group consisting of a processor, a communications chip, and a digital signal processor.

11. A substrate-less integrated circuit structure, comprising:

- a first nanowire portion and a second nanowire portion that meet at a junction;
- a plurality of gate structures over the first nanowire portion and the second nanowire portion;
- a plurality of P-type epitaxial structures and N-type epitaxial structures between corresponding adjacent ones of the plurality of gate structures, wherein a pair of the P-type epitaxial structures is over the second nanowire portion, and a pair of the N-type epitaxial structures is over the first nanowire portion;
- an open location over the junction between the first nanowire portion and the second nanowire portion, wherein the open location is directly between corresponding ones of the plurality of gate structures;
- a first backside metallization structure coupled to a bottom of the first nanowire portion; and
- a second backside metallization structure coupled to a bottom of the second nanowire portion.

12. The substrate-less integrated circuit structure of claim 11, wherein the first nanowire portion includes P-well doping, and the second nanowire portion includes N-well doping.

13. The substrate-less integrated circuit structure of claim 11, wherein the substrate-less integrated circuit structure is a silicon controlled rectifier (SCR).

14. The substrate-less integrated circuit structure of claim 11, wherein the P-type epitaxial structures are boron-doped silicon or boron-doped silicon germanium structures.

15. The substrate-less integrated circuit structure of claim 11, wherein the N-type epitaxial structures are phosphorous-doped silicon structures.

16. A computing device, comprising:

a board; and

a component coupled to the board, the component including a substrate-less integrated circuit structure, comprising:

- a first nanowire portion and a second nanowire portion that meet at a junction;
- a plurality of gate structures over the first nanowire portion and the second nanowire portion;
- a plurality of P-type epitaxial structures and N-type epitaxial structures between corresponding adjacent ones of the plurality of gate structures, wherein a pair of the P-type epitaxial structures is over the second nanowire portion, and a pair of the N-type epitaxial structures is over the first nanowire portion;
- an open location over the junction between the first nanowire portion and the second nanowire portion, wherein the open location is directly between corresponding ones of the plurality of gate structures;

a first backside metallization structure coupled to a bottom of the first nanowire portion; and
a second backside metallization structure coupled to a bottom of the second nanowire portion of the P-type epitaxial structures and pairs of the N-type epitaxial structures.

17. The computing device of claim **16**, further comprising:

a memory coupled to the board.

18. The computing device of claim **16**, further comprising:

a communication chip coupled to the board.

19. The computing device of claim **16**, wherein the component is a packaged integrated circuit die.

20. The computing device of claim **16**, wherein the component is selected from the group consisting of a processor, a communications chip, and a digital signal processor.

* * * * *