



US012384614B1

(12) **United States Patent**  
**Hermanson et al.**

(10) **Patent No.:** **US 12,384,614 B1**

(45) **Date of Patent:** **Aug. 12, 2025**

(54) **PACKING MATERIAL AND METHOD OF  
MANUFACTURING THE PACKING  
MATERIAL**

(71) Applicant: **Terry Hermanson**, New York, NY  
(US)

(72) Inventors: **Terry Hermanson**, New York, NY  
(US); **Huang Meng-Suen**, Hong Kong  
(CN)

(73) Assignee: **Terry Hermanson**, New York, NY  
(US)

(\*) Notice: Subject to any disclaimer, the term of this  
patent is extended or adjusted under 35  
U.S.C. 154(b) by 176 days.

(21) Appl. No.: **18/156,751**

(22) Filed: **Jan. 19, 2023**

**Related U.S. Application Data**

(63) Continuation of application No.  
PCT/US2021/042719, filed on Jul. 22, 2021, which is  
(Continued)

(51) **Int. Cl.**  
**B65D 81/02** (2006.01)  
**B29C 43/00** (2006.01)  
(Continued)

(52) **U.S. Cl.**  
CPC ..... **B65D 81/025** (2013.01); **B29C 43/003**  
(2013.01); **B31D 5/0039** (2013.01);  
(Continued)

(58) **Field of Classification Search**  
CPC .... B65D 81/025; B65D 81/09; B65D 81/107;  
B31D 5/0039; B31D 5/006; B31D  
2205/005; B31D 2205/006  
(Continued)

(56) **References Cited**

**U.S. PATENT DOCUMENTS**

1,189,140 A 6/1916 Lane  
2,657,158 A \* 10/1953 Gerard ..... B65D 65/44  
217/3 BC

(Continued)

**FOREIGN PATENT DOCUMENTS**

CN 102712400 A 10/2012  
CN 104371343 A 2/2015

(Continued)

**OTHER PUBLICATIONS**

Comprehensive Guide to cushioning and void fill for shipping  
packaging, Internet Archive of <https://www.ecoenclose.com/Definitive-Guide-to-Void-Fill-and-Cushioning/> (captured Sep. 18, 2019), avail-  
able at <https://web.archive.org/web/20190918180012/https://www.ecoenclose.com/Definitive-Guide-to-Void-Fill-and-Cushioning/>.

(Continued)


*Primary Examiner* — Chun Hoi Cheung

(74) *Attorney, Agent, or Firm* — Venable LLP

(57) **ABSTRACT**

A packing material including a plurality of discrete cushioning elements and methods for making the same. The discrete cushioning elements may be cellulosic cushioning elements. A flexible linkage may connect the plurality of discrete cushioning elements in the packing material. The packing material may also include a bottom cellulosic sheet connected to a top cellulosic sheet with the plurality of cellulosic cushioning elements positioned between the top cellulosic sheet and the bottom cellulosic sheet. The packing material may also be a molded packing material that includes bonds comprising adhesive and cellulosic fibers. The adhesive and cellulosic fibers of the bonds may be dispersed between the folds of each of the cellulosic cushioning elements.

**19 Claims, 14 Drawing Sheets**



**Related U.S. Application Data**

a continuation of application No. 17/197,837, filed on Mar. 10, 2021, now abandoned, and a continuation of application No. 17/197,889, filed on Mar. 10, 2021, now Pat. No. 11,161,668.

- (60) Provisional application No. 63/054,853, filed on Jul. 22, 2020.

(51) **Int. Cl.**

**B29K 105/00** (2006.01)

**B29L 31/00** (2006.01)

**B31D 5/00** (2017.01)

**B65D 81/09** (2006.01)

(52) **U.S. Cl.**

CPC ..... **B31D 5/0043** (2013.01); **B31D 5/006** (2013.01); **B31D 5/0073** (2013.01); **B65D 81/09** (2013.01); **B29K 2105/0097** (2013.01); **B29K 2105/25** (2013.01); **B29L 2031/712** (2013.01); **B31D 2205/0023** (2013.01); **B31D 2205/0058** (2013.01); **B31D 2205/0064** (2013.01)

(58) **Field of Classification Search**

USPC ..... 206/522–594  
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

2,924,154 A 2/1960 Russell et al.  
2,978,006 A 4/1961 Clemens  
3,074,543 A 1/1963 Stanley  
3,131,240 A 4/1964 Kirkpatrick  
3,509,797 A 5/1970 Johnson  
3,530,020 A 9/1970 Liebermann  
3,546,055 A 12/1970 Spertus  
3,616,158 A 10/1971 Rubens et al.  
3,650,877 A 3/1972 Johnson  
3,655,500 A 4/1972 Johnson  
3,741,411 A 6/1973 Peacock  
3,812,618 A 5/1974 Wood et al.  
4,384,442 A 5/1983 Pendleton  
4,644,733 A 2/1987 Dolinar  
4,680,918 A 7/1987 Lovell  
4,806,410 A 2/1989 Armington et al.  
4,828,913 A 5/1989 Kiss  
4,880,119 A \* 11/1989 Simon ..... B65D 81/09  
206/584  
4,937,131 A 6/1990 Baldacci et al.  
4,997,091 A 3/1991 McCrear  
5,230,943 A 7/1993 Pregont  
5,251,414 A 10/1993 Duke  
5,312,665 A 5/1994 Pratt et al.  
5,330,165 A 7/1994 van Goubergen  
5,340,638 A 8/1994 Sperner  
5,468,556 A 11/1995 Fuss et al.  
5,545,297 A 8/1996 Andersen et al.  
5,568,867 A 10/1996 Lencoski  
5,569,519 A 10/1996 Ervay et al.  
5,595,811 A 1/1997 Stout, Jr.  
5,623,815 A 4/1997 Hornstein et al.  
5,636,744 A 6/1997 Hirose  
5,639,543 A 6/1997 Isoda et al.  
5,658,624 A 8/1997 Anderson et al.  
5,674,344 A 10/1997 Thompson et al.  
5,683,772 A 11/1997 Andersen et al.  
5,688,578 A 11/1997 Goodrich  
5,756,127 A 5/1998 Grisoni et al.  
5,826,404 A 10/1998 Fuss et al.  
5,871,857 A 2/1999 Alhamad  
5,900,119 A 5/1999 Goers et al.  
5,910,079 A 6/1999 Watanabe

5,910,089 A 6/1999 Weder  
5,944,192 A 8/1999 Weder  
5,992,637 A 11/1999 Weder  
6,067,779 A 5/2000 Weder  
6,128,889 A 10/2000 Fuss  
6,254,945 B1 7/2001 Simmons  
6,298,637 B1 10/2001 Weder  
6,385,949 B2 5/2002 Weder  
6,532,721 B1 3/2003 Weder  
6,546,701 B2 4/2003 Weder et al.  
6,632,165 B1 10/2003 Letourneau et al.  
6,752,910 B2 6/2004 Sato et al.  
6,871,480 B1 3/2005 Goodrich  
6,969,548 B1 11/2005 Goldfine  
7,651,455 B2 1/2010 Yampolsky et al.  
7,803,100 B2 9/2010 Lu et al.  
8,052,037 B2 11/2011 Bussey, III et al.  
8,146,748 B2 4/2012 Vulpitta  
8,201,671 B2 6/2012 Cho  
8,360,949 B2 1/2013 Wetsch et al.  
8,763,667 B2 7/2014 De Luca  
8,900,111 B2 12/2014 Wetsch et al.  
8,999,490 B2 4/2015 Kung et al.  
9,205,621 B2 12/2015 Cheich  
9,315,312 B2 4/2016 De Luca et al.  
9,427,928 B2 8/2016 Arora et al.  
9,457,982 B2 10/2016 Wetsch et al.  
9,688,044 B2 6/2017 Deis et al.  
10,099,836 B2 10/2018 Cheich  
10,357,936 B1 7/2019 Vincent et al.  
10,392,177 B2 8/2019 Lantz  
10,766,220 B2 9/2020 Deis et al.  
10,766,221 B2 9/2020 Peis et al.  
10,792,882 B2 10/2020 Wetsch et al.  
10,828,859 B2 11/2020 Ciasullo, Jr. et al.  
11,123,943 B2 9/2021 Cheich et al.  
11,161,668 B1 11/2021 Hermanson et al.  
11,167,907 B1 11/2021 Hermanson et al.  
11,358,775 B2 6/2022 Hermanson et al.  
11,390,443 B2 7/2022 Hermanson et al.  
11,390,444 B2 7/2022 Hermanson et al.  
2002/0040859 A1 4/2002 Weder  
2003/0051819 A1 3/2003 Moustier  
2004/0050743 A1 3/2004 Slovencik et al.  
2004/0052988 A1 3/2004 Slovencik et al.  
2004/0108243 A1 6/2004 Jeannin  
2005/0230864 A1 10/2005 Ozasa et al.  
2006/0281621 A1 12/2006 Weder  
2007/0082181 A1 4/2007 Jung  
2008/0153685 A1 6/2008 Cheich et al.  
2009/0082187 A1 3/2009 Cheich et al.  
2010/0323153 A1 12/2010 Huskey  
2011/0053743 A1 3/2011 Wetsch et al.  
2011/0061986 A1 3/2011 Orsini et al.  
2012/0031957 A1 2/2012 Whitaker  
2012/0097067 A1 4/2012 Fascio  
2012/0165172 A1 6/2012 Wetsch et al.  
2013/0313277 A1 11/2013 Stewartson et al.  
2014/0155241 A1 6/2014 Cheich et al.  
2016/0060014 A1 3/2016 Timmers et al.  
2016/0221233 A1 8/2016 Kiiskinen et al.  
2018/0029764 A1 2/2018 Chung et al.  
2018/0030659 A1 2/2018 Chung et al.  
2018/0126686 A1 5/2018 Nelson et al.  
2018/0264768 A1 9/2018 Haug  
2018/0319116 A1 11/2018 Haug  
2018/0370702 A1 12/2018 Goodrich  
2020/0061951 A1 2/2020 Slovencik  
2020/0063361 A1 2/2020 Everett et al.  
2020/0115087 A1 4/2020 Hagedstedt et al.  
2020/0139661 A1 5/2020 Greenwell  
2020/0180841 A1 6/2020 Alvarez et al.  
2021/0179333 A1 6/2021 Wetsch  
2021/0237961 A1 8/2021 Lenart et al.

FOREIGN PATENT DOCUMENTS

DE 40 25 257 C2 9/1992  
DE 42 25 143 A1 2/1994

(56)

**References Cited**

## FOREIGN PATENT DOCUMENTS

EP	0560608 A1	9/1993
JP	H06-247471 A	9/1994
JP	H08-244853 A	9/1996
JP	2000118571 A	4/2000
JP	2002-225946 A	4/2002
WO	92/04253 A1	3/1992
WO	94/12576	6/1994
WO	97/09248	3/1997

## OTHER PUBLICATIONS


ExpandOS, <https://expandos.com>, visited Oct. 29, 2020.

“Paper Packaging Applications”, Paper Packaging Systems, <https://www.paperpackagingsystems.com/paper-packaging-applications-paper>, visited Oct. 29, 2020.


“Crinkle Cut Fill”, Bags and Bows Online, [https://www.bagsandbowsonline.com/retail-packaging/search?Ntt=crinkle cutfill](https://www.bagsandbowsonline.com/retail-packaging/search?Ntt=crinkle%20cutfill), visited Oct. 29, 2020.

Office Action dated Jan. 9, 2024, in Japanese Patent Application No. 2023-504354.


\* cited by examiner




**FIG. 1A**




**FIG. 1B**




**FIG. 2**




**FIG. 3A**




**FIG. 3B**




**FIG. 3C**




**FIG. 3D**




**FIG. 4A**




**FIG. 4B**




**FIG. 4C**




**FIG. 4D**



**FIG. 5**




**FIG. 6A**




**FIG. 6B**







**FIG. 7A**




**FIG. 7B**




**FIG. 8**




**FIG. 9**




**FIG. 10**




**FIG. 11**




**FIG. 12**




**FIG. 13**





**FIG. 14**



**FIG. 15**



**FIG. 16**

**FIG. 17****FIG. 18**






FIG. 19



**FIG. 20**



**FIG. 21**






FIG. 22

1

# PACKING MATERIAL AND METHOD OF MANUFACTURING THE PACKING MATERIAL

## CROSS-REFERENCE TO RELATED APPLICATIONS

This application is a continuation of International Patent Application No. PCT/US21/42719, filed Jul. 22, 2021, which claims priority to U.S. patent application Ser. No. 17/197,837, filed Mar. 10, 2021, U.S. patent application Ser. No. 17/197,889, filed Mar. 10, 2021, and U.S. Provisional Patent Application No. 63/054,853, filed Jul. 22, 2020, and titled "PACKING MATERIAL AND METHOD OF MANUFACTURING THE PACKING MATERIAL," the entirety of which are incorporated herein by reference.

## FIELD OF THE INVENTION

The invention relates to packing material, particularly packing material that includes a plurality of discrete cushioning elements made from paper. The invention is also related to methods of manufacturing the same.

## BACKGROUND OF THE INVENTION

Various packing materials are used to secure items in shipping containers, including cardboard boxes, to thereby prevent damage to these items if they move within the shipping container during shipment or other impacts during shipping, such as being dropped or hit. Such packing materials include bubble wrap, expanded polystyrene (polystyrene foam), and other plastic foam packing, which may be molded into blocks or into other shapes, peanuts, and inflated plastic bags (also known as air pillows). These plastic products may be discarded as waste after they have been used during shipping. Plastic waste takes a long time to decompose and produces carbon dioxide in the decomposition process. In addition, polystyrene foam does not readily biodegrade, and may take many, many years to break down. With an increased awareness of the negative effects of plastics and polystyrene foam on the environment, however, consumers are increasingly seeking to use environmentally-friendly, recyclable, and biodegradable products as a packing material. There are desired environmentally-friendly, recyclable, and biodegradable products that provide sufficient cushioning effects at an affordable cost.

## SUMMARY OF THE INVENTION

In one aspect, the invention relates to a packing material including a plurality of cellulosic cushioning elements, a top cellulosic sheet arranged one side of the plurality of cellulosic cushioning elements, and a bottom cellulosic sheet arranged on an opposite side of the plurality of cellulosic cushioning elements. Each cellulosic cushioning element of the plurality of cellulosic cushioning elements have a plurality of folds and are formed into a shape. The bottom cellulosic sheet is connected to the top cellulosic sheet with the plurality of cellulosic cushioning elements positioned between the top cellulosic sheet and the bottom cellulosic sheet.

In another aspect, the invention relates to a packing material including a plurality of discrete cushioning elements and a flexible linkage connecting the plurality of discrete cushioning elements. The plurality of discrete cushioning elements is arrayed in a first direction and have an

2

order with each cushioning element of the plurality of discrete cushioning elements is adjacent to at least one other cushioning element of the plurality of discrete cushioning elements. The at least one other cushioning element of the plurality of discrete cushioning elements is a first adjacent cushioning element, and each cushioning element is spaced apart from a respective first adjacent cushioning element with a first gap formed between each cushioning element and the respective first adjacent cushioning element. Each cushioning element is connected to the respective first adjacent cushioning element by the flexible linkage. The flexible linkage spans the first gap between each cushioning element and the respective first adjacent cushioning element.

In a further aspect, the invention relates to a method of manufacturing packing material. The method includes filling a plurality of pockets of a first cellulosic sheet with a plurality of cellulosic cushioning elements. Each pocket has an opening through which the pocket is filled. The method further includes applying an aqueous slurry of cellulosic fibers and adhesive to the plurality of cellulosic cushioning elements in each pocket of the first cellulosic sheet, drying the aqueous slurry and the plurality of cellulosic cushioning elements, and bonding a second cellulosic sheet to the first cellulosic sheet to cover the openings of the plurality of pockets in the first cellulosic sheet.

In yet another aspect, the invention relates to a packing material including a plurality of cellulosic cushioning elements and bonds bonding the plurality of cellulosic cushioning elements to each other. Each cellulosic cushioning element of the plurality of cellulosic cushioning elements has a plurality of folds and is formed into a shape. The bonds comprise adhesive and cellulosic fibers. The adhesive and cellulosic fibers of the bonds are dispersed between the folds of each of the cellulosic cushioning elements.

In still another aspect, the invention relates to a method of manufacturing molded packing material. The method includes filling a mold with a plurality of cellulosic cushioning elements; applying an aqueous slurry of cellulosic fibers and adhesive to the plurality of cellulosic cushioning elements in the mold; drying the aqueous slurry and the plurality of cellulosic cushioning elements to form a molded packing material; and removing the molded packing material from the mold.

In yet a further aspect, the invention relates to a method of manufacturing packing material. The method includes providing a cellulosic sheet. The cellulosic sheet has a thickness and a face surface. The face surface has a surface area. The cellulosic sheet has a thickness direction and an orthogonal direction that is orthogonal to the thickness direction. The method also includes compressing the cellulosic sheet to form a compressed cellulosic sheet; and twisting the compressed cellulosic sheet to form a crumpled cellulosic sheet.

These and other aspects of the invention will become apparent from the following disclosure.

## BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1A shows a cellulosic cushioning element that can be used as a packing material according to a preferred embodiment of the invention. FIG. 1B shows an alternative cellulosic cushioning element that can be used as the packing material.

FIG. 2 is a shipping box containing an item and a plurality of the cellulosic cushioning elements in FIG. 1A.

FIGS. 3A-3D show a method and machine used to manufacture the cellulosic cushioning element shown in FIG. 1A.

3

FIG. 3A shows a first step, FIG. 3B shows a second step, FIG. 3C shows a third step, and FIG. 3D shows a fourth step.

FIGS. 4A-4D show an alternate method and machine used to manufacture the cellulosic cushioning element shown in FIG. 1A. FIG. 4A shows a first step, FIG. 4B shows a second step, FIG. 4C shows a third step, and FIG. 4D shows a fourth step.

FIG. 5 is a perspective view of feeding rollers that may be used with the method and apparatus shown in FIGS. 4A-4D.

FIGS. 6A and 6B are cellulosic cushioning elements that may be produced by the method and apparatus shown in FIGS. 4A-4D. FIG. 6A is a cellulosic cushioning element that is produced without shaping by the feeding rollers, and FIG. 6B is a cellulosic cushioning element that is produced with the feeding rollers shown in FIG. 5.

FIGS. 7A and 7B each show a packing material with linkages connecting discrete cushioning elements. The packing material in FIGS. 7A and 7B use the cellulosic cushioning elements shown in FIG. 1A as discrete cushioning elements. FIG. 7A shows one way the linkage is attached to the cellulosic cushioning elements, and FIG. 7B shows another way the linkage is attached to the cellulosic cushioning elements.

FIG. 8 shows the packing material of FIG. 7B with alternative discrete cushioning elements.

FIG. 9 shows the packing material of FIG. 7A with alternative linkages.

FIG. 10 shows another packing material with linkages connecting discrete cushioning elements. The packing material in FIG. 10 uses the cellulosic cushioning elements shown in FIG. 1A as discrete cushioning elements.

FIG. 11 shows the packing material of FIG. 10 used on a bottle.

FIG. 12 shows a method of manufacturing the packing material shown in FIG. 9.

FIG. 13 shows another packing material using the cellulosic cushioning elements shown in FIG. 1A as discrete cushioning elements.

FIG. 14 shows further packing material using the cellulosic cushioning elements shown in FIG. 1A as discrete cushioning elements.

FIG. 15 is a cross-sectional view of the packing material shown in FIG. 14 taken along line 15-15 in FIG. 14.

FIG. 16 is an alternate cross-sectional view of the packing material shown in FIG. 14 taken along line 15-15 in FIG. 14.

FIG. 17 shows a variation of the packing material shown in FIG. 14.

FIG. 18 shows another variation of the packing material shown in FIG. 14.

FIG. 19 shows a method and machine used to manufacture the packing material shown in FIG. 14.

FIG. 20 shows a further packing material using the cellulosic cushioning elements shown in FIG. 1A.

FIG. 21 is a cross-sectional view of the packing material shown in FIG. 20 taken along line 21-21 in FIG. 20.

FIG. 22 shows a method and machine used to manufacture the packing material shown in FIG. 20.

#### DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

The packing materials disclosed herein utilize a cushioning element **100** as a base material. FIG. 1A shows a preferred cushioning element **100** that may be used in the packing materials discussed further below. This cushioning element **100** is preferably a cellulosic cushioning element **110**, being formed from paper composed of cellulosic fibers.

4

Other suitable cushioning elements **100**, as will be described in certain embodiments below, may also be used in the packing materials discussed herein. Paper is a preferred material used for the cellulosic cushioning element **110**, as paper is biodegradable. The paper used herein is preferably recycled paper (e.g., previously-used paper). Various suitable basis weights and thicknesses may be used for the cellulosic cushioning elements **110** discussed herein and they may be varied depending upon application. As will be described further below, the paper is preferably crumpled into a shape that is preferably ball-like or sphere-like or cylindrical. The cellulosic cushioning element **110** may be relatively small in size, such as approximately 0.25 inch in diameter, or relatively large in size, such as approximately one inch in diameter. But such sizes are exemplary, and various other suitable diameters may be used. The crumpled cellulosic cushioning element **110** thus includes a plurality of folds and crevices or air pockets formed between the folds of the cellulosic cushioning element **110**.

An alternative cellulosic cushioning element **111** is shown in FIG. 1B. The paper used to form the alternative cellulosic cushioning element **111** may be cut into thin strips (for example, 0.25 inch in width) and then folded a plurality of times into a shape to form the alternative cellulosic cushioning element **111**. The alternative cellulosic cushioning element **111** is thus folded to form a geometric shape, such as the square, shown in FIG. 1B. But other suitable geometric shapes may be formed. As with the cellulosic cushioning element **110**, the alternative cellulosic cushioning element **111** includes a plurality of folds and air pockets formed between the folds and strips of paper.

The invention is not limited, however, to the sizes and shapes described above and shown in FIGS. 1A and 1B. The cellulosic cushioning element **110** and alternative cellulosic cushioning element **111** may also be crumpled or folded to form elements having other shapes or forms including, for example, the form shown in FIG. 6A, below. The alternative cellulosic cushioning element **111** may be used in place of the crumpled cellulosic cushioning element **110** in each of the packing materials discussed further below.

These cellulosic cushioning elements **110** may be used on their own as packing material. FIG. 2 shows, for example, a shipping box **102** that has an item-to-be-shipped **104** placed therein. The shipping box **102** may be any suitable shipping box including a cardboard box. The cellulosic cushioning element **110** may be placed in the shipping box **102** to surround the item-to-be-shipped **104**. The cellulosic cushioning element **110** is elastically deformable to absorb energy and protect the item-to-be-shipped **104** but, even when crushed, provides additional energy (shock) absorbing to protect the item-to-be-shipped **104**. Factors impacting the amount of energy absorbed that may be modified for the desired protection include the weight of the paper, the volume or size (e.g., diameter) of the cellulosic cushioning element **110**, and the density of the cellulosic cushioning element **110**.

A method of forming the cellulosic cushioning element **110** and a machine assembly **200** used in this method will be described with reference to FIGS. 3A-3D. Initially a sheet **112** of paper is fed on top of a die **210** and, in this embodiment, between a cover plate **212** and the die **210**. The sheet **112** includes a face surface **114** with a surface area. The sheet **112** also has a thickness, which as discussed above, can be any suitable thickness. The sheet has a thickness direction and an orthogonal direction that is orthogonal to the thickness direction. In FIG. 3A, the sheet **112** is fed in the orthogonal direction of the sheet **112**. The

5

sheet 112 is nipped and fed by a feed roller 202. The feed roller 202 forms a nip with a nip forming member, which in this embodiment is a feed plate 204, but any suitable nip forming member may be used such as another roller. In this embodiment, the sheet 112 is a continuous sheet from a roll 116. However, the sheet 112 may be provided in other suitable forms such a stack of sheets 112 that cut to size and fed one-by-one to the die 210.

The die 210 has a cylindrical hole 214 with a taper 216 at the entrance of the die 210 forming a funnel shape. The sheet 112 is pressed through the die 210 with a plunger 220. The plunger 220 has a shape that corresponds to the shape of the die 210. In this embodiment, the plunger 220 is cylindrical with a spherical tip 222, but any suitable shape may be used. The cylindrical hole 214 of the die 210 has a diameter, and the diameter of the plunger 220 is smaller than the diameter of the cylindrical hole 214 so that the plunger 220 can be inserted into the cylindrical hole 214. The plunger 220 is lowered moving through a hole 218 in the cover plate 212 to press the sheet 112 in a direction crossing the orthogonal direction of the sheet 112, which is the thickness direction in this embodiment. The tip 222 of the plunger 220 contacts the face surface 114 of the sheet 112 and pushes the sheet 112 into the cylindrical hole 214 of the die 210. The sheet 112 has a surface area that is greater than the surface area of the cylindrical hole 214 at the exit of the die 210. As the plunger 220 pushes presses the sheet 112 into the taper 216 and the cylindrical hole 214 of the die 210, the sheet 112 conforms to the shape of the die 210 and the plunger 220 to form a shaped cellulosic sheet 118. Thus, in this embodiment, the shaped cellulosic sheet 118 has a hollow, cylindrical shape with a spherical tip. The plunger 220 is inserted into the cylindrical hole 214 of the die 210 such that the plunger 220 discharges the shaped cellulosic sheet 118 from the exit (bottom) of the die 210.

When the sheet 112 is supplied by the roll 116 a cutter 224 may be used to cut the sheet 112 to the appropriate length. In this embodiment, the cutter 224 is configured to move with the plunger 220 between the top of the die 210 and the feed plate 204. The cutter 224 cuts the sheet 112 just before or as the tip 222 contacts the face surface 114 of the sheet 112 to push the sheet 112 into the die 210.

After the shaped cellulosic sheet 118 exits the die 210, the shaped cellulosic sheet 118 passes between a first portion 230A and a second portion 230B of a form 230 as shown in FIG. 3B. The first portion 230A and the second portion 230B of the form 230 are then brought into contact with each other to compress the shaped cellulosic sheet 118 within a cavity 232 of the form 230 as shown in FIG. 3C. Each of the first portion 230A and the second portion 230B of the form 230 have a concavity 234 formed therein that, when the first portion 230A and the second portion 230B are brought together, form a spherical cavity 232. In this embodiment each concavity 234 is hemispherical to form the cavity 232.

The form 230 also includes a catcher 240 to help catch the shaped cellulosic sheet 118 as it passes between the first portion 230A and the second portion 230B of the form 230. The catcher 240 of this embodiment includes a plurality of teeth 242 that are splayed outward from contacting portions of the first portion 230A and the second portion 230B of the form 230. The diverging angles of the teeth 242 help compress and guide the shaped cellulosic sheet 118 into the cavity 232 as the first portion 230A and the second portion 230B are brought together. In this embodiment, the teeth 242 are interlocking teeth 242 such that the teeth 242 of the first portion 230A mesh with the teeth 242 of the second portion 230B.

6

With the shaped cellulosic sheet 118 compressed within the cavity 232 the first portion 230A and the second portion 230B may be rotated about an axis extending in the direction in which the first portion 230A and the second portion 230B are brought together (or separated). Rotating the first portion 230A and the second portion 230B of the form 230 twists the shaped cellulosic sheet 118 and may help create additional folds and pockets in the resulting the cellulosic cushioning element 110. To facilitate this process, each concavity 234 includes an outer surface 236 that is serrated. Compressing and twisting the shaped cellulosic sheet 118 forms the cellulosic cushioning element 110. After the first portion 230A and the second portion 230B are rotated, the first portion 230A and the second portion 230B are separated by being moved in a direction opposite to the direction in which they were brought together. The cellulosic cushioning element 110 is ejected from the form 230 as the first portion 230A and the second portion 230B are separated as shown in FIG. 3D. These steps are repeated to form additional cellulosic cushioning elements 110.

FIGS. 4A-4D show an alternate method for forming the cellulosic cushioning element 110 and a machine assembly 300 used in this method. As in the method and machine assembly 200 described above, a sheet 112 of paper is used to form the cellulosic cushioning element 110. Although the sheet 112 may be similar to those discussed above, the sheet 112 of this embodiment is preferably a strip of paper having a length (as will be further discussed below) longer than its width. The sheet 112 is nipped and fed by a pair of feed rollers (a first feed roller 302 and a second feed roller 304) and fed into an arcuate-shaped cylinder 310 (herein arcuate cylinder 310), as shown in FIG. 4A. FIG. 5 is a perspective view of the first feed roller 302, the second feed roller 304, and the arcuate cylinder 310.

The first feed roller 302 and the second feed roller 304 may have smooth outer surfaces, but they also may be configured to shape the sheet 112 in the thickness direction as the sheet 112 is fed. As shown in FIG. 5, for example, the first feed roller 302 includes a groove 306. The groove 306 of this embodiment is v-shaped, but any suitable shape may be used, including, for example a u-shape or a w-shape. The second feed roller 304 has a corresponding surface, which in this embodiment is a v-shaped protrusion 308. The protrusion 308 presses the sheet 112 into the groove 306 to impart a shape corresponding to the groove 306 and protrusion 308 to the sheet. FIG. 6A shows the cellulosic cushioning element 110 produced using this method and machine assembly 300 when the sheet 112 is fed with the first feed roller 302 and the second feed roller 304 having smooth outer surfaces. The cellulosic cushioning element 110 sheet shown in FIG. 6A has a plurality of folds with gaps therebetween. FIG. 6B shows the cellulosic cushioning element 110 produced using this method and machine assembly 300 when the sheet 112 is fed with the first feed roller 302 and the second feed roller 304 shown in FIG. 5. The cellulosic cushioning element 110 sheet shown in FIG. 6B is similar to the cellulosic cushioning element 110 shown in FIG. 1A, having a plurality of folds, but with a more cylindrical shape instead of spherical.

As shown in FIG. 4A, the arcuate cylinder 310 has a channel 312 formed therein with an inlet 314 and an outlet 316. The sheet 112 is fed into the channel 312 through the inlet 314 and then slides through the channel 312 until it contacts a ram 322 located at the outlet 316. In this embodiment, the sheet 112 (strip of paper) is fed into the channel 312 to have a length longer than the length of the channel 312 and the sheet 112 waves back and forth within the

channel 312. However, the length of the sheet 112 is not so limited and it may be shorter, for example.

When the sheet 112 reaches the desired length, it is cut with a cutter 324. In this embodiment, the cutter 324 is formed between an edge of the inlet 314 of the arcuate cylinder 310 and a plunger 326. The plunger 326 is connected to a rotor 328 to rotate in a circle. As shown in FIG. 4B, the plunger 326 enters the inlet 314 of the arcuate cylinder 310 and cuts the sheet 112 as it does so. The plunger 326 rotates as it moves along the channel 312 compressing the sheet against the ram 322 the plunger 326. The ram 322 and the plunger 326 of this embodiment are similar to the first portion 230A of the form 230 and second portion 230B of the form 230 discussed above. The ram 322 and the plunger 326 each include a hemispherical concavity 234 and, when brought together as shown in FIG. 4C, form a cavity 232 to compress the sheet 112 and form the cellulosic cushioning element 110. As the plunger 326 continues to rotate, the ram 322 pivots to open the cavity 232 and eject the cellulosic cushioning element 110 as shown in FIG. 4D.

The process shown in FIGS. 4A-4D repeats to form additional cellulosic cushioning elements 110. As can be seen in FIG. 4C, the next sheet 112 is fed into the inlet 314 of the arcuate cylinder 310 after the plunger 326 passes the inlet 314. Accordingly, the next sheet 112 is being fed as the previous sheet 112 is being compressed (FIG. 4C) and ejected as the cellulosic cushioning element 110 (FIG. 4D).

While the plurality of cellulosic cushioning elements 110 are used in a shipping box 102 (as discussed above with reference to in FIG. 2), such a configuration can be messy. When packing or unpacking the item-to-be-shipped 104 the individual cellulosic cushioning elements 110 can easily spill and scatter, requiring the need to clean up. To avoid this issue, each cellulosic cushioning element 110 of a plurality of cellulosic cushioning elements 110 can be connected to one another as shown in FIGS. 7A and 7B. FIGS. 7A and 7B show a packing material according to a preferred embodiment of the invention. For clarity with the other packing materials discussed herein, the packing material of this embodiment is referred to as a rope-like packing material 120.

The rope-like packing material 120 includes a plurality of discrete cushioning elements 100 that are arrayed in a length direction A. Each discrete cushioning element 100 of this embodiment is the cellulosic cushioning element 110 discussed above, but they are not so limited. Instead, each discrete cushioning element 100 may be, for example, a packing peanut 106 as shown in FIG. 8. The packing peanut 106 may be a foamed polymer resin material such as the s-shaped polystyrene foam. Other packing peanuts 106 may be used including biodegradable packing peanuts that are made from resin material of a starch such as corn.

The rope-like packing material 120 will be further described with reference to FIGS. 7A and 7B, but it also applies to the other cushioning elements 100 shown in FIG. 8. The cellulosic cushioning element 110 is arrayed in length direction A in an order. FIGS. 7A and 7B show five cellulosic cushioning elements 110 each appended with a different letter (a-e). Each cellulosic cushioning element 110 is adjacent to at least one other cellulosic cushioning element 110. For example, cellulosic cushioning element 110a is adjacent to cellulosic cushioning element 110b, and cellulosic cushioning element 110b is adjacent to both cellulosic cushioning element 110a and cellulosic cushioning element 110c. In this embodiment, the adjacent cellulosic cushioning elements 110 are spaced apart from each other with a gap (referred to as a first gap 122, herein) formed between the

adjacent cellulosic cushioning elements 110, although other suitable embodiments may be possible where, for example, adjacent cellulosic cushioning elements 110 contact one another.

The adjacent cellulosic cushioning elements 110 are connected to each other by a flexible linkage 124. The flexible linkage 124 is connected to each cellulosic cushioning element 110 and spans the first gap 122 between adjacent cellulosic cushioning element 110. In this embodiment the flexible linkage 124 is a string. The cellulosic cushioning elements 110 may be attached to the flexible linkage 124 using any suitable method, for example an adhesive. In FIG. 7A, the flexible linkage 124 (string) is wrapped around each cellulosic cushioning element 110 at least one time. In FIG. 7B, each cellulosic cushioning element 110 has a hole 126 formed through the diameter (central portion) of the cellulosic cushioning element 110, and the flexible linkage 124 (string) runs through the hole 126.

Other suitable flexible linkages 124 may be used. FIG. 9 shows an example of the rope-like packing material 120 with an alternative flexible linkage 124. The flexible linkage 124 of this embodiment includes an upper tape 132 and a lower tape 134. Although any suitable tape can be used, each of the upper tape 132 and lower tape 134 is preferably a paper (or cellulosic) strip that has a length much greater than its width (see FIG. 10). Paper is preferred, particularly when used with the cellulosic cushioning element 110 so that the entire rope-like packing material 120 can be biodegradable and recyclable. In this embodiment, the upper tape 132 and the lower tape 134 are aligned with each other and sandwich the cellulosic cushioning element 110 therebetween. An adhesive 136 is preferably applied to the inner sides of each of the upper tape 132 and the lower tape 134 to bond the upper tape 132 and the lower tape 134 to each other and to the cellulosic cushioning element 110. Any suitable adhesive 136 may be used, but in this embodiment, it is preferably a biodegradable adhesive.

In this embodiment, both the upper tape 132 and the lower tape 134 are used, but it is not so limited and the cellulosic cushioning element 110 may be connected by a single tape (e.g., either the upper tape 132 or the lower tape 134). In such a case, it is preferable to omit or remove the adhesive 136 from the portion of the tape in the first gap 122.

The flexible linkage 124 discussed above may be used with the discrete cushioning elements 100 to form other packing materials. FIG. 10 shows another packing material using the flexible linkage 124 discussed above. For clarity with the other packing materials discussed herein, the packing material of this embodiment is referred to as a net-like packing material 140. As with the other embodiments the cushioning element 100 elements may be any suitable cushioning element, but in this embodiment, the cushioning element 100 is cellulosic cushioning element 110.

The cellulosic cushioning elements 110 of the net-like packing material 140 are arrayed in two directions. The cellulosic cushioning elements 110 are arrayed in the length direction A, as discussed above, and also are arrayed in a width direction B in an order. For example, the cellulosic cushioning element 110b is adjacent to the cellulosic cushioning element 110y and the cellulosic cushioning element 110z in the width direction B, in addition to the cellulosic cushioning element 110a and the cellulosic cushioning element 110c in the length direction A. The width direction B is a direction crossing the length direction A, and in this embodiment, the width direction B is perpendicular to the length direction A.

The cellulosic cushioning elements **110** are also spaced apart with a gap (a second gap **142**) formed between adjacent cellulosic cushioning elements **110** in the width direction B. One flexible linkage **124**, a first flexible linkage **144** connects the cellulosic cushioning elements **110** in the length direction A and another flexible linkage **124**, a second flexible linkage **146** connects the cellulosic cushioning elements **110** in the width direction B. In this embodiment, there are a plurality of first flexible linkages **144** and a plurality of second flexible linkages **146** that are connected together to form the net-like structure of the net-like packing material **140**. FIG. **10** shows the first flexible linkage **144** and the second flexible linkage **146** with constructed using the tape (e.g., the upper tape **132** and the lower tape **134**), but other suitable flexible linkages **124**, such as string, may be used as discussed above.

The net-like packing material **140** may be used to pack an item-to-be-shipped **104** in the manner shown above in FIG. **1A**, but it may also be used in other suitable packing arrangements. For example, the net-like packing material **140** may be used similarly to bubble wrap and be wrapped around an item-to-be-shipped **104** such as a bottle **108**, as shown in FIG. **11**.

A method of forming the rope-like packing material **120** is shown in FIG. **9**, and a machine assembly **400** used in this method will be described with reference to FIG. **12**. The cellulosic cushioning element **110** may be formed using any suitable method or machine including the machine assembly **200** and machine assembly **300** discussed above. The machine assembly **200** is shown in FIG. **12**, for example. The machine assembly **400** shown in FIG. **12** includes a first roll **402** of a strip of paper which will become the upper tape **132** and a second roll **404** of a strip of paper which will become the lower tape **134**.

The upper tape **132** is stretched between the first roll **402** and a first laminating roller **412**, and the lower tape **134** is stretched between the second roll **404** and a second laminating roller **414**. Each of the first laminating roller **412** and the second laminating roller **414** have a plurality of recesses **416** formed in their exterior surface. Between the recesses **416** is a land **418**. The first laminating roller **412** and the second laminating roller **414** are posited to form a bonding nip therebetween in which the recesses **416** of each laminating roller oppose each other in the bonding nip and the lands **418** of each laminating roller oppose each other in the bonding nip.

The adhesive **136** is applied to at least one of the upper tape **132** and the lower tape **134**. In this embodiment, the adhesive **136** is applied to the upper tape **132** by an adhesive application unit **420**. Alternatively, another adhesive application unit **420** may be used to also apply adhesive **136** to the lower tape **134**. The adhesive application unit **420** includes a reservoir **422** holding the adhesive **136**. The adhesive **136** is transferred from the reservoir **422** to an outer surface of applying roller **424**. The adhesive application unit **420** also includes a backing roller **426**, which forms an adhesive application nip with the applying roller **424**. The upper tape **132** passes through the adhesive application nip and the adhesive **136** is applied by the applying roller **424** to a surface (which will become an inner surface) of the upper tape **132**. Other suitable adhesive application units **420** may be used including, for example, spray adhesive applicators.

After the cellulosic cushioning element **110** is formed and discharged from the form **230**, the cellulosic cushioning element **110** is guided to the entrance of the nip by, for example, a chute **406**. The cellulosic cushioning element **110**

is then located in a cavity formed by two opposing recesses **416** and separated from adjacent cellulosic cushioning element **110** by opposing lands **418**. The upper tape **132** is sandwiched between the first roll **402** and the cellulosic cushioning element **110**, and the lower tape **134** is sandwiched between the second roll **404** and the cellulosic cushioning element **110**. As the upper tape **132** and the lower tape **134** pass through the bonding nip without a cellulosic cushioning element **110** between them, the upper tape **132** and the lower tape **134** are bonded to each other to form the first gap **122**.

Another packing material is shown in FIG. **13**. For clarity with the other packing materials discussed herein, the packing material of this embodiment is referred to as a sandwich wrap **150**. The sandwich wrap **150** includes a top sheet **152** and a bottom sheet **154**. Although any suitable sheet may be used, the top sheet **152** and the bottom sheet **154** are preferably paper (cellulosic) sheets. The top sheet **152** is connected to the bottom sheet **154** with a plurality of discrete cushioning elements **100** positioned therebetween. As shown in FIG. **13**, the discrete cushioning elements **100** of this embodiment are cellulosic cushioning elements **110**. In this embodiment, the cellulosic cushioning element **110** are arrayed in the length direction A and in the width direction B. Although gaps may be present between adjacent cellulosic cushioning elements **110**. The adjacent cellulosic cushioning elements **110** of this embodiment contact each other. Each of the top sheet **152** and the bottom sheet **154** include an inner surface **156**. An adhesive **136** is applied to the inner surface **156** of each of the top sheet **152** and the bottom sheet **154** to attach the cellulosic cushioning element **110** to the top sheet **152** and the bottom sheet **154** and connect the top sheet **152** and the bottom sheet **154** to each other.

As noted above, the cushioning elements **100** may be positioned between the top sheet **152** and the bottom sheet **154** with the cushioning elements **100** spaced apart from each other. One such packing material is shown in FIGS. **14** and **15**. For clarity with the other packing materials discussed herein, the packing material of this embodiment is referred to as a wrap-like packing material **160**. FIG. **15** is a cross-sectional view of the wrap-like packing material **160** taken along line **15-15** in FIG. **14**. The wrap-like packing material **160** of this embodiment has similarities to the sandwich wrap **150**. For example, the wrap-like packing material **160** includes a top sheet **152** connected to a bottom sheet **154** with cellulosic cushioning elements **110** positioned therebetween. At least one of the top sheet **152** and the bottom sheet **154** includes a plurality of pockets **162**. In this embodiment, both the top sheet **152** and the bottom sheet **154** include a plurality of pockets **162**. Each of the pockets **162** includes an opening **164**. In the wrap-like packing material **160** shown in FIG. **15**, each opening **164** of the top sheet **152** opposes a corresponding opening **164** of the bottom sheet **154**, forming a combined pocket. An area surrounding each pocket **162** or combined pocket is referred to herein as webbing area **166**. The top sheet **152** and bottom sheet **154** are adhered to each other using, for example, the adhesive **136** discussed above in the webbing area **166**.

At least one cellulosic cushioning element **110** is located in each combined pocket. In this embodiment, each pocket **162** includes a plurality of cellulosic cushioning elements **110**. The plurality of cellulosic cushioning elements **110** in each pocket **162** or combined pocket may be bonded to each other with bonds comprising adhesive and cellulosic fibers, as will be described further below. Instead of both the top sheet **152** and the bottom sheet **154** having a plurality of pockets **162**, pockets **162** may be formed in one of the top

11

sheet 152 and the bottom sheet 154. FIG. 16 is a cross-sectional view of the wrap-like packing material 160 taken along line 15-15 in FIG. 14, where a plurality of pockets 162 are formed in the bottom sheet 154 but not the top sheet 152. In this embodiment, the top sheet 152 is bonded to the bottom sheet 154 such that the top sheet 152 covers the openings 164 of the plurality of pockets 162 in the bottom sheet 154.

To increase the flexibility of the wrap-like packing material 160, a plurality of holes 168 may be formed through both the top sheet 152 and the bottom sheet 154, as shown in FIGS. 17 and 18. The wrap-like packing material 160 shown in FIG. 17 has the holes 168 located between each pocket 162 in the length direction A and in the width direction B. Another configuration for the wrap-like packing material 160 with holes 168 is shown in FIG. 18 in which the holes 168 are formed in interstitial portions between the pockets 162.

When a single cellulosic cushioning element 110 is located in each combined pocket of the wrap-like packing material 160, a modified method and machine assembly 400 shown and discussed above with reference to FIG. 12 may be used. The first laminating roller 412 and the second laminating roller 414 may be longer and the machine assembly 200 is configured to place a plurality of cellulosic cushioning elements 110 along the length of the first laminating roller 412 and the second laminating roller 414. Instead of the first roll 402 and the second roll 404 being tape, they may be rolls of paper used to form the top sheet 152 and the bottom sheet 154.

A method of forming the wrap-like packing material 160 shown in FIG. 16 and a machine assembly 500 used in this method will be described with reference to FIG. 19. The bottom sheet 154 is provided with the plurality of pockets 162 formed therein. At a first station 502, the plurality of cellulosic cushioning elements 110 are filled in each pocket 162. Optionally, at a second station 504, the cellulosic cushioning elements 110 in each pocket 162 may be bonded together. The cellulosic cushioning elements 110 may be bonded together by an adhesive, which is preferably a biodegradable adhesive. Even more preferably, an emulsion of water, adhesive, and cellulosic (paper) fibers are sprayed into each pocket 162 at the second station 504. Each pocket 162 is conveyed and supported by a backing member, such as by the first laminating roller 412 discussed above, through a bonding nip formed between the first laminating roller 412 and a press roller 512. The top sheet 152 may be conveyed by the press roller 512 into the bonding nip and the top sheet 152 is bonded to the bottom sheet 154. Where the emulsion is used, the emulsion may then be dried resulting in a plurality of cellulosic cushioning elements 110 that are bonded by bonds comprising cellulosic fibers and the adhesive and/or a matrix of cellulosic fibers and the adhesive, as discussed further below in connection with the molded packing material 170.

Instead of using a sheet of paper alone as top sheet 152, a top sheet 152 with pockets 162 filled with cellulosic cushioning elements 110 and optionally bonded may be formed in a manner similar to the bottom sheet 154, as discussed above. This top sheet 152 with pockets may then be brought together with the bottom sheet 154 in the bonding nip to form the wrap like packing material shown in FIG. 15. Alternatively, two of the wrap-like packing materials 160 shown in FIG. 16 may be brought together to form the wrap-like packing material 160 shown in FIG. 15. In any of

12

these cases, the top sheet 152 and the bottom sheet 154 may be bonded together with an adhesive, which is preferably a biodegradable adhesive.

The cellulosic cushioning elements 110 discussed herein may also be suitable to make a polystyrene foam (or other plastic foam) replacement. FIGS. 20 and 21 show such a packing material according to a preferred embodiment of the invention. For clarity with the other packing materials discussed herein, the packing material of this embodiment is referred to as a molded packing material 170. The molded packing material 170 is shown in FIG. 20, and FIG. 21 is a cross section of the molded packing material 170 shown in FIG. 20 taken along line 21-21 in FIG. 20.

The molded packing material 170 will be formed into a shape in order to pack the item-to-be-shipped 104. Such molded shape may include recesses and protrusions. For example, the molded packing material 170 shown in FIG. 20 includes a hemispherical cavity 172 in which a portion of the item-to-be-shipped 104 can be placed. The molded packing material 170 of this embodiment includes a plurality of cellulosic cushioning elements 110 that are formed into the desired shape and then joined together. The plurality of cellulosic cushioning elements 110 may be joined together by bonds comprising adhesive and cellulosic (paper) fibers. In some embodiments, the plurality of cellulosic cushioning elements 110 may be joined together by a matrix of cellulosic fibers, and in a preferred embodiment, a matrix of cellulosic (paper) fibers and an adhesive. Additional features of the bonds and matrix will be discussed below in connection with the method of manufacturing the molded packing material 170. Optionally, the outer surfaces of the molded packing material 170 may be covered with an outer sheet 174. The outer sheet 174 is preferably a cellulosic (paper) sheet.

A method of manufacturing the molded packing material 170 shown in FIG. 20 will be described with reference to FIG. 22. First, a mold 520 having the desired shape is provided. The mold 520 may preferably be silicon. If an outer sheet 174 is used, the outer sheet 174 is placed into the mold. The mold 520 is then filled with the cellulosic cushioning elements 110. Next, an emulsion of water, cellulosic (paper) fibers, and preferably adhesive is sprayed into the mold 520 with the cellulosic cushioning elements 110. The emulsion flows around and between the cellulosic cushioning elements 110. In addition, the emulsion may also flow at least a portion of the way into crevices exposed on the outer surfaces of the plurality of cellulosic cushioning elements 110. If the outer sheet 174 is used, the outer sheet 174 may be placed on top of an exposed surface 176 of the cellulosic cushioning elements 110. The cellulosic cushioning elements 110 with the emulsion is then removed from the mold 520, such as by turning the mold 520 upside down, and then dried to form the molded packing material 170. The drying step may also take place before removing the cellulosic cushioning elements 110 from the mold 520.

As the cellulosic cushioning elements 110 with the emulsion is dried bonds form between the folds of each of the cellulosic cushioning elements 110 and also between the cellulosic cushioning elements 110. The emulsion may also form, as it is dried, a matrix around the cellulosic cushioning elements 110, and the cellulosic cushioning elements 110 may be connected to each other by the cellulosic fibers and, when used, the adhesive of the matrix. The molded packing material 170 may thus include a plurality of cellulosic cushioning elements 110 that are interconnected to each other by cellulosic fibers. The cellulosic cushioning elements 110 may retain some of the air pockets therein, and the

## 13

molded packing material 170 may also be described as having discrete groupings of air (gas) pockets interspersed within a cellulosic (paper) mass.

As discussed above, factors impacting the amount of energy absorbed include the weight of the paper, the volume or size (e.g., diameter) of the cellulosic cushioning element 110, and the density of the cellulosic cushioning element 110. In this embodiment, the amount of emulsion and the amount of the cellulosic fibers and the amount of adhesive in the emulsion may also be modified to create a packing material with the desired strength and energy absorbing properties. The emulsions discussed herein may be referred to herein as an aqueous slurry of cellulosic fibers and adhesive. In the emulsions discussed herein the cellulosic fibers are preferably the same fibers as are used in the paper for the cellulosic cushioning element 110. In addition, the adhesive of the emulsion is preferably a biodegradable emulsion.

Although this invention has been described with respect to certain specific exemplary embodiments, many additional modifications and variations will be apparent to those skilled in the art, in light of this disclosure. It is, therefore, to be understood that this invention may be practiced otherwise than as specifically described. Thus, the exemplary embodiments of the invention should be considered in all respects to be illustrative and not restrictive, and the scope of the invention to be determined by any claims supportable by this application and the equivalents thereof, rather than by the foregoing description.

What is claimed is:

1. A molded packing material comprising:  
a plurality of cellulosic cushioning elements; and  
a matrix comprising adhesive and cellulosic fibers bonding the plurality of cellulosic cushioning elements to each other,  
wherein the plurality of cellulosic cushioning elements and matrix form a mass that has been molded into a shape having exterior surfaces and an interior with some of the plurality of cellulosic cushioning elements being on the exterior surfaces of the mass and the remainder of the plurality of cellulosic cushioning elements being in the interior of the mass.
2. The molded packing material according to claim 1, further comprising at least one cellulosic sheet bonded to at least one of the exterior surfaces of the mass.
3. The molded packing material according to claim 1, wherein each cellulosic cushioning element of the plurality of the cellulosic cushioning elements is a crumpled cellulosic sheet.
4. The molded packing material according to claim 1, wherein each cellulosic cushioning element of the plurality of the cellulosic cushioning elements is a cellulosic material formed into a geometric shape with at least one pocket of air formed therein.
5. The molded packing material according to claim 1, wherein each cellulosic cushioning element of the plurality of the cellulosic cushioning elements has a sphere-like shape.

## 14

6. The molded packing material according to claim 1, wherein each cellulosic cushioning element of the plurality of the cellulosic cushioning elements is cylindrical.

7. The molded packing material according to claim 1, wherein the cellulosic cushioning elements comprise cellulosic fibers, and the cellulosic cushioning elements are the same as the cellulosic fibers of the matrix.

8. The molded packing material according to claim 1, wherein the adhesive of the matrix is a biodegradable adhesive.

9. The molded packing material according to claim 1, wherein the mass has been molded into a shape including at least one recess.

10. The molded packing material according to claim 9, further comprising at least one cellulosic sheet bonded to at least one of the exterior surfaces of the mass forming the recess.

11. A molded packing material comprising:  
a plurality of cellulosic cushioning elements; and  
a matrix comprising cellulosic fibers bonding the plurality of cellulosic cushioning elements to each other,  
wherein the plurality of cellulosic cushioning elements and matrix form a mass that has been molded into a shape having exterior surfaces and an interior with some of the plurality of cellulosic cushioning elements being on the exterior surfaces of the mass and the remainder of the plurality of cellulosic cushioning elements being in the interior of the mass.

12. The molded packing material according to claim 11, further comprising at least one cellulosic sheet bonded to at least one of the exterior surfaces of the mass.

13. The molded packing material according to claim 11, wherein each cellulosic cushioning element of the plurality of the cellulosic cushioning elements is a crumpled cellulosic sheet.

14. The molded packing material according to claim 11, wherein each cellulosic cushioning element of the plurality of the cellulosic cushioning elements is a cellulosic material formed into a geometric shape with at least one pocket of air formed therein.

15. The molded packing material according to claim 11, wherein each cellulosic cushioning element of the plurality of the cellulosic cushioning elements has a sphere-like shape.

16. The molded packing material according to claim 11, wherein each cellulosic cushioning element of the plurality of the cellulosic cushioning elements is cylindrical.

17. The molded packing material according to claim 11, wherein the cellulosic cushioning elements comprise cellulosic fibers, and the cellulosic cushioning elements are the same as the cellulosic fibers of the matrix.

18. The molded packing material according to claim 11, wherein the mass has been molded into a shape including at least one recess.

19. The molded packing material according to claim 18, further comprising at least one cellulosic sheet bonded to at least one of the exterior surfaces of the mass forming the recess.

\* \* \* \* \*