

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250258435

Kind Code

A1

Publication Date

August 14, 2025

Inventor(s)

LEE; YUNG-YAO et al.

SEMICONDUCTOR STRUCTURE AND MANUFACTURING METHOD THEREOF

Abstract

A method of manufacturing a semiconductor structure includes providing a mask including a first substrate; a first mask layer disposed over the first substrate, including a plurality of first recesses extended through the first mask layer; a second mask layer disposed over the first mask layer and including a plurality of second recesses extended through the second mask layer; providing a second substrate including a photoresist disposed over the second substrate; and projecting a predetermined electromagnetic radiation through the mask towards the photoresist, wherein the first mask layer is at least partially transparent to the predetermined electromagnetic radiation, the second mask layer is opaque to the predetermined electromagnetic radiation, and at least a portion of the second mask layer is disposed between two of the plurality of second recesses.

Inventors: LEE; YUNG-YAO (HSINCHU COUNTY, TW), HSIEH; YI-PING (HSINCHU CITY, TW)

Applicant: TAIWAN SEMICONDUCTOR MANUFACTURING COMPANY LTD.
(HSINCHU, TW)

Family ID: 1000008563594

Appl. No.: 19/097902

Filed: April 02, 2025

Related U.S. Application Data

parent US continuation 17563854 20211228 parent-grant-document US 12292686 child US 19097902

parent US division 16196439 20181120 parent-grant-document US 11226562 child US 17563854
us-provisional-application US 62734037 20180920

Publication Classification

Int. Cl.: **G03F7/20** (20060101); **G03F1/22** (20120101); **G03F1/60** (20120101); **G03F1/76** (20120101); **H01L21/027** (20060101)

U.S. Cl.:

CPC **G03F7/2002** (20130101); **G03F1/22** (20130101); **G03F1/60** (20130101); **G03F1/76** (20130101); **G03F7/2004** (20130101); **G03F7/2006** (20130101); **G03F7/2024** (20130101); **H01L21/0274** (20130101);

Background/Summary

PRIORITY CLAIM AND CROSS-REFERENCE [0001] The present application is a continuation application of U.S. application Ser. No. 17/563,854 filed on Dec. 28, 2021, which is a divisional application of U.S. patent application Ser. No. 16/196,439 filed Nov. 20, 2018, which claims priority of U.S. provisional application Ser. No. 62/734,037 filed on Sep. 20, 2018; each of these applications are incorporated herein by reference in their entireties.

BACKGROUND

[0002] Electronic equipments using semiconductor devices are essential for many modern applications. With the advancement of electronic technology, the semiconductor device is becoming increasingly smaller in size and having greater functionality and greater amounts of integrated circuitry. The manufacturing operations of the semiconductor device involve many steps and operations on such a small and thin semiconductor device.

[0003] During the manufacturing of the semiconductor device, a wafer is provided and several circuitry patterns are formed over the wafer by photolithography operations. Upon the photolithography operations, an electromagnetic radiation is irradiated on the wafer through a mask to pattern a photoresist disposed over the wafer. However, some of electromagnetic energy is absorbed by the mask. Heat is generated and cause thermal distortion of the mask. Such distortion may lead to misalignment between the mask and the wafer.

[0004] As such, there is a continuous need to modify and improve the manufacturing operations of the semiconductor device.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

[0005] Aspects of the present disclosure are best understood from the following detailed description when read with the accompanying figures. It is emphasized that, in accordance with the standard practice in the industry, various features are not drawn to scale. In fact, the dimensions of the various features may be arbitrarily increased or reduced for clarity of discussion.

[0006] FIG. 1 is a schematic top plan view of a semiconductor structure in accordance with some embodiments of the present disclosure.

[0007] FIG. 2 is a schematic cross sectional view of the semiconductor structure along AA' of FIG. 1.

[0008] FIG. 3 is a schematic top plan view of a semiconductor structure in accordance with some embodiments of the present disclosure.

[0009] FIG. 4 is a schematic cross sectional view of the semiconductor structure along BB' of FIG.

3.

[0010] FIG. 5 is a schematic top plan view of a semiconductor structure in accordance with some embodiments of the present disclosure.

[0011] FIG. 6 is a schematic cross sectional view of the semiconductor structure along CC' of FIG. 5.

[0012] FIG. 7 is a flow diagram of a method of manufacturing a semiconductor structure in accordance with some embodiments of the present disclosure.

[0013] FIGS. 7A-7L are schematic views of manufacturing a semiconductor structure by a method of FIG. 7 in accordance with some embodiments of the present disclosure.

[0014] FIG. 8 is a flow diagram of a method of manufacturing a semiconductor structure in accordance with some embodiments of the present disclosure.

[0015] FIGS. 8A-8J are schematic views of manufacturing a semiconductor structure by a method of FIG. 8 in accordance with some embodiments of the present disclosure.

DETAILED DESCRIPTION OF THE DISCLOSURE

[0016] The following disclosure provides many different embodiments, or examples, for implementing different features of the provided subject matter. Specific examples of components and arrangements are described below to simplify the present disclosure. These are, of course, merely examples and are not intended to be limiting. For example, the formation of a first feature over or on a second feature in the description that follows may include embodiments in which the first and second features are formed in direct contact, and may also include embodiments in which additional features may be formed between the first and second features, such that the first and second features may not be in direct contact. In addition, the present disclosure may repeat reference numerals and/or letters in the various examples. This repetition is for the purpose of simplicity and clarity and does not in itself dictate a relationship between the various embodiments and/or configurations discussed.

[0017] Further, spatially relative terms, such as "beneath," "below," "lower," "above," "upper" and the like, may be used herein for ease of description to describe one element or feature's relationship to another element(s) or feature(s) as illustrated in the figures. The spatially relative terms are intended to encompass different orientations of the device in use or operation in addition to the orientation depicted in the figures. The apparatus may be otherwise oriented (rotated 90 degrees or at other orientations) and the spatially relative descriptors used herein may likewise be interpreted accordingly.

[0018] The advanced lithography process, method, and materials described above can be used in many applications, including fin-type field effect transistors (FinFETs). For example, the fins may be patterned to produce a relatively close spacing between features, for which the above disclosure is well suited. In addition, spacers used in forming fins of FinFETs, also referred to as mandrels, can be processed according to the above disclosure.

[0019] In a semiconductor wafer, the circuitry patterns and the electrical components are formed by photolithography and etching operations. An electromagnetic radiation such as ultraviolet or laser is irradiated onto a photoresist over the wafer through a photomask, such that images of circuitry patterns and electrical components on the photomask are transferred to and patterned over the photoresist. The patterned photoresist becomes an etch mask. The wafer exposed from the patterned photoresist is etched to form the circuitry patterns and electrical components.

[0020] The photomask can be a multi-layer mask (MLM) defined with several regions for patterning more than one layer of the wafer. Each region of a MLM is used to form a different layer on the wafer. By forming multiple regions for different layers on the same mask, the mask production cost is reduced. Upon photolithography operations, the photomask may absorb some energy of the electromagnetic radiation irradiated onto the photomask and thus generate heat. Since different regions of the photomask involve different materials with different thermal properties (e.g. different coefficient of thermal expansion (CTE), etc.), the photomask may deform and images of

circuitry patterns or electrical components over some regions of the photomask are distorted. For example, a material absorbing the electromagnetic radiation is present at an edge region of the photomask, while such material is absent from a central region of the photomask. As such, circuitry patterns or electrical components projected from different regions of the photomask to the wafer may be misaligned, and ultimately results in poor electrical connection between circuitries or electrical components formed over the wafer.

[0021] In the present disclosure, a semiconductor structure is disclosed. The semiconductor structure is a photomask, which includes a substrate, a first mask layer disposed over the substrate and including a plurality of first recesses extended through the first mask layer, and a second mask layer disposed over the first mask layer and including a plurality of second recesses extended through the second mask layer. The first mask layer is at least partially transparent to a predetermined electromagnetic radiation, and the second mask layer is opaque to the predetermined electromagnetic radiation. At least a portion of the second mask layer is disposed between two of the plurality of second recesses. As such, each region defined over the semiconductor structure is surrounded by the second mask layer, and thermal stress around each region upon photolithography operations is substantially consistent. Therefore, alignment between regions of the semiconductor structure is improved, and quality of formation of circuit feature over a semiconductive substrate or wafer by the semiconductor structure is also improved.

[0022] FIG. 1 is a schematic top view of a semiconductor structure **100** in accordance with various embodiments of the present disclosure, and FIG. 2 is a schematic cross sectional view of the semiconductor structure **100** along AA' in FIG. 1. In some embodiments, the semiconductor structure **100** includes a substrate **101**, a first mask layer **102** and a second mask layer **103**. The semiconductor structure **100** is a mask or a photomask for photolithography operations. In some embodiments, the semiconductor structure **100** is a phase shift mask (PSM). In some embodiments, the semiconductor structure **100** is an attenuated phase shift mask. The semiconductor structure **100** includes an image of a circuit feature such as a circuitry pattern, an electrical component, etc., and is configured to project the image of the circuit feature to a semiconductive wafer or a semiconductive substrate upon photolithography operations. The semiconductor structure **100** is defined with several regions **110**. Each region **110** includes an image of circuit features for different layers of a wafer and is configured to form circuit features over different layers of a wafer.

[0023] The substrate **101** is transparent to a predetermined electromagnetic radiation. The substrate **101** allows the predetermined electromagnetic radiation passing through. In some embodiments, the substrate **101** includes a front side **101a** and a back side **101b** opposite to the front side **101a**. In some embodiments, the predetermined electromagnetic radiation can transmit from the front side **101a** to the back side **101b** or from the back side **101b** to the front side **101a**. In some embodiments, the substrate **101** is quartz, fused quartz, glass or other suitable materials. In some embodiments, the predetermined electromagnetic radiation is ultraviolet (UV), laser, visible light, x-ray, extreme ultraviolet (EUV), deep ultraviolet (DUV), ions beam, electrons beam, etc. In some embodiments, the predetermined electromagnetic radiation has a wavelength of 365 nm, 248 nm or 193 nm. The substrate **101** has a top cross section (a cross section from the top view of the semiconductor structure **100** as shown in FIG. 1) in a circular, quadrilateral, rectangular, square or other suitable shapes.

[0024] The first mask layer **102** is disposed over the substrate **101**. In some embodiments, the first mask layer **102** is disposed over the front side **101a** of the substrate **101**. The first mask layer **102** is at least partially transparent to the predetermined electromagnetic radiation. In some embodiments, the predetermined electromagnetic radiation is ultraviolet (UV), laser, visible light, x-ray, extreme ultraviolet (EUV), deep ultraviolet (DUV), ions beam, electrons beam, etc. In some embodiments, about 5% to about 20% of the predetermined electromagnetic radiation is penetrable to the first mask layer **102**. In some embodiments, about 6% to about 15% of the predetermined electromagnetic radiation is penetrable to the first mask layer **102**. In some embodiments, the first

mask layer **102** includes molybdenum silicon (MoSi).

[0025] A phase of the predetermined electromagnetic radiation passing through the first mask layer **102** is shifted 180° with respect to a phase of the predetermined electromagnetic radiation passing through the substrate **101** upon projection of the predetermined electromagnetic radiation through the first mask layer **102** and the substrate **101**. In some embodiments, the first mask layer **102** has a thickness such that a certain amount of the predetermined electromagnetic radiation can pass through the first mask layer **102** or a certain amount of the predetermined electromagnetic radiation is blocked by the first mask layer **102**. In some embodiments, the first mask layer **102** has the thickness such that the phase of the predetermined electromagnetic radiation passing through the first mask layer **102** is shifted 180° with respect to the phase of the predetermined electromagnetic radiation passing through the substrate **101** upon projection of the predetermined electromagnetic radiation through the first mask layer **102** and the substrate **101**.

[0026] The first mask layer **102** includes several first recesses **102a** extended through the first mask layer **102**. A portion of the front side **101a** of the substrate **101** is exposed from the first recess **102a**. In some embodiments, the predetermined electromagnetic radiation can pass through the first recesses **102a**. The first recesses **102a** can be projected over a semiconductive substrate or wafer by the predetermined electromagnetic radiation. Each of the first recesses **102a** is an image of a circuit feature. In some embodiments, the first recess **102a** is an image of a trace, a via, a contact, a plug, a trench, etc. In some embodiments, the first recess **102a** is extended to the substrate **101**. The first recess **102a** has a top cross section (a cross section from the top view of the semiconductor structure **100** as shown in FIG. 1) in a quadrilateral, rectangular, polygonal or other suitable shapes. In some embodiments, the first recesses **102a-1** and **102a-2** are substantially different from each other. In some embodiments, the first recesses **102a-1** and **102a-2** are different circuit features. In some embodiments, the first recesses **102a-1** and **102a-2** are configured to form the circuit features over different layers of the semiconductive substrate or wafer. The semiconductor structure **100** includes several regions **110**. In some embodiments, the semiconductor structure **100** includes two different regions **110a** and **110b**. Each region **110** includes the first recesses **102a** of various shapes and sizes. Only one first recess **102a** is shown for each region **110** in the Figures for simplicity of description.

[0027] The second mask layer **103** is disposed over the first mask layer **102**. In some embodiments, the second mask layer **103** is in contact with the first mask layer **102**. The second mask layer **103** is opaque to the predetermined electromagnetic radiation. In some embodiments, the predetermined electromagnetic radiation is ultraviolet (UV), laser, visible light, x-ray, extreme ultraviolet (EUV), deep ultraviolet (DUV), ions beam, electrons beam, etc. In some embodiments, about 100% of the predetermined electromagnetic radiation is absorbed or blocked by the second mask layer **103**. In some embodiments, the second mask layer **103** includes chromium (Cr).

[0028] In some embodiments, the second mask layer **103** is a boundary layer surrounding several regions **110**. The second mask layer **103** includes several second recesses **103a** extended through the second mask layer **103**. In some embodiments, the second recesses **103a** are disposed over the first recesses **102a** correspondingly. A portion of the front side **101a** of the substrate **101** is exposed from the second recesses **103a**. Each region **110** includes the second recess **103a**. In some embodiments, the predetermined electromagnetic radiation can pass through the second recesses **103a**. In some embodiments, the first recess **102a** is coupled with the second recess **103a**. In some embodiments, at least a portion of the first mask layer **102** is exposed from the second recess **103a**. The second recess **103a** has a top cross section (a cross section from the top view of the semiconductor structure **100** as shown in FIG. 1) in a quadrilateral, rectangular, polygonal or other suitable shapes.

[0029] A width **W1** of the second recess **103a** is substantially greater than a width **W3** of the first recess **102a**. In some embodiments, the width **W1** of the second recesses **103a** are substantially same as each other. In some embodiments, shapes of the second recesses **103a** are substantially

same as each other. In some embodiments, the width W1 of the second recess **103a** is about 5 mm to about 15 mm. In some embodiments, the width W1 of the second recess **103a** is about 8 mm to about 10 mm.

[0030] At least a portion of the second mask layer **103** is disposed between two of second recesses **103a**. For example, a portion of the second mask layer **103** is disposed between the second recesses **103a-1** and **103a-2**. Each of the second recesses **103a** is surrounded or enclosed by the second mask layer **103**. In some embodiments, at least a portion of the first mask layer **102** is disposed between two of the first recesses **102a**, and the portion of the second mask layer **103** is disposed over the portion of the first mask layer **102**. In some embodiments, the portion of the second mask layer **103** disposed between the second recesses **103a-1** and **103a-2** is disposed over the portion of the first mask layer **102** disposed between the first recesses **102a-1** and **102a-2**.

[0031] In some embodiments, a ratio of a width W2 of the portion of the second mask layer to the width W1 of the second recess **103a** is substantially greater than or equal to 0.001. In some embodiments, the width W2 of the second mask layer **103** surrounding each second recess **103a** is substantially consistent. In some embodiments, the width W2 of the second mask layer **103** is about 50 μm to about 70 μm . In some embodiments, the width W2 of the second mask layer **103** is about 60 μm .

[0032] FIG. 3 is a schematic top view of a semiconductor structure **200** in accordance with various embodiments of the present disclosure, and FIG. 4 is a schematic cross sectional view of the semiconductor structure **200** along BB' in FIG. 3. The semiconductor structure **200** is a photomask, which includes a substrate **101**, a first mask layer **102** and a second mask layer **103**, which have similar configurations as described above or illustrated in FIG. 1 or 2.

[0033] The semiconductor structure **200** is defined with several regions **110**. In some embodiments, the semiconductor structure **200** is defined with four regions **110a**, **110b**, **110c** and **110d**. Each region **110** includes the first recesses **102a** of various shapes and sizes. Only one first recess **102a** is shown for each region **110** in the Figures for simplicity of description. In some embodiments, the first mask layer **102** includes four first recesses **102a-1**, **102a-2**, **102a-3** and **102a-4**, and the second mask layer **103** includes four second recesses **103a-1**, **103a-2**, **103a-3** and **103a-4**. Each of the first recesses **102a-1**, **102a-2**, **102a-3** and **102a-4** is an image of a circuit feature. In some embodiments, the first recesses **102a-1**, **102a-2**, **102a-3** and **102a-4** are substantially different from each other. For example, the first recesses **102a-1**, **102a-2**, **102a-3** and **102a-4** are four different circuit features. In some embodiments, the first recesses **102a-1**, **102a-2**, **102a-3** and **102a-4** can be projected over a semiconductive substrate or wafer by the predetermined electromagnetic radiation. In some embodiments, the first recesses **102a-1**, **102a-2**, **102a-3** and **102a-4** are configured to form the circuit features over different layers of a semiconductive substrate or wafer.

[0034] In some embodiments, each of the second recesses **103a-1**, **103a-2**, **103a-3** and **103a-4** surrounds the corresponding first recesses **102a-1**, **102a-2**, **102a-3** and **102a-4**. In some embodiments, each region **110** is surrounded or enclosed by the second mask layer **103**.

[0035] FIG. 5 is a schematic top view of a semiconductor structure **300** in accordance with various embodiments of the present disclosure, and FIG. 6 is a schematic cross sectional view of the semiconductor structure **300** along CC' in FIG. 5. In some embodiments, the semiconductor structure **300** is a photomask which includes a substrate **101**, a first mask layer **102** and a second mask layer **103**, which have similar configurations as described above or illustrated in FIG. 1 or 2.

[0036] The semiconductor structure **300** is defined with several regions **110**. In some embodiments, the semiconductor structure **300** is defined with nine regions **110a**, **110b**, **110c**, **110d**, **110e**, **110f**, **110g**, **110h** and **110i**. Each region **110** includes the first recesses **102a** of various shapes and sizes. Only one first recess **102a** is shown for each region **110** in the Figures for simplicity of description. In some embodiments, the first mask layer **102** includes nine first recesses **102a-1**, **102a-2**, **102a-3**, **102a-4**, **102a-5**, **102a-6**, **102a-7**, **102a-8** and **102a-9**, and the second mask layer **103** includes nine second recesses **103a-1**, **103a-2**, **103a-3**, **103a-4**, **103a-5**, **103a-6**, **103a-7**, **103a-8** and **103a-9**. In

some embodiments, each of the first recesses **102a-1**, **102a-2**, **102a-3**, **102a-4**, **102a-5**, **102a-6**, **102a-7**, **102a-8** and **102a-9** is an image of a circuit feature. In some embodiments, the first recesses **102a-1**, **102a-2**, **102a-3**, **102a-4**, **102a-5**, **102a-6**, **102a-7**, **102a-8**, **102a-9** are substantially different from each other. For example, the first recesses **102a-1**, **102a-2**, **102a-3**, **102a-4**, **102a-5**, **102a-6**, **102a-7**, **102a-8** and **102a-9** are nine different circuit features. The first recesses **102a-1**, **102a-2**, **102a-3**, **102a-4**, **102a-5**, **102a-6**, **102a-7**, **102a-8** and **102a-9** are configured to form the circuitry pattern, the electrical component or the circuit feature over different layers of a semiconductive substrate or wafer.

[0037] Each of the second recesses **103a-1**, **103a-2**, **103a-3**, **103a-4**, **103a-5**, **103a-6**, **103a-7**, **103a-8** and **103a-9** includes an image of a circuit feature. In The second recesses **103a-1**, **103a-2**, **103a-3**, **103a-4**, **103a-5**, **103a-6**, **103a-7**, **103a-8** and **103a-9** are configured to form images of circuit features over different layers of a semiconductive substrate or wafer. For example, the second recesses **103a-1**, **103a-2**, **103a-3**, **103a-4**, **103a-5**, **103a-6**, **103a-7**, **103a-8** and **103a-9** are configured to form images of circuit features over nine different layers of a semiconductive substrate or wafer.

[0038] In some embodiments, each of the second recesses **103a-1**, **103a-2**, **103a-3**, **103a-4**, **103a-5**, **103a-6**, **103a-7**, **103a-8** and **103a-9** surrounds the corresponding first recesses **102a-1**, **102a-2**, **102a-3**, **102a-4**, **102a-5**, **102a-6**, **102a-7**, **102a-8**, **102a-9**. In some embodiments, each region **110** is surrounded or enclosed by the second mask layer **103**.

[0039] In the present disclosure, a method of manufacturing a semiconductor structure **100**, **200** or **300** is also disclosed. In some embodiments, a semiconductor structure **100**, **200** or **300** is formed by a method **400**. The method **400** includes a number of operations and the description and illustration are not deemed as a limitation as the sequence of the operations. FIG. 7 is an embodiment of the method **400** of manufacturing the semiconductor structure **100**, **200** or **300**. The method **400** includes a number of operations (**401**, **402**, **403**, **404**, **405**, **406**, **407**, **408**, **409**, **410** and **411**).

[0040] In operation **401**, a substrate **101** is provided or received as shown in FIG. 7A. In The substrate **101** is transparent to a predetermined electromagnetic radiation. In some embodiments, the substrate **101** includes a front side **101a** and a back side **101b** opposite to the front side **101a**. In some embodiments, the predetermined electromagnetic radiation can transmit from the front side **101a** to the back side **101b** or from the back side **101b** to the front side **101a**. In some embodiments, the substrate **101** includes quartz, fused quartz, glass or other suitable materials. In some embodiments, the predetermined electromagnetic radiation is ultraviolet (UV), laser, visible light, x-ray, extreme ultraviolet (EUV), deep ultraviolet (DUV), ions beam, electrons beam, etc. In some embodiments, the substrate **101** has similar configuration as described above or illustrated in FIGS. 1-6.

[0041] In operation **402**, a first mask layer **102** is disposed over the substrate **101** as shown in FIG. 7B. The first mask layer **102** is disposed over the front side **101a** of the substrate **101**. The first mask layer **102** is at least partially transparent to the predetermined electromagnetic radiation. In some embodiments, the first mask layer **102** includes molybdenum silicon (MoSi). In some embodiments, the first mask layer **102** is disposed by spin coating, sputtering, chemical vapor deposition (CVD) or any other suitable operations. In some embodiments, the first mask layer **102** has similar configuration as described above or illustrated in FIGS. 1-6.

[0042] In operation **403**, a first photoresist **104** is disposed over the first mask layer **102** as shown in FIG. 7C. In The first photoresist **104** is coated on the first mask layer **102**. The first photoresist **104** is a light sensitive material with chemical properties depending on an exposure of an electromagnetic radiation. In some embodiments, the first photoresist **104** is sensitive to an electromagnetic radiation such as an ultra violet (UV), that the chemical properties of the first photoresist **104** are changed upon exposure to the electromagnetic radiation. In some embodiments, the first photoresist **104** is disposed over the first mask layer **102** by spin coating or any other

suitable operations.

[0043] In operation **404**, the first photoresist **104** is patterned to form several first openings **104a** as shown in FIG. 7D. The first photoresist **104** is patterned by removing portions of the first photoresist **104**. In some embodiments, some portions of the first photoresist **104** are exposed to the electromagnetic radiation, and those exposed portions are dissolvable by a developer solution while those unexposed portions are not dissolvable by the developer solution. The first photoresist **104** is patterned after removal of the exposed portions of the first photoresist **104**. In some embodiments, the first openings **104a** are formed after removal of the exposed portions of the first photoresist **104**. In some embodiments, some portions of the first mask layer **102** are exposed from the first photoresist **104** by the first openings **104a**.

[0044] In operation **405**, portions of the first mask layer **102** exposed from the first photoresist **104** are removed to form several first recesses **102a** as shown in FIG. 7E. The first openings **104a** correspond to the first recesses **102a** respectively. In some embodiments, the first recesses **102a** are extended through the first mask layer **102**. In some embodiments, the portions of the first mask layer **102** exposed from the first photoresist **104** are removed by suitable etching operation such as plasma etching, an anisotropic dry etching, a reactive ion etching (RIE), a dry etching or etc.

[0045] In operation **406**, the first photoresist **104** is removed as shown in FIG. 7F. In some embodiment, the first photoresist **104** is removed by suitable photoresist stripping technique, such as chemical solvent cleaning, plasma ashing, dry stripping and/or the like.

[0046] In operation **407**, a second mask layer **103** is disposed over the first mask layer **102** as shown in FIG. 7G. The second mask layer **103** is opaque to the predetermined electromagnetic radiation. In some embodiments, the second mask layer **103** includes chromium (Cr). In some embodiments, the second mask layer **103** is disposed by spin coating, sputtering, chemical vapor deposition (CVD), physical vapor deposition (PVD) or any other suitable operations. In some embodiments, the second mask layer **103** has similar configuration as described above or illustrated in FIGS. 1-6.

[0047] In operation **408**, a second photoresist **105** is disposed over the second mask layer **103** as shown in FIG. 7H. The second photoresist **105** is coated on the second mask layer **103**. The second photoresist **105** is a light sensitive material with chemical properties depending on an exposure of an electromagnetic radiation. In some embodiments, the second photoresist **105** is sensitive to an electromagnetic radiation such as an ultra violet (UV), that the chemical properties of the second photoresist **105** are changed upon exposure to the electromagnetic radiation. In some embodiments, the second photoresist **105** is disposed over the second mask layer **103** by spin coating or any other suitable operations.

[0048] In operation **409**, the second photoresist **105** is patterned to form several second openings **105a** as shown in FIG. 7I. The second photoresist **105** is patterned by removing portions of the second photoresist **105**. In some embodiments, some portions of the second photoresist **105** are exposed to the electromagnetic radiation, and those exposed portions are dissolvable by a developer solution while those unexposed portions are not dissolvable by the developer solution. In some embodiments, the second photoresist **105** is patterned after removal of the exposed portions of the second photoresist **105**. The second openings **105a** are formed after removal of the exposed portions of the second photoresist **105**. Some portions of the second mask layer **103** are exposed from the second photoresist **105** by the second openings **105a**. In some embodiments, the second opening **105a** of the second photoresist **105** is substantially greater than the first opening **104a** of the first photoresist **104**.

[0049] At least a portion of the second photoresist **105** is disposed between two of the second openings **105a** after the patterning of the second photoresist **105**. In some embodiments, a width **W4** of one of the second openings **105a** is about 5 mm to about 15 mm. In some embodiments, the width **W4** is about 8 mm to about 10 mm. In some embodiments, a width **W5** of a portion of the second photoresist **105** disposed between two of the second openings **105a** is about 50 μ m to about

70 μm . In some embodiments, the width W5 is about 60 μm . In some embodiments, a ratio of the width W5 of the second photoresist **105** disposed between two of the second openings **105a** to the width W4 of one of the second openings **105a** is substantially greater than or equal to 0.001.

[0050] In operation **410**, the portions of the second mask layer **103** exposed from the second photoresist **105** are removed to form several second recesses **103a** as shown in FIGS. 7J and 7K. The second openings **105a** correspond to the second recesses **103a** respectively. The second mask layer **103** is defined with several regions **110**. Each region **110** includes at least one of the first recesses **102a**. In some embodiments, the second mask layer **103** is a boundary layer. In some embodiments, the second recesses **103a** are formed one by one. For example, the left portion of the second mask layer **103** is removed first to form one of the second recesses **103a** as shown in FIG. 7J, and then the right portion of the second mask layer is removed to form another one of the second recesses **103a** as shown in FIG. 7K. In some embodiments, the second recesses **103a** are extended through the second mask layer **103**. In some embodiments, the portions of the second mask layer **103** exposed from the second photoresist **105** are removed by suitable etching operation such as wet etching, plasma etching, an anisotropic dry etching, a reactive ion etching (RIE), a dry etching or etc.

[0051] In operation **411**, the second photoresist **105** is removed as shown in FIG. 7L. In some embodiment, the second photoresist **105** is removed by suitable photoresist stripping technique, such as chemical solvent cleaning, plasma ashing, dry stripping and/or the like. Several regions **110** In some embodiments, a semiconductor structure **100**, **200** or **300** as shown in FIGS. 1-6 is formed. In some embodiment, the semiconductor structure **100**, **200** or **300** is a multi-layer mask (MLM) configured for photolithography operations.

[0052] In the present disclosure, a method of manufacturing a semiconductor structure is also disclosed. In some embodiments, a semiconductor structure is formed by a method **500**. The method **500** includes a number of operations and the description and illustration are not deemed as a limitation as the sequence of the operations. FIG. 8 is an embodiment of the method **500** of manufacturing the semiconductor structure. The method **500** includes a number of operations (**501**, **502**, **503**, **504** and **505**).

[0053] In operation **501**, a photomask **100** is formed or provided as shown in FIG. 8A. In some embodiments, the photomask **100** is formed by the method **400** described above. The photomask **100** includes a first substrate **101**, a first mask layer **102** and a second mask layer **103**. The photomask **100** is defined with several regions **110**. The first mask layer **102** includes several first recesses **102a**, and the second mask layer **103** includes several second recesses **103a**. In some embodiments, the first recesses **102a-1** and **102a-2** are different circuit features. In some embodiments, the first recesses **102a-1** and **102a-2** can be projected over a semiconductive substrate or wafer by a predetermined electromagnetic radiation. The first recesses **102a-1** and **102a-2** are configured to form circuit features over different layers of a semiconductive substrate or wafer. At least a portion of the second mask layer **103** is disposed between two of the second recesses **103s**. In some embodiments, the photomask **100** has similar configurations as the semiconductor structure **100**, **200** or **300** described above and shown in FIGS. 1-6.

[0054] In operation **502**, a second substrate **106** is provided or received as shown in FIG. 8B. The second substrate **106** includes semiconductive materials such as silicon or other suitable materials. The second substrate **106** is a wafer. In some embodiments, the second substrate **106** is a silicon substrate or silicon wafer. In some embodiments, the second substrate **106** includes glass or ceramic. In some embodiments, the second substrate **106** is a glass substrate.

[0055] In operation **503**, a third photoresist **107** is disposed over the second substrate **106** as shown in FIG. 8C. The third photoresist **107** is a light sensitive material with chemical properties depending on an exposure of an electromagnetic radiation. In some embodiments, the third photoresist **107** is sensitive to an electromagnetic radiation such as an ultra violet (UV), that the chemical properties of the third photoresist **107** are changed upon exposure to the electromagnetic

radiation. In some embodiments, the third photoresist **107** is disposed over the second substrate **106** by spin coating or any other suitable operations.

[0056] In operation **504**, a predetermined electromagnetic radiation is projected through the photomask **100** towards the third photoresist **107** to pattern the third photoresist **107** as shown in FIG. **8D**. The second recess **103a-1** of the second mask layer **103** is aligned with a predetermined position of the third photoresist **107**. The predetermined electromagnetic radiation is irradiated from a source **108**. In some embodiments, the predetermined electromagnetic radiation is ultraviolet (UV), laser, visible light, x-ray, extreme ultraviolet (EUV), deep ultraviolet (DUV), ions beam, electrons beam, etc. In some embodiments, the first mask layer **102** is at least partially transparent to the predetermined electromagnetic radiation, the second mask layer **103** is opaque to the predetermined electromagnetic radiation.

[0057] The predetermined electromagnetic radiation can pass through the first substrate **101** and the first recesses **102a** to the third photoresist **107**, such that an image of the first recesses **102a** can be projected over the third photoresist **107** to pattern the third photoresist **107**. A phase of the predetermined electromagnetic radiation passing through the first mask layer **102** is shifted 180° with respect to a phase of the predetermined electromagnetic radiation passing through the first substrate **101** upon the projection of the predetermined electromagnetic radiation, such that a quality of the image of the first recesses **102a** projected over the third photoresist **107** is increased or improved.

[0058] In some embodiments, the photomask **100** or the first recess **102a-1** is aligned with the third photoresist **107** or the second substrate **106**, such that the image of the first recess **102a-1** can be projected over a predetermined position of the third photoresist **107**. The third photoresist **107** is patterned by removing portions of the third photoresist **107**. In some embodiments, some portions of the third photoresist **107** are exposed to the predetermined electromagnetic radiation, and those exposed portions are dissolvable by a developer solution while those unexposed portions are not dissolvable by the developer solution. The third photoresist **107** is patterned after removal of the exposed portions of the third photoresist **107**.

[0059] In operation **505**, portions of the second substrate **106** exposed from the third photoresist **107** are removed as shown in FIG. **8E**. The portions of the second substrate **106** exposed from the third photoresist **107** correspond to the first recesses **102a** respectively. In some embodiments, the portion of the second substrate **106** corresponding to the first recess **102a-1** is removed, such that a circuit feature corresponding to the first recess **102a-1** is formed over a first layer of the second substrate **106**. In some embodiments, the third photoresist **107** is removed as shown in FIG. **8F** after the formation of the first recess **102a-1** over the second substrate **106**.

[0060] In some embodiments, after the formation of the first recess **102a-1** over the first layer of the second substrate **106**, the first recess **102a-2** is formed over a second layer of the second substrate **106** as shown in FIGS. **8G-8J**. In some embodiments, a fourth photoresist **109** is disposed over the second substrate **106** as shown in FIG. **8G**. In some embodiments, the fourth photoresist **109** has similar configurations as the third photoresist **107**.

[0061] In some embodiments, after the formation of the first recess **102a-1** over the first layer of the second substrate **106**, the photomask **100** is moved to project an image of the first recess **102a-2** over the fourth photoresist **109** to form a circuit feature corresponding to the first recess **102a-2** over a second layer of the second substrate **106** as shown in FIG. **8H**. In some embodiments, the photomask **100** is moved such that the second recess **103a-2** of the second mask layer **103** is aligned with a predetermined position of the second substrate **106**. In some embodiments, the second recesses **103a-1** and **103a-2** are heated by the predetermined electromagnetic radiation upon projection of the predetermined electromagnetic radiation through the photomask **100**. In some embodiments, heat expansion of the second recesses **103a-1** is substantially the same as heat expansion of the second recess **103a-2**, since the second mask layer **103** surrounds both of the second recesses **103a-1** and **103a-2**. In some embodiments, a position of the second recess **103a-1**

as shown in FIG. 8D is vertically aligned with a position of the second recess **103a-2** as shown in FIG. 8H. In some embodiments, the source **108** irradiates the predetermined electromagnetic radiation through the second recess **103a-2** towards the fourth photoresist **109** to project the first recess **102a-2** over the fourth photoresist **109**. In some embodiments, the fourth photoresist **109** is patterned by removing a portion of the fourth photoresist **109** exposed to the predetermined electromagnetic radiation.

[0062] In some embodiments, a portion of the second substrate **106** exposed from the fourth photoresist **109** is removed as shown in FIG. 8I. In some embodiments, the first recess **102a-2** is formed over the second layer of the second substrate **106**. In some embodiments, the fourth photoresist **109** is removed after the formation of the first recess **102a-2**.

[0063] In the present disclosure, a semiconductor structure is disclosed. The semiconductor structure includes a substrate, a first mask layer disposed over the substrate and including a plurality of first recesses extended through the first mask layer, and a second mask layer disposed over the first mask layer and including a plurality of second recesses extended through the second mask layer. At least a portion of the second mask layer is disposed between two of the plurality of second recesses. As such, each region defined over the semiconductor structure is surrounded by the second mask layer, and thermal stress around each region upon photolithography operations is substantially consistent. Therefore, alignment between regions of the semiconductor structure is improved, and quality of formation of circuit feature over a semiconductive substrate or wafer by the semiconductor structure is also improved.

[0064] In some embodiments, a method of manufacturing a semiconductor structure includes providing a mask including a first substrate; a first mask layer disposed over the first substrate, including a plurality of first recesses extended through the first mask layer; a second mask layer disposed over the first mask layer and including a plurality of second recesses extended through the second mask layer; providing a second substrate including a photoresist disposed over the second substrate; and projecting a predetermined electromagnetic radiation through the mask towards the photoresist, wherein the first mask layer is at least partially transparent to the predetermined electromagnetic radiation, the second mask layer is opaque to the predetermined electromagnetic radiation, and at least a portion of the second mask layer is disposed between two of the plurality of second recesses.

[0065] In some embodiments, at least a portion of the first mask layer is disposed between two of the plurality of first recesses, and the portion of the second mask layer is disposed over the portion of the first mask layer. In some embodiments, a ratio of a width of the portion of the second mask layer to a width of one of the plurality of second recesses is substantially greater than or equal to 0.001. In some embodiments, a width of one of the plurality of second recesses is substantially greater than a width of one of the plurality of first recesses. In some embodiments, a width of one of the plurality of second recesses is about 5 mm to about 15 mm. In some embodiments, a width of the portion of the second mask layer disposed between two of the plurality of second recesses is about 50 μm to about 70 μm .

[0066] In some embodiments, the first mask layer includes molybdenum silicon (MoSi). In some embodiments, the second mask layer includes chromium (Cr). In some embodiments, the substrate is transparent to the predetermined electromagnetic radiation. In some embodiments, the substrate includes quartz. In some embodiments, about 5% to about 20% of the predetermined electromagnetic radiation is penetrable to the first mask layer. In some embodiments, the predetermined electromagnetic radiation is an ultraviolet (UV) or laser.

[0067] In some embodiments, a method of manufacturing a semiconductor structure includes providing a substrate; disposing a first mask layer over the substrate; disposing a first photoresist over the first mask layer; patterning the first photoresist to form a plurality of first openings; removing portions of the first mask layer exposed from the first photoresist to form a plurality of first recesses extended through the first mask layer; removing the first photoresist; disposing a

second mask layer over the first mask layer; disposing a second photoresist over the second mask layer; patterning the second photoresist to form a plurality of second openings; removing portions of the second mask layer exposed from the second photoresist to form a plurality of regions over the substrate; and removing the second photoresist, wherein each of the plurality of regions includes at least one of the plurality of first recesses, the first mask layer is at least partially transparent to a predetermined electromagnetic radiation, the second mask layer is opaque to the predetermined electromagnetic radiation, and at least a portion of the second photoresist is disposed between two of the plurality of second openings after the patterning of the second photoresist.

[0068] In some embodiments, the patterning of the first photoresist includes removing portions of the first photoresist, or the patterning of the second photoresist includes removing portions of the second photoresist. In some embodiments, a width of one of the plurality of second openings is about 5 mm to about 15 mm. In some embodiments, a ratio of a width of a portion of the second photoresist disposed between two of the plurality of second openings to a width of one of the plurality of second openings is substantially greater than or equal to 0.001. In some embodiments, one of the plurality of second openings is substantially greater than one of the plurality of first openings.

[0069] In some embodiments, a method of manufacturing a semiconductor structure includes forming a photomask including providing a first substrate; forming a first mask layer over the first substrate, wherein the first mask layer includes a plurality of first recesses extended through the first layer; forming a second mask layer over the first mask layer, wherein the second mask layer includes a plurality of regions over the first substrate; providing a second substrate; disposing a photoresist over the second substrate; projecting a predetermined electromagnetic radiation through the photomask towards the photoresist to pattern the photoresist; and removing portions of the second substrate exposed from the photoresist, wherein each of the plurality of regions includes at least one of the plurality of first recesses, the first mask layer is at least partially transparent to the predetermined electromagnetic radiation, the second mask layer is opaque to the predetermined electromagnetic radiation, and at least a portion of the second mask layer is disposed between two of the plurality of regions.

[0070] In some embodiments, a phase of the predetermined electromagnetic radiation passing through the first mask layer is shifted 180° with respect to a phase of the predetermined electromagnetic radiation passing through the first substrate upon the projection of the predetermined electromagnetic radiation. In some embodiments, the portions of the second substrate exposed from the photoresist correspond to the plurality of first recesses respectively.

[0071] In the present disclosure, a method of manufacturing a semiconductor structure is disclosed. The method includes providing a substrate; disposing a first mask layer over the substrate; disposing a first photoresist over the first mask layer; patterning the first photoresist to form a plurality of first openings; removing portions of the first mask layer exposed by the plurality of first openings to form a plurality of first recesses that expose portions of the substrate; removing the first photoresist; disposing a second mask layer over the first mask layer to fill the plurality of first recesses; disposing a second photoresist over the second mask layer; removing portions of the second photoresist to form a plurality of second openings that expose portions of the second mask layer; etching the second mask layer exposed by the plurality of second openings to form a plurality of second recesses and the plurality of first recesses the substrate; and removing the second photoresist. In some embodiments, an edge of the second mask layer is flush with an edge of the first mask layer and an edge of the substrate.

[0072] In some embodiments, after the removing portions of the first mask layer to form the plurality of first recesses, the plurality of first recesses extend through the first mask layer.

[0073] In some embodiments, each of the plurality of first recesses is communicated with each of the plurality of first openings.

[0074] In some embodiments, each of the plurality of second recesses is communicated with each

of the plurality of second openings and each of the plurality of first recesses.

[0075] In some embodiments, the plurality of second recesses are at a level of the second mask layer.

[0076] In some embodiments, the first mask layer is at least partially transparent to a predetermined electromagnetic radiation.

[0077] In some embodiments, the second mask layer is opaque to the predetermined electromagnetic radiation.

[0078] In some embodiments, a width of each of the plurality of second recesses is substantially greater than a width of each of the plurality of first recesses.

[0079] In some embodiments, the width of each of the plurality of second recesses is about 5 mm to about 15 mm.

[0080] In the present disclosure, another method of manufacturing a semiconductor structure is disclosed. The method includes providing a substrate; disposing a first mask layer over the substrate; disposing a first photoresist over the first mask layer; patterning the first photoresist to form a plurality of first openings; removing portions of the first mask layer exposed from the first photoresist to form a plurality of first recesses extended through the first mask layer; removing the first photoresist; disposing a second mask layer over the first mask layer; disposing a second photoresist over the second mask layer; patterning the second photoresist to form a plurality of second openings; removing a first portion of the second mask layer exposed by one of the plurality of second openings to form a first hole exposing the substrate; removing a second portion of the second mask layer exposed by another of the plurality of second openings to form a second hole exposing the substrate; and removing the second photoresist. In some embodiments, each of the first hole and the second hole includes at least one of the plurality of first recesses. In some embodiments, the first mask layer is at least partially transparent to a predetermined electromagnetic radiation, and the second mask layer is opaque to the predetermined electromagnetic radiation.

[0081] In some embodiments, the plurality of second recesses extend through the second mask layer.

[0082] In some embodiments, after the removing of the first portion and the removing of the second portion of the second mask layer, at least a portion of the second photoresist is disposed between the first hole and the second hole.

[0083] In some embodiments, at least a portion of second mask layer is disposed between the first hole and the second hole.

[0084] In some embodiments, the first hole or the second hole is communicated with one of the plurality of second openings.

[0085] In some embodiments, an edge of the second mask layer is flush with an edge of the first mask layer and an edge of the substrate.

[0086] The foregoing outlines features of several embodiments so that those skilled in the art may better understand the aspects of the present disclosure. Those skilled in the art should appreciate that they may readily use the present disclosure as a basis for designing or modifying other processes and structures for carrying out the same purposes and/or achieving the same advantages of the embodiments introduced herein. Those skilled in the art should also realize that such equivalent constructions do not depart from the spirit and scope of the present disclosure, and that they may make various changes, substitutions, and alterations herein without departing from the spirit and scope of the present disclosure.

Claims

1. A method of manufacturing a semiconductor structure, comprising: disposing a first mask layer over a substrate; forming a first photoresist pattern on the first mask layer, wherein the first

photoresist pattern includes a plurality of first openings; etching portions of the first mask layer exposed by the plurality of first openings to form a plurality of first recesses that expose portions of the substrate; removing the first photoresist pattern; disposing a second mask layer over the patterned first mask layer to fill the plurality of first recesses; forming a second photoresist pattern on the second mask layer, wherein the second photoresist pattern includes a plurality of second openings; etching portions of the second mask layer exposed by the plurality of second openings to form a plurality of second recesses and expose the plurality of first recesses; and removing the second photoresist pattern, wherein the first mask layer is at least partially transparent to a predetermined electromagnetic radiation, the second mask layer is opaque to the predetermined electromagnetic radiation.

2. The method of claim 1, wherein a width of one of the plurality of second openings is about 5 mm to about 15 mm.

3. The method of claim 1, wherein a ratio of a width of a portion of the second photoresist pattern disposed between two of the plurality of second openings to a width of one of the plurality of second openings is substantially greater than or equal to 0.001.

4. The method of claim 1, wherein one of the plurality of second openings is substantially greater than one of the plurality of first openings.

5. The method of claim 1, wherein and at least a portion of the second photoresist pattern is between two of the plurality of second openings.

6. A method of manufacturing a semiconductor structure, comprising: providing a substrate; disposing a first mask layer over the substrate; disposing a first photoresist over the first mask layer; patterning the first photoresist to form a plurality of first openings; removing portions of the first mask layer exposed by the plurality of first openings to form a plurality of first recesses that expose portions of the substrate; disposing a second mask layer over the first mask layer to fill the plurality of first recesses, wherein an edge of the second mask layer is substantially coplanar with an edge of the first mask layer and an edge of the substrate; disposing a second photoresist over the second mask layer; removing portions of the second photoresist to expose portions of the second mask layer; etching the exposed second mask layer to form a plurality of second recesses and the plurality of first recesses the substrate; and removing the second photoresist.

7. The method of claim 6, wherein after the removing portions of the first mask layer to form the plurality of first recesses, the plurality of first recesses extend through the first mask layer.

8. The method of claim 6, wherein each of the plurality of first recesses is communicated with each of the plurality of first openings.

9. The method of claim 6, further comprising removing the first photoresist before the second mask layer is disposed.

10. The method of claim 6, wherein the plurality of second recesses are at a level of the second mask layer.

11. The method of claim 6, wherein the first mask layer is at least partially transparent to a predetermined electromagnetic radiation.

12. The method of claim 11, wherein the second mask layer is opaque to the predetermined electromagnetic radiation.

13. The method of claim 6, wherein a width of each of the plurality of second recesses is substantially greater than a width of each of the plurality of first recesses.

14. The method of claim 13, wherein the width of each of the plurality of second recesses is about 5 mm to about 15 mm.

15. A method of manufacturing a semiconductor structure, comprising: forming a first mask layer over a substrate; forming a first photoresist over the first mask layer; patterning the first photoresist to form a plurality of first openings respectively exposing portions of the first mask layer; removing the exposed first mask layer to form a plurality of first recesses extended through the first mask layer; removing the first photoresist; forming a second mask layer over the first mask layer;

forming a second photoresist over the second mask layer; patterning the second photoresist to form a plurality of second openings; removing portions of the second mask layer exposed by two of the plurality of second openings to form a first hole and a second hole respectively exposing the substrate; and removing the second photoresist, wherein each of the first hole and the second hole includes at least one of the plurality of first recesses, the first mask layer is at least partially transparent to a predetermined electromagnetic radiation, and the second mask layer is opaque to the predetermined electromagnetic radiation.

16. The method of claim 15, wherein the first hole and the second hole extend through the second mask layer.

17. The method of claim 15, wherein after the removal of the portions of the second mask layer, at least a portion of the second photoresist is disposed between the first hole and the second hole.

18. The method of claim 15, wherein at least a portion of second mask layer is disposed between the first hole and the second hole.

19. The method of claim 15, wherein the first hole or the second hole is communicated with one of the plurality of second openings.

20. The method of claim 15, wherein an edge of the second mask layer is flush with an edge of the first mask layer and an edge of the substrate.
