

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250257436

Kind Code

A1

Publication Date

August 14, 2025

Inventor(s)

Anderson; Iver E. et al.

Ultra-High Strength Multiphase High-Entropy Alloys

Abstract

Refractory-reinforced multiphase high entropy alloys (RHEA's) advantageously providing high strength and fracture toughness in an as AM-deposited solidified condition and other conditions are described.

Inventors: Anderson; Iver E. (Ames, IA), White; Emma Marie Hamilton (Des Moines, IA), Johnson; Duane (Ames, IA), Argibay; Nicholas (Ames, IA), Kustas; Andrew B. (Elizabeth, CO), Chandross; Michael (Albuquerque, NM), Puckett; Raymond V. (Albuquerque, NM)

Applicant: Iowa State University Research Foundation, Inc. (Ames, IA); National Technology & Engineering Solutions of Sandia, LLC (Albuquerque, NM)

Family ID: 1000008587446

Appl. No.: 18/956367

Filed: November 22, 2024

Related U.S. Application Data

parent US continuation-in-part 17803779 20221121 parent-grant-document US 12180567 child US 18956367

us-provisional-application US 63361073 20211122

Publication Classification

Int. Cl.: C22C30/06 (20060101); B22F10/25 (20210101); B33Y70/00 (20200101)

U.S. Cl.:

CPC C22C30/06 (20130101); B22F10/25 (20210101); B33Y70/00 (20141201); B22F2303/15

Background/Summary

RELATED APPLICATION [0001] This application is a continuation-in-part of and claims priority and benefits of copending application U.S. Ser. No. 17/803,779 filed Nov. 21, 2022, which claims benefits and priority of U.S. provisional application Ser. No. 63/361,073 filed Nov. 22, 2021, the entire disclosures and drawings of both of which are incorporated herein by reference.

FIELD OF THE INVENTION

[0003] The present invention relates to refractory-reinforced multiphase high-entropy alloys specially designed for, although not limited to, additive manufacturing (AM) of AM deposited metallic structures having improved mechanical properties, such as increased strength and hardness.

BACKGROUND OF THE INVENTION

[0004] As the sophistication and quality of metal additive manufacturing (AM) continues to improve, research has shifted from feasibility studies towards process optimization.^{sup.1} Significant challenges remain to producing near net-shape parts with mechanical properties that can compete with traditional manufacturing techniques and alloys. Two new trends have recently emerged that present tantalizing opportunities to recast the value proposition for metal AM: (1) using metal AM for high-throughput materials discovery, particularly targeting high-entropy alloys (HEAs), and (2) a shift in emphasis from process optimization towards alloy design as a means of circumventing or addressing inherent limitations of AM techniques. Achieving desirable microstructures with traditional alloys via AM remains a challenge due to the inherently extreme thermal conditions; for example, a century of steel manufacturing optimization has led to processing sequences that are highly misaligned with the rapid melting and solidification typical of AM methods.

SUMMARY OF THE INVENTION

[0005] Embodiments of the present invention provide a refractory-reinforced multiphase high entropy alloy (RHEA) and alloy product advantageously providing high strength and fracture toughness in an as-built AM deposited condition as well as in a sintered condition or a rapidly solidified (RS) condition, all of which would result in a highly refined grain size.

[0006] Certain embodiments of the present invention provide an Al/Ti-rich RHEA having Al and Ti as major alloy constituents and Nb, Zr, Mo, and optional Ta as minor alloy constituents whose minor collective content is effective to provide a beneficial polyphase microstructure including four (4) compositionally distinct phases in the as-built AM or other solidified deposited condition wherein the polyphase microstructure imparts high strength and hardness to the as-deposited alloy with nearly temperature-independent hardness/strength up to 800° C., exceeding the performance of current state-of-the-art Ni-based superalloys. A sintered structure or body having a similar beneficial polyphase microstructure having high strength and hardness is provided by sintering processing such as, including but not limited to pressure assisted or electrical current assisted sintering of gas atomized powder. Certain embodiments provide the RHEA as a thermally sprayed solidified deposit or layer on a substrate surface.

[0007] A certain embodiment of the present invention provides a RHEA represented by $\text{Al}_{0.42}\text{Ti}_{0.25}\text{Nb}_{0.13}\text{Zr}_{0.08}\text{Mo}_{0.08}\text{Ta}_{0.04}$ and variants of that composition that produce a beneficial intermetallic polyphase microstructure. Still another embodiment of the invention provides a RHEA that is Ta-free (only Nb, Zr, and Mo being minor alloy constituents) represented by $\text{Al}_{0.42}\text{Ti}_{0.25}\text{Nb}_{0.17}\text{Zr}_{0.08}\text{Mo}_{0.08}$. and variants of that composition to this same end.

[0008] Another certain embodiment of the present invention provides a RHEA having an Al content greater than about 20 atomic % to less than about 70 atomic %, an Al+Ti content greater than about 55 atomic % and less than about 75 atomic %, and a collective content of Nb, Zr, Mo, and optional Ta of about 25 atomic % to about 45 atomic %.

[0009] Certain method embodiments of the present invention involve directed-energy deposition additive manufacturing (AM) using a heterogeneous (mechanically-milled at cryogenic temperatures from elemental powders) precursor powder that is laser beam melted and deposited to form the RHEA and to build an AM-printed metallic structure. Other certain embodiments involve plasma melting the RHEA constituents in a cold hearth tilt pour furnace to form a homogenous melt and then gas atomizing the melt in a manner to form generally spherical atomized alloy particles that then can be used for such AM processing. Still other certain embodiments envision thermal spraying generally spherical atomized alloy particles of the RHEA, or its constituents, as a layer or coating on a substrate surface.

[0010] The present invention advantageously can produce alloy products that include, but are not limited to, AM-printed metallic structures, sintered structures, and RS structures that comprise the RHEA having the above compositional and polyphase microstructural features to impart exceptionally high strength and hardness to the structure.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

[0011] FIGS. 1A and 1B show position and depth-dependent nanoindentation hardness of specimen, respectively; FIG. 1C shows contact force dependent micro-scratch hardness; FIG. 1D is a plan-view image of the cross-sectioned polished and epoxy-mounted specimen used in the testing; FIGS. 1E and 1F show strain-rate-dependent micro-scratch hardness and fracture toughness, respectively; and FIG. 1G is an exemplary topographical interferometric map of a micro-scratch wear track.

[0012] FIG. 2A is an SEM image of the as-deposited microstructure with 2 μm scale bar; FIG. 2B is an STEM high-angle annular dark field image showing near-surface deformation along the centerline of a 10 N micro-scratch track; FIG. 2C shows overlaid composition maps showing at least four compositionally distinct phases; for phases A1-A4, these are: (1) $\text{Al.sub.0.36Ti.sub.0.26Nb.sub.0.19Zr.sub.0.02Mo.sub.0.12Ta.sub.0.08}$, (2) $\text{Al.sub.0.42Ti.sub.0.19Nb.sub.0.12Zr.sub.0.02Mo.sub.0.13Ta.sub.0.04}$, (3) $\text{Al.sub.0.49Ti.sub.0.27Nb.sub.0.13Zr.sub.0.08Mo.sub.0.04Ta.sub.0.02}$, and (4) $\text{Al.sub.0.35Ti.sub.0.36Nb.sub.0.10Zr.sub.0.02Mo.sub.0.13Ta.sub.0.04}$; and FIG. 2D shows an image of the as-deposited microstructure with a 10 μm scale bar.

[0013] FIGS. 3A-3F are atomic-resolution high-angle annular dark field (HAADF) images and Fast Fourier Transform (FFT) patterns of the images (insets) for (FIGS. 3A, 3C, 3D, 3F) the four distinct phases and (FIGS. 3B, 3E) two interphase boundaries showing high coherence; and FIGS. 3G-3I are high-resolution images showing accommodation of plastic deformation in a 10 N micro-scratch track primarily by formation of dense dislocation walls; the scratch sliding direction is from left-to-right in FIG. 3G.

[0014] FIG. 4 contains Table 1.

[0015] FIG. 5A is a plot of nano-indentation hardness as a function of temperature for the exemplar alloy represented by $\text{Al.sub.0.42Ti.sub.0.25Nb.sub.0.13Zr.sub.0.08Mo.sub.0.08Ta.sub.0.04}$. FIG. 5B shows representative force-displacement curves showing a transition from ductile to brittle behavior after prolonged 800° C. exposure.

[0016] FIG. 6A and FIG. 6B are SEM images of the as-AM built microstructure at different magnifications. FIG. 6C and FIG. 6D are SEM images of the post heat treatment microstructure at

different magnifications.

[0017] FIGS. 7A-7G: HAADF STEM images showing (FIGS. 7A-7B) grain and phase structure, (FIG. 7C) evidence of high coherence at phase 3/4 interfaces, and (FIGS. 7D-7E) lattice structures of phases 1 and 2 with overlaid elemental composition relative intensity maps, which indicate partial chemical ordering for phases 1 and 2, and (FIGS. 7F-7G) lattice structures of phases 3 and 4 along with inset FFT patterns. The lattice constant for phase 4, a BCC solid solution, matched the DFT predicted value.

DETAILED DESCRIPTION OF THE INVENTION

[0018] Certain embodiments of the present invention provide an AM-enabled refractory-reinforced multiphase high entropy alloys (RHEA's), and alloy products thereof, whose composition and fine-grained ($\sim 10\text{ }\mu\text{m}$) microstructure is controlled to advantageously provide high strength and fracture toughness in an as-deposited (as-solidified) or as-sintered (to full density) condition. Embodiments of the present invention resulted from the discovery of a new RHEA having an average (exemplar) composition of

$\text{Al}_{0.42}\text{Ti}_{0.25}\text{Nb}_{0.13}\text{Zr}_{0.08}\text{Mo}_{0.08}\text{Ta}_{0.04}$, which alloy was found to have extraordinary mechanical properties (FIGS. 1A-1C and 1E-1F), including high strength and fracture toughness (FIG. 2A) in the as-AM solidified deposited condition. Other embodiments of the present invention involve a Ta-free alloy composition represented by

$\text{Al}_{0.42}\text{Ti}_{0.25}\text{Nb}_{0.17}\text{Zr}_{0.08}\text{Mo}_{0.08}$, which alloy can have compositionally-distinct intermetallic phases of a polyphase microstructure and beneficial mechanical properties in the as-AM built, or other solidified/sintered alloy condition, preferably being comparable to those described for the $\text{Al}_{0.42}\text{Ti}_{0.25}\text{Nb}_{0.13}\text{Zr}_{0.08}\text{Mo}_{0.08}\text{Ta}_{0.04}$ alloy in the as-AM built or other solidified/sintered alloy condition.

[0019] For purposes of illustration and not limitation, the RHEA (also designated herein as MPEA for multi-principal element alloy) exemplar alloy is Al- and Ti-rich, with a nominal exemplar composition $\text{Al}_{0.42}\text{Ti}_{0.25}\text{Nb}_{0.13}\text{Zr}_{0.08}\text{Mo}_{0.08}\text{Ta}_{0.04}$, and was found to have high hardness ($H=10\text{-}15\text{ GPa}$) and scratch-based (mode II) fracture toughness ($K_{\text{Ic}}=40\text{-}85\text{ MPa}\cdot\text{m}^{1/2}$), along with low density ($\rho=5.7\text{ g/cm}^3$), notable room-temperature indentation-based ductility ($>10\%$) and high-temperature resiliency (8 GPa hardness retained to 800° C.). The specific strength of the MPEA based alloy depends on the ratio of hardness and density is $1.8\text{-}2.6\text{ GPa}\cdot\text{cm}^3/\text{g}$, a value that surpasses all known alloys, including 1) intermetallic compounds and legacy titanium aluminides, 2) refractory MPEAs, and 3) conventional Ni-based superalloys. This specific strength is a 300% improvement over Inconel 718 based on measured peak hardness of 4.5 GPa and density of 8.2 g/cm^3 , which gives a ratio of $0.55\text{ GPa}\cdot\text{cm}^3/\text{g}$. Notably, certain alloy embodiments of the present invention enable retention of high-strength at high-temperatures, exceeding the performance of conventional Ni-based alloys.

[0020] Embodiments of the present invention include a RHEA represented by $\text{Al}_{0.42}\text{Ti}_{0.25}\text{Nb}_{0.13}\text{Zr}_{0.08}\text{Mo}_{0.08}\text{Ta}_{0.04}$ and variants of that composition, wherein the content of one or more of the constituent alloying elements can be varied that produces the beneficial polyphase microstructure including at least four (4) compositionally distinct phases in the as-deposited (as-built) or sintered condition or Rapid Solidification condition where rapid cooling casting techniques typically providing a cooling rate above $10^4\text{ }^\circ\text{C}/\text{second}$, such as melt spinning, can be used to provide a crystalline equiaxed grain size having a micron scale grain dimension less than about $10\text{ }\mu\text{m}$. Thus, Al+Ti are major alloy constituents being more than 50 atomic % of the alloy composition.

[0021] Other embodiments of the present invention were discovered to include Al/Ti-rich RHEA's having a composition comprising an Al content greater than about 20 atomic % to less than about 70 atomic %, an Al+Ti content greater than about 55 atomic % and less than about 75 atomic %, and a collective content of Nb, Zr, Mo, and optional Ta is about 25 atomic % to about 45 atomic % and having high strength and fracture toughness.

[0022] For purposes of further illustration and not limitation, certain embodiments of the invention include a RHEA alloy with a nominal exemplar composition Al.sub.0.42Ti.sub.0.25Nb.sub.0.17Zr.sub.0.08Mo.sub.0.08 and variants thereof, wherein Al and Ti are major alloy constituents wherein Al is content is greater than 20% and less than 70 atomic % with Al+Ti greater than 50 atomic % and having Nb, Zr, and Mo and optional Ta as minor alloy constituents wherein Nb is present from 13 atomic % to 17 atomic % and Ta is 0 up to 4 atomic % of the alloy and wherein the minor alloy constituents have a collective content of about 25 atomic % to about 45 atomic %. Certain embodiments of the invention envision that this alloy has a Ta content less than 4 atomic %, or has Ta entirely omitted (i.e. (0% Ta), wherein a portion or all of the Ta is replaced by increased Nb content. For example, when Ta is less than 4 atomic % of the alloy, the Nb content is greater than 13 atomic %.

[0023] Certain embodiments of the invention further envision aa RHEA that is Ta-free (only Nb, Zr, and Mo being minor alloy constituents) and that is represented by Al.sub.0.42Ti.sub.0.25Nb.sub.0.17Zr.sub.0.08Mo.sub.0.08. and variants of that composition wherein Al, Ti, Nb, Zr, and/or Mo is/are varied to provide compositionally-distinct intermetallic phases of a polyphase microstructure. To this end, a Ta-free RHEA is provided wherein, in atomic %, Al is greater than 20% and less than 70 atomic % with Al+Ti greater than 50 atomic %, Nb is 13% to 17% Nb, Zr is 5% to 15% Zr, and Mo is 2% to 8% where Nb, Zr, and Mo are present in a collective amount of about 25 atomic % to about 45 atomic %. For purposes of illustration and not limitation, a Ta-free RHEA specimen had a measured alloy composition of, in atomic %, 42.0% Al, 24.2% Ti, 16.1% Nb, 10.3% Zr, and 7.4% Mo.

[0024] The present invention will be described here-below in Examples with respect to certain illustrative alloy embodiment that achieves high strength and fracture toughness; however, the present invention is not limited to these illustrative embodiments that are offered for purposes of illustration and not limitation.

Examples

AM Synthesis

[0025] Cryo-ball milling of the alloy constituents (as Al, Ti, Nb, Zr, Mo, Ta elemental powders) was used to generate a pre-mixed but compositionally segregated precursor powder that enabled large heats of mixing and in-situ exothermic reactions to assist with powder melting during AM processing. Cryo-milling was conducted in a modified Union Process-brand attritor mill under liquid nitrogen atmosphere for 8 hours.

[0026] Alternately, as-gas atomized alloy powder having the desired alloy composition (i.e. a pre-alloyed composition) can be used as the feedstock for the AM process.

[0027] The laser-beam directed-energy deposition (LB-DED) AM technique (described by A. B. Kustas et al., Characterization of Fe—Co-1.5V soft ferromagnetic alloy processed by Laser Engineered Net Shaping (LENS), Addit. Manuf. 21, 41-51, 2018, which is incorporated herein by reference) required a surprisingly low laser beam power (100-110 W) to sufficiently melt the heterogeneous alloy precursor powder. Single track thin wall specimens of the new RHEA were fabricated (deposited and solidified) on titanium substrates using an open-architecture LB-DED system equipped with a YLS-2000 laser operating at a wavelength of 1064 nm. The laser was mounted to the spindle of a 3-axis Tormach CNC 770 and housed inside an inert atmosphere was maintained at <500 ppm O₂ and <0.5 ppm H₂O.

[0028] The Table below lists the process conditions for the thin wall consolidation. Excessive heating during fabrication was minimized by adding a two second delay between each layer

TABLE-US-00001	Laser	Table	Optic	Layer	Substrate	Power	Speed	Size	Height	Temp. (W)
	(mm/min)	(mm)	(mm)	(° C.)	100	300	2.3	0.2	200	

Mechanical Property and Microstructural Evaluation Experimental Methods

1. AlMoNbTaTiZr RHEA Scratch Test Methods

[0029] A flat RHEA specimen was produced with an average surface roughness R_a of about 25

nm. The sample was subject to grinding using SiC paper and fine polishing with steps of 9, 6, 3, and 1 μm MOL polishing cloths.

1.1 Determination of Strain Rate Dependent Hardness

[0030] Microscratch experiments (references 1, 2 and 4, 5) were performed using a Revetest Scratch Tester (RST.sup.3). To determine strain-rate dependent hardness, scratches were made by dragging a sphero-conical indenter (radius $R=200\text{ }\mu\text{m}\pm 10\text{ }\mu\text{m}$ and apex angle $\alpha=120^\circ\pm 1^\circ$) over a 3 mm track length with a 50 N normal force and a constant velocity. Five wear tracks were produced with five decades of scratch speed (proportional to strain rate) ranging 10.sup.-3 to 10.sup.1 mm/s. Each track was spaced 0.5 mm apart to avoid work hardening effects from previous tracks. To assess load dependent hardness, scratches were performed under 10, 50, 70, and 100 N normal forces at a constant velocity of 10.sup.-1 mm/s. A mildly abrasive cloth was used to clean the indenter tip between scratches to avoid transferring material between wear tracks. The spheroconical diamond indenter can be used for multiple repeated scratches due to its exceptional hardness and wear resistance.

[0031] A Bruker Contour GT-I optical interferometer with a 10 \times objective and 0.55 \times magnification was used to topographically scan each 3 mm wear track. To avoid sections of the scratch track that may have experienced acceleration/deceleration effects, the beginning and end 0.5 mm of wear track was omitted from analysis. The average and standard deviation in the wear track width was used to calculate the hardness and strain rate at a given scratch speed. The strain rate (ϵ) is a ratio of scratch velocity (v) to scratch width

$$[00001](w), \quad \epsilon = \frac{v}{w}.$$

The expression for hardness (H) is a function of a geometric constant term $8/\pi$ the normal force ($F_{\text{sub.n}}$), and the scratch width (w),

$$[00002]H = \left(\frac{8}{\pi}\right)\frac{F_n}{w^2}$$

A detailed overview of this method can be found elsewhere (see George, E. P. et al., High-entropy alloys, Nat. Rev. Mater. 4, 515-534, 2019).

[0032] Activation volume (V) and strain rate sensitivity (m) were determined from strain-rate dependent micro-scratch hardness measurements, using the following expressions,

$$[00003]V = 3\sqrt{3}kT\left(\frac{\partial \ln \dot{\epsilon}}{\partial H}\right) \text{ and } m = \frac{\partial \ln(H)}{\partial \ln(\dot{\epsilon})}$$

1.2 Determination of Fracture Toughness

[0033] Data from the microscratch experiments were also used to determine fracture toughness. Using the topographical scan from a scratch track, the average and standard deviation values for maximum penetration depth were found and analyzed.

[0034] Following classic linear elastic fracture mechanics, the sphero-conical probe tip is known to generate a semi-circular horizontal crack planer (see references 3, 6-9). Fracture toughness K , is then expressed as a function of the measured lateral force $F_{\text{sub.t}}$, the perimeter length p , and the projected contact area, A .

$$[00004]K_c = \frac{F_t}{\sqrt{2pA}}$$

The perimeter length p is calculated using the arclength formula for the spheroconical probe, where R is the 200 μm indenter radius, and $d_{\text{sub.p}}$ is the maximum penetration depth of the scratch.

$$[00005]p = 2R\arccos\left[\frac{R-d_p}{R}\right]$$

The projected contact area is a function of the tip radius R , the maximum penetration depth $d_{\text{sub.p}}$, and perimeter length p .

$$[00006]A = 1/2Rp - (R-d_p)\sqrt{R^2 - (R-d_p)^2}$$

2. AlMoNbTaTiZr RHEA Nanoindentation Methods

[0035] Nanoindentation hardness measurements were performed on a Hysitron Performech Triboindenter with a Berkovich tip using the Oliver-Pharr method (see reference 10 incorporated herein by reference). The flat RHEA AM specimen used for the microscratch experiments was

subsequently used for the nanoindentation experiments; the indents were placed near the residual scratches both to facilitate direct comparisons between results and to locate residual indents after testing. Prior to the RHEA measurements, the tip area function and load frame compliance were calibrated over the entire load range of the instrument using fused silica as the reference material. For the Berkovich tip, the tip area function $A(h_{\text{c}})$ was defined as, $A(h_{\text{c}}) = C_0 h_{\text{c}}^2 + C_1 h_{\text{c}}$, where h_{c} is the contact depth and C_0 and C_1 are coefficients related to tip shape as described by W. C. Oliver et al. in J. Mater. Res. 7, 1564, 1992.

4. Microstructural Characterization by Scanning Transmission Electron Microscopy

[0036] Microstructures of RHEA specimen were studied by scanning transmission electron microscopy (STEM). The TEM samples were prepared by focused ion beam (FIB) method. An FEI TitanTM G2 80-200 STEM with a Cs probe corrector and ChemiSTEMTM technology (X-FEGTM and SuperXTM EDS with four windowless silicon drift detectors) operated at 200 kV was used in this study. A high-angle annular dark-field (HAADF) detector was used for recording STEM images. The STEM energy-dispersive x-ray spectroscopy (EDS) was used for the compositional phase analysis. The EDS spectral imaging was acquired as a series of frames where the same region was scanned multiple times. A typical acquisition of EDS spectral imaging took more than 1 hr. An electron probe of size less than 0.13 nm, convergence angle of 18.1 mrad, and current of ~75 pA was used for data acquisition. HAADF images were recorded under similar optical conditions using an annular detector with a collection range of 60-160 mrad. Al K, Ti K, Zr L, Nb L, Mo L and Ta M lines were used for constructing the EDS maps of Al, Ti, Zr, Nb, Mo and Ta, respectively. Since the Al K, Zr L, Nb L, Mo L and Ta M lines overlap significantly, the EDS spectra were deconvoluted pixel-by-pixel using pure spectra of Al, Zr, Nb, Mo and Ta as references. The atomic concentration of the phase was calculated using the Cliff and Lorimer method.¹² The error of phase composition was estimated to be within 5%, largely due to uncertainty of the K factor used in the Lorimer method.

Results:

[0037] Thin-wall coupon specimens approximately 20×25×5 mm.³ were each printed, sectioned, potted in epoxy, and polished to a 40 nm SiO.₂ slurry via vibratory polishing, (FIG. 1D). The 3D printing was achieved using the open architecture LB-DED printer described above. The mechanical properties were studied with nanoindentation, micro-scratch, and Vickers indentation methods as described above in detail.

[0038] The discovered RHEA having an average composition of Al._{0.42}Ti._{0.25}Nb._{0.13}Zr._{0.08}Mo._{0.08}Ta._{0.04}, was found to have extraordinary mechanical properties (FIGS. 1A-1C and 1E-1F), including high strength and fracture toughness in the as-AM deposited (as-built) condition. The combination of material strength and energy-efficient processing represents a paradigm shift when compared to AM processing of other high entropy alloys (HEAs) and similarly low-density Al and Ti alloys.

[0039] This illustrative embodiment is an example of how careful feedstock design can enable energy-efficient AM processing of alloys, particularly those with compositions that would be impractical to create conventionally. The results also demonstrate that, despite low quality (from the standpoint of additive processability and flowability) cryo-ball-milled feedstock powder, the process in combination with unconventional suite of characterization tools, e.g., micro-scratch measurements of strain rate dependent strength and toughness, was extremely effective for materials development.

[0040] Results from the different strength measurement techniques were in agreement and show that this alloy exhibits a combination of high strength and fracture toughness that is promoted by a refined nanoscale multiphase microstructure (as shown via scanning transmission electron microscopy (STEM) in FIGS. 3A-3C and FIG. 4—Table 1). Using the Tabor factor, the conversion of hardness to uniaxial tensile strength, i.e., $\sigma_{\text{Y}} = H/3$ can be achieved. Microscratch tests of

strain-rate dependent hardness data was used to determine strain-rate sensitivity ($m=0.030$) and activation volume ($V=55 \text{ \AA}^3$) (details of test method set forth above). Two linear arrays of 300 nanoindentation measurements were made parallel to the micro-scratch tracks on a sectioned and polished coupon (FIG. 1D). The hardness and fracture toughness values are in good agreement with those for nanocrystalline (grain sizes $<100 \text{ nm}$) pure metals and alloys, and indicate that plasticity is primarily dislocation mediated, although Applicants do not intend to be bound in this regard. However, these values are typically associated with the prevalence of partial dislocation emission from grain boundaries and small edge dislocation line lengths, corresponding to highly-localized, steep strain fields. This result is unusual, considering that the present material is neither face-centered cubic (FCC) nor particularly fine-grained (the grain size of the tested RHEA specimens varied for each phase, from about 500 nm to, generally, less than 10 microns (FIGS. 2A-2C)).

[0041] This mechanical property data revealed several interesting features: gradual trends of (1) increasing strength moving from the coupon specimen wall towards the core of the specimen, normal to the 3D printed build direction, (2) slightly decreasing strength along the build direction away from the coupon specimen-baseplate interface, and (3) significant variability in strength (high standard deviation) with small changes in location. These trends suggest that the gradient in strength is correlated with build height, though this is likely the result of multiple factors that cannot easily be deconvoluted. More significantly, given the grain size (FIG. 2A), determined by scanning electron microscopy (SEM), and the composition variability (from STEM) of the four distinct phases A1-A4 (FIG. 2A-2C), it is likely that the variability in nanoindentation hardness at constant depth of 250 nm (FIG. 1A) shows the strength differences between the four phases. Conversely, variability in micro-scratch hardness, which is averaged over larger volumes with a coarser (roughly 500 nm) lateral resolution, is more indicative of an aggregate response, and dominated by the weakest phase and the presence of defects on similar length scales.

[0042] For $\text{Al}_{0.42}\text{Ti}_{0.25}\text{Nb}_{0.13}\text{Zr}_{0.08}\text{Mo}_{0.08}\text{Ta}_{0.04}$ (nominal atomic %), the A2 crystal structure (body-centered cubic) was found to be the most stable, with a formation energy, E_{form} , of -17.35 kJ/mol ($\sim 7.44 \text{ kJ/mol}$ lower than Al, or face-centered cubic, structure). The homogeneously A2 parent alloy has an average lattice constant of $a=3.213 \text{ \AA}$ and bulk modulus of $B=128 \text{ GPa}$. Compared to the alloy compositions in regions 1-4, both the homogeneous A1 and A2 structures were found to have E_{form} lower by $1.2\text{-}2.6 \text{ kJ/mol}$, implying that the compositions found in each region are energetically unfavorable (non-equilibrium). Finally, using a fast estimate (composition-weighted elemental melt temperatures) for the homogenous A2 alloy, the melting temperature was estimated to be $\sim 1787 \text{ K}$, whereas, using DFT formation energies in a mean-field estimate gives $T_{\text{melt}}=\Delta H/\Delta S_{\text{form}}\sim 1500 \text{ K}$, which bracket $[1500\text{-}1787 \text{ K}]$ the observed begin and end melting (see below $[1650\text{-}1780 \text{ K}]$).

[0043] Differential scanning calorimetry of the as-printed specimens was conducted to better understand the melting and solidification behavior. Results for the first heating cycle (using a rate of 20 K/minute) of the as-built specimen showed that multi-event melting begins and ends between 1650 and 1780 K , in agreement with the predicted values, with some evidence of thermally-driven microstructural evolution during the heating ramp.

[0044] Extensive structural and compositional analysis by STEM are summarized in FIGS. 2A-2C and FIG. 4—Table 1, including subatomic resolution images of the multiple phases A1-A4 as well as a phase boundary (FIG. 3A-3F). This analysis showed that there was no mechanical mixing and negligible change in grain size inside the 10 N micro-scratch track at 1 s^{-1} sliding speed, as compared to the adjacent, as-deposited material. These images, showing deformation near the surface along the track centerline (FIGS. 3G-3I), suggest that plastic deformation was primarily accommodated by intragranular deformation and the formation of dislocation walls (FIG. 3G-3I) that appear to fully transect grains. A possible explanation for the extraordinary strength and apparent ductility of this material may be in the activation of multiple dislocation types and slip

systems, enabled by the higher lattice strains characteristic of multi-element solutions with high configurational entropy. The statement regarding ductility is based on qualitative observations of the micro-scratch tracks, which showed no evidence of cracking at track edges, as is expected for brittle materials. The defect structures shown in FIG. 3A-3I may promote non-screw dislocation nucleation and glide along multiple slip planes, presumably by increasing the activation energy barrier for screw dislocation motion. This may explain the unusually high strength of the Al.sub.0.42Ti.sub.0.25Nb.sub.0.13Zr.sub.0.08Mo.sub.0.08Ta.sub.0.04 alloy compared to peak tensile strengths of about 3 GPa in ultra-nanocrystalline BCC metals. Additionally, there is evidence that some interphase boundaries are substantially (highly) coherent, with misorientation of less than 2° between phases 1/2 and 3/4, as shown in FIGS. 3B and 3E, respectively. Highly coherent phase boundaries are another mechanism that may lead to the atypical combination of high strength and ductility, by acting as barriers to dislocation motion, thus promoting accumulation while mitigating crack formation.

[0045] The alloy polyphase microstructure imparts high strength and hardness to the as-deposited alloy with nearly temperature-independent strength up to 800° C., exceeding the performance of current state-of-the-art Ni-based superalloys. FIG. 5A presents results from high temperature nanoindentation on two AM builds with the same processing conditions, which showed different initial strengths but negligible change at temperatures up to 1073 K (800° C.). Ductile mechanical response was indeed observed during deep nanoindentation measurements (>1 μm depths) for all but the post-800° C. anneal room-temperature test condition (FIG. 5B). Reasons for the transition from ductile-to-brittle behavior following the 800° C. heat treatment remain unclear.

[0046] Complementing the temperature-dependent thermomechanical property measurements, heat capacity and thermal conductivity over a temperature range of 25° C. (RT) to 300° C. were measured, in addition to the decoupled phonon subsystem contribution to thermal conductivity at room temperature (see Table I).

TABLE-US-00002 TABLE I Summary of measured and calculated (DFT and virtual crystal approximation) properties for the multiphase AM

Al.sub.0.42Ti.sub.0.25Nb.sub.0.13Zr.sub.0.08Mo.sub.0.08Ta.sub.0.04 alloy. % Experimental
Calculated difference hardness (STP), H 10-15 — — GPa density (STP), ρ 5.7 5.4 5.4 g/cm³
reduced modulus, E.sub.r 219 — — GPa melting temperature, T.sub.m 1650-1780 1500-1787 17.1
(max) K bulk modulus, B — 128 — GPa fracture toughness, K.sub.c 40-85 — — GPa Heat
capacity, pC.sub.p 1.9-2.5 — MJ/m.sup.3-K Thermal conductivity 4-5.2 — — W/m-K (total), k
Thermal conductivity @ 1.8 2.7-7.0 40-118 W/m-K 25° C. (phonon contribution), k.sub.l

[0047] It is also possible to determine an estimate of ductility from the methods employed here; following work by D. A. Tabor, A simple theory of static and dynamic hardness, *Proceedings of the Royal Society of London, Series A. Mathematical and Physical Sciences*, 192, 247-274, 1948, which is incorporated herein to this end, for a spherical indenter of diameter (D), the plastic strain as a function of indentation area diameter or track width (d) can be approximated as $\epsilon_{\text{sub.p}} \cong 20d/D$, corresponding to a ductility of at least 5% at room temperature (RT) and as high as 10% at room temperature. This indicates that this alloy has practical engineering utility in structural applications and AM processes. Table 1 indicates that the alloy was found to have limited (low) thermal conductivity, which is typical for HEA compositions.

[0048] FIG. 5A presents results from high temperature nano-indentation testing of two AM built samples made using the same processing parameters. The samples exhibited different initial strengths but negligible change up to 1073 K (800° C.). Also, ductile mechanical response was indeed observed during deep nano-indentation measurements (greater than 1 μm depths) for all samples but the post-800° C. anneal RT test condition, FIG. 5B.

[0049] Further Microstructural and Compositional Characterizations: The above discussed mechanical property data revealed several interesting features that are distinctly linked to the material polyphase microstructure. Specifically, gradual and spatially dependent trends of (1)

increasing strength towards the core of the specimen normal to the build direction, (2) slightly decreasing strength along the build direction away from the specimen-baseplate interface, and (3) significant variability in strength (high standard deviation) with small changes in location. These trends suggest that the gradient in strength is correlated with build height, though this is likely the result of multiple factors that cannot easily be deconvoluted, such as variations in thermal history and accumulation of residual stresses. Furthermore, given the relatively coarse grain size of the as-built specimen, as shown via scanning electron microscopy (SEM) channeling contrast micrographs in FIG. 6A-6B, it is likely that the variability in nanoindentation hardness is indicative of strength differences between phases. Conversely, variability in micro-scratch hardness, which is averaged over comparatively larger volumes with a coarser (roughly 500 nm) lateral resolution, is more indicative of an aggregate response, and dominated by the weakest phase and the presence of defects on similar length scales. Representative SEM micrographs of the MPEA microstructure following high-temperature nanoindentation, which included exposure to 800° C. for 1 hour, are also provided in FIG. 6C-6D and show negligible change in terms of both feature morphology and size compared to as-AM built versions of the MPEA. These results suggest that the alloy exhibits thermal stability in environments that approach half the alloy melting temperature (homologous) and supports the observed persistence of high hardness both during and following high-temperature testing. While the present results are encouraging for retention of hardness at extraordinary temperatures, based on negligible microstructure evolution following high-temperature indentation, a 1-hour exposure at 800° C. is still a relatively modest exposure time for most applications that utilize conventional Ni based superalloys.

[0050] Referring to FIGS. 7A-7G, STEM (scanning transmission electron micrograph) characterization shows a partial analysis of the complex microstructure observed in an AM-processed RHEA (MPEA) sample, wherein four chemically and structurally unique phase are identified (Table II, FIG. 7A-7B). FIG. 7C shows evidence of high coherence at phase % interfaces. Notably, all four phases have some extent of all six alloying constituents that compose the global MPEA composition, indicating a deviation from dilute alloying that is typical of conventional alloys. Two of the phases, phase 2 and 4 (FIGS. 7E and 7G) have a cubic symmetry with lattice parameters of 9.5 Å and 3.2 Å, respectively, illustrating vast differences in unit cell size. Phase 2 has a stoichiometry that is highly enriched in Al with notable fractions of Ti, Nb, and Zr constituents and relatively minor concentrations of Mo and Ta. Phase 4 is determined to be a body centered cubic (BCC) solid solution with a near-equiatomic ratio of Al and Ti and appreciable amounts of Mo and Nb and minor additions of Ta and Zr. The other two phases, that is phase 1 and phase 3, are both non-cubic and reveal a predominately tetragonal symmetry, and possible orthorhombic structure for phase 3. Both of these phases are enriched in Al compared to the other alloying constituents, with the former having appreciable Ti, Nb, and Mo content, while the latter shows higher concentrations of Ti and Nb, respectively. The lattice parameter for phase 1 is large, at 9.8 Å, similar to that for phase 2. Partial chemical ordering is also shown in the STEM images, aided by overlaid elemental maps for phase 1 and phase 2, that denote the fixed lattice positions for the alloying constituents. Thus, some of the phases are thought to, at minimum, show partial chemical of ordering and are shown to drastically influence the alloy deformation behavior, FIG. 7D-7G. These structural and chemical data are complemented by differential scanning calorimetry (DSC) that enabled a baseline understanding of the melting and solidification behavior of the sample. Results for the first heating cycle (using a rate of 20 K/minute) of the as-built specimen indicate that multi-event melting begins and ends between 1650 and 1780 K (commensurate with rule-of-mixtures estimates), with some evidence of typical thermally-driven microstructural evolution during the heating ramp (e.g., dislocation recovery, grain growth, etc.). In addition, the microstructure revealed isolated evidence of spherical zirconium oxide dispersoids (FIG. 7A), likely driven, at least in part, by the high initial oxygen concentration (about 8.5 at. %) of the cryo-ball-milled powder. The volume fraction of detected oxide dispersoids is insufficient to account for

the total measured oxygen content of the powder feedstock, suggesting that oxygen may be primarily in solution in the form of interstitial defects; it is known that group IV and V transition metals, including Ti, Zr, Nb and optional Ta, which are constituents of the present alloy, exhibit high oxygen solubility.

[0051] The structural and compositional analysis, by STEM, included atomic resolution images of the multiple phases as well as a phase boundary. As-built and post-deformation conditions, via scratch testing, were compared. This analysis showed negligible change in grain size inside the 10 N micro-scratch track, as compared to the adjacent as-deposited material. Deformation near the surface along the track centerline indicated that plastic deformation was confined to select phases, forming slip bands and dislocation walls that appear to fully transect grains but arrested by the dispersed and apparently softer phases 3 and 4 in FIG. 6A-6B.

[0052] As is apparent, embodiments of the present invention provide a multi-phase RHEA (MPEA) with high strength from a metastability in the complex energy-composition space that only occurs in a certain composition range. For an exemplar RHEA alloy in a specific composition range, multiple alloy phase compositions with common BCC phases compete via segregation to lower the average E.sub.form, creating a steady-state multi-phase alloy with a large number of grain boundaries—with associated coherency strains. Furthermore, to have this thermodynamically favored, limits for the parent phase (here Al/Ti and refractory elements) to affect BCC stability and its relative stability versus FCC and HCP were established. In particular, the parent nominal alloy (in atomic %) has a % Al ranging from about 20 to less than about 70%, as determined from the binary Al—Ti system, has the combined % (Al+Ti) ranging from over about 55 to less than about 75%, and have the refractory elements as shown, where % Mo ≥ % Nb—% Ta and % Zr is large enough to drive segregation, in this case about 8% Zr.

Towards AM-Friendly Improved MPEAs and Energy-Efficient Manufacturing

[0053] Conventional alloys explored by others to date for use with AM generally possess hardness values ranging from 1-10 GPa, and corresponding estimated yield strength values from 0.2 to 1 GPa, which is notably lower than those of the present exemplar alloy for both properties, in some cases by an order-of-magnitude. Similarly beneficial results were noted in the context of AM processing efficiency. Notably, mechanically pre-mixed, compositionally segregated and high-impurity content cryo-ball milled powder was utilized as feedstock, wherein large negative heats of mixing and very significant in situ exothermic reactions assisted with particulate melting and molten alloy homogenization in the melt pool during processing. This, in combination with the reduced alloy melting temperature, led to a low beam power (100-110 W) and, consequentially, a very low volumetric energy density (VED) of 40-50 J/mm.³ for the laser-based directed-energy deposition AM technique to sufficiently heat and melt the heterogeneous powder. Most conventional alloys, evaluated with laser-based additive methods, require significantly higher VED values to achieve high-quality metallurgical specimens, particularly for HEAs/MPEAs and refractory-based alloys, where VED values range from approximately 20 to 2000 J/mm.³. Overall, the combination of high material hardness and estimated yield strength (10-15 GPa and 3-5 GPa, respectively) and energy-efficient processing (VED=40-50 J/mm.³) for the Al.sub.0.42Ti.sub.0.25Nb.sub.0.13Zr.sub.0.08Mo.sub.0.08Ta.sub.0.04 alloy represents a paradigm shift compared to the current state-of-art. This suggests a route for careful feedstock design (perhaps with blended master alloy powders in a uniform bed or in a powder feeder) to enable energy-efficient AM processing of alloys, particularly those with compositions that would be impractical to create using conventional ingot metallurgy practices (e.g., casting of the full alloy to use in gas atomization processing). This is particularly true for refractory metal MPEAs with high concentrations of elements having dissimilar melting temperatures, such as in this case, with extremes of 933 K (Al) and 3290 K (Ta) for the lowest and highest constituent melting temperatures, respectively.

[0054] To test the ability to reach these outstanding strength and hardness values in this exemplar

MPEA with a powder feedstock that can be made by more conventional (for Ti alloys) powder making methods (plasma melting in a cold hearth and free-fall gas atomization), inert gas atomized powder having the exemplar alloy composition set forth above (in atomic %) and an average powder particle size (diameter) of 45 microns was obtained and used as the feedstock powder for the LENS-AM (laser engineered net shaping-AM) system at Sandia National Laboratories to produce an AM layer (about 6 mm thick) structure of the Ta-bearing alloy and the Ta-free alloy described above. The AM deposit of the Ta-bearing alloy exhibited a Vickers hardness of 779, which is about 7.6 GPa. A high hardness that is similar to the hardness values discussed above in the AM example made from cryo-milled heterogeneous powder.

Sintering Example

[0055] To test the ability to reach these outstanding strength and hardness values in this exemplar MPEA with a more conventional (not for forming complex shapes) full-density powder consolidation method, a sample of the same pre-alloyed gas atomized powder having the exemplar alloy composition set forth above (in atomic %) and an average powder particle size (diameter) of 45 microns was spark plasma sintered at a target temperatures of 1100, 1200 (two samples), and 1250 degrees C. at a rate of 100 degrees C./minute and 50 MPa pressure for to form a disc shape having densities of 5.43; 5.39 and 5.49 (repeat sample); and 5.46 g/cm³, respectively. The 1200 degree c. sintered samples exhibited Vickers hardness values of 853.2; 850.05; and 837.32 at different indenter loads of 200 grams; 500 grams; and 1 kilogram, which is about a hardness of 8.2 GPa. Again, this high hardness is similar to the hardness values discussed above in the AM example made from cryo-milled heterogeneous powder.

[0056] In summary, the alloys of the evaluated illustrative embodiments lie in a unique region of composition space, being significantly enriched in Al and Ti compared to a majority of other RHEA studies. These are ideal constituents to enable light-weighting of structural parts. Compositionally, the present alloy should be significantly less dense than known refractory-rich HEAs, while also retaining higher strength and more refined microstructure associated with the rapid solidification characteristics of AM. This highlights the value proposition of combining advanced alloys with advanced manufacturing methods to achieve unprecedented materials properties. This Al-RHEA has noticeable similarities with respect to strength-to-weight (normalized) properties with classical Ti—Al intermetallic alloys that have been revered for potential use in structural aerospace applications, due to their high specific strength. Since poor Ti—Al alloy workability has long challenged their widespread adoption. Given that these newly discovered RHEA embodiments are processable via near-net shape additive manufacturing methods and full density sintering methods, and that they have unusually high strength in an as-built or as-sintered form (far exceeding polycrystalline alloys), multiple opportunities lie ahead to accelerate the development of next-generation lightweight structural aerospace alloys and alloy products thereof. Optimized processing conditions for enhanced strength or improved ductility can be conducted to establish a viable pathway for scaling-up part geometries with minimal defects. The above Examples demonstrate the extraordinary mechanical property results that can be achieved by combining unconventional processing techniques (AM) or more conventional sintering techniques (e.g., spark plasma sintering) and novel materials (non-equiatom, multi-phase RHEAs). This would enable more direct comparisons of strength and toughness at similar part geometry length scales.

[0057] Although the present invention has been described with respect to certain illustrative embodiments, those skilled in the art will appreciate that modifications and changes can be made therein without departing from the spirit and scope of the invention.

Claims

- 1.** An alloy product, comprising a solidified alloy having Al and Ti as major alloy constituents wherein Al+Ti is greater than 50 atomic % and having Mo, Zr, Nb and optional Ta as minor alloy constituents wherein Ta is optional up to 4 atomic % of the alloy and wherein the minor alloy constituents have a collective content of about 25 atomic % to about 45 atomic % to provide an intermetallic polyphase microstructure.
- 2.** The product of claim 1 wherein Nb is 13 atomic % to 17 atomic % and Ta is 0 to 4 atomic %.
- 3.** The product of claim 1 wherein the intermetallic polyphase microstructure has at least four compositionally distinct intermetallic phases.
- 4.** The product of claim 1 wherein the solidified alloy has an Al content greater than about 20 atomic % to less than about 70 atomic % and an Al+Ti content greater than about 55 atomic % and less than about 75 atomic %.
- 5.** The product of claim 1 wherein the solidified alloy comprises, in atomic %, Al.sub.0.42Ti.sub.0.25Nb.sub.0.17Zr.sub.0.08Mo.sub.0.08 or variants of that composition wherein Al, Ti, Nb, Zr, and/or Mo is/are varied to provide the intermetallic polyphase microstructure.
- 6.** The product of claim 5 wherein the solidified alloy comprises, in atomic %, Al greater than 20% and less than 70 atomic % with Al+Ti greater than 50 atomic %, Nb of 13% to 17%, Zr of 5% to 15%, and Mo of 2% to 8% wherein Nb, Zr, and Mo are present in a collective amount of about 25 atomic % to about 45 atomic %.
- 7.** The product of claim 1 having a hardness of at least 7 GPa.
- 8.** The product of claim 1 wherein the solidified alloy is rapidly solidified.
- 9.** The product of claim 8 which is melt spun material, atomized particles, or 3D printed material.
- 10.** The product of claim 8 which is a laser-beam directed energy deposited material.
- 11.** The product of claim 1 which is an AM structure, an AM layer, or a thermally sprayed layer.
- 12.** An alloy product, comprising sintered alloy particles having Al and Ti as major alloy constituents wherein Al+Ti is greater than 50 atomic % and Mo, Zr, Nb and optional Ta as minor alloy constituents wherein Ta is optional up to 4 atomic % of the alloy and wherein the minor alloy constituents have a collective content of about 25 atomic % to about 45 atomic % to provide an intermetallic polyphase microstructure.
- 13.** The product of claim 12 wherein Nb is 13 atomic % to 17 atomic % and Ta is 0 to 4 atomic %.
- 14.** The product of claim 12 wherein the intermetallic polyphase microstructure has at least four compositionally-distinct intermetallic phases.
- 15.** The product of claim 12 providing a hardness of at least 7 GPa.
- 16.** The product of claim 12 wherein the sintered alloy particles have an Al content greater than about 16 atomic % to less than about 70 atomic % and an Al+Ti content greater than about 55 atomic % and less than about 75 atomic %.
- 17.** The product of claim 12 wherein the sintered alloy particles comprise, in atomic %, Al.sub.0.42Ti.sub.0.25Nb.sub.0.17Zr.sub.0.08Mo.sub.0.08. or variants of that composition that provide the intermetallic polyphase microstructure.
- 18.** The product of claim 17 wherein the sintered alloy particles comprise, in atomic %, Al greater than 20% and less than 70 atomic % with Al+Ti greater than 50 atomic %, Nb of 13% to 17%, Zr of 5% to 15%, and Mo of 2% to 8% wherein Nb, Zr, and Mo are present in a collective amount of about 25 atomic % to about 45 atomic %.
- 19.** Atomized particles comprising a solidified alloy having Al and Ti as major alloy constituents wherein Al+Ti is greater than 50 atomic % and having Mo, Zr, Nb and optional Ta as minor alloy constituents wherein Ta is optional up to 4 atomic % of the alloy and wherein the minor alloy constituents have a collective content of about 25 atomic % to about 45 atomic % to provide an intermetallic polyphase microstructure.
- 20.** The atomized particles of claim 19 wherein the solidified alloy comprises, in atomic %, Al greater than 20% and less than 70 atomic % Al+Ti greater than 50 atomic %, Nb of 13% to 17%, Zr

of 5% to 15%, and Mo of 2% to 8% wherein Nb, Zr, and Mo are present in a collective amount of about 25 atomic % to about 45 atomic %.
