

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250254443

Kind Code

A1

Publication Date

August 07, 2025

Inventor(s)

KABE; Tatsuya et al.

LIGHT DETECTOR

Abstract

A light detector is configured such that a light receiving portion having APDs and a peripheral portion are provided on a first principal surface of a p-type semiconductor substrate, and further includes a back electrode provided on a second principal surface of the semiconductor substrate and a p-type first separation portion provided between the light receiving portion and the peripheral portion. The APD has, on a first principal surface side, an n-type region and a p-epitaxial layer contacting the n-type region in a Z-direction. The peripheral portion has an n-type MISFET provided at a p-well and an n-well provided to surround entire side and bottom portions of the p-well.

Inventors: KABE; Tatsuya (Osaka, JP), ARAI; Hideyuki (Osaka, JP), AIKAWA; Hisashi (Hyogo, JP), SUGIURA; Yuki (Osaka, JP), INOUE; Akito (Osaka, JP), MORI; Mitsuyoshi (Kyoto, JP), NAKANISHI; Kentaro (Nara, JP), SAKATA; Yusuke (Osaka, JP)

Applicant: Panasonic Intellectual Property Management Co., Ltd. (Osaka, JP)

Family ID: 72610505

Appl. No.: 19/186181

Filed: April 22, 2025

Foreign Application Priority Data

JP	2019-063298	Mar. 28, 2019
----	-------------	---------------

Related U.S. Application Data

parent US continuation 17486495 20210927 parent-grant-document US 11889215 child US 18541932

parent WO continuation PCT/JP2020/010235 20200310 PENDING child US 17486495

parent US division 18541932 20231215 parent-grant-document US 12328518 child US 19186181

Publication Classification

Int. Cl.: H04N25/766 (20230101); H10F39/00 (20250101); H10F39/18 (20250101)

U.S. Cl.:

CPC H04N25/766 (20230101); H10F39/18 (20250101); H10F39/8037 (20250101);
H10F39/811 (20250101);

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATIONS [0001] This is a Divisional of U.S. patent application Ser. No. 18/541,932, filed on Dec. 15, 2023, which is a Continuation of U.S. patent application Ser. No. 17/486,495, filed on Sep. 27, 2021, now U.S. Pat. No. 11,889,215, which is a Continuation of International Application No. PCT/JP2020/010235, filed on Mar. 10, 2020, which claims priority to Japanese Patent Application No. 2019-063298, filed on Mar. 28, 2019. The entire disclosures of these applications are incorporated by reference herein.

BACKGROUND

[0002] The present disclosure relates to a light detector, and particularly relates to a light detector including avalanche photodiodes.

[0003] In recent years, in a wide variety of fields such as medical treatment, communication, biology, chemistry, monitoring, vehicle installation, and radiation detection, a highly-sensitive light detector has been utilized. As one technique for sensitivity enhancement, an avalanche photodiode (hereinafter referred to as an “APD”) has been used. The APD is a photodiode configured to multiply a signal charge, which is generated by photoelectric conversion of light having entered a photoelectric conversion layer, by means of avalanche breakdown to enhance light detection sensitivity. With the APD, even a slight number of photons can be detected.

[0004] Japanese Unexamined Patent Publication No. 2017-005276 discloses an APD array having a separation region between adjacent APDs.

[0005] Such a separation region includes a p-type semiconductor layer extending inward of a principal surface of a semiconductor substrate, and the potential of the p-type semiconductor layer is the same as that of the semiconductor substrate, i.e., a ground potential (hereinafter referred to as a GND potential). Moreover, an n-type field-effect transistor (hereinafter referred to as an n-type MISFET) is provided inside the p-type semiconductor layer. Further, an n-type well is formed in a region of the p-type semiconductor layer or a region between the APDs, and in such an n-type well, a p-type field-effect transistor (hereinafter referred to as a p-type MISFET) is provided.

[0006] In a light detector configured such that a light receiving portion formed with APDs and a peripheral circuit portion configured to exchange a signal with the light receiving portion are formed on the same semiconductor substrate, a configuration in which the layout of the peripheral circuit portion can be freely set has been demanded for enhancing the degree of freedom in circuit design.

[0007] However, the typical configuration disclosed in Japanese Unexamined Patent Publication No. 2017-005276 fails to provide the technique of arranging a CMOS circuit and other circuits outside the APD array in optional layout.

[0008] The present disclosure has been made in view of the above-described point, and an object of the present disclosure is to provide a light receiving portion configured such that a light receiving portion having one or more avalanche photodiodes and a peripheral circuit portion configured to exchange a signal with the light receiving portion are provided on a principal surface of the same

semiconductor substrate and configured so that the degree of freedom in the layout of the peripheral circuit portion can be enhanced.

SUMMARY

[0009] For accomplishing the above-described object, the light detector according to the present disclosure is a light detector in which a light receiving portion and a peripheral portion are provided on a semiconductor substrate. The light receiving portion includes: an n-type first region; a p-type second semiconductor layer; and a p-type first semiconductor layer. The first region, the second semiconductor layer, and the first semiconductor layer are stacked in this order. A maximum p-type impurity concentration in the first semiconductor layer is higher than a maximum p-type impurity concentration in the second semiconductor layer. The peripheral portion includes: a p-type first well; an n-type third well; and the first semiconductor layer. The third well surrounds entire side and bottom portions of the first well as viewed in a section.

[0010] According to the light detector of the present disclosure, the light receiving portion and the peripheral circuit portion can be electrically separated from each other, and the layout of the peripheral circuit portion relative to the light receiving portion can be freely changed.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

[0011] FIG. 1 is a schematic plan view of a light detector according to one embodiment.

[0012] FIG. 2 is a schematic sectional view along an II-II line of FIG. 1.

[0013] FIG. 3A is a schematic sectional view along an IIIA-IIIA line of FIG. 1.

[0014] FIG. 3B is a schematic sectional view along an IIIB-IIIB line of FIG. 1.

[0015] FIG. 3C is a schematic sectional view along an IIIC-IIIC line of FIG. 1.

[0016] FIG. 4 is a schematic sectional view of a light detector according to a first variation.

[0017] FIG. 5 is a schematic sectional view of a light detector according to a second variation.

[0018] FIG. 6 is a schematic sectional view of a light detector according to a third variation.

[0019] FIG. 7 is a schematic sectional view of a light detector according to a fourth variation.

DETAILED DESCRIPTION

[0020] Hereinafter, an embodiment of the present disclosure will be described in detail with reference to the drawings. Description of the preferred embodiment below is merely illustrative in nature, and is not intended to limit the present disclosure and applications or uses thereof.

Embodiment

[Configuration of Light Detector]

[0021] FIG. 1 shows a plan view of a light detector according to the present embodiment, and FIG. 2 shows a schematic sectional view along an II-II line of FIG. 1. Note that for the sake of convenience in description, a circuit configuration in a pixel **110** and a connection relationship between a light receiving portion **100** and a peripheral circuit portion **200** are not shown in the figure. Moreover, FIG. 2 shows only part of the peripheral circuit portion **200**. Further, a contact and a wire connected to a transistor in the peripheral circuit portion **200** are not shown in the figure, and description thereof will be omitted.

[0022] Note that in the light detector **1000**, a side on which a wire (hereinafter referred to as a first wiring layer **520**) in a first layer is provided will be sometimes referred to as an upper side and a side on which a back electrode **300** is provided will be sometimes referred to as a lower side. FIG. 2 does not show a wiring layer and an insulating layer positioned on the upper side with respect to the first wiring layer **520**, and description of these layers will be omitted.

[0023] As shown in FIG. 1, the light detector **1000** includes the light receiving portion **100** and the peripheral circuit portion **200**, and these portions are provided on a first principal surface S1 of a p-type semiconductor substrate **10** (hereinafter sometimes merely referred to as a substrate **10**) (see

FIG. 2). Note that in the present embodiment, the substrate **10** is made of single-crystal silicon.

[0024] In description below, a row direction of the pixels **110** in FIG. **1** will be sometimes referred to as an X-direction, and a column direction of the pixels **110** will be sometimes referred to as a Y-direction. Moreover, a direction perpendicular to each of the X-direction and the Y-direction, i.e., a depth direction of the substrate **10** in this case, will be sometimes referred to as a Z-direction.

[0025] A plurality of pad electrodes **550** is provided at predetermined intervals at the periphery of the light detector **1000**, and power-supply voltage supplied to the light receiving portion **100** and the peripheral circuit portion **200** is supplied from the outside through a predetermined pad electrode **550**. Note that a later-described n-well **21** is continuously formed on a first principal surface **S1** side of the substrate **10** positioned on the lower side of the pad electrode **550** and is electrically connected to a power supply of a predetermined voltage V_{dd2} through the pad electrode **550**.

[0026] The light receiving portion **100** is a so-called pixel array in which the pixels **110** are arrayed in a matrix at predetermined intervals, and the position of a peripheral edge (hereinafter sometimes referred to as a pixel array end **101**) of the light receiving portion **100** is determined within the first principal surface **S1**. Moreover, the size of the pixel **110** and an interval between adjacent pixels **110** are also fixed. That is, the light receiving portion **100** is configured as a pixel array whose layout is fixed. On the other hand, the layout of the peripheral circuit portion **200** of the present embodiment can be freely changed. This will be described later.

[0027] As described in detail later, the pixel **110** has an APD **111** and a pixel circuit portion **112** electrically connected to the APD **111** to read a signal charge generated at the APD **111**.

[0028] The peripheral circuit portion **200** is arranged at the periphery of the light receiving portion **100**, and has a vertical scanning circuit **210**, a horizontal scanning circuit **230**, a readout circuit **220**, and a buffer amplifier **240**. As described above, the peripheral circuit portion **200** may include a circuit other than above. For example, in a case where a column analog-digital converter (not shown in the figure, and hereinafter sometimes referred to as a column ADC) is provided in the readout circuit **220**, a digital-analog converter (not shown in the figure) may be provided at the peripheral circuit portion **200**.

[0029] The vertical scanning circuit **210** operates pixel circuit portions **112** of a selected row to output signal charges generated at APDs **111** of such a row to the readout circuit **220** through not-shown vertical signal lines. The readout circuit **220** is a circuit configured to remove a noise component contained in the input signal charge or convert the signal charge as an analog signal into a digital signal. The signal transferred to the readout circuit **220** is transferred to the buffer amplifier **240** by drive of the horizontal scanning circuit **230**, and is output to a not-shown signal processing circuit at a subsequent stage. After having been subjected to signal processing such as white balance in the signal processing circuit, the signal is transferred to a display (not shown in the figure), a memory (not shown in the figure), etc., and light received by the light receiving portion **100** is, for example, converted into an image.

[0030] An image is captured while a voltage to be applied to the back electrode **300** is switched for each frame, and these images are synthesized so that a video with a wide dynamic range can be captured.

[0031] Next, the structures of the pixel **110** and the peripheral circuit portion **200** will be further described.

[0032] As shown in FIG. **2**, the substrate **10** includes a p-type semiconductor layer (a first semiconductor layer) **11** and a p-epitaxial layer (a second semiconductor layer) **12** stacked on the p-type semiconductor layer **11**, and the back electrode **300** is provided across the entirety of a second principal surface **S2** of the substrate **10**. A p-type impurity concentration in the p-epitaxial layer **12** is about 1×10^{16} cm⁻³. Note that the concentration is not limited to above and the value thereof may be changed as necessary. Moreover, a p-type impurity concentration in the p-type semiconductor layer **11** is higher than that of the p-epitaxial layer **12**. Particularly, in the vicinity of

the second principal surface **S2**, such a concentration that the second principal surface **S2** can be in ohmic contact with the back electrode **300**, such as about $1 \times 10^{18} \text{ cm}^{-3}$ is preferred.

[0033] The APD **111** includes an n-type region (a first region) **20** provided to extend inward of the substrate **10** from the first principal surface **S1** and the p-epitaxial layer (a second region) **12** positioned on the lower side of the n-type region **20**. An n-type impurity concentration in the n-type region **20** is set to about $5 \times 10^{16} \text{ cm}^{-3}$ to about $1 \times 10^{19} \text{ cm}^{-3}$.

[0034] By application of negative voltage to the back electrode **300**, a pn junction formed at an interface between the n-type region **20** and the p-epitaxial layer **12** is brought into a reverse bias state, and a multiplication region AM is formed. The multiplication region AM is a region where a charge generated by photoelectric conversion of received light ($h\nu$ shown in FIG. 2) is multiplied by avalanche multiplication.

[0035] When electrons generated by photoelectric conversion in the p-epitaxial layer **12** positioned on the lower side of the multiplication region AM reach the multiplication region AM by drift, a carrier number is multiplied by 1 to 100,000 by avalanche multiplication. At this point, electrons generated by avalanche multiplication are accumulated in the n-type region **20**. Moreover, holes generated at the same time as generation of the electrons are drifted to the back electrode **300**, and are discharged to the outside of the light detector **1000**, i.e., the outside of the substrate **10**, through the back electrode **300**.

[0036] Accordingly, holes not utilized as signals are discharged to the outside of the light detector **1000** in a short period of time so that time variation in voltage and spatial non-uniformity in the light detector **1000** can be reduced. Thus, a light detection efficiency is improved.

[0037] The pixel circuit portion **112** is arranged with a predetermined interval L2 from the APD **111** in the X-direction, and has a p-well (a fourth well) **17** provided to extend inward of the substrate **10** from the first principal surface **S1**, an n-well (a fifth well) **23** provided to surround side and bottom portions of the p-well **17**, and a n-type MISFET (a third transistor) provided at the p-well **17**.

[0038] The n-well **23** is formed at the substrate **10** such that a depth from the first principal surface **S1** is equal to or greater than that of the n-type region **20**. Note that the depth of the n-type region **20** is set to about $2 \mu\text{m}$. Moreover, the n-well **23** has different n-type impurity concentrations between a portion (hereinafter sometimes referred to as a side portion **23a** of the n-well **23**) surrounding the side portion of the p-well **17** and a portion (hereinafter sometimes referred to as a bottom portion **23b** of the n-well **23**) extending inward of the substrate **10** in contact with the bottom portion of the p-well **17**, and the n-type impurity concentration in the side portion **23a** of the n-well **23** is higher than the n-type impurity concentration in the bottom portion **23b**. Note that various methods for changing the impurity concentration between the side portion **23a** and the bottom portion **23b** of the n-well **23** have been known. For example, an n-type impurity may be ion-implanted into the entire region of the n-well **23** by means of a not-shown resist mask, and may be additionally implanted into a region corresponding to the side portion **23a** of the n-well **23** by means of another resist mask. Alternatively, phosphorus may be implanted into the substrate **10** and arsenic may be implanted into the first principal surface **S1** side by means of the same resist mask, and these substances may be thermally diffused to form the n-well **23**. In this case, the coefficient of thermal diffusion of phosphorus is higher than that of arsenic, and for this reason, an impurity profile becomes moderate and a field intensity near the bottom portion **23b** decreases. Note that through a not-shown contact, the n-well **23** is fixed to a predetermined potential such as V_{dd2} ($=3.3 \text{ V}$).

[0039] The n-type MISFET **40** has at least an n-type source **42** and a drain **43** provided at the first principal surface **S1** and a gate **41** provided between the n-type source **42** and the drain **43** at the first principal surface **S1** through a gate insulating layer (not shown in the figure) provided on the first principal surface **S1**.

[0040] The n-type region **20** is electrically connected to the drain **43** of the n-type MISFET through a first contact **51**, the first wiring layer **520**, and a second contact **52**, and the n-type source **42** of

the n-type MISFET **40** is electrically connected to a first circuit block **260** of the readout circuit **220** through a third contact **53** and the first wiring layer **520**. Electrons accumulated in the n-type region **20** are transferred to the readout circuit **220** (see FIG. **1**) in such a manner that the n-type MISFET **40** is turned on, and the light detector **1000** detects light having entered the light receiving portion **100** and outputs an electric signal.

[0041] A p-type second separation portion **16** is provided between the n-type region **20** and the side portion **23a** of the n-well **23**. The second separation portion **16** is provided to extend inward of the substrate **10** from the first principal surface **S1**. The depth of the second separation portion **16** is shallower than that of the n-type region **20**, and in the present embodiment, is about 1 μm which is about the half of the depth of the n-type region **20**. Note that the depth is not limited to above and may be another value as necessary.

[0042] A p-type impurity concentration in the second separation portion **16** is set to about $1 \times 10^{16} \text{ cm}^{-3}$ to about $1 \times 10^{18} \text{ cm}^{-3}$. Note that the p-type impurity concentration in the second separation portion **16** is set lower than p-type impurity concentrations in the p-well (the fourth well) **17**, a later-described first separation portion **13**, a later-described p-well (a first well) **14**.

[0043] The n-type region **20** and the side portion **23a** of the n-well **23** are provided with the above-described interval **L2** in a direction parallel with the first principal surface **S1**, such as the X-direction, and the width of the second separation portion **16** is set smaller than the interval **L2**. That is, a structure is employed, in which the p-epitaxial layer **12**, the p-type second separation portion **16**, and the p-epitaxial layer **12** are arranged between the n-type region **20** and the side portion **23a** of the n-well **23** in the X-direction. Note that although not shown in the figure, even in a case where the APDs **111** are adjacent to each other, the second separation portion **16** is provided between these adjacent APDs **111** and a structure in which the p-epitaxial layer **12**, the p-type second separation portion **16**, and the p-epitaxial layer **12** are arranged is employed between these APDs **111**.

[0044] The p-type first separation portion **13** is provided between the light receiving portion **100** and the first circuit block **260** of the readout circuit **220**. The first separation portion **13** is provided to extend inward of the substrate **10** from the first principal surface **S1**, and the depth thereof is deeper than those of the second separation portion **16** and the p-well (the first well) **14** provided at the first circuit block **260** and shallower than that of the n-well (the third well) **21** provided at the first circuit block **260**. In the present embodiment, the depth of the first separation portion **13** is set to about 1.3 μm . Note that the depth is not limited to above and may be another value as necessary.

[0045] In the X-direction, the light receiving portion **100** and the first separation portion **13** are provided with an interval of equal to or greater than 1 μm . Similarly, the first separation portion **13** and the n-well **21** of the first circuit block **260** are provided with an interval of equal to or greater than 1 μm . The width of the first separation portion **13** is set to equal to or greater than 0.3 μm . Note that the width is not limited to above and may be another value as necessary.

[0046] A structure is employed, in which the p-epitaxial layer **12**, the p-type first separation portion **13**, and the p-epitaxial layer **12** are arranged between the light receiving portion **100** and the first circuit block **260** of the readout circuit **220** in the X-direction. On the first principal surface **S1** side of the p-epitaxial layer **12**, a shallow trench isolation (STI) **60** having a predetermined depth such as a depth of 0.3 μm to 0.5 μm is formed. The STI **60** is an element separation layer obtained in such a manner that after the substrate **10** has been dug from the first principal surface **S1** to form a groove portion and predetermined treatment has been performed for a surface of the groove portion, the groove portion is filled with a silicon oxide film and planarization is performed by chemical mechanical polishing (CMP). The STI **60** is formed to surround the first separation portion **13**, specifically cover a peripheral edge of the first separation portion **13**, as viewed from above.

[0047] The first circuit block **260** is, for example, a correlated double sampling circuit (hereinafter

sometimes referred to as a CDS circuit) configured to remove the noise component of the signal charge generated at the APD **111**, and is an analog circuit block. Note that the first circuit block **260** is not limited to above and other circuits such as a gain adjustment circuit may be employed.

[0048] The first circuit block **260** has the p-well (the first well) **14** provided to extend inward of the substrate **10** from the first principal surface **S1**, the n-well (the third well) **21** provided to surround side and bottom portions of the p-well **14**, and an n-type MISFET (a first transistor) provided at the p-well **14**.

[0049] The n-well **21** has the same level of depth as that of the n-well **23** of the pixel circuit portion **112**. Moreover, the n-well **21** has different n-type impurity concentrations between a portion (hereinafter sometimes referred to as a side portion **21a** of the n-well **21**) surrounding the side portion of the p-well **14** and a portion (hereinafter sometimes referred to as a bottom portion **21b** of the n-well **21**) extending inward of the substrate **10** in contact with the bottom portion of the p-well **14**, and the n-type impurity concentration in the side portion **21a** of the n-well **21** is higher than the n-type impurity concentration in the bottom portion **21b**. With this configuration, occurrence of punch-through among the p-well **14**, the n-well **21**, and the first separation portion **13** can be reduced.

[0050] In the X-direction and the Y-direction, the bottom portion **21b** of the n-well **21** is formed to extend outward of the side portion **21a**, and the amount **L3** of such protrusion is about 0.5 μm to about 0.7 μm . Note that the amount is not limited to above and may be another value as necessary. Note that the method for changing the impurity concentration between the side portion **21a** and the bottom portion **21b** of the n-well **21** is as in description of the method for forming the n-well **23** of the pixel circuit portion **112**.

[0051] The p-well **14** has the same level of depth and the same level of p-type impurity concentration as those of the p-well **17** of the pixel circuit portion **112**. Note that each of p-type impurity concentrations in the p-well **14** of the first circuit block **260**, a p-well **15** of a later-described second circuit block **270**, and the p-well **17** of the pixel circuit portion **112** is set higher than a p-type impurity concentration in the first separation portion **13**.

[0052] The n-type MISFET **30** has at least n-type source and drain **32, 32** provided at the first principal surface **S1** and a gate **31** provided between the source and the drain **32, 32** at the first principal surface **S1** through a gate insulating layer (not shown in the figure).

[0053] On the first principal surface **S1** side of the gate **31** and the source and the drain **32, 32** of the n-type MISFET **30**, a silicide layer **70** as a conductor layer is formed. The above-described STI **60** is formed at a boundary portion between the p-well **14** and the n-well **21**, and the silicide layer **70** is also formed on the first principal surface **S1** side of the side portion **21a** of the n-well **21** surrounded by the STI **60**. The silicide layer **70** is formed in a self-aligned manner by a so-called salicide technique.

[0054] The n-well **21** is electrically connected to the first wiring layer **520** through the silicide layer **70** and a first well contact **54**. The first wiring layer **520** is electrically connected to the power supply of the predetermined voltage **Vdd2**, and in the present embodiment, **Vdd2** is 3.3 V. Note that **Vdd2** is not limited to above and may be another value as necessary. The p-well **14** is electrically connected to a GND potential through a not-shown well contact.

[0055] The readout circuit **220** further has the second circuit block **270**, and the second circuit block **270** is, for example, a digital circuit block such as a counter of the column ADC provided for each column. Note that the second circuit block **270** is not limited to above and may be other circuits.

[0056] The second circuit block **270** has the p-well (the first well) **15**, the n-well (the third well) **21**, and an n-type MISFET (a first transistor) **33** provided at the p-well **15**. The n-type MISFET **33** has at least n-type source and drain **35, 35** provided at the first principal surface **S1** and a gate **34** provided between the source and the drain **35, 35** at the first principal surface **S1** through a gate insulating layer (not shown in the figure). The n-well **21** of the second circuit block **270** has a

depth, an impurity concentration, and a sectional profile similar to those of the n-well **21** of the first circuit block **260**. The protrusion amount **L3** of the bottom portion **21b** is also similar to that of the n-well **21** of the first circuit block **260**.

[0057] Moreover, the second circuit block **270** has another n-well (a second well) **22** provided inside the n-well (the third well) **21** and a p-type MISFET (a second transistor) **36** provided at the n-well **22**. The n-well (the second well) **22** is, in the X-direction, provided at the substrate **10** in contact with the p-well (the first well) **15**.

[0058] The p-type MISFET **36** has at least p-type source and drain **38, 38** provided at the first principal surface **S1** and a gate **37** provided between the source and the drain **38, 38** at the first principal surface **S1** through a gate insulating layer (not shown in the figure). On the first principal surface **S1** side of the gate **37** and the source and the drain **38, 38** of the p-type MISFET **36**, the silicide layer **70** is formed. The STI **60** is formed at a boundary portion between the p-well **15** and the n-well **21, 22**.

[0059] The n-well **21** is electrically connected to the first wiring layer **520** through the silicide layer **70** and a second well contact **55**. The first wiring layer **520** is electrically connected to a power supply of a predetermined voltage **Vdd1**, and in the present embodiment, **Vdd1** is 1.2 V. Note that **Vdd1** is not limited to above and may be another value as necessary. The p-well **15** is electrically connected to the GND potential through a not-shown well contact. The n-well **22** has the same potential as that of the n-well **21**.

[0060] Note that the first circuit block **260** and the second circuit block **270** are different from each other in **Vdd1**, **Vdd2** equivalent to the drive voltage of the transistor. Thus, for optimizing performance of the transistor provided at each block, the p-well **14** of the first circuit block **260** and the p-well **15** of the second circuit block **270** may be different from each other in a depth or an impurity profile, for example. Note that as long as performance required for the p-type MISFET **36** is satisfied, the p-type MISFET **36** may be, instead of the n-well **22**, provided on the first principal surface **S1** side of the side portion **21a** of the n-well **21** at the second circuit block **270**.

[0061] The above-described first separation portion **13** is provided between the first circuit block **260** and the second circuit block **270**. In the X-direction, the first circuit block **260** and the second circuit block **270** are provided with the interval **L1**. Specifically, the n-well **21** of the first circuit block **260** is provided with an interval of equal to or greater than 1 μm from the first separation portion **13**. The first separation portion **13** is provided with an interval of equal to or greater than 1 μm from the n-well **21** of the second circuit block **270**. The width of the first separation portion **13** is set to equal to or greater than 0.3 μm . Note that these values are not limited to above and may be other values as necessary.

[0062] A structure is employed, in which the p-epitaxial layer **12**, the p-type first separation portion **13**, and the p-epitaxial layer **12** are arranged between the first circuit block **260** and the second circuit block **270** in the X-direction. On the first principal surface **S1** side of the p-epitaxial layer **12**, the STI **60** having the predetermined depth is formed. The STI **60** is formed to surround the first separation portion **13**, specifically cover the peripheral edge of the first separation portion **13**, as viewed from above.

[0063] Note that other circuit blocks may be provided inside the readout circuit **220**. In this case, each circuit block also has the n-well **21**, and the first separation portion **13** is provided between adjacent circuit blocks. The first separation portion **13** and the n-well **21** of the circuit block adjacent thereto are provided with a predetermined interval such as an interval of equal to or greater than 1.0 μm . As viewed from above, the STI **60** is formed to surround the periphery of the first separation portion **13**. Moreover, the first separation portion **13** is provided between the readout circuit **220** and the horizontal scanning circuit **230** and between the light receiving portion **100** and the vertical scanning circuit **210** with a predetermined interval from these elements. As viewed from above, the STI **60** is formed to surround the periphery of the first separation portion **13**, specifically the peripheral edge of the first separation portion **13**.

[0064] Note that no silicide layer **70** is formed on the first principal surface **S1** side of any first separation portion **13** and such a first separation portion **13** is directly covered with an insulating layer **500** containing silicon oxide as a main component and is formed with no well contact.

[0065] As shown in FIG. **2**, a plurality of pn junctions is formed inside the substrate **10**. Focusing on the inside of the pixel **110**, in a case where predetermined negative voltage is applied to the back electrode **300**, the interface between the n-type region **20** and the p-epitaxial layer **12** and an interface between the p-well **17** and the n-well **23** are brought into the reverse bias state, and a depletion layer is formed. In this case, an end portion (hereinafter merely referred to as a depletion layer end) of the depletion layer is formed to extend longer on a p-epitaxial layer **12** side with a lower impurity concentration. Note that FIG. **2** shows the depletion layer end formed at each pn junction by a dashed line.

[0066] In the light detector **1000** described in the present embodiment, the impurity concentrations of the n-type region **20** and the n-well **23** of the pixel circuit portion **112**, the impurity concentrations of the p-epitaxial layer **12** and the second separation portion **16**, the interval **L2** between the n-type region **20** and the n-well **23**, and the width and depth of the second separation portion **16** are properly set, and accordingly, a portion between the n-type region **20** and the n-well **23** is depleted, the potential of such a region is destabilized, and the depletion layer end does not reach the first principal surface **S1**. With this configuration, the interval between the APD **111** and the pixel circuit portion **112** can be narrowed while these elements are electrically separated from each other. Moreover, the size of the pixel **110** can be decreased.

[0067] Focusing on a portion between the first circuit block **260** and the second circuit block **270**, the interface between the n-well **21** and the p-epitaxial layer **12** is in the reverse bias state, and therefore, the depletion layer is formed to extend from such an interface. The first separation portion **13** having a higher impurity concentration than those of the p-epitaxial layer **12** and the second separation portion **16** is provided between the first circuit block **260** and the second circuit block **270**, and the interval between each circuit block and the first separation portion **13** is set to equal to or greater than the predetermined value. With this configuration, a depletion layer extending from an interface between the n-well **21** of the first circuit block **260** and the p-epitaxial layer **12** and a depletion layer extending from an interface between the n-well **21** of the second circuit block **270** and the p-epitaxial layer **12** are formed not to overlap with each other in the X-direction. In the Z-direction, a depletion layer end of the former and a depletion layer end of the latter reach the first principal surface **S1**.

[0068] The depletion layers are formed as described above, a field intensity between the first circuit block **260** and the second circuit block **270** in the X-direction and the Y-direction can be reduced and the first circuit block **260** and the second circuit block **270** can be reliably electrically separated from each other. With this configuration, even in operation of the APD **111**, the first circuit block **260** and the second circuit block **270** can be independently driven. The first circuit block **260** and the second circuit block **270** can be electrically separated from each other without full depletion of a portion therebetween, and therefore, the layout of each block can be freely changed. Moreover, noise between the circuit blocks can be blocked.

[0069] A depletion layer similar to that between the first circuit block **260** and the second circuit block **270** is also formed between the light receiving portion **100** and the first circuit block **260**. Thus, the light receiving portion **100**, specifically the pixel array end **101**, and the first circuit block **260** can be reliably electrically separated from each other. Moreover, the light receiving portion **100** and the first circuit block **260** can be electrically separated from each other without full depletion of a portion therebetween, and therefore, the layout of the first circuit block **260** relative to the light receiving portion **100**, specifically the pixel array end **101**, can be freely changed.

[Structure of Portion below Pad Electrode]

[0070] FIG. **3A** shows a schematic sectional view along an IIIA-IIIA line of FIG. **1**, FIG. **3B** shows a schematic sectional view along an IIIB-IIIB line, and FIG. **3C** shows a schematic sectional view

along an IIIC-IIIC line. Note that for the sake of convenience in description, the p-type semiconductor layer **11** and the back electrode **300** are not shown in the figure.

[0071] In a typical semiconductor device, a chip has been formed with as many dummy gate patterns as possible for effectively reducing uneven gate etching, uneven CMP for planarizing an interlayer insulating layer, and a proximity effect in lithography.

[0072] With miniaturization of a transistor, the thickness of the interlayer insulating layer has been decreased in the typical semiconductor device. However, in this case, an interval between a wiring layer positioned on the lower side of a pad electrode and the dummy gate pattern is narrowed, and the potential of the dummy pattern become unstable when current flows in the wiring layer.

Depending on conditions, there is a probability that short-circuit between the dummy gate pattern and a substrate is caused due to damage of a gate insulating layer (not shown in the figure) right below the dummy pattern. Moreover, there is also a probability that the interlayer insulating layer between the wire and the dummy gate pattern is damaged.

[0073] For these reasons, in the present embodiment, as shown in FIGS. **3A** to **3C**, the n-well **21** is continuously formed on the first principal surface **S1** side of the substrate **10** positioned on the lower side of the pad electrodes **550**, and the n-well **21** is electrically connected to the power supply of the voltage **Vdd2** such that the potential thereof is fixed. With this configuration, the potential of a dummy gate pattern (hereinafter referred to as a dummy gate **400**) can be stabilized, and, e.g., short-circuit between such a pattern and the substrate **10** can be prevented. Moreover, the dummy gates **400** are provided at predetermined pitches on the lower side of the pad electrodes **550**, and therefore, uneven gate etching, an uneven thickness of the interlayer insulating layer after CMP, and the proximity effect in lithography can be reduced.

[0074] Note that FIGS. **3A** to **3C** show a structure in which the first and second wiring layers **520**, **540**, a well contact array **510** electrically connecting the first wiring layer **520** and the silicide layer **70** to each other, and a via array **530** electrically connecting the first wiring layer **520** and the second wiring layer **540** to each other are provided among the pad electrodes **550** and the dummy gates **400**, but the present disclosure is not limited to above and three or more wiring layers may be provided. Moreover, a passivation film **560** covering a peripheral edge of the pad electrode **550** is preferably a film containing a silicon nitride film as a main component, but may be made of a material such as a silicon oxide film. Entrance of moisture into the light detector **1000** can be reduced, and mechanical protection of the light detector **1000** can be provided. The passivation film **560** more preferably has a multilayer structure (not shown in the figure) of a first film containing a silicon nitride film as a main component and a second film containing polyimide as a main component, but the first film may be made of a material such as a silicon oxide film.

Advantageous Effects Etc

[0075] As described above, the light detector **1000** according to the present embodiment is the light detector **1000** configured such that the light receiving portion **100** having the plurality of APDs **111** arranged in a matrix at the predetermined intervals and the peripheral circuit portion **200** configured to exchange a signal with the light receiving portion **100** are provided on the first principal surface **S1** of the p-type substrate **10**.

[0076] The light detector **1000** includes at least the back electrode **300** provided on the second principal surface **S2** of the substrate **10** facing the first principal surface **S1** and configured to apply the predetermined voltage to the substrate **10** and the p-type first separation portion **13** provided between the light receiving portion **100** and the peripheral circuit portion **200** with the predetermined interval from the light receiving portion **100** and the peripheral circuit portion **200** in the X-direction.

[0077] The APD **111** has at least the n-type region (the first region) **20** provided to extend inward of the substrate **10** from the first principal surface **S1** and the p-epitaxial layer (the second region) **12** provided in contact with the n-type region **20** in the Z-direction.

[0078] The peripheral circuit portion **200** has at least the p-well (the first well) **14** provided to

extend inward of the substrate **10** from the first principal surface **S1**, the n-type MISFET (the first transistor) **30** provided at the p-well **14**, and the n-well (the third well) **21** provide to surround the side and bottom portions of the p-well **14**.

[0079] With this configuration of the light detector **1000**, in a case where the predetermined voltage is applied to the back electrode **300** and the APDs **111** are operated, a field intensity between the light receiving portion **100** and the peripheral circuit portion **200** in the direction parallel with the first principal surface **S1** can be reduced, and the light receiving portion **100** and the peripheral circuit portion **200** can be reliably electrically separated from each other. Moreover, the light receiving portion **100** and the peripheral circuit portion **200** can be electrically separated from each other without full depletion of a portion therebetween, and therefore, the layout of the peripheral circuit portion **200** relative to the light receiving portion **100** can be freely changed.

[0080] The peripheral circuit portion **200** includes the plurality of circuit blocks, and the first separation portion **13** is provided between the circuit blocks adjacent to each other in the direction parallel with the first principal surface **S1** with the predetermined interval from each circuit block. At least one of the plurality of circuit blocks has at least the p-well (the first well) **15**, the n-type MISFET (the first transistor) **33**, and the n-well (the third well) **21**.

[0081] With this configuration of the peripheral circuit portion **200**, in a case where the APDs **111** are operated, the field intensity between adjacent circuit blocks can be reduced, and these circuit blocks can be reliably electrically separated from each other. Moreover, adjacent circuit blocks can be electrically separated from each other without full depletion of a portion therebetween, and therefore, the layout of each circuit block can be freely changed.

[0082] At least two of the plurality of circuit blocks may be driven by application of different voltages. In a case where, e.g., the sizes of the transistors provided at the circuit blocks are different from each other, the drive voltages are properly set so that each circuit block can be accurately operated.

[0083] The plurality of circuit blocks may include a digital circuit block formed with a digital circuit and an analog circuit block formed with an analog circuit.

[0084] As viewed from above, the STI **60** is formed between the light receiving portion **100** and the n-well (the third well) **21** of the peripheral circuit portion **200** and between the n-wells (the third wells) **21** of adjacent circuit blocks to surround the first separation portion **13**, specifically cover the peripheral edge of the first separation portion **13**.

[0085] With this configuration, in a case where the APDs **111** are operated, even if the depletion layer end reaches the first principal surface **S1** of the substrate **10**, the flow of leakage current along the first principal surface **S1** can be reduced.

[0086] As viewed in the section, the bottom portion **21b** of the n-well (the third well) **21** is preferably provided to extend outward of the side portion **21a** of the n-well (the third well) **21**. With this configuration, a field intensity at a peripheral edge portion of the n-well **21** in the substrate **10** can be reduced, and the light receiving portion **100** and the peripheral circuit portion **200** or adjacent circuit blocks can be reliably electrically separated from each other. Note that the protrusion amount **L3** of the bottom portion **21b** with respect to the side portion **21a** of the n-well **21** may be changed as necessary according to, e.g., the size of the peripheral circuit portion **200** or the degree of separation between adjacent circuit blocks.

[0087] Of the circuit blocks having the p-wells (the first wells) **15**, the n-type MISFETs (the first transistors) **33**, and the n-wells (the third wells) **21**, at least one circuit block has the n-well (the second well) **22** provided inside the n-well (the third well) **21** in contact with the p-well (the first well) **15** in the direction parallel with the first principal surface **S1** and the p-type MISFET (the second transistor) **36** provided at the n-well (the second well) **22**.

[0088] With this configuration, a circuit block including a CM OS circuit can be arranged in the light detector **1000**.

[0089] The potentials of the p-wells (the first wells) **14**, **15** are fixed to the GND potential (a first

potential), and the potential of the n-well (the third well) **21** is fixed to the potential (a second potential) different from the GND potential, such as Vdd1 (=1.2 V) or Vdd2 (=3.3 V). Moreover, the potential of the n-well (the second well) **22** and the potential of the n-well (the third well) **21** are the same potential.

[0090] With this configuration, the n-type MISFETs (the first transistors) **30**, **33** and the p-type MISFET (the second transistor) **36** each formed at the p-wells (the first wells) **14**, **15** and the n-well (the second well) **22** can be accurately operated.

[0091] The substrate **10** includes at least the p-type semiconductor layer (the first semiconductor layer) **11** and the p-epitaxial layer (the second semiconductor layer) **12** provided on the first principal surface S1 side of the p-type semiconductor layer **11**, and the p-type impurity concentration in the p-epitaxial layer **12** is lower than the p-type impurity concentration in the p-type semiconductor layer **11**.

[0092] With this configuration, the p-type semiconductor layer **11** and the back electrode **300** are in electric contact (ohmic contact) with each other, and holes generated in the p-epitaxial layer **12** by photoelectric conversion move to the multiplication region AM by drift without great scattering of the holes. Accordingly, the multiplication factor of electrons generated in the multiplication region AM is enhanced.

[0093] The light receiving portion **100** further has the pixel circuit portions **112** each provided with the predetermined interval from the APDs **111** in the X-direction. The pixel circuit portion **112** at least has the p-well (the fourth well) **17** provided to extend inward of the substrate **10** from the first principal surface S1, the n-type MISFET (the third transistor) **40** provided at the p-well **17**, and the n-well (the fifth well) **23** provided to surround the side and bottom portions of the p-well **17**.

[0094] With this configuration of the light receiving portion **100**, the output signal of the APD **111** can be transferred to the outside such as the readout circuit **220**.

[0095] The p-type second separation portion **16** is further provided between the APD **111** and the pixel circuit portion **112** adjacent to each other with the predetermined interval from each of the APD **111** and the pixel circuit portion **112** in the X-direction.

[0096] The p-type impurity concentration in the second separation portion **16** is set lower than the p-type impurity concentration in the first separation portion **13**.

[0097] With the second separation portion **16** provided as described above, the n-type region of the APD **111** and the n-well **23** of the pixel circuit portion **112** are depleted. Accordingly, the APD **111** and the pixel circuit portion **112** can be electrically separated from each other while the interval therebetween is narrowed. Moreover, the size of the pixel **110** can be decreased.

[0098] No STI **60** is formed between the APD **111** and the pixel circuit portion **112** adjacent to each other.

[0099] Generally, stress is likely to be caused at an interface between the STI **60** and the substrate **10**, and if the STI **60** is provided between the APD **111** and the pixel circuit portion **112**, leakage current might flow due to such stress. Particularly, when the size of the pixel **110** is decreased while the area of the APD **111** is held in the light receiving portion **100**, the interval between the APD **111** and the pixel circuit portion **112** is narrowed, and the width of the STI **60** is narrowed accordingly. Meanwhile, when the width is narrowed as described above, the stress at a corner portion of a bottom portion of the STI **60** increases, and the leakage current is likely to be caused between the APD **111** and the pixel circuit portion **112**. There is a probability that the output signal of the APD **111** is erroneously detected due to mixing of such leakage current with the signal charge.

[0100] On the other hand, according to the present embodiment, the second separation portion **16** is provided between the APD **111** and the pixel circuit portion **112** adjacent to each other, and on the other hand, no STI **60** is formed therebetween. Thus, the leakage current due to the stress etc. can be reduced, and the APD **111** and the pixel circuit portion **112** can be reliably separated from each other.

[0101] The potential of the p-well (the fourth well) **17** is fixed to the same GND potential as those

of the p-wells (the first wells) **14**, **15**, and on the other hand, the potential of the n-well (the fifth well) **23** is fixed to Vdd2 (=3.3 V).

[0102] With this configuration, the n-type MISFET (the third transistor) **40** can be accurately operated, and the signal charge of the APD **111** can be transferred to the readout circuit **220**.

[0103] The insulating layer **500** is provided on the first principal surface **S1** to cover the light receiving portion **100** and the peripheral circuit portion **200**. The n-type MISFET (the first transistor) **30** has at least the n-type source and drain **32**, **32** provided at the first principal surface **S1** and the gate **31** provided between the source and the drain **32**, **32** at the first principal surface **S1** through the not-shown gate insulating layer. On the source and the drain **32**, **32** and the first principal surface **S1** side of the gate **31**, the conductor layer containing metal, the silicide layer **70** in this case, is formed. On the other hand, on the first principal surface **S1** side of the first separation portion **13**, no silicide layer **70** is formed.

[0104] With this configuration, the electric resistance of the n-type MISFET **30** can be reduced for performance enhancement. Moreover, no silicide layer **70** is formed on the first separation portion **13**, and therefore, a leakage current increase between the light receiving portion **100** and the peripheral circuit portion **200** or between adjacent circuit blocks can be suppressed.

First Variation

[0105] FIG. **4** shows a schematic sectional view of a light detector according to the present variation. Note that the same reference numerals are used to represent elements similar to those of the embodiment in FIG. **4** and subsequently-shown FIGS. **5** to **7** and description thereof will be omitted.

[0106] A configuration described in the present variation is different from the configuration described in the embodiment in that a p-type region (a second region) **18** is provided right below the n-type region **20**. The p-type region **18** is provided inside the p-epitaxial layer **12**, and a p-type impurity concentration in the p-type region **18** is set higher than the p-type impurity concentration of the p-epitaxial layer **12**.

[0107] With this configuration, the field intensity in the multiplication region AM increases, and therefore, an avalanche breakdown voltage can be reduced. Accordingly, the circuit configuration of the light detector **1000** can be simplified.

Second Variation

[0108] FIG. **5** shows a schematic sectional view of a light detector according to the present variation, and a configuration described in the present variation is different from the configuration described in the embodiment on the following points.

[0109] A p-epitaxial layer **12a** has the gradient of the impurity concentration in the Z-direction. Specifically, the p-type impurity concentration of the p-epitaxial layer **12a** decreases from the second principal surface **S2** to the first principal surface **S1**, and a portion of the p-epitaxial layer **12a** close to the first principal surface **S1**, i.e., a portion (a second region) where the p-type impurity concentration is low, contacts the n-type region **20** to form a pn junction. Moreover, in the present variation, a region including a joint surface between the second region and the n-type region **20** is the multiplication region AM, and the p-type impurity concentration in the p-epitaxial layer **12a** is adjusted such that avalanche multiplication occurs in such a region.

[0110] As described above, electrons generated by photoelectric conversion in the p-epitaxial layer **12** are drifted to the multiplication region AM due to the built-in potential of the pn junction formed by the n-type region **20** and the p-epitaxial layer **12**, and are avalanche-multiplied in the multiplication region AM.

[0111] As in the present variation, the gradient of the p-type impurity concentration is provided in the p-epitaxial layer **12a**, and therefore, electrons generated at a location deep in the substrate **10** by photoelectric conversion are also easily drifted to the multiplication region AM. Accordingly, the multiplication factor of the electrons can be further enhanced. Moreover, holes can be easily discharged to the outside of the substrate **10**.

[0112] Due to an electric field generated in the Z-direction inside the p-epitaxial layer **12a**, hole movement in the X-direction or the Y-direction can be reduced, and the sensitivity of the light detector **1000** can be enhanced. Moreover, inflow of holes from an adjacent APD **111** can be reduced, and the mixed color of the light detector **1000** can be reduced.

Third Variation

[0113] FIG. **6** shows a schematic sectional view of a light detector according to the present variation, and a configuration described in the present variation is different from the configuration described in the embodiment in that a p+ region **19** is provided on the first principal surface **S1** side of the n-type region **20**.

[0114] The p-type impurity concentration of the p+ region **19** is, for example, set to 1×10^{18} cm.^{sup.}−³ to 1×10^{20} cm.^{sup.}−³. Note that the concentration is not limited to above and may be another value as necessary. Note that the p-type impurity concentration of the p+ region **19** is set higher than the p-type impurity concentrations of the second separation portion **16** and the p-well (the fourth well) **17**. Moreover, the p+ region **19** is fixed to a predetermined potential such as the GND potential through a not-shown contact.

[0115] At an interface between the substrate **10** and the insulating layer **500**, i.e., the first principal surface **S1** of the substrate **10**, a dangling bond which is an unbonded hand of a silicon atom is present to form a surface level.

[0116] With a high density of the surface level, electrons are generated from the surface level, and as a noise component, are superimposed on the output signal of the APD **111**.

[0117] On the other hand, according to the present variation, the p+ region **19** is provided on the first principal surface **S1** side of the n-type region **20**, and therefore, the electrons generated at the surface level can be rejoined to holes inside the p+ region **19** and be annihilated. Accordingly, the noise component contained in the output signal of the APD **111** can be significantly reduced, and the sensitivity of the light detector **1000** can be enhanced.

Fourth Variation

[0118] FIG. **7** shows a schematic sectional view of a light detector according to the present variation, and a configuration described in the present variation is different from the configuration described in the first embodiment in that the pixel circuit portion **112** includes a p-type MISFET (a second transistor) **39** formed at an n-well (a fourth well) **24**. Of the readout circuit **220** of the peripheral circuit portion **200**, the second circuit block **270** is omitted.

[0119] That is, the light detector **1000** according to the present variation is the light detector **1000** configured such that the light detector **1000** having the plurality of APDs **111** arranged in a matrix at the predetermined intervals and the peripheral circuit portion **200** configured to exchange a signal with the light receiving portion **100** are provided on the first principal surface **S1** of the p-type semiconductor substrate **10**.

[0120] The light detector **1000** includes at least the back electrode **300** provided on the first principal surface **S1** of the substrate **10** facing the first principal surface **S1** and configured to apply the predetermined voltage to the substrate **10** and the p-type first separation portion **13** provided with the predetermined interval from each of the light receiving portion **100** and the peripheral circuit portion **200** in the X-direction.

[0121] The APD **111** has at least the n-type region (the first region) **20** provided to extend inward of the substrate **10** from the first principal surface **S1** and the p-epitaxial layer (the second region) **12** provided in contact with the n-type region **20** in the Z-direction.

[0122] The peripheral circuit portion **200** has at least the p-well (the first well) **14** provided to extend inward of the substrate **10** from the first principal surface **S1**, the n-type MISFET (the first transistor) **30** provided at the p-well **14**, and the n-well (the third well) **21** provided to surround the side and bottom portions of the p-well **14**.

[0123] The light receiving portion **100** further has the pixel circuit portions **112** provided with the predetermined interval from the APDs **111** in the X-direction. The pixel circuit portion **112** has at

least the n-well (the fourth well) **24** and the p-type MISFET (the second transistor) **39** provided at the n-well **24**. The p-type second separation portion **16** is further provided between the APD **111** and the pixel circuit portion **112** adjacent to each other with the predetermined interval from each of the APD **111** and the pixel circuit portion **112** in the X-direction.

[0124] With this configuration of the light detector **1000**, advantageous effects similar to those provided by the configuration described in the first embodiment can be provided. That is, the light receiving portion **100** and the peripheral circuit portion **200** can be electrically separated from each other without full depletion of a portion therebetween, and therefore, the layout of the peripheral circuit portion **200** relative to the light receiving portion **100** can be freely changed.

[0125] The APD **111** and the pixel circuit portion **112** can be electrically separated from each other while the interval therebetween is narrowed. Moreover, the size of the pixel **110** can be decreased.

[0126] Note that in FIG. 7, the transistor provided at the first circuit block **260** of the peripheral circuit portion **200** is the n-type MISFET **30**, but may be a p-type MISFET. In this case, the p-well **14** is omitted. Moreover, as shown in FIG. 2, the second circuit block **270** may be provided at the readout circuit **220**.

OTHER EMBODIMENTS

[0127] Note that the components described in the embodiments including the first to fourth variations can be combined as necessary to form a new embodiment. For example, the p+ region **19** described in the third variation may be applied to the configuration described in the first variation.

[0128] The first circuit block **260** and the second circuit block **270** may switch arrangement positions with each other. A plurality of circuit blocks may be provided at a circuit other than the readout circuit **220**. Moreover, the peripheral circuit portion **200** may include not only a so-called MOS circuit but also an analog circuit block including a bipolar transistor. A so-called BiCMOS circuit including a bipolar transistor and a CMOS may be included. It may only be required that the first separation portion **13** is provided between adjacent circuit blocks with the predetermined interval from each of these circuit blocks and the STI **60** is provided to surround the first separation portion **13** as viewed from above.

[0129] Note that in FIGS. 2 and 4 to 7, the STI **60** is provided to surround the first separation portion **13** to cover the peripheral edge of the first separation portion **13**, but the STI **60** may be provided to cover the entirety of the first separation portion **13** as viewed from above. For example, in a case where the width of the first separation portion **13** in the X-direction is close to the minimum machining dimension of the STI **60**, the STI **60** is provided to cover the entirety of the first separation portion **13** and surround the first separation portion **13** as viewed from above. That is, in the embodiments including each variation, it may only be required that the STI **60** is provided to surround the first separation portion **13** to cover at least the peripheral edge of the first separation portion **13** as viewed from above.

[0130] In each variation and each embodiment, the light detector **1000** configured such that the APDs **111** are arranged in a matrix has been described by way of example, but may include only one APD **111**.

[0131] The first separation portion **13** may be provided between the APD **111** and the pixel circuit portion **112**. In this case, the pixel circuit portion **112** corresponds to part of the peripheral circuit portion **200**, and the degree of freedom in the layout of the pixel circuit portion **112** is improved. For example, such a configuration may be applied to a light detector **1000** as a line sensor provided only with one row or column of APDs **111**.

[0132] Note that in the embodiments including each variation, a so-called front surface illumination (FSI) type light detector has been described by way of example, but the arrangement relationship between the light receiving portion **100** and the peripheral circuit portion **200** in the present disclosure and the circuit blocks included in the peripheral circuit portion **200**, particularly the arrangement relationship between the first separation portion **13** and the n-well **21**, can be also applied to a back surface illumination (BSI) type light detector. In this case, instead of providing

the back electrode **300**, a transparent electrode (not shown in the figure) is provided on a light receiving surface (the first principal surface **S1**) of each APD **111**.

[0133] In the embodiments including the first to third variations, the APD **111** and the n-type MISFET **40** for reading the signal charge generated at the APD **111** have been described as the elements included in the pixel circuit portion **112**, but an element etc. other than above may be included. For example, the drain **43** of the n-type MISFET **40** may be a floating diffusion, and a reset transistor (not shown in the figure) and a source follower transistor (not shown in the figure) connected to the floating diffusion may be provided. Moreover, a selection transistor (not shown in the figure) connected in series with the source follower transistor may be provided, and may be turned on to read the signal charge to the not-shown vertical signal line. Similarly, in the fourth variation, a reset transistor (not shown in the figure) and a source follower transistor (not shown) may be provided at the pixel circuit portion **112**. Moreover, a selection transistor (not shown in the figure) connected in series with the source follower transistor may be provided.

[0134] In the specification of the present application, the substrate **10** may be of an n-type, and the region (equivalent to the n-type region **20** of FIG. 2) of the APD **111** where the charge is accumulated may be of a p-type. Accordingly, the first and second separation portions **13**, **16** are of an n-type, and the conductive type of each well and the conductive type of the transistor are opposite to those described in the embodiments and each variation.

[0135] The light detector of the present disclosure is useful for application to a light detector configured so that the degree of freedom in the layout of a peripheral circuit portion can be enhanced and light detection can be performed with a high sensitivity.

Claims

1. A light detector in which a light receiving portion and a peripheral portion are provided on a semiconductor substrate, wherein: the light receiving portion includes: an n-type first region; a p-type second region; a p-type second semiconductor layer; and a p-type first semiconductor layer, the first region, the second region, the second semiconductor layer, and the first semiconductor layer are stacked in this order, a maximum p-type impurity concentration in the first semiconductor layer is higher than a maximum p-type impurity concentration in the second semiconductor layer, the peripheral portion includes: a p-type first well; an n-type third well; and the first semiconductor layer, and the third well surrounds at least one side portion and a bottom portion of the first well as viewed in a cross section.
2. The light detector according to claim 1, wherein the semiconductor substrate has a first principal surface and a second principal surface opposite to the first principal surface, the first region is stacked on a first principal surface side, the first semiconductor layer is stacked on a second principal surface side, the first semiconductor layer is in contact with the second principal surface in the peripheral portion, and an impurity concentration on the second principal surface side in the first semiconductor layer is higher than an impurity concentration in the second semiconductor layer.
3. The light detector according to claim 1, wherein the peripheral portion has the second semiconductor layer, and the second semiconductor layer is in contact with both a side portion of the third well and the first semiconductor layer.
4. The light detector according to claim 1, wherein the peripheral portion has a plurality of circuit blocks and has the second semiconductor layer between the plurality of circuit blocks, and the second semiconductor layer is in contact with the first semiconductor layer.
5. The light detector according to claim 4, wherein a thickness of the third well is larger than a thickness of the first region as viewed in the cross section.
6. The light detector according to claim 5, wherein the light receiving portion has one or more avalanche photodiodes.

7. The light detector according to claim 6, wherein the third well surrounds both side portions of the first well and the bottom portion of the first well as viewed in the cross section.

8. A light detector in which a light receiving portion and a peripheral portion are provided on a semiconductor substrate, wherein: the light receiving portion includes: an n-type first region; a p-type second region; a p-type second semiconductor layer; and a p-type first semiconductor layer, the first region, the second region, the second semiconductor layer, and the first semiconductor layer are stacked in this order, a maximum p-type impurity concentration in the first semiconductor layer is higher than a maximum p-type impurity concentration in the second semiconductor layer, the peripheral portion includes: a p-type first well; an n-type third well; an n-type fourth well; and the first semiconductor layer, the isolation contacts side portions of the third well and the fourth well, and the third well surrounds side and bottom portions of the first well as viewed in a cross section, and a side end of the third well extends longer toward a first principal surface of the semiconductor substrate than a side end of the first well as viewed in the cross section.

9. A light detector in which a light receiving portion and a peripheral portion are provided on a semiconductor substrate, wherein: the light receiving portion includes: an n-type first region; a p-type second region; a p-type second semiconductor layer; and a p-type first semiconductor layer, the first region, the second region, the second semiconductor layer, and the first semiconductor layer are stacked in this order, a maximum p-type impurity concentration in the first semiconductor layer is higher than a maximum p-type impurity concentration in the second semiconductor layer, the peripheral portion includes: a p-type first well; an n-type third well; and the first semiconductor layer, and the third well surrounds side and bottom portions of the first well as viewed in a cross section, and the side and bottom portions have different impurity concentrations from each other.

10. The light detector according to claim 1, wherein the third well in the peripheral portion surrounds an entirety of the one side portion and an entirety of the bottom portion of the first well as viewed in the cross section.

11. The light detector according to claim 6, wherein: the third well covers at least the one side portion and the bottom portion of the first well, and a p-type layer surrounds side and bottom portions of the third well as viewed in the cross section.

12. The light detector according to claim 1, wherein a maximum p-type impurity concentration in the second region is higher than a maximum p-type impurity concentration in the second semiconductor layer.

13. The light detector according to claim 1, wherein a thickness of the first region is thicker than a thickness of the second region.
