



US 20250250695A1

(19) **United States**(12) **Patent Application Publication****Kuhl et al.**(10) **Pub. No.: US 2025/0250695 A1**(43) **Pub. Date: Aug. 7, 2025**

(54) **REACTOR WITH ADVANCED ARCHITECTURE FOR THE ELECTROCHEMICAL REACTION OF CO₂, CO AND OTHER CHEMICAL COMPOUNDS**

(71) Applicant: **Twelve Benefit Corporation**, Berkeley, CA (US)

(72) Inventors: **Kendra Kuhl**, Oakland, CA (US);
Etosha Cave, Berkeley, CA (US);
George Leonard, Oakland, CA (US)

(73) Assignee: **Twelve Benefit Corporation**, Berkeley, CA (US)

(21) Appl. No.: **19/186,467**

(22) Filed: **Apr. 22, 2025**

Related U.S. Application Data

(63) Continuation of application No. 18/299,672, filed on Apr. 12, 2023, now Pat. No. 12,297,552, which is a continuation of application No. 16/949,538, filed on Nov. 2, 2020, now Pat. No. 11,680,327, which is a continuation of application No. 15/586,182, filed on May 3, 2017, now Pat. No. 10,822,709.

(60) Provisional application No. 62/331,387, filed on May 3, 2016.

Publication Classification

(51) **Int. Cl.**

C25B 9/23 (2021.01)

C25B 3/25 (2021.01)

C25B 3/26 (2021.01)

C25B 11/051 (2021.01)

C25B 11/057 (2021.01)

C25B 13/02 (2006.01)

C25B 13/08 (2006.01)

(52) **U.S. Cl.**

CPC **C25B 9/23** (2021.01); **C25B 3/25**

(2021.01); **C25B 3/26** (2021.01); **C25B 11/051**


(2021.01); **C25B 11/057** (2021.01); **C25B**


13/02 (2013.01); **C25B 13/08** (2013.01)

(57)

ABSTRACT

A platform technology that uses a novel membrane electrode assembly, including a cathode layer, an anode layer, a membrane layer arranged between the cathode layer and the anode layer, the membrane conductively connecting the cathode layer and the anode layer, in a CO_x reduction reactor has been developed. The reactor can be used to synthesize a broad range of carbon-based compounds from carbon dioxide and other gases containing carbon.



**FIG. 1**




FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6




FIG. 7




FIG. 8

**REACTOR WITH ADVANCED
ARCHITECTURE FOR THE
ELECTROCHEMICAL REACTION OF CO₂,
CO AND OTHER CHEMICAL COMPOUNDS**

STATEMENT OF GOVERNMENT SUPPORT

[0001] The Government has rights in this invention pursuant to a User Agreement FP00003032 between Opus 12, Incorporated and The Regents of the University of California, which manages and operates Ernest Orlando Lawrence Berkeley National Laboratory for the US Department of Energy under Contract No. DE-AC02-05CH11231.

INCORPORATION BY REFERENCE

[0002] An Application Data Sheet is filed concurrently with this specification as part of the present application. Each application that the present application claims benefit of or priority to as identified in the concurrently filed Application Data Sheet is incorporated by reference herein in its entirety and for all purposes.

TECHNICAL FIELD

[0003] The present disclosure generally relates to the field of electrochemical reactions, and more particularly, to devices and methods for electrochemically reducing CO_x (CO₂, CO, or combinations thereof) into carbon-containing chemical compounds.

BACKGROUND

[0004] Anthropogenic CO₂ emissions have been linked to climate change.

[0005] As a response to increasing concerns about global greenhouse gas emissions, technologies that can recycle CO₂ into high-value products have received growing interest.

[0006] Electrochemical reduction of CO_x (CO₂, CO, or combinations thereof) combines just three inputs: CO_x, a source of protons, and electricity, and converts them into fuels, chemicals, and other products such as methanol, ethanol, carbon monoxide and acetic acid. However, it has not been possible to achieve industrial-scale production of such fuels and chemicals. One barrier has been the lack of a suitable electrochemical reactor. One difficulty in achieving an efficient reactor using conventional designs is the poor transport of CO_x to the catalyst surface in the reactor due to the low solubility of CO_x in aqueous solutions and the inability to control the competing water reduction reaction that leads to hydrogen production.

[0007] This disclosure describes a new and useful electrochemical reactor for reduction of CO_x that addresses the aforementioned disadvantages of conventional reactors. Gas-phase CO_x, as opposed to CO_x dissolved in water, can be supplied to the reactor to achieve efficient transport and product production rates. The ion conducting polymer surrounding the CO_x conversion catalyst minimizes the competing hydrogen formation reaction. The reactor has high energy efficiency, high current density, fast response time, and robustness, while also providing flexibility in the kinds of chemical products it can produce.

BRIEF DESCRIPTION OF THE FIGURES

[0008] The foregoing aspects and others will be readily appreciated by the skilled artisan from the following description of illustrative embodiments when read in conjunction with the accompanying drawings.

[0009] FIG. 1 shows a standard membrane electrode assembly used in a conventional water electrolysis reactor, which makes hydrogen and oxygen.

[0010] FIG. 2 is a schematic illustration of a membrane electrode assembly for use in a new CO_x reduction reactor (CRR), according to an embodiment of the invention.

[0011] FIG. 3 is a schematic drawing that shows a possible morphology for two different kinds of catalysts supported on a catalyst support particle, according to an embodiment of the invention.

[0012] FIG. 4 is a schematic illustration of a membrane electrode assembly for use in a new CRR, according to another embodiment of the invention.

[0013] FIG. 5 is a schematic drawing that shows the membrane electrode assembly for use in a new CRR, according to yet another embodiment of the invention.

[0014] FIG. 6 is a schematic drawing that shows the major components of a CO_x reduction reactor (CRR), according to an embodiment of the invention.

[0015] FIG. 7 is a schematic drawing that shows the major components of a CRR with arrows showing the flow of molecules, ions, and electrons according to one embodiment of the invention.

[0016] FIG. 8 is a schematic drawing that shows the major inputs and outputs of the CRR reactor.

SUMMARY

[0017] In one embodiment of the invention, a membrane electrode assembly (MEA) for use in a CO_x reduction reactor is provided. The MEA has a cathode layer comprising reduction catalyst and a first ion-conducting polymer and an anode layer comprising oxidation catalyst and a second ion-conducting polymer. There is a polymer electrolyte membrane comprising a third ion-conducting polymer between the anode layer and the cathode layer. The polymer electrolyte membrane provides ionic communication between the anode layer and the cathode layer. There is also a cathode buffer layer comprising a fourth ion-conducting polymer between the cathode layer and the polymer electrolyte membrane, the cathode buffer. There are three classes of ion-conducting polymers: anion-conductors, cation-conductors, and cation-and-anion-conductors. At least two of the first, second, third, and fourth ion-conducting polymers are from different classes of ion-conducting polymers.

[0018] In one arrangement, the reduction catalyst is selected from the group consisting of V, Cr, Mn, Fe, Co, Ni, Cu, Sn, Zr, Nb, Mo, Au, Ru, Rh, Pd, Ag, Cd, Hf, Ta, W, Re, Ir, Pt, Hg, Al, Si, In, Ga, Tl, Pb, Bi, Sb, Te, Sm, Tb, Ce, and Nd, and combinations thereof, and/or any other suitable reduction catalysts. The reduction catalyst can further comprise conductive support particles selected from the group consisting of carbon, boron-doped diamond, fluorine-doped tin oxide, and combinations thereof, and/or any other suitable reduction catalysts.

[0019] In one arrangement, the cathode layer comprises between 10 and 90 wt % first ion-conducting polymer. The first ion-conducting polymer can comprise at least one ion-conducting polymer that is an anion-conductor.

[0020] The first ion-conducting polymer can comprise one or more covalently-bound, positively-charged functional groups configured to transport mobile negatively-charged ions. The first ion-conducting polymer can be selected from the group consisting of aminated tetramethyl polyphenylene; poly(ethylene-co-tetrafluoroethylene)-based quaternary ammonium polymer; quaternized polysulfone), blends thereof, and/or any other suitable ion-conducting polymers. The first ion-conducting polymer can be configured to solubilize salts of bicarbonate or hydroxide.

[0021] The first ion-conducting polymer can comprise at least one ion-conducting polymer that is a cation-and-anion-conductor. The first ion-conducting polymer can be selected from the group consisting of polyethers that can transport cations and anions and polyesters that can transport cations and anions. The first ion-conducting polymer can be selected from the group consisting of polyethylene oxide, polyethylene glycol, polyvinylidene fluoride, and polyurethane.

[0022] In one arrangement, the oxidation catalyst is selected from the group consisting of metals and oxides of Ir, Pt, Ni, Ru, Pd, Au, and alloys thereof, IrRu, PtIr, Ni, NiFe, stainless steel, and combinations thereof, and/or any other suitable metals or metal oxides. The oxidation catalyst can further contain conductive support particles selected from the group consisting of carbon, boron-doped diamond, and titanium.

[0023] In one arrangement, the anode layer comprises between 5 and 95 wt % second ion-conducting polymer. The second ion-conducting polymer can comprise at least one ion-conducting polymer that is a cation-conductor.

[0024] The second ion-conducting polymer can comprise one or more polymers that contain covalently-bound, negatively-charged functional groups configured to transport mobile positively-charged ions. The second ion-conducting polymer can be selected from the group consisting of ethanesulfonyl fluoride, 2-[1-[difluoro-[(trifluoroethenyl)oxy]methyl]-1,2,2,2-tetrafluoroethoxy]-1,1,2,2-tetrafluoro-, with tetrafluoroethylene, tetrafluoroethylene-perfluoro-3,6-dioxo-4-methyl-7-octenesulfonic acid copolymer, other perfluorosulfonic acid polymers, blends thereof, and/or any other suitable ion-conducting polymer.

[0025] In one arrangement, the third ion-conducting polymer comprises at least one ion-conducting polymer that is a cation-conductor. The third ion-conducting polymer can comprise one or more covalently-bound, negatively-charged functional groups configured to transport mobile positively-charged ions. The third ion-conducting polymer can be selected from the group consisting of ethanesulfonyl fluoride, 2-[1-[difluoro-[(trifluoroethenyl)oxy]methyl]-1,2,2,2-tetrafluoroethoxy]-1,1,2,2-tetrafluoro-, with tetrafluoroethylene, tetrafluoroethylene-perfluoro-3,6-dioxo-4-methyl-7-octenesulfonic acid copolymer, other perfluorosulfonic acid polymers, blends thereof, and/or any other suitable ion-conducting polymer.

[0026] In one arrangement, the cathode buffer layer has a porosity between 0.01% and 95% (e.g., approximately between, by weight, by volume, by mass, etc.). However, in other arrangements, the cathode buffer layer can have any suitable porosity (e.g., between 0.01-95%, 0.1-95%, 0.01-75%, 1-95%, 1-90%, etc.).

[0027] In one arrangement, the fourth ion-conducting polymer comprises at least one ion-conducting polymer that is an anion-conductor. The fourth ion-conducting polymer can comprise one or more covalently-bound, positively-

charged functional groups configured to transport mobile negatively-charged ions. The fourth ion-conducting polymer can be selected from the group consisting of aminated tetramethyl polyphenylene; poly(ethylene-co-tetrafluoroethylene)-based quaternary ammonium polymer; quaternized polysulfone; blends thereof; and/or any other suitable ion-conducting polymer.

[0028] In one arrangement, the first ion-conducting polymer and the fourth ion-conducting polymer are from the same class. In one arrangement, the second ion-conducting polymer and the third ion-conducting polymer are from the same class.

[0029] In one arrangement, the membrane electrode assembly further comprises an anode buffer layer between the anode layer and the polymer electrolyte membrane, the anode buffer layer comprising a fifth ion-conducting polymer.

[0030] The membrane electrode assembly wherein the fifth ion-conducting polymer comprises at least one ion-conducting polymer that is a cation-conductor. The fifth ion-conducting polymer can comprise one or more covalently-bound, negatively-charged functional groups configured to transport mobile positively-charged ions.

[0031] The fifth ion-conducting polymer can be selected from the group consisting of ethanesulfonyl fluoride, 2-[1-[difluoro-[(trifluoroethenyl)oxy]methyl]-1,2,2,2-tetrafluoroethoxy]-1,1,2,2-tetrafluoro-, with tetrafluoroethylene, tetrafluoroethylene-perfluoro-3,6-dioxo-4-methyl-7-octenesulfonic acid copolymer, other perfluorosulfonic acid polymers, blends thereof, and/or any other suitable ion-conducting polymer. The second ion-conducting polymer and the fifth ion-conducting polymer can be from the same class.

[0032] In one arrangement, the anode buffer layer has a porosity between 0.01% and 95% (e.g., approximately between, by weight, by volume, by mass, etc.). However, in other arrangements, the anode buffer layer can have any suitable porosity (e.g., between 0.01-95%, 0.1-95%, 0.01-75%, 1-95%, 1-90%, etc.).

[0033] In another embodiment of the invention, a membrane electrode assembly (MEA) for use in a CO_x reduction reactor is provided. The MEA has a cathode layer comprising reduction catalyst and a first ion-conducting polymer and an anode layer comprising oxidation catalyst and a second ion-conducting polymer. There is a polymer electrolyte membrane between the anode layer and the cathode layer. The polymer electrolyte membrane comprises a third ion-conducting polymer and provides ionic communication between the anode layer and the cathode layer. There are three classes of ion-conducting polymers: anion-conductors, cation-conductors, and cation-and-anion-conductors. At least two of the first, second, and third ion-conducting polymers are from different classes of ion-conducting polymers.

[0034] In another embodiment of the invention, CO_x reduction reactor is provided. The reactor has at least one electrochemical cell, which comprises any of the membrane electrode assemblies described herein. The reactor also has a cathode support structure adjacent to the cathode, the cathode support structure comprising a cathode polar plate, at least one cathode gas diffusion layer, at least one inlet and at least one outlet. There is also an anode cell support structure adjacent to the anode. The anode support structure

comprises an anode polar plate and at least one anode gas diffusion layer, at least one inlet and at least one outlet.

[0035] In yet another embodiment of the invention, a method of operating a CO_x reduction reactor is provided. The method results in production of reaction products. The process can include: providing an electrochemical reactor comprising at least one electrochemical cell comprising a membrane electrode assembly, a cathode support structure adjacent to the cathode that includes a cathode polar plate, at least one cathode gas diffusion layer, at least one gas inlet and at least one gas outlet, and an anode cell support structure adjacent to the anode that includes an anode polar plate and at least one anode gas diffusion layer, at least one inlet and at least one outlet; applying a DC voltage to the cathode polar plate and the anode polar plate; supplying one or more oxidation reactants to the anode and allowing oxidation reactions to occur; supplying one or more reduction reactants to the cathode and allowing reduction reactions to occur; collecting oxidation reaction products from the anode; and collecting reduction reaction products from the cathode.

[0036] The oxidation reactants can be selected from the group consisting of hydrogen, methane, ammonia, water, or combinations thereof, and/or any other suitable oxidation reactants. In one arrangement, the oxidation reactant is water.

[0037] The reduction reactants can be selected from the group consisting of carbon dioxide, carbon monoxide, and combinations thereof, and/or any other suitable reduction reactants. In one arrangement, the reduction reactant is carbon dioxide.

DESCRIPTION OF THE PREFERRED EMBODIMENTS

[0038] The preferred embodiments are illustrated in the context of reduction of CO_x (CO₂, CO, or combinations thereof) to produce useful chemicals and fuels. The skilled artisan will readily appreciate, however, that the materials and methods disclosed herein will have application in a number of other contexts where reduction reactions are desirable, particularly where production of a variety of chemicals in a variety of reaction conditions is important. The reactor used to reduce CO_x could also be used to reduce other compounds, including but not limited to: N₂, SO_x, NO_x, acetic acid, ethylene, O₂ and any other suitable reducible compound or combinations thereof.

[0039] All publications referred to herein are incorporated by reference in their entirety for all purposes as if fully set forth herein.

[0040] Table 1 lists some abbreviations that are used throughout this application.

TABLE 1

Abbreviation	Description
CO _x	CO ₂ , CO or a combination thereof
CRR	CO _x reduction reactor
MEA	membrane electrode assembly
PEM	polymer electrolyte membrane

[0041] The term, “ion-conducting polymer” is used herein to describe a polymer electrolyte having greater than approximately 1 mS/cm specific conductivity for anions and/or cations. The term, “anion-conductor,” describes an

ion-conducting polymer that conducts anions primarily (although there will still be some small amount of cation conduction) and has a transference number for anions greater than approximately 0.85 at around 100 micron thickness. The terms “cation-conductor” and/or “cation-conducting polymer” describe an ion-conducting polymer that conducts cations primarily (e.g., there can still be an incidental amount of anion conduction) and has a transference number for cations greater than approximately 0.85 at around 100 micron thickness. For an ion-conducting polymer that is described as conducting both anions and cations (a “cation-and-anion-conductor”), neither the anions nor the cations has a transference number greater than approximately 0.85 or less than approximately 0.15 at around 100 micron thickness. To say a material conducts ions (anions and/or cations) is to say that the material is an ion-conducting material.

[0042] Hydration is useful in effecting ion conduction for most ion-conducting polymers. Humidification of CO_x or anode feed material can be used for the delivery of liquid water to the MEA to maintain hydration of ion-conducting polymers.

[0043] In one embodiment of the invention, a CO_x reduction reactor (CRR) that uses a novel membrane electrode assembly in an electrochemical cell has been developed. Table 2 lists some examples of useful chemicals that can be produced from CO_x in such a reactor.

TABLE 2

Exemplary CO ₂ and CO Reduction Products		
Formic Acid	Carbon Monoxide	Methanol
Glyoxal	Methane	Acetic Acid
Glycolaldehyde	Ethylene Glycol	Acetaldehyde
Ethanol	Ethylene	Hydroxyacetone
Acetone	Allyl Alcohol	Propionaldehyde
n-Propanol	Syngas	

Membrane Electrode Assembly

[0044] A conventional membrane electrode assembly (MEA) 100 used for water electrolysis to make hydrogen and oxygen is shown in FIG. 1. The MEA 100 has a cathode 120 and an anode 140 separated by an ion-conducting polymer layer 160 that provides a path for ions to travel between the cathode 120 and the anode 140. The cathode 120 and the anode 140 each contain ion-conducting polymer, catalyst particles, and electronically conductive catalyst support. The ion-conducting polymer in the cathode 120, anode 140, and ion-conducting polymer layer 160 are either all cation-conductors or all anion-conductors.

[0045] The conventional MEA 100 is not suitable for use in a CRR. When all of the ion-conducting polymers are cation-conductors, the environment favors water reduction to make hydrogen in an unwanted side reaction. The production of hydrogen lowers the rate of CO_x product production and lowers the overall efficiency of the process. When all of the ion-conducting polymers are anion-conductors, then CO₂ reacts with hydroxide anions in the ion-conducting polymer to form bicarbonate anions. The electric field in the reactor moves the bicarbonate anions from the cathode side of the cell to the anode side of the cell. At the anode, bicarbonate anions can decompose back into CO₂ and hydroxide. This results in the net movement of CO₂ from the

cathode to the anode of the cell, where it does not react and is diluted by the anode reactants and products. This loss of CO₂ to the anode side of the cell reduces the efficiency of the process.

[0046] A new membrane electrode assembly (MEA) **200** for use in a CRR is shown in FIG. 2, according to an embodiment of the invention. The MEA **200** has a cathode **220** and an anode **240** separated by an ion-conducting polymer layer **260** that provides a path for ions to travel between the cathode **220** and the anode **240**. In general, it is especially useful if the cathode and anode layers of the MEA are porous in order to facilitate gas and fluid transport and to maximize the amount of catalyst surface area that is available for reaction.

[0047] The cathode **220** contains a blend of reduction catalyst particles, electronically-conductive support particles that provide support for the reduction catalyst particles, and a cathode ion-conducting polymer. There are tradeoffs in choosing the amount of cathode ion-conducting polymer in the cathode. It is important to include enough cathode ion-conducting polymer to provide sufficient ionic conductivity. But it is also important for the cathode to be porous so that reactants and products can move through it easily and to maximize the amount of catalyst surface area that is available for reaction. In various arrangements, the cathode ion-conducting polymer makes up somewhere in the range between 30 and 70 wt %, between 20 and 80 wt %, or between 10 and 90 wt %, of the material in the cathode layer, or any other suitable range. The wt % of ion-conducting polymer in the cathode is selected to result in the cathode layer porosity and ion-conductivity that gives the highest current density for CO_x reduction. Examples of materials that can be used for the reduction catalyst particles include but are not limited to transition metals such as V, Cr, Mn, Fe, Co, Ni, Cu, Zr, Nb, Mo, Au, Ru, Rh, Pd, Ag, Cd, Hf, Ta, W, Re, Ir, Pt, and Hg, and combinations thereof, and/or any other suitable materials. Other catalyst materials can include alkali metals, alkaline earth metals, lanthanides, actinides, and post transition metals, such as Sn, Si, Ga, Pb, Al, Ti, Sb, Te, Bi, Sm, Tb, Ce, Nd and In or combinations thereof, and/or any other suitable catalyst materials. Catalysts can be in the form of nanoparticles that range in size from approximately 1 to 100 nm or particles that range in size from approximately 0.2 to 10 nm or particles in the size range of approximately 1-1000 nm or any other suitable range.

[0048] The conductive support particles in the cathode can be carbon particles in various forms. Other possible conductive support particles include boron-doped diamond or fluorine-doped tin oxide. In one arrangement, the conductive support particles are Vulcan carbon. The conductive support particles can be nanoparticles. The size range of the conductive support particles is between approximately 20 nm and 1000 nm or any other suitable range. It is especially useful if the conductive support particles are compatible with the chemicals that are present in the cathode **220** when the CRR is operating, are reductively stable, and have a high hydrogen production overpotential so that they do not participate in any electrochemical reactions.

[0049] In general, such conductive support particles are larger than the reduction catalyst particles, and each conductive support particle can support many reduction catalyst particles. FIG. 3 is a schematic drawing that shows a possible morphology for two different kinds of catalysts supported on a catalyst support particle **310**, such as a

carbon particle. Catalyst particles **330** of a first type and second catalyst particles **350** of a second type are attached to the catalyst support particle **310**. In various arrangements, there is only one type of catalyst particle or there are more than two types of catalyst particles attached to the catalyst support particle **310**.

[0050] Again, with reference to FIG. 2, the anode **240** contains a blend of oxidation catalyst and an anode ion-conducting polymer. There are tradeoffs in choosing the amount of ion-conducting polymer in the anode. It is important to include enough anode ion-conducting polymer to provide sufficient ionic conductivity. But it is also important for the anode to be porous so that reactants and products can move through it easily, and to maximize the amount of catalyst surface area that is available for reaction. In various arrangements, the ion-conducting polymer in the anode makes up approximately 50 wt % of the layer or between approximately 5 and 20 wt %, 10 and 90 wt %, between 20 and 80 wt %, between 25 and 70 wt %, or any suitable range. It is especially useful if the anode **240** can tolerate high voltages, such as voltages above about 1.2 V vs. a reversible hydrogen electrode. It is especially useful if the anode **240** is porous in order to maximize the amount of catalyst surface area available for reaction and to facilitate gas and liquid transport.

[0051] There are a variety of oxidation reactions that can occur at the anode depending on the reactant that is fed to the anode and the anode catalyst(s). Table 3 lists oxidation reactions that can occur at the anode and some exemplary catalysts that support those reactions. The oxidation catalyst can be in the form of a structured mesh or can be in the form of particles. If the oxidation catalyst is in the form of particles, the particles can be supported by electronically-conductive support particles. The conductive support particles can be nanoparticles. It is especially useful if the conductive support particles are compatible with the chemicals that are present in the anode **240** when the CRR is operating and are oxidatively stable so that they do not participate in any electrochemical reactions. It is especially useful if the conductive support particles are chosen with the voltage and the reactants at the anode in mind. In some arrangements, the conductive support particles are titanium, which is well-suited for high voltages. In other arrangements, the conductive support particles are carbon, which can be most useful at low voltages. In general, such conductive support particles are larger than the oxidation catalyst particles, and each conductive support particle can support many oxidation catalyst particles. An example of such an arrangement is shown in FIG. 3 and is discussed above. In one arrangement, the oxidation catalyst is iridium ruthenium oxide. Examples of other materials that can be used for the oxidation catalyst include, but are not limited to, those shown in Table 3. It should be understood that many of these metal catalysts can be in the form of oxides, especially under reaction conditions.

TABLE 3

Feed Material	Anode Oxidation Reaction	Exemplary Catalysts
Hydrogen	$\text{H}_2 \rightarrow 2\text{H}^+ + 2\text{e}^-$	Pt, Ni, Ru, other transition metals, and alloys and oxides thereof
Methane	$\text{CH}_4 + \text{H}_2\text{O} \rightarrow \text{CH}_3\text{OH} + 2\text{H}^+ + 2\text{e}^-$	Pd, Pd alloys and oxides thereof

TABLE 3-continued

Feed Material	Anode Oxidation Reaction	Exemplary Catalysts
Methane	$\text{CH}_4 + 2\text{H}_2\text{O} \rightarrow 7\text{CO}_2 + 8\text{H}^+ + 8\text{e}^-$	Pt, Au, Pd, and alloys and oxides thereof
Ammonia	$2\text{NH}_3 \rightarrow \text{N}_2 + 6\text{H}^+ + 6\text{e}^-$	Ru, Pt and oxides thereof
Water	$2\text{H}_2\text{O} \rightarrow \text{O}_2 + 4\text{H}^+ + 4\text{e}^-$	Ir, IrRu, PtIr, Pt, Au, Ni, NiFe, Mn, Stainless steel and oxides thereof

[0052] The ion-exchange layer **260** can include three sublayers: a cathode buffer layer **225**, a polymer electrolyte membrane (PEM) **265**, and an optional anode buffer layer **245**. Some layers in the ion-exchange layer can be porous, but it is useful if at least one layer is nonporous so that reactants and products of the cathode cannot pass to the anode and vice versa.

[0053] The polymer electrolyte membrane **265** has high ionic conductivity (greater than about 1 mS/cm), and is mechanically stable. Mechanical stability can be evidenced in a variety of ways such as through high tensile strength, modulus of elasticity, elongation to break, and tear resistance. Many commercially-available membranes can be used for the polymer electrolyte membrane **265**. Examples include, but are not limited to, various Nafion® formulations, GORE-SELECT, FumaPEM® (PFSA) (FuMA-Tech GmbH), and Aquivion® (PFSA) (Solvay).

[0054] It is important to note that when the polymer electrolyte membrane **265** is a cation conductor and is conducting protons, it contains a high concentration of protons during operation of the CRR, while the cathode **220** operates best when a low concentration of protons is present. It can be useful to include a cathode buffer layer **225** between the polymer electrolyte membrane **265** and the cathode **220** to provide a region of transition from a high concentration of protons to a low concentration of protons. In one arrangement, the cathode buffer layer **225** is an ion-conducting polymer with many of the same properties as the ion-conducting polymer in the cathode **220**. The cathode buffer layer **225** provides a region for the proton concentration to transition from the polymer electrolyte membrane **265**, which has a high concentration of protons to the cathode **220**, which has a low proton concentration. Within the cathode buffer layer **225**, protons from the polymer electrolyte membrane **265** encounter anions from the cathode **220**, and they neutralize one another. The cathode buffer layer **225** helps ensure that a deleterious number of protons from the polymer electrolyte membrane **265** does not reach the cathode **220** and raise the proton concentration. If the proton concentration of the cathode **220** is too high, CO_x reduction does not occur. High proton concentration is considered to be in the range of approximately 10 to 0.1 molar and low concentration is considered to be less than approximately 0.01 molar.

[0055] The cathode buffer layer **225** can include a single polymer or multiple polymers. If the cathode buffer layer **225** includes multiple polymers, the multiple polymers can be mixed together or can be arranged in separate, adjacent layers. Examples of materials that can be used for the cathode buffer layer **225** include, but are not limited to, FumaSep FAA-3, Sustainion®, Tokuyama anion exchange membrane material, and polyether-based polymers, such as polyethylene oxide (PEO), and blends thereof, and/or any other suitable ion-conducting polymer or material. The

thickness of the cathode buffer layer is chosen to be sufficient that CO_x reduction activity is high due to the proton concentration being low. This sufficiency can be different for different cathode buffer layer materials. In general, the thickness of the cathode buffer layer is between approximately 200 nm and 100 μm , between 300 nm and 75 μm , between 500 nm and 50 μm , or any suitable range.

[0056] It can be useful if some or all of the following layers are porous: the cathode **220**, the cathode buffer layer **225**, the anode **240** and the anode buffer layer **245**. In some arrangements, porosity is achieved by combining inert filler particles with the polymers in these layers. Materials that are suitable as inert filler particles include, but are not limited to, TiO_2 , silica, PTFE, zirconia, and alumina. In various arrangements, the size of the inert filler particles is between 5 nm and 500 μm , between 10 nm and 100 μm , or any suitable size range. In other arrangements, porosity is achieved by using particular processing methods when the layers are formed. One example of such a processing method is laser ablation, where nano to micro-sized channels are formed in the layers. Laser ablation can additionally or alternatively achieve porosity in a layer by subsurface ablation. Subsurface ablation can form voids within a layer, upon focusing the beam at a point within the layer, and thereby vaporizing the layer material in the vicinity of the point. This process can be repeated to form voids throughout the layer, and thereby achieving porosity in the layer. The volume of a void is preferably determined by the laser power (e.g., higher laser power corresponds to a greater void volume), but can additionally or alternatively be determined by the focal size of the beam, or any other suitable laser parameter. Another example is mechanically puncturing a layer to form channels through the layer. The porosity can have any suitable distribution in the layer (e.g., uniform, an increasing porosity gradient through the layer, a random porosity gradient, a decreasing porosity gradient through the layer, a periodic porosity, etc.).

[0057] In some CRR reactions, bicarbonate is produced at the cathode **220**. It can be useful if there is a polymer that blocks bicarbonate transport somewhere between the cathode **220** and the anode **240**, to prevent migration of bicarbonate away from the cathode. It can be that bicarbonate takes some CO_2 with it as it migrates, which decreases the amount of CO_2 available for reaction at the cathode. In one arrangement, the polymer electrolyte membrane **265** includes a polymer that blocks bicarbonate transport. Examples of such polymers include, but are not limited to, Nafion® formulations, GORE-SELECT, FumaPEM® (PFSA) (FuMA-Tech GmbH), and Aquivion® (PFSA) (Solvay). In another arrangement, there is an anode buffer layer **245** between the polymer electrolyte membrane **265** and the anode **240**, which blocks transport of bicarbonate. If the polymer electrolyte membrane is an anion-conductor, or does not block bicarbonate transport, then an additional anode buffer layer to prevent bicarbonate transport can be useful. Materials that can be used to block bicarbonate transport include, but are not limited to Nafion® formulations, GORE-SELECT, FumaPEM® (PFSA) (FuMA-Tech GmbH), and Aquivion® (PFSA) (Solvay). Of course, including a bicarbonate blocking feature in the ion-exchange layer **260** is not particularly desirable if there is no bicarbonate in the CRR.

[0058] In another embodiment of the invention, the anode buffer layer **245** provides a region for proton concentration

to transition between the polymer electrolyte membrane **265** to the anode **240**. The concentration of protons in the polymer electrolyte membrane **265** depends both on its composition and the ion it is conducting. For example, a Nafion polymer electrolyte membrane **265** conducting protons has a high proton concentration. A FumaSep FAA-3 polymer electrolyte membrane **265** conducting hydroxide has a low proton concentration. For example, if the desired proton concentration at the anode **240** is more than 3 orders of magnitude different from the polymer electrolyte membrane **265**, then an anode buffer layer **245** can be useful to effect the transition from the proton concentration of the polymer electrolyte membrane **265** to the desired proton concentration of the anode. The anode buffer layer **245** can include a single polymer or multiple polymers. If the anode buffer layer **245** includes multiple polymers, the multiple polymers can be mixed together or can be arranged in separate, adjacent layers. Materials that can be useful in providing a region for the pH transition include, but are not limited to, Nafion, FumaSep FAA-3, Sustainion®, Tokuyama anion exchange polymer, and polyether-based polymers, such as polyethylene oxide (PEO), blends thereof, and/or any other suitable materials. High proton concentration is considered to be in the range of approximately 10 to 0.1 molar and low concentration is considered to be less than approximately 0.01 molar. Ion-conducting polymers can be placed in different classes based on the type(s) of ions they conduct. This has been discussed in more detail above. There are three classes of ion-conducting polymers described in Table 4 below. In one embodiment of the invention, at least one of the ion-conducting polymers in the cathode **220**, anode **240**, polymer electrolyte membrane **265**, cathode buffer layer **225**, and anode buffer layer **245** is from a class that is different from at least one of the others.

[0059] Some Class A ion-conducting polymers are known by tradenames such as 2259-60 (Pall RAI), AHA by Tokuyama Co, Fumasep® FAA-3 (fumatech GbbH), Sustainion®, Morgane ADP by Solvay, or Tosflex® SF-17 by Tosoh anion exchange membrane material. Some Class C ion-conducting polymers are known by tradenames such as various formulations of Nafion® (DuPont™), GORE-SELECT® (Gore), Fumapem® (fumatech GmbH), and Aquivion® PFSA (Solvay).

[0060] A new membrane electrode assembly (MEA) **400** for use in a CRR is shown in FIG. 4, according to another embodiment of the invention. The MEA **400** has a cathode **420**, an anode **440**, and an ion-conducting polymer layer **460**. The ion-conducting polymer layer **460** contains an ion-conducting polymer membrane **465** and a cathode buffer layer **425**. The anode **440** and the ion-conducting polymer membrane **465** contain ion-conducting polymers that are cation conductors, and the ion-conducting polymer membrane **465** does not allow for appreciable amounts of bicarbonate to reach the anode **440**, so no anode buffer layer is used here.

[0061] A new membrane electrode assembly (MEA) **500** for use in a CRR is shown in FIG. 5, according to yet another embodiment of the invention. The MEA **500** has a cathode **520**, an anode **540**, and an ion-conducting polymer membrane **560**. In this arrangement, the transition from a high proton concentration within the ion-conducting polymer membrane **560** to a low proton concentration in the cathode layer is achieved at the interface of the cathode layer **520** and the ion-conducting polymer membrane **560**, so no additional buffer layer between these two layers is used. The ability to achieve the difference in proton concentration without the buffer layer depends on the kinds of ion-conducting polymers used in the cathode layer **520** and in the ion-conducting

Ion-Conducting Polymers			
Class	Description	Common Features	Examples
A. Anion-conducting	Greater than approximately 1 mS/cm specific conductivity for anions, which have a transference number greater than approximately 0.85 at around 100 micron thickness	Positively charged functional groups are covalently bound to the polymer backbone	aminated tetramethyl polyphenylene; poly(ethylene-co-tetrafluoroethylene)-based quaternary ammonium polymer, quaternized polysulfone
B. Conducts both anions and cations	Greater than approximately 1 mS/cm conductivity for ions (including both cations and anions), which have a transference number between approximately 0.15 and 0.85 at around 100 micron thickness	Salt is soluble in the polymer and the salt ions can move through the polymer material	polyethylene oxide; polyethylene glycol; poly(vinylidene fluoride); polyurethane
C. Cation-conducting	Greater than approximately 1 mS/cm specific conductivity for cations, which have a transference number greater than approximately 0.85 at around 100 micron thickness	Negatively charged functional groups are covalently bound to the polymer backbone	perfluorosulfonic acid polytetrafluoroethylene co-polymer, sulfonated poly(ether ether ketone); poly(styrene sulfonic acid-co-maleic acid)

polymer membrane **560** and the way in which the ion-conducting polymers mix at the interface of the layers.

[0062] In another specific example, the membrane electrode assembly includes a cathode layer including a reduction catalyst and a first anion-conducting polymer (e.g., Sustainion, FumaSep FAA-3, Tokuyama anion exchange polymer), an anode layer including an oxidation catalyst and a first cation-conducting polymer (e.g., PFSA polymer), a membrane layer including a second cation-conducting polymer and arranged between the cathode layer and the anode layer to conductively connect the cathode layer and the anode layer, and a cathode buffer layer including a second anion-conducting polymer (e.g., Sustainion, FumaSep FAA-3, Tokuyama anion exchange polymer) and arranged between the cathode layer and the membrane layer to conductively connect the cathode layer and the membrane layer. In this example, the cathode buffer layer can have a porosity between about 1 and 90 percent by volume, but can additionally or alternatively have any suitable porosity (including, e.g., no porosity). In other examples the cathode layer can have any suitable porosity (e.g., between 0.01-95%, 0.1-95%, 0.01-75%, 1-95%, 1-90%, etc.).

[0063] In a related example, the membrane electrode assembly can include an anode buffer layer that includes a third cation-conducting polymer, and is arranged between the membrane layer and the anode layer to conductively connect the membrane layer and the anode layer. The anode buffer layer preferably has a porosity between about 1 and 90 percent by volume, but can additionally or alternatively have any suitable porosity (including, e.g., no porosity). However, in other arrangements and examples, the anode buffer layer can have any suitable porosity (e.g., between 0.01-95%, 0.1-95%, 0.01-75%, 1-95%, 1-90%, etc.).

[0064] In another specific example, the membrane electrode assembly includes a cathode layer including a reduction catalyst and a first anion-conducting polymer (e.g., Sustainion, FumaSep FAA-3, Tokuyama anion exchange polymer), an anode layer including an oxidation catalyst and a first cation-conducting polymer, a membrane layer including a second anion-conducting polymer (e.g., Sustainion, FumaSep FAA-3, Tokuyama anion exchange polymer) and arranged between the cathode layer and the anode layer to conductively connect the cathode layer and the anode layer, and an anode buffer layer including a second cation-conducting polymer and arranged between the anode layer and the membrane layer to conductively connect the anode layer and the membrane layer.

[0065] In a related example, the membrane electrode assembly can include a cathode buffer layer that includes a third anion-conducting polymer, and is arranged between the cathode layer and the membrane layer to conductively connect the cathode layer and the membrane layer. The third anion-conducting polymer can be the same or different from the first and/or second anion-conducting polymer, the cathode buffer layer preferably has a porosity between about 1 and 90 percent by volume, but can additionally or alternatively have any suitable porosity (including, e.g., no porosity). However, in other arrangements and examples, the cathode buffer layer can have any suitable porosity (e.g., between 0.01-95%, 0.1-95%, 0.01-75%, 1-95%, 1-90%, etc.).

[0066] The porosities (e.g., of the cathode buffer layer, of the anode buffer layer, of the membrane layer, of the cathode layer, of the anode layer, of other suitable layers, etc.) of the

examples described above and other examples and variations preferably have a uniform distribution, but can additionally or alternatively have any suitable distribution (e.g., a randomized distribution, an increasing gradient of pore size through or across the layer, a decreasing gradient of pore size through or across the layer, etc.). The porosity can be formed by any suitable mechanism, such as inert filler particles (e.g., diamond particles, boron-doped diamond particles, polyvinylidene difluoride/PVDF particles, polytetrafluoroethylene/PTFE particles, etc.) and any other suitable mechanism for forming substantially non-reactive regions within a polymer layer. The inert filler particles can have any suitable size, such as a minimum of about 10 nanometers and a maximum of about 200 nanometers, and/or any other suitable dimension or distribution of dimensions.

CO_x Reduction Reactor (CRR)

[0067] FIG. 6 is a schematic drawing that shows the major components of a CO_x reduction reactor (CRR) **605**, according to an embodiment of the invention.

[0068] The CRR **605** has a membrane electrode assembly **600** as described above in reference to FIG. 2. The membrane electrode assembly **600** has a cathode **620** and an anode **640**, separated by an ion-exchange layer **660**. The ion-exchange layer **660** can include three sublayers: a cathode buffer layer **625**, a polymer electrolyte membrane **665**, and an optional anode buffer layer **645**. In addition, the CRR **605** has a cathode support structure **622** adjacent to the cathode **620** and an anode support structure **642** adjacent to the anode **640**.

[0069] In one embodiment of the invention, the cathode **620** contains an ion-conducting polymer as described in Class A in Table 4 above, the anode **640** contains an ion-conducting polymer as described in Class C in Table 4 above, and the polymer electrolyte membrane **665** contains an ion-conducting polymer as described as Class C in Table 4 above. In one arrangement, the cathode buffer layer **625** contains at least two ion-conducting polymers: one as described in Class A and one as described in Class B in Table 4 above.


[0070] In another embodiment of the invention, the cathode **620** contains both an ion-conducting polymer as described in Class A and an ion-conducting polymer as described in Class B, the anode **640** contains an ion-conducting polymer as described in Class C, the polymer electrolyte membrane **665** contains an ion-conducting polymer as described in Class A, the cathode buffer layer **625** contains both an ion-conducting polymer as described in Class A and an ion-conducting polymer as described in Class B, and the anode buffer layer **645** contains an ion-conducting polymer as described in Class C. Other combinations of ion-conducting polymers are also possible.

[0071] The cathode support structure **622** has a cathode polar plate **624**, usually made of graphite, to which a voltage can be applied. There can be flow field channels, such as serpentine channels, cut into the inside surfaces of the cathode polar plate **624**. There is also a cathode gas diffusion layer **626** adjacent to the inside surface of the cathode polar plate **624**. In some arrangements, there is more than one cathode gas diffusion layer (not shown). The cathode gas diffusion layer **626** facilitates the flow of gas into and out of the membrane electrode assembly **600**. An example of a cathode gas diffusion layer **626** is a carbon paper that has a carbon microporous layer.

[0072] The anode support structure 642 has an anode polar plate 644, usually made of metal, to which a voltage can be applied. There can be flow field channels, such as serpentine channels, cut into the inside surfaces of the anode polar plate 644. There is also an anode gas diffusion layer 646 adjacent to the inside surface of the anode polar plate 644. In some arrangements, there is more than one anode gas diffusion layer (not shown). The anode gas diffusion layer 646 facilitates the flow of gas into and out of the membrane electrode assembly 600. An example of an anode gas diffusion layer 646 is a titanium mesh or titanium felt. In some arrangements, the gas diffusion layers 626, 646 are microporous.

[0073] There are also inlets and outlets (not shown) associated with the support structures 622, 642, which allow flow of reactants and products, respectively, to the membrane electrode assembly 600. There are also various gaskets (not shown) that prevent leakage of reactants and products from the cell.

[0074] In one embodiment of the invention, a direct current (DC) voltage is applied to the membrane electrode assembly 600 through the cathode polar plate 624 and the anode polar plate 642. Water is supplied to the anode 640 and is oxidized over an oxidation catalyst to form molecular oxygen (O₂), releasing protons (H⁺) and electrons (e⁻). The protons migrate through the ion-exchange layer 660 toward the cathode 620. The electrons flow through an external circuit (not shown). In one embodiment of the invention, the reaction is described as follows:



[0075] In other embodiments of the invention, other reactants can be supplied to the anode 640 and other reactions can occur. Some of these are listed in Table 3 above.

[0076] The flow of reactants, products, ions, and electrons through a CRR 705 reactor is indicated in FIG. 7, according to an embodiment of the invention.

[0077] The CRR 705 has a membrane electrode assembly 700 as described above in reference to FIG. 2. The membrane electrode assembly 700 has a cathode 720 and an anode 740, separated by an ion-exchange layer 760. The ion-exchange layer 760 can include three sublayers: a cathode buffer layer 725, a polymer electrolyte membrane 765, and an optional anode buffer layer 745. In addition, the CRR 705 has a cathode support structure 722 adjacent to the cathode 720 and an anode support structure 742 adjacent to the anode 740.

[0078] The cathode support structure 722 has a cathode polar plate 724, usually made of graphite, to which a voltage can be applied. There can be flow field channels, such as serpentine channels, cut into the inside surfaces of the cathode polar plate 724. There is also a cathode gas diffusion layer 726 adjacent to the inside surface of the cathode polar plate 724. In some arrangements, there is more than one cathode gas diffusion layer (not shown). The cathode gas diffusion layer 726 facilitates the flow of gas into and out of the membrane electrode assembly 700. An example of a cathode gas diffusion layer 726 is a carbon paper that has a carbon microporous layer.

[0079] The anode support structure 742 has an anode polar plate 744, usually made of metal, to which a voltage can be applied. There can be flow field channels, such as serpentine channels, cut into the inside surfaces of the anode polar plate 744. There is also an anode gas diffusion layer 746 adjacent to the inside surface of the anode polar plate 744. In some

arrangements, there is more than one anode gas diffusion layer (not shown). The anode gas diffusion layer 746 facilitates the flow of gas into and out of the membrane electrode assembly 700. An example of an anode gas diffusion layer 746 is a titanium mesh or titanium felt. In some arrangements, the gas diffusion layers 726, 746 are microporous.

[0080] There can also be inlets and outlets associated with the support structures 722, 742, which allow flow of reactants and products, respectively, to the membrane electrode assembly 700. There can also be various gaskets that prevent leakage of reactants and products from the cell.








[0081] CO_x can be supplied to the cathode 720 and reduced over CO_x reduction catalysts in the presence of protons and electrons. The CO_x can be supplied to the cathode 720 at pressures between 0 psig and 1000 psig or any other suitable range. The CO_x can be supplied to the cathode 720 in concentrations below 100% or any other suitable percentage along with a mixture of other gases. In some arrangements, the concentration of CO_x can be as low as approximately 0.5%, as low as 5%, or as low as 20% or any other suitable percentage.

[0082] In one embodiment of the invention, between approximately 10% and 100% of unreacted CO_x is collected at an outlet adjacent to the cathode 720, separated from reduction reaction products, and then recycled back to an inlet adjacent to the cathode 720. In one embodiment of the invention, the oxidation products at the anode 740 are compressed to pressures between 0 psig and 1500 psig.

[0083] In one embodiment of the invention, multiple CRRs (such as the one shown in FIG. 6) are arranged in an electrochemical stack and are operated together. The CRRs that make up the individual electrochemical cells of the stack can be connected electrically in series or in parallel. Reactants are supplied to individual CRRs and reaction products are then collected.

[0084] The major inputs and outputs to the reactor are shown in FIG. 8. CO_x, anode feed material, and electricity are fed to the reactor. CO_x reduction product and any unreacted CO_x leave the reactor. Unreacted CO_x can be separated from the reduction product and recycled back to the input side of the reactor. A node oxidation product and any unreacted anode feed material leave the reactor in a separate stream. Unreacted anode feed material can be recycled back to the input side of the reactor.

[0085] Various catalysts in the cathode of a CRR cause different products or mixtures of products to form from CO_x reduction reactions. Examples of possible CO_x reduction reactions at the cathode are described as follows:



[0086] In another embodiment of the invention, a method of operating a CO_x reduction reactor, as described in the embodiments of the invention above, is provided. It involves applying a DC voltage to the cathode polar plate and the

anode polar plate, supplying oxidation reactants to the anode and allowing oxidation reactions to occur, supplying reduction reactants to the cathode and allowing reduction reactions to occur, collecting oxidation reaction products from the anode; and collecting reduction reaction products from the cathode.

[0087] In one arrangement, the DC voltage is greater than -1.2V . In various arrangements, the oxidation reactants can be any of hydrogen, methane, ammonia, water, or combinations thereof, and/or any other suitable oxidation reactants. In one arrangement, the oxidation reactant is water. In various arrangements, the reduction reactants can be any of carbon dioxide, carbon monoxide, and combinations thereof, and/or any other suitable reduction reactants. In one arrangement, the reduction reactant is carbon dioxide.

[0088] In another specific example, the CO_x reduction reactor includes a membrane electrode assembly, which includes a cathode layer that includes a reduction catalyst and a first anion-conducting polymer (e.g., FumaSep FAA-3, Sustainion, Tokuyama anion exchange polymer). The reactor also includes an anode layer that includes an oxidation catalyst and a first cation-conducting polymer (e.g., Nafion 324, Nafion 350, Nafion 417, Nafion 424, Nafion 438, Nafion 450, Nafion 521, Nafion 551, other Nafion formulations, Aquivion, GORE-SELECT, Flemion, PSFA, etc.). The reactor also includes a membrane layer that includes a second cation-conducting polymer, wherein the membrane layer is arranged between the cathode layer and the anode layer and conductively connects the cathode layer and the anode layer. The reactor also includes a cathode manifold coupled to the cathode layer, and an anode manifold coupled to the anode layer. In this example, the cathode manifold can include a cathode support structure adjacent to the cathode layer, wherein the cathode support structure includes a cathode polar plate, a cathode gas diffusion layer arranged between the cathode polar plate and the cathode layer, a first inlet fluidly connected to the cathode gas diffusion layer, and a first outlet fluidly connected to the cathode gas diffusion layer. Also in this example, the anode manifold can include an anode support structure adjacent to the anode layer, wherein the anode support structure includes an anode polar plate, an anode gas diffusion layer arranged between the anode polar plate and the anode layer, a second inlet fluidly connected to the anode gas diffusion layer, and a second outlet fluidly connected to the anode gas diffusion layer. In a related example, the membrane electrode assembly of the reactor includes a cathode buffer layer that includes a second anion-conducting polymer (e.g., FumaSep FAA-3, Sustainion, Tokuyama anion exchange polymer), and is arranged between the cathode layer and the membrane layer and conductively connects the cathode layer and the membrane layer. The buffer layer(s) of this example (e.g., cathode buffer layer, anode cathode layer) can have a porosity between about 1 and 90 percent by volume, but can alternatively have any suitable porosity (including, e.g., no porosity). However, in other arrangements and examples, the buffer layer(s) can have any suitable porosity (e.g., between 0.01-95%, 0.1-95%, 0.01-75%, 1-95%, 1-90%, etc.). In a related example, the first and second anion-conducting polymers of the membrane electrode assembly can be the same anion-conducting polymer (e.g., comprised of identical polymer formulations).

[0089] This invention has been described herein in considerable detail to provide those skilled in the art with

information relevant to apply the novel principles and to construct and use such specialized components as are required. However, it is to be understood that the invention can be carried out by different equipment, materials and devices, and that various modifications, both as to the equipment and operating procedures, can be accomplished without departing from the scope of the invention itself.

1.-20. (canceled)

21. A CO_x reduction reactor comprising;

a membrane electrode assembly comprising:

a cathode layer comprising a reduction catalyst and a first anion-conducting polymer, wherein the reduction catalyst composition comprises a first catalyst particle supported on an electronically conductive support particle and a second catalyst particle supported on the electronically conductive support particle, wherein the first catalyst particle and the second catalyst particle are different materials, and wherein the first catalyst particle and the second catalyst particle catalyze CO_x reduction;

an anode layer comprising an oxidation catalyst and a first cation-conducting polymer; and

a membrane layer comprising a second anion-conducting polymer, the membrane layer arranged between the cathode layer and the anode layer, the membrane layer conductively connecting the cathode layer and the anode layer; and

a cathode manifold coupled to the cathode layer.

22. The CO_x reduction reactor of claim **21**, further comprising:

an anode manifold coupled to the anode layer.

23. The CO_x reduction reactor of claim **22**, further comprising:

a hydrogen (H_2) source, wherein the anode manifold is configured to distribute H_2 from the H_2 source to the anode layer.

24. The CO_x reduction reactor of claim **21**, wherein the electronically conductive support particle is selected from the group consisting of carbon, boron-doped diamond, fluorine-doped tin oxide, and combinations thereof.

25. The CO_x reduction reactor of claim **21**, wherein the first catalyst particle is gold and the second catalyst particle is silver.

26. The CO_x reduction reactor of claim **21**, wherein the membrane layer physically contacts the anode layer.

27. The CO_x reduction reactor of claim **21**, further comprising:

an anode buffer layer comprising a second cation-conducting polymer and arranged between the anode layer and the membrane layer to conductively connect the anode layer and the membrane layer.

28. The CO_x reduction reactor of claim **22**, wherein the cathode manifold comprises a cathode support structure adjacent to the cathode layer, the cathode support structure comprising:

a cathode polar plate;

a cathode gas diffusion layer arranged between the cathode polar plate and the cathode layer;

a first inlet fluidly connected to the cathode gas diffusion layer; and

a first outlet fluidly connected to the cathode gas diffusion layer; and

wherein the anode manifold comprises an anode support structure adjacent to the anode layer, the anode support structure comprising:

- an anode polar plate;
- an anode gas diffusion layer arranged between the anode polar plate and the anode layer;
- a second inlet fluidly connected to the anode gas diffusion layer; and
- a second outlet fluidly connected to the anode gas diffusion layer.

29. A COx reduction reactor comprising:

- a membrane electrode assembly comprising:

- a cathode layer comprising a reduction catalyst and a first anion-conducting polymer;
 - an anode layer comprising an oxidation catalyst and a first cation-conducting polymer; and

- a membrane layer comprising a second anion-conducting polymer, the membrane layer arranged between the cathode layer and the anode layer, the membrane layer conductively connecting the cathode layer and the anode layer;

- a cathode manifold coupled to the cathode layer;

- a hydrogen (H₂) source; and

- an anode manifold coupled to the anode layer, wherein the anode manifold is configured to distribute H₂ from the H₂ source to the anode layer.

30. The COx reduction reactor of claim **29**, wherein the reduction catalyst composition comprises a first catalyst particle supported on an electronically conductive support particle and a second catalyst particle supported on the electronically conductive support particle

31. The COx reduction reactor of claim **30**, wherein the first catalyst particle and the second catalyst particle are different materials.

32. The COx reduction reactor of claim **30**, wherein the first catalyst particle and the second catalyst particle catalyze COx reduction.

33. The COx reduction reactor of claim **29**, wherein the cathode manifold comprises a cathode support structure adjacent to the cathode layer, the cathode support structure comprising:

- a cathode polar plate;
- a cathode gas diffusion layer arranged between the cathode polar plate and the cathode layer;
- a first inlet fluidly connected to the cathode gas diffusion layer; and
- a first outlet fluidly connected to the cathode gas diffusion layer; and

- wherein the anode manifold comprises an anode support structure adjacent to the anode layer, the anode support structure comprising:

- an anode polar plate;
 - an anode gas diffusion layer arranged between the anode polar plate and the anode layer;
 - a second inlet fluidly connected to the anode gas diffusion layer; and
 - a second outlet fluidly connected to the anode gas diffusion layer.

34. The COx reduction reactor of claim **30**, wherein the electronically conductive support particle is selected from the group consisting of carbon, boron-doped diamond, fluorine-doped tin oxide, and combinations thereof.

35. The COx reduction reactor of claim **30** wherein the first catalyst particle is gold and the second catalyst particle is silver.

36. The COx reduction reactor of claim **30**, wherein the membrane layer physically contacts the anode layer.

37. The COx reduction reactor of claim **30**, further comprising:

- an anode buffer layer comprising a second cation-conducting polymer and arranged between the anode layer and the membrane layer to conductively connect the anode layer and the membrane layer.

* * * * *