

CONCRETE TEST REPORT

TO	ABC ENGINEERING LTD. 545 SYCAMORE WAY WINDY CITY, AB
----	--

PROJECT NAME: Local Business Complex				SCOPE: MATERIAL TESTING					
SAMPLE	TYPE	CURE LOC.	TEST DATE	AGE (DAYS)	AVG. DIAMETER (mm)	AVG. LENGTH (mm)	MAX. LOAD (kN)	COMPRESSIVE STRENGTH (MPa)	FRACTURE TYPE
A	Cylinder	Lab	2021-08-12	7	101.6	203.2	178	22.0	b
	Cylinder	Lab			101.6	203.2			b
	Cylinder	Lab			101.6	203.2			b
	Cylinder	Lab			101.6	203.2			c
SPEC. STRENGTH 35 MPa @ 28 DAYS									
CEMENT TYPE GU/GUL					CONCRETE TEMP. 24.0 °C				
SCM CONTENT FLY ASH					AIR TEMP. 23.0 °C				
MAXIMUM SIZE AGGREGATE 14 mm					SLUMP 180 mm				
BATCH TIME 12:12					SPEC. SLUMP 190 mm				
ADMIXTURES					SLUMP FLOW NA mm				
SUPER-P JAZZ 1 DOSE					AIR CONTENT 1.2 %				
SUPPLIER TOP CONCRETE LTD.					CAST TIME 13:05				
MIX NO. KJF83302					CAST DATE 2021-08-05				
TRUCK NO. 113					CAST BY CMF				
LOAD VOL. 16 m3					LOCATION L09, E Slab				
WATER ADDED					COMMENTS				
TICKET NO. 69835									
AUTH									
					PREPARED BY SOME COMPANY				
					BY TECH INITIALS				