## **CONCRETE TEST REPORT**

TO ABC ENGINEERING LTD.
545 SYCAMORE WAY
WINDY CITY, AB

PROJECT NAME: Local Business SCOPE: MATERIAL TESTING

Complex

SAMPLE	ТҮРЕ	CURE LOC.	TEST DATE	AGE (DAYS)	AVG. DIAMETER (mm)	AVG. LENGTH (mm)	MAX. LOAD (kN)	COMPRESSIVE STRENGTH (MPa)	FRACTURE TYPE
Α	Cylinder	Lab	2021-06-27	7	101.6	203.2	289	35.7	b
В	Cylinder	Lab	2021-07-18	28	101.6	203.2	502	62.0	b
С	Cylinder	Lab	2021-07-18	28	101.6	203.2	424	52.3	b
D	Cylinder	Lab	2021-08-15	56	101.6	203.2	503	62.1	С

SPEC. STRENGT	ГН	55	MPa	@ 56	DAYS	CONCRETE TEMP. 24.0 °C AIR TEMP. 23.0 °C SLUMP 180 mm SPEC. SLUMP 190 mm
CEMENT TYPE					GU/GUL	SLUMP FLOW NA mm SPEC. FLOW AIR CONTENT 1.2 %
SCM CONTENT MAXIMUM SIZE BATCH TIME ADMIXTURES SUPER-P JAZZ	AGG	REGA	TE	14 12:12 1	FLY ASH mm	CAST TIME 13:05 CAST DATE 2021-06-20 CAST BY CMF  LOCATION L08, GL A1, A2, A'1, A'2, B1 COMMENTS
SUPPLIER MIX NO.	LTD. KJF93	CONC 3390	RETE			
TRUCK NO.  LOAD VOL.  WATER ADDED	104		:	TICKET NO. 16 m3 AUTH	12702	
						PREPARED BY SOME COMPANY BY TECH INITIALS