CONCRETE TEST REPORT

TO ABC ENGINEERING LTD.
545 SYCAMORE WAY
WINDY CITY, AB

PROJECT NAME: Local Business

Complex

SCOPE:

MATERIAL TESTING

SAMPLE	ТҮРЕ	CURE LOC.	TEST DATE	AGE (DAYS)	AVG. DIAMETER (mm)	AVG. LENGTH (mm)	MAX. LOAD (kN)	COMPRESSIVE STRENGTH (MPa)	FRACTURE TYPE
Α	Cylinder	Lab	2021-07-11	7	101.6	203.2	302	37.3	b
В	Cylinder	Lab	2021-08-01	28	101.6	203.2	501	61.8	b
С	Cylinder	Lab	2021-08-01	28	101.6	203.2	438	54.1	b
D	Cylinder	Lab	2021-08-29	56	101.6	203.2	511	63.1	С

SPEC. STRENGT	H 5	5	MPa	@	56	DAYS	CONCRETE TEI	MP. 180	24.0 mm	°C AIR TEMP. SPEC. SLUMP	23.0 190	°C mm
CEMENT TYPE						GU/GUL	SLUMP FLOW AIR CONTENT	NA 1.2	mm %	SPEC. FLOW		
SCM CONTENT MAXIMUM SIZE BATCH TIME ADMIXTURES SUPER-P JAZZ	AGGRE	GA T	ΓΕ		14 12:12 1	FLY ASH mm	CAST TIME CAST DATE LOCATION L09, GL B2, B3, COMMENTS		07-04	CAST BY	CMF	
SUPPLIER MIX NO. TRUCK NO. LOAD VOL. WATER ADDED	TOP CC LTD. KJF933 ¹ 180		RETE	N (CKET D. m3 JTH	23101						
							PREPARED BY SO BY TECH INITIAL		MPANY			