

CONCRETE TEST REPORT

TO

ABC ENGINEERING LTD.  
545 SYCAMORE WAY  
WINDY CITY, AB

PROJECT NAME:				Local Business Complex		SCOPE:		MATERIAL TESTING	
---------------	--	--	--	------------------------	--	--------	--	------------------	--

SAMPLE	TYPE	CURE LOC.	TEST DATE	AGE (DAYS)	AVG. DIAMETER (mm)	AVG. LENGTH (mm)	MAX. LOAD (kN)	COMPRESSIVE STRENGTH (MPa)	FRACTURE TYPE
A	Cylinder	Lab	2021-05-15	7	101.6	203.2	256	31.6	b
	Cylinder	Lab			101.6	203.2			b
	Cylinder	Lab			101.6	203.2			b
	Cylinder	Lab			101.6	203.2			c

SPEC. STRENGTH				55	MPa	@	56	DAYS	CONCRETE TEMP.		24.0	°C	AIR TEMP.		23.0	°C	
CEMENT TYPE				GU/GUL				SLUMP		180	mm	SPEC. SLUMP		190	mm		
SCM CONTENT				FLY ASH				SLUMP FLOW		NA	mm	SPEC. FLOW					
MAXIMUM SIZE AGGREGATE				14	mm				AIR CONTENT		1.2	%	CAST TIME		13:05		
BATCH TIME				12:12					CAST DATE		2021-05-08	CAST BY		CMF			
ADMIXTURES								LOCATION		L02, GL C4, C5, E4, E5							
SUPER-P JAZZ				1	DOSE				COMMENTS								
SUPPLIER				TOP CONCRETE LTD.													
MIX NO.				KJF93390													
TRUCK NO.				139					TICKET NO.		29416						
LOAD VOL.				16	m3												
WATER ADDED								AUTH									
								PREPARED BY		SOME COMPANY							
								BY TECH		INITIALS							