

CONCRETE TEST REPORT

TO	ABC ENGINEERING LTD. 545 SYCAMORE WAY WINDY CITY, AB
----	--

PROJECT NAME:				Local Business Complex		SCOPE:		MATERIAL TESTING	
---------------	--	--	--	------------------------	--	--------	--	------------------	--

SAMPLE	TYPE	CURE LOC.	TEST DATE	AGE (DAYS)	AVG. DIAMETER (mm)	AVG. LENGTH (mm)	MAX. LOAD (kN)	COMPRESSIVE STRENGTH (MPa)	FRACTURE TYPE
A	Cylinder	Lab	2021-07-30	7	101.6	203.2	167	20.6	b
B	Cylinder	Lab	2021-08-20	28	101.6	203.2	291	36.0	b
C	Cylinder	Lab	2021-08-20	28	101.6	203.2	266	32.9	b
	Cylinder	Lab			101.6	203.2			c

SPEC. STRENGTH				35	MPa	@	28	DAYS	CONCRETE TEMP.		24.0	°C	AIR TEMP.	23.0	°C	
CEMENT TYPE				GU/GUL				SLUMP		180	mm	SPEC. SLUMP		190	mm	
SCM CONTENT				FLY ASH				SLUMP FLOW		NA	mm	SPEC. FLOW				
MAXIMUM SIZE AGGREGATE				14	mm				AIR CONTENT		1.2	%	CAST TIME		13:05	
BATCH TIME				12:12					CAST DATE		2021-07-23	CAST BY		CMF		
ADMIXTURES								LOCATION		L08, E Slab						
SUPER-P JAZZ				1	DOSE				COMMENTS							
SUPPLIER		TOP CONCRETE LTD.														
MIX NO.		KJF83302														
TRUCK NO.		172														
LOAD VOL.		16 m3														
WATER ADDED		AUTH														
PREPARED BY SOME COMPANY																
BY TECH INITIALS																