

CONCRETE TEST REPORT

TO

ABC ENGINEERING LTD.  
545 SYCAMORE WAY  
WINDY CITY, AB

PROJECT NAME:Local Business Complex

SCOPE:MATERIAL TESTING

SAMPLE	TYPE	CURE LOC.	TEST DATE	AGE (DAYS)	AVG. DIAMETER (mm)	AVG. LENGTH (mm)	MAX. LOAD (kN)	COMPRESSIVE STRENGTH (MPa)	FRACTURE TYPE
A	Cylinder	Lab	2021-08-01	7	101.6	203.2	303	37.4	b
	Cylinder	Lab			101.6	203.2			b
	Cylinder	Lab			101.6	203.2			b
	Cylinder	Lab			101.6	203.2			c

SPEC. STRENGTH55 MPa @ 56 DAYS

CEMENT TYPEGU/GUL

SCM CONTENTFLY ASH

MAXIMUM SIZE AGGREGATE14 mm

BATCH TIME12:12

ADMIXTURESSUPER-P JAZZ1 DOSE

SUPPLIERTOP CONCRETE LTD.

MIX NO.KJF93390

TRUCK NO.132

LOAD VOL.16 m3

WATER ADDED

TICKET NO.11635

AUTH

CONCRETE TEMP.24.0 °C

SLUMP180 mm

SLUMP FLOWNA mm

AIR CONTENT1.2 %

CAST TIME13:05

CAST DATE2021-07-25

LOCATIONL08, GL C4, C5, E4, E5

COMMENTS

PREPARED BY SOME COMPANY

BY TECH INITIALS

AIR TEMP.23.0 °C

SPEC. SLUMP190 mm

SPEC. FLOW

CAST BYCMF