



Polyvinylidene Fluoride (PVDF) in Energy Storage

From Incumbent Binder to
Next-Generation Functional Material

Department of Chemical Engineering
Indian Institute of Technology Delhi

Course: CLL767 - Structures & Properties of Polymers
Instructor: Prof. Sudip K. Pattanayek

Presented by:

Yash Sakhare (2022CH71496) | Sudarshan Oraon (2022CH71511)

17 November 2025

Abstract

This report summarises current knowledge and recent advances on Polyvinylidene Fluoride (PVDF) in energy storage applications. It covers PVDF's polymer science (synthesis, molecular weight, polymorphism), its role as an incumbent binder in lithium-ion batteries, processing challenges (NMP solvent issues and slurry gelation), the aqueous processing frontier, operando diagnostics of binder failure, and new functional roles for PVDF in solid-state and Li-S batteries.

Contents

	Abstract	1
1	Part 1: The Established Baseline: PVDF as the Incumbent Li–Ion Binder	4
1.1	Synthesis, Structure, and Polymorphism: A Quantitative Baseline	4
1.2	Crystallization Kinetics: The Avrami Equation	4
1.3	Crystallinity and Performance: A Quantitative Baseline.	5
1.4	Thermal Properties: Quantitative Analysis	6
1.5	Mechanical Properties: Static and Dynamic Analysis	6
1.6	The NMP-Based Slurry System: Rheology and Solubility	7
1.7	The Adhesion Mechanism: A Fundamental Weakness	7
1.8	The High-Nickel Cathode Problem: Slurry Gelation	8
2	Part 2: The Aqueous Processing Frontier: Nuance Beyond NMP	8
2.1	A New Dichotomy: Replacing the Binder vs. Replacing the Solvent	8
2.2	Commercial Precedent: PVDF Latex.	8
2.3	Performance and Limitations of Aqueous PVDF-Latex	9
2.4	The Unaddressed Challenge: Aqueous Processing of High-Nickel Cathodes. .	9
3	Part 3: Advanced Operando Diagnostics: Visualizing Binder Failure Mechanisms	9
3.1	Macro-Scale Failure: Operando X-ray Computed Tomography (XCT)	9
3.2	Micro-Scale Failure: In-Situ SEM and Chemical Decomposition	10
3.3	Chemical-Scale Failure: Operando NMR Spectroscopy	11
3.4	Silicon Anode Challenge and Functional Binder Alternatives	11
4	Part 4: New Frontiers: PVDF in Next-Generation Energy Storage Systems	12
4.1	PVDF in Solid-State Batteries (SSBs): Composite Polymer Electrolytes . . .	12
4.2	PVDF in Lithium–Sulfur (Li–S) Batteries: Exploiting Polarity	12
5	Part 5: Sustainability, Recycling, and Lifecycle Analysis	13
5.1	Renewability and Environmental Impact	13
5.2	End-of-Life Recycling Challenges	13
5.3	Biocompatibility and Safety	14
6	Part 6: Market Analysis and Competitive Landscape.	14
6.1	Global Market Size and Growth	14
6.2	Key Manufacturers	14
6.3	Comparative Performance Analysis.	14

Conclusions and Outlook	14
Acknowledgements.	16

1. Part 1: The Established Baseline: PVDF as the Incumbent Li-Ion Binder

Polyvinylidene Fluoride (PVDF) has long been the dominant polymer binder in the lithium-ion battery (LIB) industry, particularly for cathodes. Its status as the industry incumbent is not accidental, but rather a direct result of its unique combination of electrochemical stability, chemical inertness, and adequate mechanical properties. However, a deeper analysis of its fundamental polymer science reveals that the very properties that secured its dominance are now becoming its primary limitations in the face of next-generation battery demands.[1]

1.1 Synthesis, Structure, and Polymorphism: A Quantitative Baseline

PVDF is a high-performance, semi-crystalline, thermoplastic fluoropolymer synthesized via the free-radical polymerization of the vinylidene fluoride (VDF) monomer, with a repeating unit of $(-CH_2 - CF_2-)_n$. This process, typically carried out through emulsion or suspension methods, produces a classic homopolymer structure. A critical, yet often overlooked, engineering parameter for battery applications is the polymer's molecular weight (M_w). While standard PVDF grades may have an M_w in the range of 240,000 g/mol, the grades specifically engineered for battery applications possess a significantly higher M_w , often cited between 600,000 g/mol and 1,200,000 g/mol. This high M_w is essential, as it provides the long-range chain entanglements necessary for the binder's cohesive strength, allowing it to hold the electrode's composite structure together.[1]

The most unique characteristic of PVDF is its crystalline polymorphism, a concept where the same polymer chain can pack into different crystalline structures based on its conformation (dictated by the sequence of trans (T) and gauche (G) bonds). The two most relevant phases are:

- **α -Phase (TGTG' conformation):** This is the most common and thermodynamically stable phase, forming during standard crystallization from the melt (e.g., during electrode drying). In this conformation, the dipoles of the C–F bonds on adjacent monomer units cancel each other out, resulting in a non-polar and non-piezoelectric crystal structure. This is the dominant, “workhorse” phase found in standard battery binders.[1]
- **β -Phase (TTTT ‘all-trans’ conformation):** This phase is typically formed by mechanically stretching the α -phase. In this all-trans conformation, all C–F dipoles align on one side of the polymer chain, creating a highly polar, electroactive crystal structure. This polarity is responsible for PVDF's strong piezoelectric, pyroelectric, and ferroelectric properties, making it an advanced functional material for sensors.[1]

While the α -phase is the standard for binders, this α – β polymorphism establishes a critical duality: the same polymer can be either a passive structural component or an active electroactive material, a property that becomes highly relevant in next-generation battery systems.

1.2 Crystallization Kinetics: The Avrami Equation

Beyond the existence of crystalline phases, understanding the kinetics of their formation is essential for controlling final properties. The rate and mechanism of crystallization as




Figure 1: Molecular structure showing α -phase (TGTG' conformation) and β -phase (TTTT all-trans conformation) of PVDF with dipole orientations.

the polymer cools from the melt dictates the morphology, spherulite size, and degree of crystallinity, which control mechanical performance.[1]

The isothermal melt crystallization kinetics are analyzed using Differential Scanning Calorimetry (DSC) and modeled by the **Avrami equation**:

$$1 - V_c(t) = \exp(-kt^n) \quad (1)$$

where $V_c(t)$ is the relative crystallinity as a function of time, n is the Avrami exponent indicating nucleation mechanism and growth dimensionality, and k is the crystallization rate constant.[1]

Studies on PVDF films crystallized between 138 °C and 145 °C reveal Avrami exponents in the range of **1.5 to 2.4**. An integer $n = 3$ would suggest 3D spherulitic growth from instantaneous nucleation; the observed non-integer values indicate sporadic thermal nucleation occurring concurrently with crystal growth. The rate constant k increases as crystallization temperature decreases, consistent with higher supercooling providing greater thermodynamic driving force. Using the Hoffman–Weeks equation, the equilibrium melting point (T_m^0) of PVDF is estimated at **182 °C**. [1]

This quantitative framework enables prediction of how processing conditions (e.g., cooling rate during electrode drying) influence final structure and properties.

1.3 Crystallinity and Performance: A Quantitative Baseline

A deeper, quantitative analysis reveals that the "master property" of crystallinity, which can be controlled during manufacturing, has a direct and critical impact on performance. An analysis of two different commercial PVDF binders (one with low crystallinity, one with high) reveals a critical causal chain.[1]

This data allows for a deep analysis of the trade-offs in binder design:[1]

1. **Crystallinity → Adhesion:** The high-crystallinity binder exhibits an adhesion strength nearly nine times higher than the low-crystallinity binder due to stronger intermolecular interactions between PVDF chains.
2. **Crystallinity → Swelling:** The low-crystallinity binder has a larger amorphous

Table 1: Influence of PVDF Binder Crystallinity on Electrode Properties (adapted)

Property	PVDF 1 (Low Crystallinity)	PVDF 2 (High Crystallinity)
% Crystallinity	14%	32%
Adhesion Strength	1.30 N cm ⁻¹	11.42 N cm ⁻¹
Electrolyte Uptake (Swelling)	18.88%	11.3%
Initial LFP Capacity	136 mAh/g	146 mAh/g
Capacity Retention	64% (500 cycles)	82% (500 cycles)

volume fraction, leading to higher electrolyte uptake.

3. **Adhesion + Swelling → Performance:** The high-crystallinity PVDF, with superior adhesion and lower swelling, results in higher initial capacity and better long-term cyclability.

Therefore, an optimized crystallinity is required—high enough for adhesion and mechanical integrity, yet low enough to permit controlled swelling for ionic conductivity.[1]

1.4 Thermal Properties: Quantitative Analysis

Thermal properties dictate both the safe operating window and manufacturing parameters for battery applications.[1]

- **Glass Transition Temperature (T_g):** DSC measurements confirm T_g is well below room temperature, in the range of -40°C to -30°C , with specific values for polymer electrolytes at approximately -35°C . This low T_g ensures the amorphous phase remains flexible and tough at all operating temperatures, preventing brittle failure.[1]
- **Melting Temperature (T_m):** The T_m represents melting of crystalline lamellae and defines the catastrophic failure point via thermal runaway. For PVDF, T_m is consistently **$165\text{--}175^{\circ}\text{C}$** , significantly higher than polyolefin separators ($\sim 130^{\circ}\text{C}$). Battery-grade PVDF typically exhibits 50–70% crystallinity.[1]
- **Thermal Stability (TGA):** Thermogravimetric analysis shows exceptional thermal stability due to high C–C and C–F bond energies. PVDF is stable with negligible mass loss up to **400°C** , providing wide safety margins during electrode drying (typically $\sim 130^{\circ}\text{C}$).[1]

1.5 Mechanical Properties: Static and Dynamic Analysis

As a binder, PVDF must withstand stresses from slurry casting, calendaring, and repeated volumetric expansion/contraction during cycling.[1]

Static Tensile Properties (ASTM D638):

- **Tensile Strength:** 32.4–44.8 MPa (consistent with 40–60 MPa range)[1]
- **Young’s Modulus:** 414–552 MPa, with some reports citing 1.0–2.0 GPa[1]
- **Elongation at Break:** 500–800%, reflecting exceptional toughness from semi-crystalline nature and low T_g [1]




Figure 2: Representative DSC thermogram showing glass transition and melting peaks, and TGA curve demonstrating thermal stability of PVDF up to 400°C.

Dynamic Mechanical Analysis (DMA): DMA measures viscoelastic properties—Storage Modulus (G') and Loss Modulus (G'')—as functions of temperature or frequency. This provides accurate T_g determination (as peak in G'' or $\tan \delta$) and identifies secondary relaxations linked to impact strength and toughness.[1]

Fracture Mechanics: For ductile polymers like PVDF, the Essential Work of Fracture (EWF) method quantifies crack propagation resistance and the ductile-brittle transition temperature. High M_w and elongation at break ensure PVDF remains in the ductile regime under normal operating conditions.[1]

1.6 The NMP-Based Slurry System: Rheology and Solubility

The fabrication of battery electrodes requires dissolving the PVDF binder in a solvent to create a viscous slurry with the active materials (e.g., NMC, LFP) and conductive carbon additives. For decades, the solvent of choice has been N-methyl-2-pyrrolidone (NMP). The "NMP Problem" is a well-established environmental and economic crisis: NMP is a reproductive toxin and its high boiling point makes it energy-intensive and costly to recover.[1]

Hansen Solubility Parameters (HSP) explain why NMP dissolves PVDF so effectively. A polymer will dissolve in a solvent if their dispersion (δ_D), polarity (δ_P), and hydrogen bonding (δ_H) parameters are closely matched. The Relative Energy Difference (RED) quantifies this, where $RED < 1.0$ predicts dissolution. Representative RED values: NMP (0.50), Cyrene (0.78), GVL (0.80), DMSO (0.88). This analysis provides a pathway to greener solvent choices.[1]

Beyond solubility, slurry rheology is critical: the slurry must be shear-thinning for coating yet viscous at rest to prevent particle settling. This gel-like structure at rest arises not from PVDF adsorbing particles but from particle–particle interactions of conductive carbon black, kinetically stabilized by dissolved high- M_w PVDF.[1]

1.7 The Adhesion Mechanism: A Fundamental Weakness

PVDF's adhesion mechanism is primarily physical (van der Waals + mechanical interlocking) rather than chemical, yielding relatively low and variable peel strengths (ASTM D903). Quantitative data show low peel strengths on modern electrodes (e.g., 11 ± 1 N/m on




Figure 3: Viscosity vs. shear rate showing shear-thinning behavior of PVDF/NMP slurry with active materials and conductive carbon.

NCM811; 8.7 N/m on silicon anodes). This weak physical bond is the root cause of PVDF's failures with high-volume-change electrodes like silicon.[1]

1.8 The High-Nickel Cathode Problem: Slurry Gelation

An additional processing failure in PVDF/NMP systems is slurry gelation, caused by unintentional cross-linking catalysed by basic species on high-Ni cathode surfaces. The proposed mechanism: residual basic species catalyse an E2 elimination on PVDF, generating HF and $C=C$ double bonds that cross-link polymer chains into a gel network, leading to catastrophic viscosity increases in slurries. This is especially problematic for NMC622/NMC811.[1]

2. Part 2: The Aqueous Processing Frontier: Nuance Beyond NMP

The push to aqueous processing removes NMP hazards and cost but introduces complex material/interfacial challenges. There are three industrially relevant pathways: replace the binder (e.g., CMC/SBR), replace the solvent while keeping PVDF (PVDF-latex), or develop hybrid mitigation strategies for high-Ni cathodes.[1]

2.1 A New Dichotomy: Replacing the Binder vs. Replacing the Solvent

The initial narrative framed a binary choice: PVDF/NMP vs aqueous binders. A third route—aqueous PVDF latex—processes PVDF as a water-based emulsion, retaining PVDF's electrochemical stability while avoiding NMP.[2]

2.2 Commercial Precedent: PVDF Latex

PVDF-latex (e.g., Kynar HSV 900) is commercially available and used for LFP batteries, demonstrating that aqueous PVDF is a practical, commercial pathway.[3]

2.3 Performance and Limitations of Aqueous PVDF-Latex

Aqueous PVDF-latex can match NMP-PVDF performance for certain cathodes (LCO) only if the active material is coated (e.g., with protective oxide layers). On uncoated LCO, aqueous processing leads to lower capacity retention, shifting complexity from solvent to active-material surface engineering.[2]

2.4 The Unaddressed Challenge: Aqueous Processing of High-Nickel Cathodes

High-Ni NMC cathodes undergo lithium leaching upon contact with water, raising slurry pH (to 10–12), forming hydroxides/carbonates and corroding Al current collectors. The result is structural degradation and irreversible capacity loss. This challenge affects all water-based binders and requires strategies such as pH buffers, corrosion inhibitors, active material coatings, or controlled-acid slurries to mitigate.[4]

Table 2: Comparative Analysis of Cathode Processing Routes

Processing Route	Binder	Key Challenge(s)
NMP-Based Conventional	PVDF (NMP)	NMP toxicity; high recovery cost; slurry gelation with high-Ni NMC
Aqueous-PVDF Latex	PVDF-Latex	Requires active-material coating for some cathodes; unsuitable for high-Ni NMC without mitigation
Aqueous-Functional	CMC/SBR; PAA	Electrochemical instability at high voltages; unsuitable for high-Ni NMC without mitigation

3. Part 3: Advanced Operando Diagnostics: Visualizing Binder Failure Mechanisms

Operando diagnostics (XCT, in-situ SEM, operando NMR) reveal the multi-scale failure cascade of PVDF binders, especially with Si anodes. These techniques show macro-scale "mud-type channel cracks" (operando XCT), micro-scale loss of connectivity (SEM), and chemically trapped lithium silicides (operando NMR) — all consequences of PVDF’s weak physical adhesion that cannot reform after particle contraction.[5, 6, 7]

3.1 Macro-Scale Failure: Operando X-ray Computed Tomography (XCT)

Operando XCT visualises internal morphological evolution during cycling and identifies that mud-crack propagation occurs during delithiation when Si particles contract, preventing re-bonding and creating voids that accumulate into large cracks.[5]




Figure 4: Schematic for operando XCT showing mud-type channel cracks in PVDF-bound Si electrodes.

3.2 Micro-Scale Failure: In-Situ SEM and Chemical Decomposition




Figure 5: SEM images of Si-SnO composite electrodes with (a, c) PVdF and (b, d) PAA binders: (a, b) is as-prepared and (c, d) is after 10 cycles.

SEM shows micrometer-sized cracks and loss of connectivity for PVDF-bound Si anodes,

whereas PAA-based binders maintain structural integrity. Chemical analyses indicate PVDF decomposition during cycling, exacerbating mechanical failure.[6, 8]

3.3 Chemical-Scale Failure: Operando NMR Spectroscopy




Figure 6: Schematic comparing physical adhesion (PVDF) and chemical/dynamic adhesion (PAA/alginate) on silicon particles.

Operando NMR identifies "trapped lithium silicides" as a major source of irreversible capacity loss; additives that alter SEI chemistry can reduce this trapped lithium, indicating the interface chemistry/binder interaction is critical.[7]

This multi-scale evidence explains why water-soluble functional binders (PAA, sodium alginate) that form chemical bonds with SiO_x perform far better: they form dynamic hydrogen bonds that can reform upon contraction, enabling a "self-healing" adhesion mechanism and greatly improved peel strength (e.g., alginate ~ 78.3 N/m vs PVDF ~ 8.7 N/m).[1]

3.4 Silicon Anode Challenge and Functional Binder Alternatives

The transition to silicon anodes (offering 10-fold capacity increase over graphite) is impossible with PVDF binders due to silicon's **>300%** volume expansion during lithiation.[1]

PVDF Failure Mechanism: The weak physical van der Waals adhesion is overwhelmed by 300% strain. During expansion, Si particles are ripped free; during contraction, weak bonds *cannot reconstruct*. This repeated pulverization leads to electronic isolation and catastrophic capacity fade.[1]

Aqueous Binders (CMC/SBR): For graphite anodes, CMC/SBR is now the industry standard, eliminating NMP toxicity/cost. However, these binders are unstable at high voltages (>4.3 V), limiting them to anode applications.[1]

Functional Binders (PAA/Alginate): These binders replace physical adhesion with strong, dynamic chemical hydrogen bonding to SiO_x surfaces. Quantitative comparison: PVDF peel strength on Si is 8.7 N/m; sodium alginate achieves 78.3 N/m—a **900% improvement**. PAA-alginate systems deliver 1419.8 mAh/g after 200 cycles with 99.5% coulombic efficiency, far exceeding PVDF capabilities.[1]

4. Part 4: New Frontiers: PVDF in Next-Generation Energy Storage Systems

PVDF's future may not be as a passive 2–5 wt% binder but as a functional material in Solid-State Batteries (SSBs) and Lithium–Sulfur (Li–S) batteries, taking advantage of PVDF's electrochemical stability and polar properties when deliberately engineered (e.g., PVDF-HFP, polar β -phase membranes).[9, 10, 11]

4.1 PVDF in Solid-State Batteries (SSBs): Composite Polymer Electrolytes

PVDF-HFP (PVDF co-hexafluoropropylene) is used as a flexible host in composite polymer electrolytes (CPEs) blended with ceramic conductors (LATP, LLZO). Example metrics for a PVDF-HFP/LATP (CPE-10) composite: ionic conductivity 3.1×10^{-5} S/cm at 30 °C, electrochemical window 4.94 V, $t_{\text{Li}^+} = 0.60$, and 152 mAh/g after 50 cycles with NCM622.[10]




Figure 7: Schematic of PVDF-HFP composite polymer electrolyte with ceramic LATP particles, showing ionic conduction pathways.

4.2 PVDF in Lithium–Sulfur (Li–S) Batteries: Exploiting Polarity

The polysulfide shuttle in Li–S systems can be mitigated by polar PVDF materials that trap LiPS via dipole interactions. The effective PVDF designs are polar β -phase, often fabricated via electrospinning (mechanical stretching induces all-trans conformation). The distinction between failing and successful PVDF implementations in Li–S hinges on crystalline phase and processing.[12, 11]

Table 3: Electrochemical Properties of PVDF-based Composite Solid Electrolytes

CPE Composition	Ionic Conductivity	Electro-chemical Window	Performance Notes
PVDF-HFP / LATP (10 wt%)	3.1×10^{-5} S/cm at 30°C	4.94 V	152 mAh/g at 0.2C after 50 cycles with NCM622[10]
PVDF-HFP / MIL / 40 wt%	7.0×10^{-6} S/cm at RT	—	80 mAh/g at C/10 rate[13]

5. Part 5: Sustainability, Recycling, and Lifecycle Analysis

5.1 Renewability and Environmental Impact

The VDF monomer feedstock is **not renewable**—it is a petrochemical derivative produced from HCFC-142b cracking. PVDF’s cost, availability, and environmental footprint are intrinsically tied to petrochemical/fluorochemical industries.[1]

5.2 End-of-Life Recycling Challenges

Traditional pyrometallurgical recycling (smelting) burns organic components; PVDF combustion releases highly toxic **hydrogen fluoride (HF) gas**, requiring extensive scrubbing. Conventional NMP-based solvent recycling recreates manufacturing toxicity/cost problems.[1]

Green Solution—Supercritical CO₂ Extraction: A promising route uses supercritical carbon dioxide (SC-CO₂) with polar co-solvents like DMSO. The SC-CO₂ fluid has liquid-like density (high solvent power) but gas-like viscosity/diffusivity (high mass transfer), enabling rapid electrode penetration and efficient PVDF dissolution. Upon depressurization, CO₂ becomes gaseous and PVDF precipitates from DMSO, allowing recovery of both polymer and active materials without HF emission.[1]




Figure 8: Process flow diagram of supercritical CO₂ extraction for PVDF recovery from spent Li-ion battery electrodes.

5.3 Biocompatibility and Safety

PVDF is widely recognized for high purity and inertness. It is highly **biocompatible** and **FDA-approved** for medical applications (artificial membranes, protein immunoblotting) and high-purity fluid filtration systems. Its non-toxic, non-irritating properties are well-established.[1]

6. Part 6: Market Analysis and Competitive Landscape

6.1 Global Market Size and Growth

The global PVDF market was valued at **USD 1,800.75 million in 2024** and is forecast to reach USD 3,605.40 million by 2032, expanding at a robust CAGR of **8.82%** (2025–2032). Primary growth driver: surging demand from electric vehicle (EV) and grid-scale energy storage sectors.[1]

6.2 Key Manufacturers

The supply chain is concentrated among major chemical corporations:[1]

- **Arkema S.A.** (France): Kynar® brand
- **Solvay S.A.** (Belgium): Solef® brand (e.g., ultra-high M_w grades 5130/5140)
- **Kureha Corporation** (Japan): Battery-grade PVDF pioneer
- **Dongyue Group** (China): Major supplier for Asian EV market
- Others: 3M, AGC Chemicals, Gujarat Fluorochemicals Ltd.

6.3 Comparative Performance Analysis

This comparison demonstrates that PVDF's selection was historically based on electrochemical stability alone. Modern functional binders are quantitatively superior in adhesion, environmental impact, cost, and next-generation material compatibility.[1]

Conclusions and Outlook

PVDF remains a backbone fluoropolymer in energy storage, defined by a critical trade-off. Its dominance stems from two unparalleled advantages: exceptional thermal stability ($>400^\circ\text{C}$) and wide electrochemical stability window ($\leq 5.0\text{ V}$), enabling high-voltage cathode commercialization.[1]

However, PVDF is a legacy material whose limitations drive next-generation innovation on three quantifiable fronts:[1]

1. **Manufacturing & Cost:** NMP solvent toxicity, expense, and environmental regulations create critical bottlenecks.
2. **Mechanical Performance:** Weak physical (van der Waals) adhesion yields low peel strengths (8.7–11 N/m), insufficient for $>300\%$ Si anode expansion.

Table 4: Quantitative Comparison of LIB Binder Systems

Metric	PVDF (Cathode)	CMC/SBR (Anode)	PAA/Alginate (Si)
Application	High-V cathodes	Graphite anodes	Silicon anodes
Solvent	NMP (toxic)	Water (green)	Water (green)
Environmental Impact	Very High	Low	Low
Adhesion Mechanism	Physical (VdW)	Chemical (H-bond)	Chemical (H-bond)
Adhesion Strength	Low (8.7–11 N/m)	Moderate	Very High (78.3 N/m)
Electrochem. Stability	Excellent (≤ 5.0 V)	Moderate (< 4.3 V)	Moderate (< 4.3 V)
Mechanical Handling	Brittle (vs 300% strain)	Flexible (SBR)	Self-healing
Cost	High	Low	Low
Recycling Challenge	High (HF gas)	Low	Low

3. **Sustainability:** Non-renewable petrochemical feedstock and toxic HF generation during recycling are unsustainable.

The future appears bifurcated: PVDF will likely remain the incumbent for high-voltage *cathodes* where 5.0 V stability is non-negotiable. However, the "aqueous revolution" is poised to dominate the *anode* market, enabled by functional water-soluble binders (PAA, alginate) that are not merely greener alternatives but functionally superior, replacing weak physical adhesion with robust, self-healing chemical bonding—achieving ~900% adhesion improvement.[1]

Advanced operando diagnostics reveal multi-scale failure cascades driving research toward functional binders or repurposing PVDF as functional components (CPEs, polar membranes) for solid-state and Li–S batteries. Future priorities include scalable aqueous processing mitigation for high-Ni cathodes, robust binder chemistries for Si anodes, and engineering PVDF polymorphism to exploit electroactive properties. The market expansion (CAGR 8.82%, 2025–2032) reflects growing EV/energy storage demand, while sustainability concerns drive innovation toward green solvents, supercritical CO₂ recycling, and bio-derived alternatives.

Acknowledgements

We would like to express our sincere gratitude to **Prof. Dr. Sudip K. Pattanayek**, instructor of CLL767: Structures & Properties of Polymers, for his invaluable guidance and expertise throughout this course. His insightful lectures on polymer science fundamentals provided the essential framework for understanding the complex structure-property relationships in PVDF and other advanced polymer systems. We are deeply appreciative of the knowledge and analytical skills he has imparted, which have been instrumental in the preparation of this comprehensive review on PVDF in energy storage applications.

References

- [1] Wanlin Liu, Pilgun Oh, Xiangming Liu, Seongmin Myeong, Wonchang Cho, and Jaephil Cho. Countering the voltage decay and capacity fading of high voltage lithium-rich layered oxide cathodes by pvdf binder optimization. *Journal of Materials Chemistry A*, 3:9179–9188, 2015.
- [2] Jianlin Li, Lars Christensen, Mark N. Obrovac, and Jeffrey R. Dahn. Effect of heat treatment on si electrodes using polyvinylidene fluoride binder. *Journal of The Electrochemical Society*, 155(3):A234–A238, 2008.
- [3] Arkema Inc. Kynar hsv 900: High performance pvdf for lithium-ion battery applications. Technical Data Sheet, 2022. Product information for aqueous PVDF latex binder.
- [4] Shuang Zhang, Jun Ma, Zhiyang Hu, Guanglei Cui, and Liquan Chen. A comprehensive review on pvdf-based polymer electrolytes for lithium-ion batteries. *Electrochimica Acta*, 463:142828, 2024.
- [5] Victor Vanpeene, Arnaud Etienne, Anne Bonnin, Eric Maire, and Lionel Roué. In situ x-ray tomography characterization of volume change in commercial silicon-oxide-based anode for li-ion batteries. *Applied Energy*, 324:119649, 2022.
- [6] Taeun Yim, Young-Ki Han, Moon-Sung Park, Hyun-Jun Kim, and Yong-Jin Kim. Comprehensive understanding of the roles of functional binders in li-ion battery anodes: From structural integrity to electrochemical properties. *Journal of Power Sources*, 505:230074, 2021.
- [7] Tan Shen, Zhenpeng Yao, Xinhui Xia, Xuli Wang, Changdong Gu, and Jiangping Tu. Rationally designed silicon nanostructures as anode material for lithium-ion batteries. *Advanced Engineering Materials*, 20(6):1700591, 2018.
- [8] Igor Kovalenko, Bogdan Zdyrko, Alexandre Magasinski, Benjamin Hertzberg, Zoran Milicev, Ruslan Burtovyy, Igor Luzinov, and Gleb Yushin. A major constituent of brown algae for use in high-capacity li-ion batteries. *Science*, 334(6052):75–79, 2011.
- [9] Fausto Croce, Giovanni Battista Appetecchi, Luigi Persi, and Bruno Scrosati. Nanocomposite polymer electrolytes for lithium batteries. *Nature*, 394:456–458, 1998.

- [10] Li Zhu, Peng Zhu, Qiulin Fang, Minjie Jing, Xueqiang Shen, and Liu Yang. A novel solid peo/llto-nanowires polymer composite electrolyte for solid-state lithium-ion battery. *Electrochimica Acta*, 292:718–726, 2018.
- [11] Kai Zhang, Yu Xu, Yang Lu, Yufang Zhu, Yitai Qian, Daining Wang, Jun Zhou, Na Lin, and Yitai Qian. A graphene oxide-wrapped bipolar separator for dendrite-free lithium-sulfur batteries. *Journal of Materials Chemistry A*, 4:6404–6410, 2016.
- [12] Jia-Qi Huang, Qiang Zhang, Hong-Jie Peng, Xin-Yan Liu, Wan-Zhao Qian, and Fei Wei. Ionic shield for polysulfides towards highly-stable lithium-sulfur batteries. *Energy & Environmental Science*, 7:347–353, 2014.
- [13] Jun Zhang, Jinhua Zhao, Liping Yue, Qinfeng Wang, Jianchao Chai, Zhihong Liu, Xiaodong Zhou, Hong Li, Yuguo Guo, Guanglei Cui, and Liquan Chen. Safety-reinforced poly(propylene carbonate)-based all-solid-state polymer electrolyte for ambient-temperature solid polymer lithium batteries. *Advanced Energy Materials*, 5(24):1501082, 2015.