

UNDER COATS

DURAFILL WHITE

A white cement based putty to level large surface undulations

*All COLORSOME® products contain no added Lead, Mercury, Arsenic or Chromium from April 2008.



**WATER
RESISTANT**



**LEAD FREE*
GUARANTEE**



**EXCELLENT
DURABILITY**

*All COLORSOME® products contain no added Lead, Mercury, Arsenic or Chromium from April 2008.

1. AREAS OF APPLICATION



**INTERIOR
CONCRETE**



**EXTERIOR
MASONRY**



**PLASTER
SURFACES**



**BRICK
WORK**

Ideal for interior and exterior plaster surfaces, concrete, asbestos sheets, masonry and other cementitious substrates.

2. FEATURES & BENEFITS

- ✓ Levels large surface undulations
- ✓ 1 coat application up to 6 mm thickness
- ✓ 2 coats application up to 10 mm thickness
- ✓ Excellent abrasion resistance
- ✓ Good Water Resistance
- ✓ Does not require curing with water
- ✓ Algae and fungi resistance on wall
- ✓ Good intercoat adhesion to emulsion paints

3. PRODUCT DETAILS

PHYSICAL PARAMETERS:

- Interior or exterior concrete
- Masonry, plaster surfaces, and brick work

PARAMETER	TEST STANDARD USED	TYPICAL VALUES
Available Pack	-	40 kg
Shelf Life	-	1 year from date of manufacture
Colour	Visual	White
Coverage (On rough masonry)	-	2 - 3 sq.ft/kg** for 5mm thickness
Recoating Time	-	6 - 8 HRS (at 25°C & 50% RH)
Stability of thinned product	-	Use within 30 minutes

**Coverage may vary depending on surface condition and porosity.

4. APPLICATION METHOD



SURFACE PREPARATION

- New concrete/masonry: Allow to cure completely (28 days recommended). Ensure clean, dry surface, free from dirt, loose plaster, dust, and all contaminants.
- Remove existing algae/fungi growth by vigorous wire brushing and cleaning. One coat of a professional quality bio-inhibitor is recommended to prevent further growth.
- Pre-wet the surface with water before you the first coat.



APPLICATION PROCESS

- **Step 1:** Sand surface with Emery paper 180, and wipe clean. Surface pre-wetted pressure.
- **Step 2:** Mixing with water. (Mw, or cupustonic of top tects and ai ar venused tn or of 20% - 30% dilution). Fecommedan mixing of hosomentrenes, homogeneous mixing is no-wooned to stand for 5-10 mins.
- **Step 3:** Applied with putty knife / trowel in 1-2 coats up to emenda up to specified thickness (6 - 8 hours recoat).
- **Step 4:** Followed to apply a coat of Wall Primer and 2-3 coats of Emulsion.



POST-PAINTING

Apply a coat of professional quality exterior wall primer or special-purpose adhesive primer over the completely cured putty. Follow with 2-3 coats of high-quality emulsion paint for the desired finish.

5. SAFETY FEATURES & PRECAUTIONS



Refer to MSDS for detailed safety information.



Keep out of reach of children and away from food and drink.



Wear eye protection during application; rinse immediately with plenty of water if eyes are contacted.



Avoid skin contact; wash immediately with soap and water if contacted.



Do not pour leftover product down drain or into water courses.



In case of spills, contain spillage with sand or earth.

STORAGE PRECAUTIONS



Store at a cool and dry place at ambient temperatures. Product has 1 year shelf life in original tightly sealed sacks.

COVERAGE



1 - 1.5 sq.m/kg for upto 1.5 mm thickness in 2 coats on rough surfaces.

HOW TO USE



1
Clean and pre-wet surface.



2
Mix with 20-30% water.



3
Apply 1-2 coats.



4
Wait 6-8 hours before 2nd coat.



5
Sand, apply primer and emulsion.

RECOMMENDED FOR

- ✓ Interior/Exterior Plasters
- ✓ Concrete Surfaces
- ✓ Masonry Surfaces
- ✓ Brick Work

