



PREMIUM ELASTOMERIC WATERPROOFING COATING

Elasticore Pro

High-performance, flexible coating for long-lasting waterproofing and crack bridging.



*All COLORSOME® products contain no added Lead, Mercury, Arsenic or Chromium.

1. AREAS OF APPLICATION



ROOFS & TERRACES



BALCONIES & WET AREAS



EXTERIOR WALLS



DRY AREAS

2. FEATURES AND BENEFITS

- ✓ EXCELLENT CRACK BRIDGING (Up to 4mm)
- ✓ HIGH ELONGATION (>450%)
- ✓ UV RESISTANT for durability
- ✓ BREATHABLE MEMBRANE prevents blistering
- ✓ EASY APPLICATION by brush or roller
- ✓ Excellent Washability
- ✓ Smooth Premium Finish
- ✓ Highly Durable Film
- ✓ Scrub Resistant
- ✓ Multisurface Application

3. PRODUCT DETAILS

PRODUCT PARAMETERS:

- Colour: White (Base)
- Packaging: 20 L Pail
- Shelf life: 2 Years

SPECIFICATIONS:

PARAMETER	TEST STANDARD USED	TYPICAL VALUES
Specific Gravity	ASTM D1475	1.28 ± 0.02
Solid Content by Weight	ASTM D1644	60 ± 2%
Elongation at Break	ASTM D412	>450%
Tensile Strength	ASTM D412	>1.5 MPa
Crack Bridging Ability	EN 1062-7	Up to 4 mm
Adhesion Strength	ASTM D4541	>0.8 MPa
Water Vapour Permeability	EN ISO 7783	Sd < 2 m (Class I)
Drying Time (Touch Dry)	-	2 – 4 hours

4. APPLICATION METHOD



SURFACE PREPARATION:

- Ensure substrate is clean, dry, sound, and free from dust, oil, grease, and loose materials.
- Repair cracks and defects with a suitable material.
- Prime as required.



PRIMING:

- Prime absorbent surfaces with a suitable primer diluted 1:1 with water.
- Allow to dry.



APPLICATION:

- Apply 'Elasticore Pro' in two coats using a brush, roller, or airless spray.
- Apply the second coat at 90° to the first after the first is fully dry (min. 8 hours).
- Ensure uniform thickness and proper coverage.
- Do not apply in wet conditions or if rain is imminent.

5. SAFETY FEATURES & PRECAUTIONS



Keep out of reach of children.



Avoid contact with skin and eyes.



Use protective gloves and eyewear during application.



In case of contact, rinse immediately with plenty of water and seek medical advice.



Ensure good ventilation during application.



Do not empty into drains or water courses.



Store in a cool, dry place away from direct sunlight.



Dispose of waste and containers responsibly according to local regulations.



6. STORAGE PRECAUTIONS



Store in a sealed container, in a cool, frost-free, dry area between 5°C and 30°C.

7. RECOMMENDED FOR

- ✓ New and existing concrete roofs, balconies, wet areas, and facades.
- ✓ Terraces & parapets
- ✓ Bathrooms & kitchens
- ✓ Water tanks & planters

8. HOW TO USE

- 1 PREPARE SURFACE (Clean & Dry)
- 2 PRIME (If necessary)
- 3 APPLY COAT 1 (Allow dry 8hr)
- 4 APPLY COAT 2 (Allow cure 7 days)



EXCELLENT CRACK BRIDGING (Up to 4mm)



HIGH ELONGATION (>450%)



UV RESISTANT



BREATHABLE MEMBRANE



EASY APPLICATION



LONG-LASTING PERFORMANCE