

WATERPROOFING

FlexiShield Pro

Premium, Flexible Waterproofing Coating



WATER BASED



LEAD FREE*
GUARANTEE



UV
RESISTANT

*All COLORSOME® products contain no added Lead, Mercury, Arsenic or Chromium compounds.

1. AREAS OF APPLICATION



CONCRETE
ROOFS



WALLS



BATHROOMS



FOUNDATION
WALLS



PARAPET
WALLS

Ideal for concrete roofs, walls, bathrooms, foundation walls, parapet walls and other exterior surfaces.

2. FEATURES AND BENEFITS

- ✓ Superior waterproofing protection
- ✓ Excellent 200% elongation for flexibility
- ✓ Creates a hydrophobic barrier
- ✓ Highly durable and washable finish
- ✓ Thermal resistance properties
- ✓ Easy application by brush or roller
- ✓ Non-toxic, safe for users
- ✓ No added heavy metals

3. PRODUCT DETAILS

CHEMICAL PARAMETERS:

Acrylic Emulsion Polymer

PHYSICAL PARAMETERS:

- Colour and appearance: White (viscous paste)
- Packaging: 20 L
- Shelf life: 2 Years
- Coverage: 1.5 - 2 kg per sq. m in two coats for 1mm DFT

PHYSICAL PARAMETERS:

PARAMETER	TEST STANDARD USED	TYPICAL VALUES
Viscosity (con sunit)	ASTM CD 1475	200 ng/d
Weight Per Liter	ASTM D 2370	>1.5 MPa
Elongation (%)	ASTM D 2270	450%
Crack Bridging	AS-NZ 4548	Up to 4mm
Solid Content (%)	ASTM C 1250	60%
Drying Time	BS EN 12390 - 0	20 mm
Water Permeability 7 Pa, 72 hours	Visual	White

4. APPLICATION METHOD



SURFACE PREPARATION

New Concrete Primer: should be cured for at least 28 days old and have a moisture content of less than 5 - 10%. Excessive laitance should be removed by mechanical methods. Dust and other detats should be removed by vacuum cleaning. Any fine clecks or pin holes should be covered with Epoxy-based mortar.

Old Concrete Planer: damaged areas or surface irregularities should be repaired using epoxy-based mortar. All cracks larger than hairline shall be considered as moving and must be repaired with epoxy-based mortar.

All delaminated and splashed areas of concrete shall be repaired prior to application of PUD with epoxy-based mortar.



PRIMING

- Apply Epoxy Primer as per recommended coverage of 80 - 100 Gram per square meter.

[Mixing ratio of Resin: Hardener: Water is 1 : 1 : 2 parts by weight]
- Allow primer to surface dry for 2 - 3 hours.



APPLICATION

Before application, mix the material well with mechanical mixer to get homogeneous brush able consistency. Apply mixed material with brush or roller at recommended coverage for first coat and allow to dry for 8 - 10 hours before 2nd coat applications, depending on the ambient conditions and surface temperature.

Similarly apply 2nd coat at recommended coverage, boot coat should be applied to cross - direction to each other.

Wet test may be performed when at least 72 hours have passed since application of the final coat.

5. SAFETY FEATURES & PRECAUTIONS



Kindly refer to the MSDS for Waterproof Primer which gives detailed information on safety measures.



Store the container with the lid tightly closed in an upright position, in a cool, dry place.



Keep out of reach of children and away from eatables.



Wear eye protection during application.



Wash skin with soap and plenty of water upon contact.



Do not breathe vapour or spray.



Store in a cool, dry place.

STORAGE PRECAUTIONS



Store at a cool and dry place at ambient temperatures.



RECOMMENDED FOR



- ✓ Roof Waterproofing
- ✓ External Wall Protection
- ✓ Damp prone areas
- ✓ Before Top Coat Application

HOW TO USE

- 1 Clean the surface and remove dust and loose particles.
- 2 Apply 1 coat of Epoxy Primer evenly.
- 3 Let it dry for 4-6 hours before applying top coat.



WATERPROOF



CRACK BRIDGING



UV RESISTANT



WEATHER RESISTANT

