



WATERPROOFING HydroShield

PREMIUM ELASTOMERIC WATERPROOFING COATING

HydroShield is a dual-function, high-performance waterproofing coating for horizontal and vertical surfaces.



WATER BASED



LEAD FREE



NO ADDED LEAD,
MERCURY OR
ARSENIC OR
CHROMIUM

1. AREAS OF APPLICATION



TERRACES



CHAJJAS



WET AREAS



PARAPET
WALLS

Ideal for terraces, chajjas, wet areas, retaining walls, parapet walls and other exterior surfaces.

2. FEATURES AND BENEFITS

- ✓ Best-in-class waterproofing of up to 3 bars pressure on vertical walls and 5 bars on horizontal surfaces.
- ✓ Superior crack bridging ability of up to 0.5mm on horizontal surfaces.
- ✓ Superior adhesion on all masonry and cementitious surfaces.
- ✓ 5 Years waterproofing warranty.
- ✓ Single product for both vertical and horizontal application.
- ✓ Water Based formulation.
- ✓ No Added Lead, Mercury, Arsenic or Chromium.

3. PRODUCT DETAILS

CHEMICAL PARAMETERS:

Elastomeric Acrylic Coating

PHYSICAL PARAMETERS:

- Colour and appearance: White (viscous pastes)
- Packaging: 20 L
- Shelf life: 5 years
- Coverage: 1.5 – 2.0 kg per sq. m in two coats for 1mm DFT
- Pack Size: 20 L

PHYSICAL PARAMETERS:

PARAMETER	TEST STANDARD USED	TYPICAL VALUES
Weight Per Liter	ASTM D 1475	1.2 kg
Tensile Strength	ASTM D 2370	>1.5 MPa
Elongation	ASTM D 2370	450%
Crack Bridging Ability	AS-NZ 4548	Up to 4mm
Solid Content	ASTM C 1250	60%
Water Impermeability 7 MPa, 72 hours	BS EN 12390-8	0 mm
Colour of Dry Film	Visual	White

4. APPLICATION METHOD



1 SURFACE PREPARATION

New concrete primer should be cured for at least 28 days and have a moisture content of less than 5%. Excessive laitance, dust, and debris should be removed mechanically, ensuring proper drainage.

Clean using loose paint, dust, or grease using wire brushing or water jet.



2 PRIMING

Apply Wall Primer as per recommended coverage of 80 – 100 g/m² on vertical walls and terraces.

Allow primer to dry completely.

Acrylic Wall Putty is recommended for vertical surfaces.

Crack Filler is recommended for both horizontal and vertical surfaces.



3 APPLICATION

Before application, mix the material with a mechanical mixer to get a homogeneous, brushable consistency. Apply mixed material with brush or roller at recommended coverage for first coat and allow to dry for 8 – 10 hours before second coat application, depending on the ambient conditions and surface temperature.

Similarly apply 2nd coat at recommended coverage, both coats should be applied in cross-direction to each other. Wet test may be performed when at least 72 hours have passed since application of the final coat.

5. SAFETY FEATURES & PRECAUTIONS



Refer to the MSDS for HydroShield for detailed information on safety measures.



Store upright in a cool, dry place away from direct sunlight.



Keep out of reach of children and away from foodstuffs.



Wear eye protection during application.



If swallowed, seek medical advice immediately.



Do not breathe vapour or spray near nose pad during sanding.



Do not pour leftover paint down the drain.



No added Lead, Mercury or Arsenic or Chromium compounds.

6. STORAGE PRECAUTIONS



Store at a cool and dry place at ambient temperatures.



RECOMMENDED FOR



- ✓ New Construction
- ✓ Renovation
- ✓ Damp prone areas
- ✓ Before Top Coat Application

HOW TO USE

- 1 Clean the surface and remove dust and loose particles.
- 2 Apply 1 coat of Wall Primer evenly.
- 3 Apply 2 coats of product evenly.
- 4 Let it dry for 4–6 hours before applying top coat.



WATERPROOF
BARRIER



CRACK BRIDGING



UV RESISTANT