

METALOCK ZINC PRO

PREMIUM ZINC PHOSPHATE COATING
ADVANCED CORROSION PROTECTION

Metalock Zinc Pro is a high-performance two-component epoxy zinc phosphate primer engineered to deliver exceptional corrosion protection and long-term durability for metal structures in the most demanding environments. Its advanced formulation provides superior adhesion, high surface tolerance, and excellent anti-rust properties. Metalock Zinc Pro can be used as both a primer and a topcoat, ensuring maximum performance and compatibility with a wide range of industrial coating systems.



SUPERIOR CORROSION PROTECTION

High zinc phosphate content offers excellent barrier protection against rust and corrosion.



EXCELLENT ADHESION

Strong bonding to mild steel and other metal substrates for long-lasting results.



HIGH SURFACE TOLERANCE

Effective performance even on less-than-ideal surface preparations.



DUAL-USE SYSTEM

Functions as both a primer and a topcoat for versatile application.



BUILT FOR EXTREME DURABILITY

Ideal for harsh industrial and marine environments where reliable corrosion protection is critical.

AVAILABLE PACK SIZES



1. WHY CHOOSE METALOCK ZINC PRO?



High-Performance Protection

Zinc phosphate technology provides superior corrosion resistance, extending the life of metal structures.



Excellent Adhesion

Ensures strong bonding on mild steel and delivers a tough, durable finish that resists peeling and chipping.



High Surface Tolerance

Ideal for surfaces with minor imperfections, reducing the need for extensive surface preparation.



Dual-Use Primer & Topcoat

Can be used as a standalone system or under a compatible topcoat for enhanced protection and finish.



System Compatibility

Compatible with most conventional and two-component industrial coating systems.



Long-Lasting Performance

Provides a hard, anti-corrosive film with excellent durability in aggressive conditions.

2. IDEAL FOR



New Construction Metal Surfaces

Ideal for structural steel, fabrication, tanks, pipelines, and more.



Industrial Maintenance Applications

Perfect for refineries, power plants, chemical plants, warehouses, and machinery.



Mild Steel Substrates

Engineered for ferrous metals and steel components.



3. PRODUCT DETAILS

TECHNICAL INFORMATION

- **Product Type**
Two-Component Epoxy Zinc Phosphate Primer
- **Technology**
Zinc Phosphate
- **Finish**
Matt
- **Application**
New construction metal surfaces; Maintenance applications; Mild steel substrates
- **Mixing Ratio**
As per data sheet
- **Thinner**
Epoxy Thinner
- **No. of Coats**
1-2 Coats Recommended
- **Drying Time (25°C)**
Surface Dry: 30 - 60 mins
Hard Dry: 6 - 8 hours
Recoat: 8 - 12 hours
- **Coverage**
9 - 12 m²/l/coat* (50 microns DFT)
- **Shelf Life**
12 months from date of manufacture
- **Color**
Grey Green

*Coverage may vary depending on surface profile, porosity and application method.

KEY BENEFITS



Superior Corrosion Protection



Excellent Adhesion to Mild Steel



High Surface Tolerance



Dual-Use Primer and Topcoat



System Compatibility



Long-Lasting Durability



Reliable Performance in Harsh Conditions

4. HOW TO APPLY



1 PREPARE SURFACE

Ensure the metal substrate is clean, dry, and free from loose rust, scale, oil, grease, dust, or other contaminants.

- Use abrasive blasting (Sa 2½) or power tool cleaning (St 2/3).
- Remove moisture completely before application.



2 MIX COMPONENTS

Thoroughly blend the two-component epoxy system according to the specified mixing ratio until a uniform consistency is achieved.

- Stir the base component well.
- Add hardener as per ratio.
- Mix continuously and allow induction time if specified.



3 APPLY COATING

Apply the mixture evenly to the surface using brush, roller, or airless spray.

- Maintain recommended film thickness.
- Allow sufficient time for curing before handling or overcoating.

5. SAFETY FEATURES & PRECAUTIONS



Wear protective gloves



Wear eye protection



Use in well-ventilated areas



Avoid inhalation of vapors



Keep out of reach of children



In case of contact with eyes, rinse immediately with plenty of water and seek medical advice.

- Keep container tightly closed when not in use.
- Do not ingest or inhale. If swallowed, seek medical advice immediately.
- Refer to the Material Safety Data Sheet (MSDS) for complete safety information.

STORAGE PRECAUTIONS



- Store in a cool, dry place away from direct sunlight and heat sources.
- Keep containers tightly closed when not in use.
- Protect from moisture and frost.
- Do not store near food, beverages or animal feed.
- Shelf life: 12 months from date of manufacture.

RECOMMENDED FOR

- ✓ New Construction Projects
- ✓ Industrial Maintenance Applications
- ✓ Mild Steel Substrates
- ✓ Fabrication Industries
- ✓ Power Plants
- ✓ Refineries & Petrochemical Plants
- ✓ Marine & Offshore Structures

SCAN TO KNOW MORE



SUPERIOR CORROSION PROTECTION



EXCELLENT ADHESION



HIGH SURFACE TOLERANCE



DUAL-USE SYSTEM



LONG-LASTING PERFORMANCE