

## Research article

# Utilization path of bulk industrial solid waste: A review on the multi-directional resource utilization path of phosphogypsum

Fenghui Wu <sup>a,b</sup>, Yuanchaun Ren <sup>a,b</sup>, Guangfei Qu <sup>a,b,\*</sup>, Shan Liu <sup>a,b</sup>, Bangjin Chen <sup>a,b</sup>, Xinxin Liu <sup>a,b</sup>, Chenyang Zhao <sup>a,b</sup>, Junyan Li <sup>a,b</sup>

<sup>a</sup> Faculty of Environmental Science and Engineering, Kunming University of Science and Technology, Yunnan, Kunming, 650500, China

<sup>b</sup> National Regional Engineering Research Center-NCW, Kunming, 650500, Yunnan, China

## ARTICLE INFO

### Keywords:

Resource utilization  
Solid wastes  
Multiple directions  
Diversification

## ABSTRACT

Phosphogypsum is one of the hottest issues in the field of environmental solid waste treatment, with complex and changeable composition. Meanwhile, phosphogypsum contains a large number of impurities, thus leading to the low resource utilization rate, and it can only be stockpiled in large quantities. Phosphogypsum occupies a lot of land and poses a serious pollution threat to the ecological environment. This paper mainly summarizes the existing pretreatment and resource utilization technology of phosphogypsum. The pretreatment mainly includes dry method and wet method. The resource utilization technology mainly includes building materials, chemical raw materials, agriculture, environmental functional materials, filling materials, carbon sequestration and rare and precious extraction. Although there are many aspects of resource utilization of phosphogypsum, the existing technology is far from being able to consume a large amount of accumulated and generated phosphogypsum. Through the analysis, the comparison and mechanism analysis of the existing multifaceted and multi-level resource treatment technologies of phosphogypsum, the four promising resource utilization directions of phosphogypsum are put forward, mainly including prefabricated building materials, eco-friendly materials and soil materials, and new green functional materials and chemical fillers. Moreover, this paper summarizes the research basis of multi field and all-round treatment and disposal of phosphogypsum, which reduces repeated researches and development, as well as the treatment cost of phosphogypsum. This paper could provide a feasible research direction for the resource treatment technology of phosphogypsum in the future, so as to improve the consumption of phosphogypsum and reduce environmental risks.

## 1. Introduction

Phosphogypsum is one of the main by-products produced in the production of phosphoric acid in phosphorus chemical enterprises (Gu and Chen, 2020; Kovler, 2012). As one of the main strategic resources in the world, especially in agriculture and military industry, phosphoric acid is produced from the treatment of apatite with sulfuric acid ( $H_2SO_4$ ). The production of PG is very tremendous in worldwide (Zhang et al., 2012a), because phosphorus chemical industries are widely distributed all over the world. Approximately 1–3 tons of PG is

generated per ton of apatite consumed for an annual worldwide production about 258 Mt in 2018 (Saadaoui et al., 2017). Over 280 Mt of PG output every year in the world is currently being discarded at coastal or else and stored at production sites as stockpiles (Maazoun and Bouassida, 2018), with about 80 Mt emitted in China (Ding et al., 2019). The familiar formula of the production of PG can be written as Eq. (1).



As environmental issues have become the focus of attention in the process of social development, PG has become one of the most important

**Abbreviations:** PG, Phosphogypsum; REE, Rare earth elements; MTE, Metal trace elements;  $\alpha$ -HH,  $\alpha$ -Hemihydrate ( $\alpha$ - $CaSO_4 \cdot 0.5H_2O$ ); CTAB, Ammonium bromide; PEG, Polyethylene glycol; PG-SPC, PG-sulfur polymer cements; HH-CSWs, Calcium sulfate hemihydrate whisker; CSWs,  $CaSO_4$  whiskers;  $\alpha$ -CSH,  $\alpha$ -Calcium sulfate hemihydrate; SRB, Sulfate reducing bacteria; SDBS, Sodium dodecyl benzene sulfonate; nHAp, Hydroxyapatite nanoparticles; Aft, Ettringite; FA, Fly ash; BCP, Biphasic calcium phosphate; CLG, Chemical Looping Gasification; BMED, Bipolar membrane electrodialysis; CMS, CO<sub>2</sub> mineral sequestration; CCUS, Carbon capture, utilization, and storage; CCS, Carbon capture and storage; C-S-H, Calcium-Silicate-Hydrate.

\* Corresponding author. Faculty of Environmental Science and Engineering, Kunming University of Science and Technology, Yunnan, Kunming, 650500, China.

E-mail address: [qgflab@sina.com](mailto:qgflab@sina.com) (G. Qu).

striking spots of environmental protection problems (Wang et al., 2018; Ngsbraga, 2018; Ben Chokriet al., 2017; Perez-Lopez et al., 2016; V-M et al., 2021; D, 1977; Lieberman et al., 2020; Liu, 2100). The global resource utilization rate of phosphogypsum is less than 15%. With the continuous decline of phosphate rock grade, the production of phosphogypsum increases year by year (Tayibi et al., 2009). The main components of phosphogypsum are  $\text{CaSO}_4 \cdot n\text{H}_2\text{O}$  ( $n = 0, 1.5, 2$ ), mixed with calcium phosphate in various forms, silica and a broad range of other impurities such as iron oxide ( $\text{Fe}_2\text{O}_3$ ), magnesium (Mg) and aluminum (Al), sulfides, organic matter and metal trace elements (MTE) (Hammas-Nasri et al., 2016; Masmoudi-Soussi et al., 2019; El Zrelli et al., 2019; Kuzmanovic et al., 2020). These impurities mainly exist in phosphogypsum in the form of lattice doping, atom replacement, surface adsorption and interstitial filling. The impurities and the lattice morphology seriously restrict the resource utilization of PG (Szajerski, 2020). Presently, research on the resource utilization field of PG primarily centers on the following aspects: preparing cement coproduced sulfuric acid (Rosales et al., 2020), preparing building materials (Wang et al., 2020a), soil conditioner (Samet et al., 2019), and preparing high-strength gypsum (Lu et al., 2019a), preparing  $\text{CaCO}_4$  (Chen et al., 2020a), calcium sulfate whiskers (CSWs) (Tan et al., 2017), agricultural fertilizer (Dias et al., 2010; Abril et al., 2009; Cruciol et al., 2016), soil amendments (Kassir et al., 2012; Hentati et al., 2015; Li et al., 2015), and so forth (Canovas et al., 2019). Especially, many works revealed the enormous opportunities related to the use of PG in different application fields. Different production methods and equipment of PG could lead to subtle changes in the composition and properties of PG (Meskini et al., 2021; Min et al., 2008a; Ajam et al., 2009; Huang and Lin, 2010; Gai-ducis et al., 2011; Shen et al., 2014; Bouchima et al., 2013; ZCKA et al., 2014; Rashad, 2015; Zhao et al., 2015; Hua et al., 2016; Youqiang Huang et al., 2016; Li et al., 2017). As a result, large-scale utilization rate of PG is low, and a series of environment problems are caused by long-term accumulation, which seriously restricts the development of

phosphorus chemical enterprises, so that the utilization of PG is a quite important problem (Ennaciri and Bettach, 2018; Wdrychowicz et al., 2019).

To sum up, the treatment of PG is always the key problem of solid waste treatment. However, new key technologies and field that could be used to consume PG on a large scale are still required, aiming to further improve the rate of resource utilization. This paper reviewed the research status of different high-added value utilization and harmless treatment of PG, and the advantages and disadvantages of PG treatment technology were analyzed and compared. Finally, the effective development prospect of PG treatment was proposed to solve the problem of massive stacking and production of PG.

## 2. The basic characteristics and properties of PG

With the development of science and technology, more and more characterization methods of materials are applied to PG to detect the composition, physical and chemical properties, and so on.

Many research literatures illustrate the main components and basic properties of PG, as shown in Fig. 1. The basic characterization shows that the main components of PG are  $\text{CaSO}_4 \cdot 2\text{H}_2\text{O}$  and  $\text{SiO}_2$ , accounting for more than 90%, and some toxic and harmful elements, including phosphorus(P), fluorine(F), arsenic (As), chromium (Cr), cadmium (Cd), metal trace elements (MTE), and rare earth elements (REE). The particle size distribution of most PG produced is mainly in the range of 10–1000  $\mu\text{m}$ , and it belongs to fine powder. The moisture content of PG is 5%–28%, which results in the agglomeration of fine particles and reduces the generation of dust. The micro morphology of PG is mainly flake irregular, rhombic and other crystal morphology, and a lot of impurities are adsorbed on its surface. The basic research on PG provides theoretical support for its subsequent resource utilization research.




Fig. 1. SEM-EDS, XRD, XRF and particle size distribution characterizations of PG (Mi et al., 2019; Gong et al., 2020a; Wu et al., 2020).

### 3. Pretreatment technologies and application of PG

#### 3.1. Pretreatment technologies of PG

At present, the pretreatment methods of PG mainly include ultrasonic pretreatment, microwave treatment (Kavitha et al., 2013), thermal treatment (Ségalen et al., 2015), chemical conditioning and water leaching (ColomboPalumboJZet al., 2014).

##### 3.1.1. Wet pretreatment methods

For a long time, the majority of science and technology workers have conducted a lot of researches on the pretreatment of PG (Singh, 2002), and mainly focused on the following aspect, namely water washing method that can remove a large number of impurities such as P, F and heavy metals adsorbed on  $\text{CaSO}_4 \cdot 2\text{H}_2\text{O}$ . However, PG is slightly soluble in water, the washing liquid belongs to secondary wastewater, which is easy to cause secondary pollution and increase the treatment cost of secondary pollutants. The traditional flotation method can remove organic matter suspended in PG slurry naturally adding flotation agents, but fails to thoroughly remove P and F. Besides, the method is slow and inefficient. Lime was added to the PG, the soluble P and F in the lime and PG reacted to form insoluble P and F, and the precipitation method reduced the influence of soluble P and F on the building materials. However, after a long time, insoluble P and F will slowly dissolve out, which cannot fundamentally reduce the influence of P and F on PG (Reijnders, 2007; Wang et al., 2020b; Gijbels et al., 2020; Mashifana, 2019). Obviously, there are still many problems to be solved in the wet pretreatment of PG. In order to reduce the treatment cost of PG and improve its resource utilization efficiency, new pretreatment technologies still need to be developed.

##### 3.1.2. Thermal pretreatment methods

The thermal treatment method is the main technology for PG dehydration and stimulating gelling activity (Cao et al., 2022a; Ma et al., 2020). Thermal treatment is the best method in reducing the content of organic matter and removing volatile impurities (Liu et al., 2020; Contreras et al., 2015; Yang et al., 2011; Azouazi et al., 2001). Azouazi et al. (2001) found a reduction in the average radionuclide leaching rate from 26.4% to 6%, with thermal treatment at 800 °C. Ren et al. (Contreras et al., 2015) tested different thermal treatment conditions and reported a significant decrease in the content of soluble P and F. Cesniene (Cao et al., 2022b) evaluated PG thermal treatment at 400 °C, 600 °C and 800 °C for 1 h each to obtain anhydrous calcium sulfate. Singh and Garg (2005a) thermal treated PG at 1000 °C for a period of 4 h–5 h to make anhydrous calcium sulfate to be used in polymerized flooring composition. Min et al. (2008b) used a temperature of 135 °C for 3 h in the thermal treatment process. Degirmenci (Degirmenci, 2008) prepared hemihydrate gypsum at 150 °C for 2 h. Canut et al. (Cavalcanti Canut et al., 2008) prepared anhydrous gypsum at 160 °C for 1 h. Garg et al. (2016) prepared anhydrous calcium sulfate by calcining PG at temperatures of 150°C–160 °C for 4 h. Bumanis et al. (2018) thermal treated PG at the temperatures of 100 °C, 120 °C, 140 °C, 160 °C, and 180 °C for 4 h to obtain a binder material. Liu et al. (2020) tested different conditions to PG thermal treatment: 0.5 h, 1 h, 1.5 h, and 2 h of residence time on kiln and temperatures of 150 °C, 350 °C, 600 °C, and 800 °C. The authors stated that the increase in the thermal treatment temperature and time resulted in the conversion of soluble phosphorus impurities ( $2\text{CaHPO}_4 \cdot 2\text{H}_2\text{O}$ ) into calcium pyrophosphate ( $\text{Ca}_2\text{P}_2\text{O}_7$ ), with an insoluble and harmless substance. Rodrigo H. Geraldo et al. (2020) evaluated the temperature of 150 °C with residence times on the kiln of 1 h and 2 h, and they found that adequate parameters can obtain considerable HH- $\text{CaSO}_4$  content with lower energy consumption. The main bottleneck of thermal treatment is that it needs high temperature, thus leading to high energy consumption. Moreover, under high temperature, many volatile components volatilize and need to be treated with tail gas, which increases the process complexity and treatment cost.

#### 3.2. The application of PG in building materials

With the rapid development of the construction industry and the continuous improvement of people's living standards, the demand for building materials is also increasing. Most building raw materials come from natural sources and destroy the ecological environment. Due to the huge storage and output of PG and the special properties of PG, it can be used as a substitute for building raw materials. The by-product PG is often used as a building material (Rashad, 2017). The following mainly introduces several main utilization directions of phosphogypsum in the field of building materials.

##### 3.2.1. Preparation of $\alpha$ -HH from PG

$\alpha$ -Hemihydrate ( $\alpha\text{-CaSO}_4 \cdot 0.5\text{H}_2\text{O}$ ,  $\alpha$ -HH) is also called high-strength gypsum, and it is a high value-added cementitious material with superior workability, remarkable mechanical strength and excellent environmental performance (Jiang et al., 2016). Furthermore, it has been widely applied in the chemical and construction industry (Ma et al., 2018). Preparation of  $\alpha$ -HH using PG as raw material is an important utilization approach. A traditional method to synthesize  $\alpha$ -HH is in an autoclave under high temperature and pressure. However, the autoclave method is strictly limited by its special equipment and safety issues (Li et al., 2013). Recently, the solution method was proposed to prepare  $\alpha$ -HH under normal condition, and  $\text{NaCl}$ ,  $\text{KCl}$ ,  $\text{CaCl}_2$ ,  $\text{MgCl}_2$ ,  $\text{Na}_2\text{SO}_4$  and their mixed salts were used as a crystallization agent (Guan et al., 2012; Guan et al., 2009; Shen BHG and Fu, 2009). Van Driessche et al. (Van Driessche et al., 2012) found the recrystallization of PG at under-saturated conditions (Stawski et al., 2016), and the experimental evidence has revealed the dissolution and re-nucleation mechanism of PG (Ossorio et al., 2017). Saha et al. (2012) also demonstrated that the transformation of  $\alpha$ -HH to PG was a multistep particle formation model, where an amorphous phase forms first, followed by the transformation into a crystalline product, and the addition of citric acid significantly delays the reorganization to PG crystals. The morphology of  $\alpha$ -HH is one of the most important factors affecting mechanical properties. Generally,  $\alpha$ -HH particles with a low aspect ratio possess better workability and mechanical strength than that of needle-like or higher aspect ratio crystals (Duan et al., 2017). Therefore, the preparation of  $\alpha$ -HH with a special morphology of crystals is very important in the industry, and the morphology of  $\alpha$ -HH can be effectively regulated by crystal modifier. Currently, the crystal modifiers mainly include inorganic salt, organic acid, surfactant, alcohols and macromolecule. Extensive studies have proved that the organic acid can suppress the crystal growth of  $\alpha$ -HH along the c-axis. For example, the short hexagonal prism  $\alpha$ -HH prepared from PG in glycerol-water solutions could be obtained by adding succinic acid (Guan et al., 2017a, 2017b; Li et al., 2018, 2019; Wang et al., 2017a; Tan et al., 2020; Yang et al., 2016a; Chen et al., 2018; Lu et al., 2019b), (Ma et al., 2018). With the continuous development of the research on the preparation of  $\alpha$ -HH from PG, many methods and processes have emerged. As displayed in Table 1, a variety of preparation methods and effects of  $\alpha$ -HH are proposed.

Although the preparation of  $\alpha$ -HH from PG is the best way of high value-added resource utilization, its cost and energy consumption are relatively high. Combined with the huge accumulation and output of PG, it is unable to achieve a large amount of consumption.

##### 3.2.2. The application of PG in construction and building field

PG is widely used in the field of building materials. The following aspects are discussed: ① Application of PG in retarder (Akin Altun and Sert, 2004; Huang et al., 2020; Singh, 2003; Garg et al., 2009; Kuryatnyk et al., 2008). ② Waterproof material (Wang et al., 2020c). ③ Burn-free bricks and gypsum blocks (Zhou et al., 2012, 2016a, 2020; Yang et al., 2009; Zielinski, 2015), the mechanism of two-step hydration process (Zhou et al., 2014a; Zhou et al., 2016b; Zhou et al., 2014b; Lz et al., 2016). ④ Road material (Li et al., 2020; Silva et al., 2019; Tsika and Voudrias, 2020; Moussa et al., 1984; Saleh and Rahman, 2016; Singh

and Garg, 2005b; Verbeek and Plessis, 2005; Lopez et al., 2011), (Rashad, 2015). ⑥Self-leveling mortar (Wang and Jia, 2019; Yang et al., 2016b). ⑦Foam concrete (Bencic et al., 2011; del Río-Merino et al., 2022). ⑧Non-autoclaved aerated concrete (Colak, 2000; Rubio-Avalos et al., 2005; Bazelová et al., 2010; Bencic et al., 2011; del Río-Merino et al., 2022; Huang et al., 2013; Umponpanarat Wansomet et al., 2015; TianYan et al., 2016; Lin et al., 2013). ⑨Haydraulic binder (Diouri et al., 2022), (Kuryatnyk et al., 2008). It is a kind of functional material, while its dosage is small. Facing a large amount of PG, its contribution rate seems to be relatively weak.

No matter what kind of materials PG is used for, its mechanism of action is similar, as illustrated in Fig. 2.

The utilization mechanism of PG in the field of building materials mainly includes: (1) dissolution crystallization. PG has a slight solubility in water, especially that salt solution can enhance the solubility. The dissolution process destroys the lattice structure of PG, releases impurities, and then recrystallizes to form pure calcium sulfate-based materials. (2) According to the principle of dehydration rehydration, the main component of PG is calcium sulfate dihydrate that has stable properties and no gelling activity. However, it can remove  $1.5\text{H}_2\text{O}$  to form  $\beta$ ,  $\alpha$ -HH, with excellent performance in all aspects. As an important building material, it can remove  $2\text{H}_2\text{O}$  to form anhydrous calcium sulfate and remove most harmful impurities of dehydration at the same time. Rehydration can form high performance building materials.

The consumption of PG accounts for a large proportion in the field of building materials, but with the enhancement of public awareness of environmental protection, PG building materials are resisted. Compared with natural materials, most people are not willing to accept solid waste based building materials, and the market of PG based building materials becomes a constraint. Only by changing the public's awareness of solid waste and the government's strong support can the utilization of PG in the field of building materials have a qualitative breakthrough.

### 3.3. The application of PG in preparation of chemical raw materials

The main components of PG are Ca, S and O source. More than 80% of the content can be used as special raw materials for chemical reaction. In many studies, the application of PG as Ca and S source as raw material is introduced in detail.

#### 3.3.1. Production of $\text{H}_2\text{SO}_4$ from PG and co-production of cement

The technology of producing  $\text{H}_2\text{SO}_4$  and cement with PG as main raw material has matured research and application. The apparent solid-solid reaction between CaS and PG has been widely applied in the production of sulfuric acid and cement (Wang et al., 2020d). López FA et al. studied the microencapsulation of PG into a sulfur polymer matrix to prepare a

new type of PG-sulfur polymer cements (PG-SPC) to be utilized in the manufacture of building materials (López et al., 2011). Sichuan Wu et al. prepared iron-rich calcium sulfoaluminate cement, with gypsum as the sole calcium oxide source and its incorporation into mineral phases (Wu et al., 2021). Although the research of this technology has been relatively mature, it still has various disadvantages, such as high preparation cost, high energy consumption and gaseous pollution, so most of its application has been discontinued, and relatively cheap and safe treatment technology needs to be developed.

#### 3.3.2. Preparation of calcium sulfate whiskers from PG

The main component of PG is crystalline calcium sulfate ( $\text{CaSO}_4 \cdot n\text{H}_2\text{O}$ ,  $n = 0, 0.5, 2$ ) (Kovler, 2012). Therefore, the preparation of ( $\text{CaSO}_4$  whiskers) CSWs from PG is a feasible way for high value-added utilization of gypsum solid waste and reduction of resource waste (Zhang et al., 2012a), and it is also one of the most valuable research directions for the resource utilization of PG. CSWs has a lot of advantages, including high temperature resistance, chemical corrosion resistance, good toughness, high strength, easy surface treatment, and strong affinity with polymers such as rubber and plastics (Perez-Lopez et al., 2016). If the PG produced every year in the world can be prepared into the CSWs for resource utilization, it can not only solve the problem of the fate of a large number of PG, but also produce good economic effect.

So far, there are many methods for crystal preparation, including solution growth, melt growth and vapor growth, as shown in Table 2.


In addition to the above synthesis methods, biochemical activation method can enhance the nucleation ability in the crystallization process. The common hydrothermal synthesis methods are exhibited in Table 3.

Although CSWs has high economic value, its preparation cost is high, time is long, and output is low, so it is necessary to investigate a new process of PG whisker preparation with low cost and high yield.

#### 3.3.3. The application of sulfur and calcium source in PG

PG contains a lot of S elements that can be used to prepare sulfur-containing chemical raw materials and pyrolysis, and the utilization of PG will decompose gradually from water to calcium sulfate when it is heated in inert atmosphere. The transformation to CaS was completed at 1080 °C (Msila et al., 2015), and reductive decomposition of PG had high S concentration coal to  $\text{SO}_2$  in an inert atmosphere (Zheng et al., 2011). Liping Ma (Zheng et al., 2018) researched on thermal decomposing properties of PG with Fe addition under multi-atmosphere control, proposed a series of technical process for the decomposition of PG with Fe addition, such as  $\text{K}_2\text{SO}_4$ . The pure  $\text{K}_2\text{SO}_4$  is colorless crystal, and the appearance of agricultural  $\text{K}_2\text{SO}_4$  is light yellow.  $\text{K}_2\text{SO}_4$  is a prominent water-soluble potassium fertilizer. Gan Z et al. proposed an efficient methodology via the co-reaction of K-feldspar and PG for the extraction of soluble potassium salts. The reaction parameters were systematically investigated with the highest S recovery ratio of about 60% (Gan et al., 2016; Ennaciri et al., 2019; Abu-Eishah et al., 2000). In addition, ammonium sulfate preparation from PG waste (Kandil et al., 2016) and chemical looping gasification of PG, as an oxygen carrier (Jing et al., 2019), were the utilization way of sulfur source in PG. The utilization of S source in PG has broad application prospects. At present, there are many researches on the preparation of  $\text{K}_2\text{SO}_4$ , while the mature production process has not yet been formed, and it is still in the laboratory research stage. Therefore, the research on the utilization of sulfur source needs to be further promoted.

The research on the utilization of Ca source in PG involves a wide range of aspects, including the resource utilization of PG, the formation of Ca based cementitious materials in building materials, pure Ca chemicals in chemical raw materials, etc. (Hammas et al., 2013)







**Fig. 2.** Preparation process and mechanism of building materials.

### 3.4. The application of PG in agriculture

PG contains a lot of S, Ca, P and other metal components, many of which are essential for plant growth. However, because of its strong acidity and corrosiveness, it cannot be directly used in soil, but after harmless treatment, it can be used as saline alkali soil, alkaline soil and non-food crop soil. PG, as sulfate source for sulfate-reducing bacteria (de Oliveira Melgaco et al., 2020), had positive effects on the bacterial richness and diversity, and negative effects on the fungal richness and diversity. PG changed the composition and succession of the microbial community by influencing different physiochemical properties during various composting stages where the pH was the main explanatory factor (Lei et al., 2021).

PG belongs to acidic waste and contains trace plant growth elements. Guerrero JL et al. used PG to improve salt marshes soil (Guerrero et al., 2019). The salt-marsh sediment produces a “barrier effect” for the 238U series natural radionuclides coming from the PG stacks decreasing rapidly their activity concentration with depth (Papaslioti et al., 2020) effect of PG and poultry manure on aggregate-associated alkaline characteristics in bauxite residue (Xue et al., 2020), and the main reaction equations are shown in chemical formulas (2) - (9).



Based on natural soil covers with organic amendment, these findings propose the possibility of using naturally-occurring SRB in the PG for bioremediation strategies (Castillo et al., 2012). Due to the variety of harmful components and potential harm forms in PG, the utilization of PG in agriculture is limited.

### 3.5. Preparation of environmental functional materials

PG has significant physical properties, so it has broad prospects in the preparation of environmental functional materials. Zhao L used sodium dodecyl sulfonate and modified PG to prepare the exclusive adsorption material for copper, and the removal rate is as high as 99.23% (Zhao et al., 2020). As the raw material for the preparation of adsorption materials, PG has broad application prospects, but its preparation cost, secondary pollution, waterproof performance and other factors need to be considered (Kadirova et al., 2014). Some researchers used phosphogypsum and clay to store radioactive element uranium (VI), and its adsorption capacity is 0.09 mol/kg, which indicated that it has good effects and has a certain utilization prospect in radioactive material treatment (Syczewski et al., 2020). PG was utilized to prepare hydroxyapatite nanoparticles (nHAp) via microwave irradiation technology, and the adsorption behaviour of F onto the nHAp derived from PG was investigated to evaluate the potential application of this material for the treatment of the wastewater polluted with F. The results indicated that the nHAp derived from PG can be used as an efficient adsorbent for the removal of F from aqueous solution (Zhang et al., 2012b). The utilization of PG for the preparation of porous sound absorbs material (Ma et al., 2020). Gong prepared Nano-CaSO<sub>4</sub> from PG, and this method is economical and applicable for the comprehensive utilization of PG (Gong et al., 2020b). Although the application of PG in the preparation of environmental functional materials has a high utilization prospect,

the research on the occurrence mechanism, migration and transformation law of many toxic and harmful substances in PG is still not clear, and there exists the risk of secondary pollution to the environment.

### 3.6. The application of filling materials

The technical feasibility and economic rationality of various PG comprehensive utilization schemes are based on the effective control of PG impurity composition and moisture content. Through the analysis of the resource application of PG in engineering and agriculture, it is difficult for the existing resource technology to achieve the purpose of large-scale efficient resource utilization of PG, and it is hard to have good economic value. The existing chemical enterprises have not achieved the commercialized output and harmless discharge of PG waste residue. Since PG contains a large number of impurities with complex components and there is still a risk of leaching after generating resource products, pretreatment is required before the comprehensive utilization of PG. According to different components and utilization directions of PG, different treatment and disposal methods were adopted, so as to realize the modification of PG composition and structure and improve the resource application performance and economic value of PG (Rong et al., 2020).

The research and development applications of PG comprehensive utilization products should be inclined towards the direction of large dosage, high added value and many ways. The application in cement retarder, building gypsum cementitious materials and new building materials will be the main direction. Paying attention to the impurity removal and modification of PG can lay a solid foundation for PG to replace natural gypsum, effectively expand the application field and improve the content of PG ingredients. Therefore, the project mainly modifies PG in advance and solidifies its harmful impurities, so that it can be used as ecological restoration materials. Combined with the actual situation of the project, it can be used as pit filling. Most importantly, it can not only solve the problem of massive stockpiling of PG, but also meet the purpose of secondary utilization of PG in the future (Zhang et al., 2021).

### 3.7. The application of CO<sub>2</sub> capture

The emission of greenhouse gas carbon dioxide rises sharply with the accelerated development of economy. As a major environmental problem faced by mankind, the greenhouse effect caused by excessive carbon dioxide emission seriously threatens the earth's environment on which mankind depends. In view of the technical and economic difficulties in the development and application of new energy, the existing energy structure is difficult to change significantly in the short term, and carbon dioxide emissions will rise sharply. Therefore, the solidification of carbon dioxide and related resource regeneration have attracted close attention, with broad development prospect. The main methods of carbon reduction are solidification transformation and separation and purification. Solidification and transformation technology includes carbonate product generation and storage technology. At present, Tianjin Institute of Industrial Biotechnology uses carbon dioxide to synthesize starch. Separation and purification technologies include solvent absorption method, adsorption method, membrane separation method, low-temperature distillation method, and newly developed carbon dioxide recombination method, electrochemical method, biological carbon dioxide recovery technology and hydrate method. Although the above technologies have made great progress, they generally have the disadvantages of high energy consumption and high investment. Meanwhile, there are some problems in the reaction process to be further solved. The threats of global warming and climate change provide a new driving force for carbon dioxide separation technology (Zhang et al., 2020).

At present, the research on the carbon neutralization of PG is shown

in Fig. 3, mainly including A-F carbon solidification mechanism, in which A mechanism mainly treats waste with waste, mixes other solid wastes with phosphogypsum, dissolves and carbonizes, so as to achieve the synergistic solidification effect of  $\text{CO}_2$ ; B mechanism is mainly the synergistic carbon solidification of minerals, such as potassium feldspar; C mechanism is mainly the mechanism of plant synergistic carbon solidification, and mainly uses the photosynthesis of plants, the absorption of roots and the secretion of hormones; D mechanism is mainly the excitation of basic chemical reagents; E is mainly solidified and stabilized by the generated CAS after thermal decomposition. Compared with D mechanism, F mechanism increases the pretreatment stage. The above six carbon curing mechanisms are the most common methods at present. Due to the huge output of industrial solid waste, carbon neutralization with industrial solid waste has become a research hotspot (Kumar et al., 2020). As the main component of PG is crystalline calcium sulfate ( $\text{CaSO}_4 \cdot 2\text{H}_2\text{O}$ ), the treatment of industrial carbon dioxide, containing tail gas with waste gypsum, is an important way of high value-added utilization of waste gypsum solid waste, thus reducing resource waste and carbon emission reduction. On the other hand, it is the most valuable research direction of resource utilization of waste gypsum solid waste. If China uses gypsum waste to treat industrial carbon dioxide containing tail gas for resource utilization, it can not only solve the fate of a large number of waste gypsum solid waste, but also achieve the goal of carbon emission reduction and produce good economic value. What's more, it can improve the earth's environment with good social and economic benefits. Most importantly, it has deeply practiced the concept

that green water and green mountains are golden mountains and silver mountains (Gan et al., 2016) (Romero-Hermida et al., 2017).

### 3.8. The application of extracting rare earth elements

A growing interest has emerged towards resource development and processing of rare earth elements (REE) that have become indispensable elements in human daily life (Goodenough et al., 2016), (Virolainen et al., 2019). Depending on the type and source of the PG, the REE content ranges between 0.05% and 2% (Binnemans et al., 2015a; Walawalkar et al., 2016). Between 2020 and 2025, the global demand for REE will gradually increase, which could make the source of REE a key factor to be considered as the solid waste or the search for alternative sources (Wang et al., 2017b; Binnemans et al., 2015b). PG is an example of such environmentally harmful wastes containing REE (70%–85%) (Binnemans et al., 2015b; Aly and Mohammed, 1999). Previous studies proved that leaching PG with acids creates favorable conditions for the migration of REE from the solid phase to the leach solution (Kurkinen et al., 2021), (Costis et al., 2021; Brueckner et al., 2020; Gasser et al., 2019). As one of the hot solid wastes all over the world, PG contains a variety of rare and precious heavy metals. With the rapid development of the industry, the market demand for rare and precious heavy metals is gradually increasing. Extracting rare and precious heavy metals from solid wastes has become an important way for high value-added treatment of solid wastes as one of the main sources of rare and precious heavy metals. While reducing the development of natural






Fig. 3. Process and mechanism of carbon dioxide solidification (Zhang et al., 2020).



resources, environmental protection is realized. The PG leaching solution is long-term precipitation and surface runoff, which carries out long-term flushing of PG and transfers a large number of rare and precious heavy metals to the leaching solution. The leaching solution is continuously transpiration and volatilization in the atmosphere, thus realizing the high concentration enrichment of REE in the leaching solution (Andreevet al., 2014; Kurkinen et al., 2021; Plyatsuk et al., 2020; Gupta and Krishnamurthy, 1992; John et al., 2018; Qi and Qi, 2018; Zheng et al., 2019), and the main reaction equations are shown in chemical formulas (10) and (11) under acidic conditions (Z et al., 2015).



Carbonate and bicarbonate salts are preferred as precipitation agents. The precipitation takes place in ambient conditions. Depending on the time of the reaction, either hydrated REE carbonates (Equation (12)) or REE hydroxy carbonates are formed (Paul et al., 2018; Chi et al., 2003).



The decomposition of the phosphates from monazite with caustic soda can be summarized with the following Equations (13) and (14) (Zhang et al., 2016; Sadri et al., 2017).



The common extraction technology of REE is displayed in Fig. 4. The main steps are as follows. After the PG was washed by water or solvent, the solid components of PG were dried at a certain temperature, and the components of washing solution can be recycled. This process was called pretreatment stage. Solid PG was digested by leaching agent. Segmented digestion can be set according to the demand. After valuable elements were leached, solid-liquid separation was carried out and the liquid part was collected. This process was called dissolution of REE. The liquid part used special adsorption materials to purify and separate REE, while the liquid part can be recycled. This part is called REE purification and separation. The whole process realized the extraction of REE. In addition, ion-exchange resins, leaching agents, and eluents were systematically investigated for the recovery of REE from PG by a resin in leach process. Based on the equilibrium batch experiments performed with and without an ion-exchange resin, it is not necessary to break the gypsum structure to recover REE (Voncken, 2016; Virolainen et al., 2019; Omodara et al., 2019; Riddle et al., 2021), (Costis et al., 2021).


Although there have been a lot of studies on the extraction of rare and precious metals from PG, the existing technical means cannot be

used for low-cost extraction due to its high cost and low content of rare and precious metals, which leads to the failure of industrial application.

### 3.9. Other application fields

PG prepares biphasic calcium phosphate (BCP) (Mohamed et al., 2014), and hydrothermal synthesis of nanocrystalline hydroxyapatite is from PG waste (Bensalah et al., 2018). Syngas can be obtained through a properly designed lignite Chemical Looping Gasification (CLG) of PG oxygen carrier (Yang et al., 2017), and the main reaction equations are shown in chemical formulas (15) - (22).

#### (a) Lignite gasification



#### (b) PG reduction

##### Main reaction:



Of course, a hot research in recent years, the resource research direction of PG does stay in the above aspects. Here, we will not discuss it one by one.

## 4. Main resource utilization mechanism of PG

In the process of resource utilization of PG, there are the following main mechanisms (As shown in Figs. 5 and 6.). First, multi physical strengthening of dissolution and decomposition in the crystallization mechanism. PG dissolves in water or solvent. Ultrasonic, temperature, electromagnetic, stirring speed and other physical conditions will accelerate the destruction of PG crystal lattice, accelerate its dissolution, and release rare and precious heavy metals, phosphorus, fluorine and





Fig. 4. Extraction technology of REE.

Fig. 5. Resource utilization mechanism of PG.



**Fig. 6.** The solidification mechanism of PG (Chen et al., 2020b).

other impurities. The released substances react with the added solvents to form new and different kinds of substances, including rare and precious heavy metals, chemical raw materials, calcium based and sulfur based pure chemicals. Combined with the research reports of peers at home and abroad, it is not difficult to infer that the crystallization mechanism mainly dissociates the elements (atoms, molecules and ions) that make up the crystal that strictly controls the growth conditions, and re combines them under the driving of chemical potential, so that multiple physical fields can provide different forms of energy and conditions. Therefore, there are multiple physical field coupling effects that can regulate the crystal growth and crystal transformation of PG and improve the controllability of gypsum products. When an electric field is applied during the dissolution and crystallization of PG, the electrons released by the electric field can make PG produce a large number of high-energy molecular excited states and secondary electrons. A series of physicochemical changes will occur in the excited states and secondary electrons with higher energy, such as chemical bond fracture, suprathreshold ionization, suprathreshold dissociation, bond softening, coulomb explosion, the reorientation of molecules in strong field, and the formation of new excited states. When the magnetic field is applied, they are directionally distributed under the action of the magnetic field due to the uniform paramagnetic and diamagnetic substances in PG. When ultrasonic field is applied, the energy provided by ultrasonic can change and break the original lattice shape of waste gypsum. When the temperature is applied, it can provide the energy required for gypsum crystal growth and crystal form. Secondly, as shown in Fig. 5, PG decomposes and reacts with external additives to form precipitates, complexes and gelling active substances, which improves the stability, plasticity and gelling activity of PG. At the same time, the toxic and harmful impurities in PG are solidified and stabilized in the form of coordination, capsule wrapping and adsorption, as shown in Fig. 6. The heavy metals, phosphorus and fluorine mainly form hydroxide and normal acid salt precipitation ( $\text{NH}_4\text{MgPO}_4 \cdot 6\text{H}_2\text{O}$ ,  $\text{Mn}_5(\text{PO}_4)_2(\text{OH})_4$ ,  $\text{Mn}_3(\text{PO}_4)_2 \cdot 3\text{H}_2\text{O}$ ,  $\text{Mn}(\text{OH})_2$ ,  $\text{Ca}(\text{OH})_2$ ,  $\text{Mg}_2(\text{PO}_4)\text{F}$ ,  $\text{CaMgPO}_4\text{F}$ ,  $\text{MgF}_2$ ,  $\text{CaF}_2$  and  $\text{Ca}_3(\text{PO}_4)_2$ ), which reduces its release efficiency under normal environment and realizes the long-term solidification and stabilization effect.

## 5. Conclusion and future prospects

As one of the main industrial by-products, PG has become one of the hot spots in the research of bulk solid waste, mainly including multi-directional building materials, preparation of chemical raw materials and other aspects, because of its huge output and storage. However, due to the special properties of PG, it is still unable to consume a large amount of PG to reduce the environmental risk of PG. The following research directions of PG are proposed.

- (1) Research on the sustainability of PG cycle can be improved by the combination of electrodialysis and bipolar membrane (Monat

et al., 2020). The result is a cleaner and more circular process, as NaOH can be recycled for dissolving PG, while  $\text{H}_2\text{SO}_4$  can be reintroduced into the industrial phosphoric acid production or used to leach valuable metals out of the PG. However, to assess the feasibility of BMED integration, its industrial application research needs further exploration.

- (2) Prefabricated building materials. With the continuous improvement of people's living standards, many works of art and crafts can be seen everywhere in our daily life. PG is mainly composed of calcium sulfate, which has good plasticity and can be prepared into a variety of process exhibits. The rheological property control of PG is an important technical means for PG to be used in prefabricated building materials. It has broad research value and significance to improve the utilization rate and consumption of PG, especially in 3D printing of PG.
- (3) New green functional materials. PG contains more than 80% calcium sulfate dihydrate that is a green material. The main harmful components in PG are phosphorus, fluorine and heavy metals. The harmful components are solidified and will not release and migrate with time. On this basis, green environmental protection materials with special functions are prepared.
- (4) Ecological and environmental friendly filling materials and soil utilization. With the continuous development of mineral resources, there are many mines on the earth's surface, resulting in many geological disasters. Backfilling after harmless treatment of PG not only solves the problems of environmental risks and geological disasters, but also solves the problem of massive accumulation of PG. At the same time, facing the world soil barren, grain crops reduce production. In order to solve the problem of people's livelihood while solving the PG destination, phosphorus source is used in PG as fertilizer of food crops. However, the low cost harmless treatment of PG has been the limiting factor of large-scale treatment of PG.
- (5) Chemical filler. The inexpensive chemical filler can obviously enhance the mechanical properties of rubbers, plastics, adhesives and papers, with great potential to become ideal reinforcing materials.

The large-scale processing technology of PG is not a problem that can be solved by a single technology, but a variety of technologies for collaborative disposal. On the other hand, the comprehensive and multi-level integrated processing technology has become the main research hotspot of PG consumption.

## Declaration of competing interest

The authors declare that they have no known competing financial interests or personal relationships that could have appeared to influence the work reported in this paper.

## Acknowledgments

This work is supported by The National Key Research and Development Plan-Ecological Link Technology for Clean processing of Typical by-products of Unconventional Wet/thermal Production (2018YFC1900203). The National Natural Science Foundation of China - Migration and transformation of heavy metals in lead and zinc tailings and the stabilization (51968033).

## Appendix A. Supplementary data

Supplementary data to this article can be found online at <https://doi.org/10.1016/j.jenvman.2022.114957>.

## References

- Abrial, J.M., Garcia-Tenorio, R., Perianez, R., et al., 2009. Occupational dosimetric assessment (inhalation pathway) from the application of phosphogypsum in agriculture in South West Spain [J]. *J. Environ. Radioact.* 100 (1), 29–34. <https://doi.org/10.1016/j.jenvrad.2008.09.000>.
- Abu-Eishah, S.I., Bani-Kananeh, A.A., Allawzi, M.A., 2000. K<sub>2</sub>SO<sub>4</sub> production via the double decomposition reaction of KCl and phosphogypsum [J]. *Chem. Eng.* 76 (3), 197–207. [https://doi.org/10.1016/S1385-8947\(99\)00158-8](https://doi.org/10.1016/S1385-8947(99)00158-8).
- Ajami, L., Ouezdou, M.B., Felfoul, H.S., et al., 2009. Characterization of the Tunisian phosphogypsum and its valorization in clay bricks [J]. *Construct. Build. Mater.* 23 (10), 3240–3247. <https://doi.org/10.1016/j.conbuildmat.2009.05.009>.
- Akin Altun, I., Sert, Y., 2004. Utilization of weathered phosphogypsum as set retarder in Portland cement [J]. *Cement Concr. Res.* 34 (4), 677–680. <https://doi.org/10.1016/j.cemconres.2003.10.017>.
- Aly, M.M., Mohammed, N.A., 1999. Recovery of lanthanides from Abu Tartur phosphate rock, Egypt [J]. *Hydrometallurgy* 52 (2), 199–206. [https://doi.org/10.1016/S0304-386X\(99\)00018-3](https://doi.org/10.1016/S0304-386X(99)00018-3).
- Andreev, V.A., et al., 2014. Phosphogypsum Technology with the Extraction of Valuable Components [J]. *A. V. Procedia Chemistry.* <https://doi.org/10.1016/j.proche.2014.11.031>.
- Azouazi, M., Ouahidi, Y., Fakhi, S., et al., 2001. Natural radioactivity in phosphates, phosphogypsum and natural waters in Morocco [J]. *J. Environ. Radioact.* 54 (2), 231–242. [https://doi.org/10.1016/S0265-931X\(00\)00153-3](https://doi.org/10.1016/S0265-931X(00)00153-3).
- Bazelová, Z., Pach, L., Lokaj, J., 2010. The effect of surface active substance concentration on the properties of foamed and non-foamed gypsum [J]. *Ceramics* 54 (4), 379–385. <https://www.webofscience.com/wos/alldb/full-record/WOS:000286027800014>.
- Ben, Romdhane, Chokri, et al., 2017. Phosphogypsum: potential uses and problems-a review [J]. *Int. J. Environ. Stud.* <https://doi.org/10.1080/00207233.2017.1330582>.
- Bensalah, H., Bekheet, M.F., Younssi, S.A., et al., 2018. Hydrothermal synthesis of nanocrystalline hydroxyapatite from phosphogypsum waste [J]. *J. Environ. Chem. Eng.* 6 (1), 1347–1352. <https://doi.org/10.1016/j.jece.2018.01.052>.
- Binnemanns, K., Jones, P.T., Blanpain, B., et al., 2015a. Towards zero-waste valorisation of rare-earth-containing industrial process residues: a critical review [J]. *J. Clean. Prod.* 99 (Jul.15), 17–38. <https://doi.org/10.1016/j.jclepro.2015.02.089>.
- Binnemanns, K., Jones, P.T., Blanpain, B., et al., 2015b. Towards zero-waste valorisation of rare-earth-containing industrial process residues: a critical review [J]. *J. Clean. Prod.* 99, 17–38. <https://doi.org/10.1016/j.jclepro.2015.02.089>.
- Bouchchima, L., Rouis, M.J., Choura, M., 2013. Engineering properties of wade sand lime-cement-phosphogypsum building brick grade MW [J]. *Int. J. Eng. Adv. Technol.* 2 (4), 43–49. <https://www.researchgate.net/publication/28056580>.
- Brenicis, R., Skujans, J., Iljins, U., et al., 2011. Research of Hemp Fibrous Reinforcement Effect to Bending Strength and Sound Absorption of Foam Gypsum [J], pp. 32–37. <https://www.webofscience.com/wos/alldb/full-record/WOS:000379311400005>.
- Brueckner, L., Elwert, T., Schirmer, T., 2020. Extraction of rare earth elements from phospho-gypsum: concentrate digestion, Leaching, and Purification [J]. *Metals* 10 (1). <https://doi.org/10.3390/met10010131>.
- Bumanis, G., Zorica, J., Bajare, D., et al., 2018. Technological properties of phosphogypsum binder obtained from fertilizer production waste. In: International Scientific Conference Environmental and Climate Technologies, Conect 2018, pp. 301–308. <https://doi.org/10.1016/j.egypro.2018.07.096>.
- Canovas, C.R., Chapron, S., Arrachart, G., et al., 2019. Leaching of rare earth elements (REEs) and impurities from phosphogypsum: a preliminary insight for further recovery of critical raw materials [J]. *J. Clean. Prod.* 219, 225–235. <https://doi.org/10.1016/j.jclepro.2019.02.104>.
- Cao, W., Yi, W., Peng, J., et al., 2022a. Preparation of anhydrite from phosphogypsum: influence of phosphorus and fluorine impurities on the performances [J]. *Construct. Build. Mater.* 318, 126021. <https://doi.org/10.1016/j.conbuildmat.2021.126021>.
- Cao, W., Yi, W., Peng, J., et al., 2022b. Recycling of phosphogypsum to prepare gypsum plaster: effect of calcination temperature [J]. *J. Build. Eng.* 45, 103511. <https://doi.org/10.1016/j.jobe.2021.103511>.
- Castillo, J., Perez-Lopez, R., Sarmiento, A.M., et al., 2012. Evaluation of organic substrates to enhance the sulfate-reducing activity in phosphogypsum [J]. *Sci. Total Environ.* 439C (Nov.15), 106–113. <https://doi.org/10.1016/j.scitotenv.2012.09.035>.
- Cavalcanti Canut, M.M., Feliciano Jacomino, V.M., Bratveit, K., et al., 2008. Microstructural analyses of phosphogypsum generated by Brazilian fertilizer industries [J]. *Mater. Char.* 59 (4), 365–373. <https://doi.org/10.1016/j.matchar.2007.02.001>.
- Chen, X., Gao, J., Liu, C., et al., 2018. Effect of neutralization on the setting and hardening characters of hemihydrate phosphogypsum plaster [J]. *Construct. Build. Mater.* 190 (NOV.30), 53–64. <https://doi.org/10.1016/j.conbuildmat.2018.09.095>.
- Chen, Q., Ding, W., Sun, H., et al., 2020a. Utilization of phosphogypsum to prepare high-purity CaCO<sub>3</sub> in the NH<sub>4</sub>Cl-NH<sub>4</sub>OH-CO<sub>2</sub> system [J]. *ACS Sustain. Chem. Eng.* 8 (31), 11649–11657. <https://doi.org/10.1021/acssuschemeng.0c03070>.
- Chen, H., Long, Q., Zhang, Y., et al., 2020b. A novel method for the stabilization of soluble contaminants in electrolytic manganese residue: using low-cost phosphogypsum leachate and magnesia/calcium oxide [J]. *Ecotoxicol. Environ. Saf.* 194, 110384. <https://doi.org/10.1016/j.ecoenv.2020.110384>.
- Chi, R., Zhou, Z., Xu, Z., et al., 2003. Solution-chemistry analysis of ammonium bicarbonate consumption in rare-earth-element precipitation [J]. *Metall. Mater. Trans. B* 34 (5), 611–617. <https://doi.org/10.1007/s11663-003-0031-z>.
- Colak, A., 2000. Density and strength characteristics of foamed gypsum [J]. *Cement Concr. Compos.* 22 (3), 193–200. [https://doi.org/10.1016/S0958-9465\(00\)00008-1](https://doi.org/10.1016/S0958-9465(00)00008-1).
- Colombo, Palumbo, J.Z., et al., 2014. Review on iron availability in soil: interaction of Fe minerals, plants, and microbes [J]. *J. Soil Sediment.* 14 (3), 538–548. <https://doi.org/10.1007/s11368-013-0814-z>, 2014.
- Contreras, M., Perez-Lopez, R., Gazquez, M.J., et al., 2015. Fractionation and fluxes of metals and radionuclides during the recycling process of phosphogypsum wastes applied to mineral CO<sub>2</sub> sequestration [J]. *Waste Manag.* 45, 412–419. <https://doi.org/10.1016/j.wasman.2015.06.046>.
- Costis, S., Mueller, K.K., Coudert, L., et al., 2021. Recovery potential of rare earth elements from mining and industrial residues: a review and cases studies [J]. *J. Geochem. Explor.* 221, 106699. <https://doi.org/10.1016/j.gexplo.2020.106699>.
- Crusciol, C.A.C., Artigiani, A.C.C.A., Arf, O., et al., 2016. Soil fertility, plant nutrition, and grain yield of upland rice affected by surface application of lime, silicate, and phosphogypsum in a tropical no-till system [J]. *Catena* 137, 87–99. <https://doi.org/10.1016/j.catena.2015.09.009>.
- THE VEBA PHOSPHORIC ACID PROCESS, 1977. ScienceDirect [J]. N. Dev. Phosphate Fert. Technol. 314–329. <https://doi.org/10.1016/B978-0-444-41535-6.50021-5>.
- Degirmenci, N., 2008. Utilization of phosphogypsum as raw and calcined material in manufacturing of building products [J]. *Construct. Build. Mater.* 22 (8), 1857–1862. <https://doi.org/10.1016/j.conbuildmat.2007.04.024>.
- Dias, N.M.P., Caires, E.F., Pires, L.F., et al., 2010. Radiological impact of phosphogypsum application in agriculture. In: Alarcon, R., Arellano, H.F., Cole, P.L. (Eds.), VIII Latin American Symposium on Nuclear Physics and Applications, p. 447. <https://doi.org/10.1063/1.3480230>, +.
- Ding, W., Chen, Q., Sun, H., et al., 2019. Modified mineral carbonation of phosphogypsum for CO<sub>2</sub> sequestration [J]. *J. CO<sub>2</sub> Util.* 34, 507–515. <https://doi.org/10.1016/j.jcou.2019.08.002>.
- Diouri, C., Echekbani, I., Lahiou, K., et al., 2022. Valorization of Moroccan Phosphogypsum in Road Engineering: Parametric Study [J]. *Materials Today: Proceedings.* <https://doi.org/10.1016/j.matpr.2022.01.084>.
- Van Driessche, A.E.S., Benning, L.G., Rodriguez-Blanco, J.D., et al., 2012. The role and implications of bassanite as a stable precursor phase to gypsum precipitation [J]. *Science* 336 (6077), 69–72. <https://doi.org/10.1126/science.1215648>.
- Duan, Z., Li, J., Li, T., et al., 2017. Influence of crystal modifier on the preparation of α-hemihydrate gypsum from phosphogypsum [J]. *Construct. Build. Mater.* 133, 323–329. <https://doi.org/10.1016/j.conbuildmat.2016.12.060>.
- Ennaciri, Y., Bettach, M., 2018. Procedure to convert phosphogypsum waste into valuable products [J]. *Mater. Manuf. Process.* 33 (16), 1727–1733. <https://doi.org/10.1080/10426914.2018.1476763>.
- Ennaciri, Y., Alaoui-Belghiti, H.E., Bettach, M., 2019. Comparative study of K<sub>2</sub>SO<sub>4</sub> production by wet conversion from phosphogypsum and synthetic gypsum [J]. *J. Mater. Res. Technol.* 8 (3), 2586–2596. <https://doi.org/10.1016/j.jmrt.2019.02.013>.
- Gaiducis, S., Zvirionaitė, J., Maciulaitis, R., Jakovlev, G., 2011. Resistance of phosphogypsum cement pozzolanic compositions against the influence of water [J]. *Mater. Sci.* 17 (3), 308–313. <https://doi.org/10.5755/j01.ms.17.3.599>.
- Gan, Z., Cui, Z., Yue, H., et al., 2016. An efficient methodology for utilization of K-feldspar and phosphogypsum with reduced energy consumption and CO<sub>2</sub> emissions [J]. *Chin. J. Chem. Eng.* 24, 1541–1551. <https://doi.org/10.1016/j.cjche.2016.04.001>, 011.
- Garg, M., Jain, N., Singh, M., 2009. Development of alpha plaster from phosphogypsum for cementitious binders [J]. *Construct. Build. Mater.* 23 (10), 3138–3143. <https://doi.org/10.1016/j.conbuildmat.2009.06.024>.
- Garg, M., Pundir, A., Singh, R., 2016. Modifications in water resistance and engineering properties of beta-calcium sulphate hemihydrate plaster-superplasticizer blends [J]. *Mater. Struct.* 49 (8), 3253–3263. <https://doi.org/10.1617/s11527-015-0717-0>.
- Gasser, M.S., Ismail, Z.H., Elgoud, E., et al., 2019. Process for lanthanides-Y leaching from phosphogypsum fertilizers using weak acids [J]. *J. Hazard Mater.* 378, 120762. <https://doi.org/10.1016/j.hazmat.2019.120762>.
- Geraldo, R.H., Costa, A.R.D., Kanai, J., et al., 2020. Calcination parameters on phosphogypsum waste recycling [J]. *Construct. Build. Mater.* 256, 119406. <https://doi.org/10.1016/j.conbuildmat.2020.119406>.
- Gijbels, K., Nguyen, H., Kinnunen, P., et al., 2020. Radiological and leaching assessment of an ettringite-based mortar from ladle slag and phosphogypsum [J]. *Cement Concr. Res.* 128, 105954. <https://doi.org/10.1016/j.cemconres.2019.105954>.
- Gong, X., Liu, J., Sun, Z., et al., 2020a. Effects of phosphogypsum and calcined phosphogypsum content on the basic physical and mechanical properties of portland

- cement mortar [J]. *J. Test. Eval.* 48 (5), 3539–3549. <https://doi.org/10.1520/JTE2018038>.
- Gong, S., Li, X., Song, F., et al., 2020b. Preparation and application in HDPE of nano-CaSO<sub>4</sub> from phosphogypsum [J]. *ACS Sustain. Chem. Eng.* 8 (11), 4511–4520. <https://doi.org/10.1021/acssuschemeng.9b07632>.
- Goodenough, K.M., Schilling, J., Jonsson, E., et al., 2016. Europe's rare earth element resource potential: an overview of REE metallogenetic provinces and their geodynamic setting [J]. *Ore Geol. Rev.* 72, 838–856. <https://doi.org/10.1016/j.oregeorev.2015.09.019>.
- Gu, K., Chen, B., 2020. Loess stabilization using cement, waste phosphogypsum, fly ash and quicklime for self-compacting rammed earth construction [J]. *Construct. Build. Mater.* 231, 117195. <https://doi.org/10.1016/j.conbuildmat.2019.117195>.
- Guan, B., Yang, L., Wu, Z., et al., 2009. Preparation of  $\alpha$ -calcium sulfate hemihydrate from PG in K-Mg-containing concentrated CaCl<sub>2</sub> solution under mild conditions [J]. *Fuel* 88 (7), 1286–1293. <https://doi.org/10.1016/j.fuel.2009.01.004>.
- Guan, B., Kong, B., Fu, H., et al., 2012. Pilot scale preparation of  $\alpha$ -calcium sulfate hemihydrate from PG in Ca-K-Mg aqueous solution under atmospheric pressure [J]. *Fuel* 98, 48–54. <https://doi.org/10.1016/j.fuel.2012.03.03>.
- Guan, Q., Tang, H., Wei, S., et al., 2017a. Insight into influence of glycerol on preparing  $\alpha$ -CaSO<sub>4</sub>H<sub>2</sub>O from flue gas PG in glycerol-water solutions with succinic acid and NaCl [J]. *Ind. Eng. Chem. Res.* 56 (35) <https://doi.org/10.1021/acs.iecr.7b02067>.
- Guan, Q.-J., Sun, W., Hu, Y.-H., et al., 2017b. Synthesis of alpha-CaSO<sub>4</sub> center dot 0.5H<sub>2</sub>O from flue gas PG regulated by C4H<sub>4</sub>O<sub>4</sub>Na<sub>2</sub> center dot 6H<sub>2</sub>O and NaCl in glycerol-water solution [J]. *RSC Adv.* 7 (44), 27807–27815. <https://doi.org/10.1039/C7RA03280C>.
- Guerrero, J.L., Gutiérrez-Ivarez, I., Mosqueda, F., et al., 2019. Evaluation of the radioactive pollution in the salt-marshes under a phosphogypsum stack system [J]. *Environ. Pollut.* 258, 113729. <https://doi.org/10.1016/j.envpol.2019.113729>.
- Gupta, C.K., Krishnamurthy, 1992. Extractive metallurgy of rare earths [J]. *Int. Mater. Rev.* <https://doi.org/10.1179/1879139513Y.0000000081>.
- Hammas, I., Horchani-Naifer, K., Férid, M., 2013. Solubility study and valorization of phosphogypsum salt solution [J]. *Int. J. Miner. Process.* 123 (36), 87–93. <https://doi.org/10.1016/j.minpro.2013.05.008>.
- Hammas-Nasri, I., Horchani-Naifer, K., Férid, M., et al., 2016. Rare earths concentration from phosphogypsum waste by two-step leaching method [J]. *Int. J. Miner. Process.* 149, 78–83. <https://doi.org/10.1016/j.minpro.2016.02.011>.
- Hentati, O., Abrantes, N., Caetano, A.L., et al., 2015. Phosphogypsum as a soil fertilizer: ecotoxicity of amended soil and elutriates to bacteria, invertebrates, algae and plants [J]. *J. Hazard. Mater.* 294, 80–89. <https://doi.org/10.1016/j.jhazmat.2015.03.034>.
- Hua, S., Wang, K., Yao, X., et al., 2016. Effects of fibers on mechanical properties and freeze-thaw resistance of phosphogypsum-slag based cementitious materials [J]. *Construct. Build. Mater.* 121 (SEP.15), 290–299. <https://doi.org/10.1016/j.conbuildmat.2016.06.00>.
- Huang, Y., Lin, Z.S., 2010. Investigation on phosphogypsum–steel slag–granulated blast-furnace slag–limestone cement [J]. *Construct. Build. Mater.* 24 (7), 1296–1301. <https://doi.org/10.1016/j.conbuildmat.2009.12.006>.
- Huang, B., Zhang, Y., Li, D.X., 2013. Study on the Influences of Foaming Gypsums Performance [C]. Trans Tech Publications, pp. 222–227. <https://doi.org/10.3303/CET1125027>.
- Huang, Y., Qian, J., Lu, L., et al., 2020. Phosphogypsum as a component of calcium sulfoaluminate cement: hazardous elements immobilization, radioactivity and performances [J]. *J. Clean. Prod.* 248, 119287. <https://doi.org/10.1016/j.jclepro.2019.119287>.
- Jiang, G., Wang, H., Chen, Q., et al., 2016. Preparation of alpha-calcium sulfate hemihydrate from PG in chloride-free Ca(NO<sub>3</sub>)<sub>2</sub> solution under mild conditions [J]. *Fuel* 174, 235–241. <https://doi.org/10.1016/j.fuel.2016.01.07>.
- Jing, Y.A., A.L.M., Jie, Y.A., et al., 2019. Chemical looping gasification of phosphogypsum as an oxygen carrier: the Ca and S migration mechanism using the DFT method [J]. *Sci. Total Environ.* 689, 854–864. <https://doi.org/10.1016/j.scitotenv.2019.06.506>.
- John, D., Elizabeth, H., Gamini, S., 2018. Sulfuric Acid Baking and Leaching of Rare Earth Elements, Thorium and Phosphate from a Monazite Concentrate: Effect of Bake Temperature from 200 to 800°C [J]. *Hydrometallurgy*. <https://doi.org/10.1016/j.hydromet.2018.06.002>. S0304386X18301658-.
- Kadirova, Z.C., Hojaberdiiev, M., Bo, L., et al., 2014. Ion uptake properties of low-cost inorganic sorption materials in the CaO-Al<sub>2</sub>O<sub>3</sub>–SiO<sub>2</sub> system prepared from phosphogypsum and kaolin [J]. *J. Clean. Prod.* 83, 483–490. <https://doi.org/10.1016/j.jclepro.2014.06.084>.
- Kandil, A.H.T., Cheira, M.F., Gado, H.S., et al., 2016. Ammonium sulfate preparation from phosphogypsum waste [J]. *J. Radiat. Res. Appl. Sci.* 10 (1), 24–33. <https://doi.org/10.1016/j.jrras.2016.11.001>.
- Kassir, L.N., Darwish, T., Shaban, A., et al., 2012. Mobility of selected trace elements in Mediterranean red soil amended with phosphogypsum: experimental study (vol 184, pg 4397, 2012) [J]. *Environ. Monitor. Assess.* 184 (10), 6465. <https://doi.org/10.1007/s10661-011-2272-7>. 6465.
- Kavitha, S., Kumar, S.A., Yogalakshmi, K.N., et al., 2013. Effect of enzyme secreting bacterial pretreatment on enhancement of aerobic digestion potential of waste activated sludge interceded through EDTA [J]. *Bioresour. Technol.* 150, 210–219. <https://doi.org/10.1016/j.biotech.2013.10.021>.
- Kovler, K., 2012. Radioactive materials [J]. *Toxic. Build. Mater.* 185 (3), 196–240. <https://doi.org/10.1533/9780857096357.196>.
- Kumar, S.S., Kumar, A., Singh, S., et al., 2020. Industrial wastes: fly ash, steel slag and phosphogypsum- potential candidates to mitigate greenhouse gas emissions from paddy fields [J]. *Chemosphere* 241. <https://doi.org/10.1016/j.chemosphere.2019.124824>.
- Kurkinen, S., Virolainen, S., Sainio, T., 2021. Recovery of rare earth elements from phosphogypsum waste in resin-in-leach process by eluting with biodegradable complexing agents [J]. *Hydrometallurgy* 201, 105569. <https://doi.org/10.1016/j.hydromet.2021.105569>.
- Kuryatnyk, T., Luz, C.A.D., Ambroise, J., et al., 2008. Valorization of phosphogypsum as hydraulic binder [J]. *J. Hazard Mater.* 160 (2–3), 681–687. <https://doi.org/10.1016/j.jhazmat.2008.03.014>.
- Kuzmanovic, P., Todorovic, N., Forkapic, S., et al., 2020. Radiological characterization of phosphogypsum produced in Serbia [J]. *Radiat. Phys. Chem.* 166 <https://doi.org/10.1016/j.radphyschem.2019.108463>.
- Lei, L., Gu, J., Wang, X., et al., 2021. Microbial succession and molecular ecological networks response to the addition of superphosphate and phosphogypsum during swine manure composting [J]. *J. Environ. Manag.* 279, 111560. <https://doi.org/10.1016/j.jenvman.2020.111560>.
- Li, F., Liu, J., Yang, G., et al., 2013. Effect of pH and succinic acid on the morphology of  $\alpha$ -calcium sulfate hemihydrate synthesized by a salt solution method [J]. *J. Cryst. Growth* 374, 31–36. <https://doi.org/10.1016/j.jcrysgr.2013.03.04>.
- Li, J-y, Liu, Z-d, Zhao, W-z, et al., 2015. Alkaline slag is more effective than phosphogypsum in the amelioration of subsoil acidity in an Ultisol profile [J]. *Soil Tillage Res.* 149, 21–32. <https://doi.org/10.1016/j.still.2014.12.017>.
- Li, X., Du, J., Gao, L., et al., 2017. Immobilization of phosphogypsum for cemented paste backfill and its environmental effect [J]. *J. Clean. Prod.* 156 (jul.10), 137–146. <https://doi.org/10.1016/j.jclepro.2017.04.04>.
- Li, X., Zhang, Q., Ke, B., et al., 2018. Insight into the effect of maleic acid on the preparation of  $\alpha$ -hemihydrate gypsum from phosphogypsum in Na<sub>2</sub>SO<sub>4</sub> solution [J]. *J. Cryst. Growth* 493, 34–40. <https://doi.org/10.1016/j.jcrysgr.2018.04.025>.
- Li, X., Zhang, Q., Shen, Z., et al., 2019. L-aspartic acid: a crystal modifier for preparation of hemihydrate from phosphogypsum in CaCl<sub>2</sub> solution [J]. *J. Cryst. Growth* 511, 48–55. <https://doi.org/10.1016/j.jcrysgr.2019.01.02>.
- Li, B., Wei, S., Zhen, Y-w, 2020. An effective recycling direction of water-based drilling cuttings and phosphogypsum co-processing in road cushion layer [J]. *Environ. Sci. Pollut. Control Ser.* 27 (14), 17420–17424. <https://doi.org/10.1007/s11356-020-08406-y>.
- Lieberman, R.N., Izquierdo, M., Cordoba, P., et al., 2020. The geochemical evolution of brines from phosphogypsum deposits in Huelva (SW Spain) and its environmental implications [J]. *Sci. Total Environ.* 700, 134444. <https://doi.org/10.1016/j.scitotenv.2019.134444>.
- Lin, Y., Yun, Y., Hu, Z., 2013. Utilization of phosphogypsum for the preparation of non-autoclaved aerated concrete [J]. *Construct. Build. Mater.* 44 (jul), 600–606. <https://doi.org/10.1016/j.conbuildmat.2013.03.070>.
- Liu Ying, Development of Decision Support System for Economic Evaluation of Phosphorus Chemical Industry [D]: Zhengzhou University. <https://doi.org/10.7666/d.y2100898>.
- Li, S., Ouyang, J., Ren, J., 2020. Mechanism of calcination modification of phosphogypsum and its effect on the hydration properties of phosphogypsum-based supersulfated cement [J]. *Construct. Build. Mater.* 243, 118226. <https://doi.org/10.1016/j.conbuildmat.2020.118226>.
- Lopez, F.I.A., Gazquez, M., Alguacil, F.J., et al., 2011. Microencapsulation of phosphogypsum into a sulfur polymer matrix: physico-chemical and radiological characterization [J]. *J. Hazard Mater.* 192 (1), 234–245. <https://doi.org/10.1016/j.jhazmat.2011.05.010>.
- López, F.A., Gázquez, M., Alguacil, F.J., et al., 2011. Microencapsulation of phosphogypsum into a sulfur polymer matrix: physico-chemical and radiological characterization [J]. *J. Hazard Mater.* 192 (1), 234–245. <https://doi.org/10.1016/j.jhazmat.2011.05.010>.
- Lu, W., Ma, B., Su, Y., et al., 2019a. Preparation of  $\alpha$ -hemihydrate gypsum from phosphogypsum in recycling CaCl<sub>2</sub> solution [J]. *Construct. Build. Mater.* 214, 399–412. <https://doi.org/10.1016/j.conbuildmat.2019.04.148>.
- Lu, W., Ma, B., Su, Y., et al., 2019b. Preparation of  $\alpha$ -hemihydrate gypsum from phosphogypsum in recycling CaCl<sub>2</sub> solution [J]. *Construct. Build. Mater.* 214 (JUL.30), 399–412. <https://doi.org/10.1016/j.conbuildmat.2019.04.148>.
- Lz A, Az A, Ke LA, et al. Research on the pretreatment and mechanical performance of undisturbed phosphogypsum [J], Case Stud. Construct. Mater., 13:e00400. <https://doi.org/10.1016/j.cscm.2020.e00400>.
- Ma, B., Lu, W., Su, Y., et al., 2018. Synthesis of  $\alpha$ -hemihydrate gypsum from cleaner phosphogypsum [J]. *J. Clean. Prod.* 195, 396–405. <https://doi.org/10.1016/j.jclepro.2018.05.228>.
- Ma, B., Jin, Z., Su, Y., et al., 2020. Utilization of hemihydrate phosphogypsum for the preparation of porous sound absorbing material [J]. *Construct. Build. Mater.* 234, 117346. <https://doi.org/10.1016/j.conbuildmat.2019.117346>.
- Maazoun, H., Bouassida, M., 2018. Phosphogypsum Management Challenges in Tunisia [J].
- Mashifana, T.P., 2019. Chemical treatment of phosphogypsum and its potential application for building and construction [J]. *Procedia Manuf.* 35, 641–648. <https://doi.org/10.1016/j.promfg.2019.06.007>.
- Masmoudi-Soussi, A., Hammas-Nasri, I., Horchani-Naifer, K., et al., 2019. Study of Rare Earths Leaching after Hydrothermal Conversion of Phosphogypsum [J], Chemistry Africa. <https://doi.org/10.1007/s42250-019-00048-z>.
- Meskini, S., Samdi, A., Ejjouani, H., et al., 2021. Valorization of phosphogypsum as a road material: stabilizing effect of fly ash and lime additives on strength and durability [J]. *J. Clean. Prod.* 323, 129161. <https://doi.org/10.1016/j.jclepro.2021.129161>.
- Mi, Y., Chen, D., Wang, A., 2019. Effects of phosphorus impurities on the preparation of  $\alpha$ -calcium sulfate hemihydrate from waste phosphogypsum with the salt solution method under atmospheric pressure [J]. *CrystEngComm* 21 (16), 2631–2640. <https://doi.org/10.1039/C9CE00140A>.

- Min, Y., Jueshi, Q., Ying, P., 2008a. Activation of fly ash-lime systems using calcined phosphogypsum [J]. *Construct. Build. Mater.* 22 (5), 1004–1008. <https://doi.org/10.1016/j.conbuildmat.2006.12.005>.
- Min, Y., Qian, J., Ying, P., 2008b. Activation of fly ash-lime systems using calcined phosphogypsum [J]. *Construct. Build. Mater.* 22 (5), 1004–1008. <https://doi.org/10.1016/j.conbuildmat.2004.04.03>.
- Mohamed, K.R., Mousa, S.M., El Bassyouni, G.T., 2014. Fabrication of nano structural biphasic materials from phosphogypsum waste and their in vitro applications [J]. *Mater. Res. Bull.* 50, 432–439. <https://doi.org/10.1016/j.materresbull.2013.11.023>.
- Monat, L., Chaudhury, S., Nir, O., 2020. Enhancing the sustainability of phosphogypsum recycling by integrating electrodialysis with bipolar membranes [J]. *ACS Sustain. Chem. Eng.* 8 (6), 2490–2497. <https://doi.org/10.1021/acssuschemeng.9b07038>.
- Moussa, D., Crispel, J.J., Legrand, C., et al., 1984. Laboratory study of the structure and compactibility of Tunisian phosphogypsum (SFAX) for use in embankment construction [J]. *Resour. Conserv.* 11 (2), 95–116. [https://doi.org/10.1016/0166-3097\(84\)90014-2](https://doi.org/10.1016/0166-3097(84)90014-2).
- Msila, X., Barnard, W., Billing, D.G., 2015. Raman spectroscopic study of phosphogypsum thermal reduction with the carbonaceous material [J]. *Spectrochim. Acta Part A Molecular & Biomolecular Spectroscopy* 149, 317–322. <https://doi.org/10.1016/j.saa.2015.04.017>.
- Ngsbraga, Mars, 2018. Assessment of phosphogypsum use in a nursery for plant propagation [J]. *Int. J. Environ. Stud.* 75 (2), 284–293. <https://doi.org/10.1080/00207233.2017.1356631>.
- de Oliveira Melgaco, L.A., Quites, N.C., Leao, V.A., 2020. Phosphogypsum as sulfate source for sulfate-reducing bacteria in a continuous fluidized-bed reactor [J]. *Eng. Sanitária Ambient.* 25 (1), 157–165. <https://doi.org/10.1590/S1413-4152202020180007>.
- Odumoda, L., Pitkäaho, S., Turpeinen, E.-M., et al., 2019. Recycling and substitution of light rare earth elements, cerium, lanthanum, neodymium, and praseodymium from end-of-life applications - a review [J]. *J. Clean. Prod.* 236, 117573. <https://doi.org/10.1016/j.jclepro.2019.07.048>.
- Ossorio, M., Stawski, T.M., Rodriguez-Blanco, J.D., et al., 2017. Physicochemical and additive controls on the multistep precipitation pathway of gypsum [J]. *Minerals* 7 (8). <https://doi.org/10.3390/min7080140>.
- Papastioti, E.-M., Perez-Lopez, R., Parvainen, A., et al., 2020. Effects of redox oscillations on the phosphogypsum waste in an estuarine salt-marsh system [J]. *Chemosphere* 242. <https://doi.org/10.1016/j.chemosphere.2019.125174>.
- Paul, K., Andre, A., Alexandra, N., et al., 2018. Trends in structure and thermodynamic properties of normal rare earth carbonates and rare earth hydroxycarbonates [J]. *Minerals* 8 (3), 106. <https://doi.org/10.3390/min8030106>.
- Perez-Lopez, R., Macias, F., Ruiz Canovas, C., et al., 2016. Pollutant flows from a phosphogypsum disposal area to an estuarine environment: an insight from geochemical signatures [J]. *Sci. Total Environ.* 553, 42–51. <https://doi.org/10.1016/j.scitotenv.2016.02.070>.
- Pljatsuk, L., Balintova, M., Chernysh, Y., et al., 2020. The process of environmentally safe biochemical recycling of phosphogypsum. In: Ivanov, V., Trojanowska, J., Machado, J. (Eds.), *Advances in Design, Simulation and Manufacturing II*, pp. 843–852. [https://doi.org/10.1007/978-3-030-22365-6\\_84](https://doi.org/10.1007/978-3-030-22365-6_84).
- Qi, D., 2018. Chapter 1 - extraction of rare earths from RE concentrates. In: Qi, D. (Ed.), *Hydrometallurgy of Rare Earths*. Elsevier, pp. 1–185. <https://doi.org/10.1016/B978-0-12-813920-2.00001-5>.
- Rashad, A.M., 2015. Potential use of phosphogypsum in alkali-activated fly ash under the effects of elevated temperatures and thermal shock cycles - ScienceDirect [J]. *J. Clean. Prod.* 87 (1), 717–725. <https://doi.org/10.1016/j.jclepro.2014.09.080>.
- Rashad, A.M., 2017. Phosphogypsum as a construction material [J]. *J. Clean. Prod.* 166. <https://doi.org/10.1016/j.jclepro.2017.08.04>.
- Reijnders, L., 2007. Cleaner phosphogypsum, coal combustion ashes and waste incineration ashes for application in building materials: A review [J]. *Build. Environ.* 42 (2), 1036–1042. <https://doi.org/10.1016/j.buildenv.2005.09.016>.
- Riddle, M.E., Tatara, E., Olson, C., et al., 2021. Agent-based modeling of supply disruptions in the global rare earths market [J]. <https://doi.org/10.1016/j.rcrx.2020.100042>, 164–105193.
- del Rio-Merino, M., Vidales-Barriguete, A., Piña-Ramírez, C., et al., 2022. A review of the research about gypsum mortars with waste aggregates [J]. *J. Build. Eng.* 45, 103338. <https://doi.org/10.1016/j.jobe.2021.103338>.
- Romero-Hermida, I., Santos, A., Pérez-López, R., et al., 2017. New method for carbon dioxide mineralization based on phosphogypsum and aluminium-rich industrial wastes resulting in valuable carbonated by-products [J]. *J. CO2 Util.* 18, 15–22. <https://doi.org/10.1016/j.jcou.2017.01.002>.
- Rong, K., Lan, W., Li, H., 2020. Industrial experiment of goaf filling using the filling materials based on hemihydrate phosphogypsum [J]. *Minerals* 10 (4). <https://doi.org/10.3390/min10040324>.
- Rosales, J., Perez, S.M., Cabrera, M., et al., 2020. Treated phosphogypsum as an alternative set regulator and mineral addition in cement production [J]. *J. Clean. Prod.* 244 <https://doi.org/10.1016/j.jclepro.2019.118752>.
- Rubio-Avalos, J.C., Manzano-Ramírez, A., Lluna-Bárcenas, J.G., et al., 2005. Flexural behavior and microstructure analysis of a gypsum-SBR composite material [J]. *Mater. Lett.* 59 (2), 230–233. <https://doi.org/10.1016/j.matlet.2004.07.054>.
- Saadaoui, E., Ghazel, N., Ben Romdhane, C., et al., 2017. Phosphogypsum: potential uses and problems – a review [J]. *Int. J. Environ. Stud.* 1–10. <https://doi.org/10.1080/00207233.2017.1330582>.
- Sadri, F., Rashchi, F., Amini, A., 2017. Hydrometallurgical digestion and leaching of Iranian monazite concentrate containing rare earth elements Th, Ce, La and Nd [J]. *Int. J. Miner. Process.* <https://doi.org/10.1016/j.minpro.2016.12.003>.
- Saha, A., Lee, J., Pancera, S.M., et al., 2012. New insights into the transformation of calcium sulfate hemihydrate to gypsum using time-resolved cryogenic transmission electron microscopy [J]. *Langmuir* 28 (30), 11182–11187. <https://doi.org/10.1021/la3024474>.
- Saleh, E., Rahman, R.A., 2016. Management of hazardous wastes || Characterization and Valorization of Norm Wastes for Construction Materials [J], 10.5772/61668 (Chapter 2). <https://doi.org/10.5772/61668>.
- Samet, M., Karray, F., Mhiri, N., et al., 2019. Effect of phosphogypsum addition in the composting process on the physico-chemical properties and the microbial diversity of the resulting compost tea [J]. *J. Environ. Sci. Pollut. Control Ser.* 26 (21), 21404–21415. <https://doi.org/10.1007/s11356-019-05327-3>.
- Ségalen, C., Dieudé-Fauvel, E., Baudez, J.C., 2015. Electrical and rheological properties of sewage sludge - impact of the solid content [J]. *Water Res.* 82, 25–36. <https://doi.org/10.1016/j.watres.2015.04.008>.
- Shen BHG, Z.X., Fu, H.L., 2009. Effect of potassium sodium tartrate and sodium citrate on the preparation of α-calcium sulfate hemihydrate from flue gas desulfurization gypsum in a concentrated electrolyte solution [J]. *J. Am. Ceram. Soc.* 92 (12), 2894–2899. <https://doi.org/10.1111/j.1551-2916.2009.03330.x>.
- Shen, Y., Qian, J., Chai, J., et al., 2014. Calcium sulphoaluminite cements made with phosphogypsum: production issues and material properties [J]. *Cement Concr. Compos.* 48, 67–74. <https://doi.org/10.1016/j.cemconcomp.2014.01.009>.
- Silva, M.V., de Rezende, L.R., Mascarenha, MMdA., et al., 2019. Phosphogypsum, tropical soil and cement mixtures for asphalt pavements under wet and dry environmental conditions. *Resour. Conserv. Recycl.* 144, 123–136. <https://doi.org/10.1016/j.resconrec.2019.01.029>.
- Singh, M., 2002. Treating waste phosphogypsum for cement and plaster manufacture [J]. *Cement Concr. Res.* 32 (7), 1033–1038. [https://doi.org/10.1016/S0008-8846\(02\)00723-8](https://doi.org/10.1016/S0008-8846(02)00723-8).
- Singh, M., 2003. Effect of phosphatic and fluoride impurities of phosphogypsum on the properties of selenite plaster [J]. *Cement Concr. Res.* 33 (9), 1363–1369. [https://doi.org/10.1016/S0008-8846\(03\)00068-1](https://doi.org/10.1016/S0008-8846(03)00068-1).
- Singh, M., Garg, M., 2005a. Study on anhydrite plaster from waste phosphogypsum for use in polymerised flooring composition [J]. *Construct. Build. Mater.* 19 (1), 25–29.
- Singh, M., Garg, M., 2005b. Study on anhydrite plaster from waste phosphogypsum for use in polymerised flooring composition [J]. *Construct. Build. Mater.* 19 (1), 25–29. <https://doi.org/10.1016/j.conbuildmat.2004.04.038>.
- Stawski, T.M., van Driessche, A.E.S., Ossorio, M., et al., 2016. Formation of calcium sulfate through the aggregation of sub-3 nanometre primary species [J]. *Nat. Commun.* 7 <https://doi.org/10.1038/ncomms1117>.
- Syczewski, M.D., Borkowski, A., Gasainski, A., et al., 2020. Phosphogypsum and clay mineral/phosphogypsum ceramic composites as useful adsorbents for uranium uptake [J]. *Appl. Geochem.* 123 <https://doi.org/10.1016/j.ageochem.2020.104793>.
- Szajerski, P., 2020. Distribution of uranium and thorium chains radionuclides in different fractions of phosphogypsum grains [J]. *Environ. Sci. Pollut. Control Ser.* 27 (13), 15856–15868. <https://doi.org/10.1007/s11356-020-08090-y>.
- Tan, H., Dong, F., Bian, L., et al., 2017. Preparation of anhydrous calcium sulfate whiskers from phosphogypsum in H<sub>2</sub>O-H<sub>2</sub>SO<sub>4</sub> autoclave-free hydrothermal system [J]. *Mater. Trans.* 58 (8), 1111–1117. <https://doi.org/10.2320/matertrans.M2017042>.
- Tan, H., Zheng, A., Kang, X., et al., 2020. Influence of different additives on the mechanical performance of a-hemihydrate gypsum from phosphogypsum [J]. *Mater. Technol.* 54 (5), 697–703. <https://doi.org/10.17222/mit.2020.003>.
- Tayibi, H., Choura, M., López, F.A., et al., 2009. Environmental impact and management of phosphogypsum [J]. *J. Environ. Manag.* 90 (8), 2377–2386. [https://doi.org/10.1016/0048-9697\(94\)90002-7](https://doi.org/10.1016/0048-9697(94)90002-7).
- Tian, Yan, Yun, et al., 2016. Utilization of original phosphogypsum for the preparation of foam concrete [J]. *Construct. Build. Mater.* 115, 143–152. <https://doi.org/10.1016/j.conbuildmat.2016.04.028>.
- Tsioka, M., Voudrias, E.A., 2020. Comparison of alternative management methods for phosphogypsum waste using life cycle analysis [J]. *J. Clean. Prod.* 266, 121386. <https://doi.org/10.1016/j.jclepro.2020.121386>.
- Umponpanarat, P., Wansom, S., et al., 2015. Thermal conductivity and strength of foamed gypsum formulated using aluminum sulfate and sodium bicarbonate as gas-producing additives [J]. *Mater. Struct.* 49 (4), 1115–1126. <https://doi.org/10.1617/s11527-015-0562-1>.
- V-M, M.D., B, M.C., F, A., et al., 2021. Assessing the behaviour of heavy metals in abandoned phosphogypsum deposits combining electrical resistivity tomography and multivariate analysis [J]. *J. Environ. Manag.* 278, 111517. <https://doi.org/10.1016/j.jenvman.2020.111517>.
- Verbeek, C., Plessis, B., 2005. Density and flexural strength of phosphogypsum-polymer composites [J]. *Construct. Build. Mater.* 19 (4), 265–274. <https://doi.org/10.1016/j.conbuildmat.2004.07.011>.
- Virolainen, S., Repo, E., Sainio, T., 2019. Recovering rare earth elements from phosphogypsum using a resin-in-leach process: selection of resin, leaching agent, and eluent [J]. *Hydrometallurgy* 189, 105125. <https://doi.org/10.1016/j.hydromet.2019.105125>.
- Voncken, J., 2016. *The Rare Earth Elements - an Introduction* [M].
- Walawalkar, M., Nichol, C.K., Azimi, G., 2016. Process investigation of the acid leaching of rare earth elements from phosphogypsum using HCl, HNO<sub>3</sub>, and H<sub>2</sub>SO<sub>4</sub> [J]. *Hydrometallurgy* 166, 195–204. <https://doi.org/10.1016/j.hydromet.2016.06.008>.
- Wang, Q., Jia, R., 2019. A novel gypsum-based self-leveling mortar produced by phosphorus building gypsum [J]. *Construct. Build. Mater.* 226, 11–20. <https://doi.org/10.1016/j.conbuildmat.2019.07.289>.
- Wang, X., Zhou, M., Ke, X., et al., 2017a. Synthesis of alpha hemihydrate particles with lithium and carboxylates via the hydrothermal method [J]. *Powder Technol.* 317, 293–300. <https://doi.org/10.1016/j.powtec.2017.03.008>.

- Wang, X., Ge, J., Li, J., et al., 2017b. Market impacts of environmental regulations on the production of rare earths: a computable general equilibrium analysis for China [J]. *J. Clean. Prod.* 154, 614–620. <https://doi.org/10.1016/j.jclepro.2017.03.200>.
- Wang, M., Luo, H., Chen, Y., et al., 2018. Leaching characteristics of calcium and strontium from phosphogypsum under acid rain [J]. *Bull. Environ. Contam. Toxicol.* 100 (2), 310–315. <https://doi.org/10.1007/s00128-017-2218-z>.
- Wang, Q., Cui, Y., Xue, J., 2020a. Study on the improvement of the waterproof and mechanical properties of hemihydrate phosphogypsum-based foam insulation materials [J]. *Construct. Build. Mater.* 230, 117014. <https://doi.org/10.1016/j.conbuildmat.2019.117014>.
- Wang, J., Dong, F., Wang, Z., et al., 2020b. A novel method for purification of phosphogypsum [J]. *Physicochem. Probl. Mineral Process.* 56 (5), 975–983. <https://doi.org/10.37190/ppmp/127854>.
- Wang, Q., Cui, Y., Xue, J., 2020c. Study on the improvement of the waterproof and mechanical properties of hemihydrate phosphogypsum-based foam insulation materials [J]. *Construct. Build. Mater.* 230, 117014. <https://doi.org/10.1016/j.conbuildmat.2019.117014>.
- Wang, Y., Wan, T., Zhong, Y., et al., 2020d. Environmental sustainability of renewable phosphogypsum by Ca<sup>2+</sup> characterization and process optimization [J]. *J. Therm. Anal. Calorim.* 139 (6), 3457–3471. <https://doi.org/10.1007/s10973-019-08718-3>.
- Wdrychowicz, M., Bydaek, A.W., Skrzekut, T., et al., 2019. Analysis of the mechanical strength, structure and possibilities of using waste phosphogypsum in aluminum powder composites [J]. *SN Appl. Sci.* 1 (9) <https://doi.org/10.1007/s42452-019-0995->.
- Wu, S., Yao, X., Ren, C., et al., 2020. Recycling phosphogypsum as a sole calcium oxide source in calcium sulfoaluminate cement and its environmental effects [J]. *J. Environ. Manag.* 271, 11098. <https://doi.org/10.1016/j.jenvman.2020.110986>.
- Wu, S., Yao, X., Ren, C., et al., 2021. Effect of iron on the preparation of iron-rich calcium sulfoaluminate cement using gypsum as the sole calcium oxide source and its incorporation into mineral phases [J]. *Construct. Build. Mater.* 290, 123214. <https://doi.org/10.1016/j.conbuildmat.2021.123214>.
- Xue, S., Ke, W., Zhu, F., et al., 2020. Effect of phosphogypsum and poultry manure on aggregate-associated alkaline characteristics in bauxite residue [J]. *J. Environ. Manag.* 256 <https://doi.org/10.1016/j.jenvman.2019.109981>.
- Yang, J., Liu, W., Zhang, L., et al., 2009. Preparation of load-bearing building materials from autoclaved phosphogypsum [J]. *Construct. Build. Mater.* 23 (2), 687–693. <https://doi.org/10.1016/j.conbuildmat.2008.02.011>.
- Yang, M., Sun, Q., 2011. Fly ash-calcined phosphogypsum cementitious materials with different thermally treated phosphogypsum. In: Zhao, J. (Ed.), *Advances in Building Materials*, pp. 816–819. Pts 1-3. <https://doi.org/10.4028/www.scientific.net/AMR.261-263.816>.
- Yang, L., Cao, J., Li, C., 2016a. Enhancing the hydration reactivity of hemi-hydrate phosphogypsum through a morphology-controlled preparation technology [J]. *Chin. J. Chem. Eng.* 24, 1298–1305. <https://doi.org/10.1016/j.cjche.2016.04.009>.
- Yang, L., Zhang, Y., Yan, Y., 2016b. Utilization of original phosphogypsum as raw material for the preparation of self-leveling mortar [J]. *J. Clean. Prod.* 127 (Jul. 20), 204–213. <https://doi.org/10.1016/j.jclepro.2016.04.054>.
- Yang, J., Ma, L., Dong, S., et al., 2017. Theoretical and experimental demonstration of lignite chemical looping gasification of phosphogypsum oxygen carrier for syngas generation [J]. *Fuel* 194 (APR.15), 448–459. <https://doi.org/10.1016/j.fuel.2016.12.077>.
- Youqiang, Huang, Jianxin, et al., 2016. The chloride permeability of persulphated phosphogypsum-slag cement concrete [J]. *J. Wuhan Univ. Technol. Mater. Sci.* 1031–1037 <https://doi.org/CNKI:SUN:WLGY.0.2016-05-015>.
- Z, Z., Jia, Q., W, L., 2015. Progress in the separation processes for rare earth resources - ScienceDirect [J]. *Handb. Phys. Chem. Rare Earths* 48, 287–376. <https://doi.org/10.1016/B978-0-444-63483-2.00004-1>.
- ZCKA, B., MHB, C., LB, D., et al., 2014. Ion uptake properties of low-cost inorganic sorption materials in the CaO-Al<sub>2</sub>O<sub>3</sub>-SiO<sub>2</sub> system prepared from phosphogypsum and kaolin - ScienceDirect [J]. *J. Clean. Prod.* 83, 483–490. <https://doi.org/10.1016/j.jclepro.2014.06.084>.
- Zhang, D., Luo, H., Zheng, L., et al., 2012a. Utilization of waste phosphogypsum to prepare hydroxyapatite nanoparticles and its application towards removal of fluoride from aqueous solution [J]. *J. Hazard Mater.* 241, 418–426. <https://doi.org/10.1016/j.jhazmat.2012.09.066>.
- Zhang, D., Luo, H., Zheng, L., et al., 2012b. Utilization of waste phosphogypsum to prepare hydroxyapatite nanoparticles and its application towards removal of fluoride from aqueous solution [J]. *J. Hazard Mater.* 241–242 (NOV.30), 418–426. <https://doi.org/10.1016/j.jhazmat.2012.09.066>.
- Zhang, J., Zhao, B., Schreiner, B., 2016. *Separation Hydrometallurgy of Rare Earth Elements*[M]. Springer International Publishing.
- Zhang, W., Zhang, F., Ma, L., et al., 2020. CO<sub>2</sub> capture and process reinforcement by hydrolysate of phosphogypsum decomposition products [J]. *J. CO<sub>2</sub> Util.* 36, 253–262. <https://doi.org/10.1016/j.jcou.2019.11.020>.
- Zhang, S., Zhao, Y., Ding, H., et al., 2021. Recycling flue gas desulfurisation gypsum and phosphogypsum for cemented paste backfill and its acid resistance [J]. *Construct. Build. Mater.* 275, 122170. <https://doi.org/10.1016/j.conbuildmat.2020.122170>.
- Zhao, L., Wan, T., Yang, X., et al., 2015. Effects of kaolinite addition on the melting characteristics of the reaction between phosphogypsum and CaS [J]. *J. Therm. Anal. Calorim.* 119 (3), 2119–2126. <https://doi.org/10.1007/s10973-015-4400-z>.
- Zhao, L., Zhang, Q., Li, X., et al., 2020. Adsorption of Cu(II) by phosphogypsum modified with sodium dodecyl benzene sulfonate [J]. *J. Hazard Mater.* 387, 121808. <https://doi.org/10.1016/j.jhazmat.2019.121808>.
- Zheng, S., Ping, N., Ma, L., et al., 2011. Reductive decomposition of phosphogypsum with high-sulfur-concentration coal to SO<sub>2</sub> in an inert atmosphere [J]. *Chem. Eng. Res. Des.* 89 (12), 2736–2741. <https://doi.org/10.1016/j.cherd.2011.03.016>.
- Zheng, D., Ma, L., Wang, R., et al., 2018. Research on thermal decomposing properties of phosphogypsum with Fe addition under multi-atmosphere control [J]. *Thermochim. Acta* 661, 59–66. <https://doi.org/10.1016/j.tca.2018.01.011>.
- Zheng, J., Li, J., Ling, L., et al., 2019. Crystal regulation of gypsum via hydrothermal treatment with hydrogen ion for Cr(VI) extraction [J]. *J. Hazard Mater.* 390, 120614. <https://doi.org/10.1016/j.jhazmat.2019.05.007>.
- Zhou, J., Hui, G., Zhu, S., et al., 2012. Utilization of waste phosphogypsum to prepare non-fired bricks by a novel Hydration-Recrystallization process [J]. *Construct. Build. Mater.* 34, 114–119. <https://doi.org/10.1016/j.conbuildmat.2012.02.045>.
- Zhou, J., Yu, D., Shu, Z., et al., 2014a. A novel Two-step Hydration Process of preparing cement-free non-fired bricks from waste phosphogypsum [J]. *Construct. Build. Mater.* 73 (dec.30), 222–228. <https://doi.org/10.1016/j.conbuildmat.2014.09.075>.
- Zhou, J., Yu, D., Shu, Z., et al., 2014b. A novel Two-step Hydration Process of preparing cement-free non-fired bricks from waste phosphogypsum [J]. *Construct. Build. Mater.* 73, 222–228. <https://doi.org/10.1016/j.conbuildmat.2014.09.075>.
- Zhou, J., Sheng, Z., Li, T., et al., 2016a. Preparation of hardened tiles from waste phosphogypsum by a new intermittent pressing hydration [J]. *Ceram. Int.* 42 (6), 7237–7245. <https://doi.org/10.1016/j.ceramint.2016.01.117>.
- Zhou, J., Sheng, Z., Li, T., et al., 2016b. Preparation of hardened tiles from waste phosphogypsum by a new intermittent pressing hydration [J]. *Ceram. Int.* 7237–7245. <https://doi.org/10.1016/j.ceramint.2016.01.117>.
- Zhou, J., Li, X., Zhao, Y., et al., 2020. Preparation of paper-free and fiber-free plasterboard with high strength using phosphogypsum [J]. *Construct. Build. Mater.* 243, 118091. <https://doi.org/10.1016/j.conbuildmat.2020.118091>.
- Zielinski, M., 2015. Influence of constant magnetic field on the properties of waste phosphogypsum and fly ash composites [J]. *Construct. Build. Mater.* 89 (aug.1), 13–24. <https://doi.org/10.1016/j.conbuildmat.2015.04.029>.
- El Zrelli, R., Rabaoui, L., van Beek, P., et al., 2019. Natural radioactivity and radiation hazard assessment of industrial wastes from the coastal phosphate treatment plants of Gabes (Tunisia, Southern Mediterranean Sea) [J]. *Mar. Pollut. Bull.* 146, 454–461. <https://doi.org/10.1016/j.marpolbul.2019.06.075>.