

QES 1.0

Analysis | Editor | Report

Select problem

P002

Orange Peel

x

x

x

CLEAR

P005

Crater

x

x

x

P025

Bleeding

x

x

x

Temperature

25

Humidity

68

Air pressure

4,5

Paint temperature

23

Viscosity

15

Flow rate

230

Flash off time

6

Dew point

18

Film thickness

18

stage

Basecoat

ANALYSIS

SUBMIT

Cause ID	Score
C073	19
C097	19
C034	19
C041	17
C049	16
C067	16
C026	16
C036	16
C078	16
C091	16
C092	16
C077	15
C098	15
C040	15
C025	15
C037	14
C046	14
C044	14
C072	14
C071	14
C029	14
C035	14
C079	14
C023	13
C009	13
C017	13
C027	13
C028	13
C057	13
C024	13

RANK	CAUSE ID	CAUSE NAME	SCORE
1	C073	Incorrect parameter adjustment	19
2	C097	Incorrect process setting	19
3	C034	Solvent contamination	19
4	C041	Low spray pressure	17
5	C049	High line speed	16
6	C067	Poor booth ventilation	16
7	C026	Paint contamination	16
8	C036	Poor paint compatibility	16
9	C078	Wrong material selection	16
10	C091	Incoming material variation	16
11	C092	Supplier quality issue	16
12	C077	Failure to follow SOP	15
13	C098	Unknown contamination source	15
14	C040	Resin degradation	15
15	C025	Expired paint	15
16	C037	Incorrect paint temperature	14
17	C046	Spray speed too fast	14
18	C044	Spray distance too far	14
19	C072	Wrong machine setup	14
20	C071	Wrong paint mixing procedure	14
21	C029	Wrong paint batch	14
22	C035	Wrong catalyst	14

Select problem	issue list
Temperature	Sensor measurements
Humidity	Sensor measurements
Paint temperature	Sensor measurements
Viscosity	Sensor measurements
Flow rate	Sensor measurements
stage	Detection Stage
ANALYSIS	Run QES Diagnosis
SUBMIT	Save case to submit

QES 1.0

Analysis Editor Report

Select problem

INSERT NEW CASE

LOAD OLD DATA

RENEW

Select causes

		0	▲▼	x
		0	▲▼	x
		0	▲▼	x
		0	▲▼	x
		0	▲▼	x
		0	▲▼	x
		0	▲▼	x
		0	▲▼	x
		0	▲▼	x
		0	▲▼	x
		0	▲▼	x
		0	▲▼	x
		0	▲▼	x
		0	▲▼	x
		0	▲▼	x
		0	▲▼	x
		0	▲▼	x
		0	▲▼	x
		0	▲▼	x
		0	▲▼	x
		0	▲▼	x
		0	▲▼	x

Select problem	issue list
Select causes	causes list
Insert new case	Create new base case
Load old data	Load a base case for editing
Renew	Update Case

QES 1.0

Analysis | Editor | Report

Case ID	Problem ID	Problem name	Cause ID	Cause name	Score	Root
						☐
						☐
Send to Report						☐
						☐
Cancel						☐
						☐
						☐
						☐
						☐
						☐
						☐
						☐
Temperature						☐
Humidity						☐
Air pressure						☐
Paint temperature						☐
Viscosity						☐
Flow rate						☐
Flash off time						☐
Dew point						☐
Film thickness						☐
						☐
						☐
						☐

Case ID	select a case from submit
Root	Check if confirmed after corrective action
Send to report	Submit verified root cause
Submitted cases are used to improve future diagnoses	