



Technology Data Sheet (TDS)

TINMORRY PLA-GF

Version 1.0

• Basic Introduction

TINMORRY PLA-GF is a glass fiber reinforced PLA composite. After multiple formula iterations and optimizations, it has achieved excellent overall performance. It maintains the ease of printing of normal PLA (wide machine compatibility and high printing quality), and also has a higher printing speed (up to 300 mm/s at a nozzle temperature of 230 °C), significantly higher comprehensive mechanical properties, and a more refined appearance (the surface has a fiber texture that can minimize layer lines). In addition, compared with PLA-CF, its price is more advantageous and its colors are richer. Therefore, TINMORRY PLA-GF is a basic filament with extremely high cost performance.

Note:1. Since the ABS-GF filament contains glass fiber, please use a nozzle with a diameter of ≥ 0.4 mm to decrease the risk of nozzle clogging; and please use hard enough nozzles such as those made of hardened steel, and do not use relatively soft nozzles such as those made of brass or stainless steel to slow down the wear of them. 2. Because the fan settings in the adaptive printing parameters of TINMORRY PLA-GF are quite different from those of normal PLA and PLA-CF, please ask customer service for recommended profiles as a reference before printing to avoid using the wrong parameters and reducing the strength of the prints due to excessive cooling.

• Specifications

Subjects	Data
Diameter	1.75 ± 0.03 mm
Net filament weight	1000 g
Length	333 ± 5 m
Spool material	ABS ((Temperature resistance: 80 °C) or Cardboard (Temperature resistance: 150 °C)
Spool size	External Diameter: 198 mm; Inner Diameter: 56 mm; Width: 65 mm

• Recommended Printing Settings

Subjects	Data
Drying settings before printing	55 - 60 °C, 6 - 8 h (Blast drying oven, or filament drying box)
Printing temperature and humidity	$\leq 30\text{ }^{\circ}\text{C}$, $\leq 25\%$ RH (Put in an air-tight container and sealed with desiccant)
Storage temperature and humidity	$\leq 30\text{ }^{\circ}\text{C}$, $\leq 20\%$ RH (Sealed with desiccant)
Compatible support material	Itself or support filament for PLA
Compatible printer type	Open-frame, enclosed-frame
Compatible nozzle material	Hardened steel, tungsten carbide, etc
Compatible nozzle size	0.4, 0.6, 0.8 mm
Compatible plate type	Textured PEI Plate or other plate
Plate surface preparation	Glue
Nozzle temperature	210 - 240 °C
Bed temperature	60 - 70 °C (depending on the printer and plate types)
Max Printing speed	300 - 320 mm/s (230 °C, Bambu X1C, P1S, A1)
Chamber temperature	< 40 °C

• Properties

The commonly used physical properties, mechanical properties, chemical properties, printing properties and other properties of TINMORRY PLA-GF have been tested and are shown in the tables below.

The annealing process of the specimens used in the test is: 50 °C, 3 h → 55 °C, 3 h → 60 °C, 3 h. Note that this process is for reference only. The optimal annealing process for each prints is also related to the shape, size, structure, printing parameters, etc. of the prints themselves.

• Physical Properties

Subjects	Testing Methods	Data
Density	ISO 1183	1.25 g/cm ³
Saturated water absorption rate	25 °C, 55% RH	0.42%
Melt index	210 °C, 2.16 kg	5.7 ± 0.5 g/ 10 min
Glass transition temperature	DSC, 10 °C/min	55 °C
Crystallization temperature	DSC, 10 °C/min	N / A
Melting temperature	DSC, 10 °C/min	156 °C
Vicar softening temperature	ISO 306, GB/T 1633	Not annealed: 62 °C Annealed: 78 °C
Heat deflection temperature 1	ISO 75, 1.82 MPa	Not annealed: 56 °C Annealed: 61 °C

Heat deflection temperature 2	ISO 75, 0.45 MPa	Not annealed: 58 °C Annealed: 72 °C
-------------------------------	------------------	--

• Mechanical Properties

Properties	Testing Methods	Data
Tensile strength (XY)	ISO 527, GB/T 1040	43 ± 4 MPa
Tensile strength (Z)	ISO 527, GB/T 1040	31 ± 3 MPa
Young's modulus (XY)	ISO 527, GB/T 1040	2757 ± 139 MPa
Young's modulus (Z)	ISO 527, GB/T 1040	2263 ± 154 MPa
Breaking elongation rate (XY)	ISO 527, GB/T 1040	4.4% ± 1.2%
Breaking elongation rate (Z)	ISO 527, GB/T 1040	1.3% ± 0.6%
Bending strength (XY)	ISO 178, GB/T 9341	102 ± 3 MPa
Bending strength (Z)	ISO 178, GB/T 9341	75 ± 3 MPa
Bending modulus (XY)	ISO 178, GB/T 9341	3557 ± 126 MPa
Bending modulus (Z)	ISO 178, GB/T 9341	3236 ± 168 MPa
Impact strength (XY)	ISO 179, GB/T 1043	Not annealed: 21.2 ± 1.1 kJ/m ² Annealed: 28.6 ± 1.3 kJ/m ²
Impact strength (Z)	ISO 179, GB/T 1043	Not annealed: 10.3 ± 1.2 kJ/m ² Annealed: 12.6 ± 1.3 kJ/m ²

Before and after annealing, only the impact properties of the specimens change relatively significantly, so they are listed; while the bending and tensile properties change very little, so they are not listed.

• Chemical and Other Properties

Subjects	Data
Component	PLA
Skin irritation	May cause allergy in some people, and wearing gloves is suggested
Resistance to water	Yes
Resistance to oil and grease	Resistant to most kinds of daily oil and grease
Resistance to organic solvent	Not resistant to some organic solvents
Resistance to weak acid	Yes for a short time
Resistance to strong acid	Not resistant
Resistance to weak alkali	Not resistant
Resistance to strong alkali	Not resistant
Flammability	Yes
Odor during printing	Odorless
Odor during combustion	Slightly pungent

• Specimen Info


Subjects	Data
Size	Shown at the following pictures
Nozzle temperature	230 °C

Bed temperature	55 °C
Printing speed	XY:200 mm/s; Z: 70 mm/s
Infill density	100%
Infill pattern	Concentric


Statements:

1. The test specimens were printed under the key parameters mentioned above. Before testing, all specimens were placed in an indoor environment at about 25 °C for 12 hours. Please note that different ambient temperatures, fan speeds and layer times can lead to varying cooling, which can affect the mechanical properties of the specimens, especially those in the Z-direction. Additionally, different printers can also result in variations in printing quality.
2. If high printing quality is required, it is recommended to dry every kind of TINMORRY filaments before printing and use an air-tight container and desiccant to protect them from moisture during the printing process (with humidity inside the container less than 25%) to reduce the risk of issues related to moisture absorption in filaments. The recommended drying conditions are shown above. Note that when drying them, avoid placing the spools near the heater to prevent damage to the spools or the filaments due to excessive temperature. Do not use a kitchen oven or microwave oven.
3. After annealing, the strength, stiffness, toughness and heat resistance of TINMORRY PLA-GF prints can be increased to varying degrees. However, some prints may undergo shrinkage or deformation after the annealing process. Note that the annealing effect is also affected by the size, structure, wall thickness, and infill density of the prints themselves. If you want to anneal them, it is recommended to use a blast drying oven which has uniform temperature, and it is recommended to first anneal at about 50 °C for about 4 hours, then slowly increase the temperature to about 55 °C and keep it for about 4 to 6 hours (the annealing temperature can be further increased to 60 °C according to actual conditions, but it is not recommended to exceed 65 °C); if the prints are significantly deformed halfway, it should be stopped immediately and a lower temperature should be used instead.

1. Tensile Test



2. Bending Test and Impact Test



• Disclaimer

The above properties data is obtained by TINMORRY through testing with standard samples, standard methods, and specific equipment, and is for reference and comparison only; if some data are changed, TINMORRY will update this TDS, but may not be able to inform the users, and please forgive us. The actual performance of 3D prints depends not only on the performance of the filaments used, but also on many factors, such as the degree of moisture absorption of the filaments, the printer, environmental conditions, model characteristics, printing parameters, etc.. When using TINMORRY FDM 3D printing filaments, users are responsible for the legality, safety, and performance of the prints. TINMORRY is responsible for the quality of our filaments, but not for any damage or injury that occurs during using them, or the usage scenarios of them.