Flexible Termination System (FT-CAP), X7R Dielectric, 6.3 – 250 VDC (Commercial Grade)



Overview


The KEMET Flexible Termination (FT-CAP) multilayer ceramic capacitor in X7R dielectric incorporates a unique, flexible termination system that is integrated with the KEMET standard termination materials. A conductive silver epoxy is utilized between the base metal and nickel barrier layers of KEMET's standard termination system in order to establish pliability, while maintaining terminal strength, solderability and electrical performance. This technology was developed in order to address the primary failure mode of MLCCs – flex cracks, which are typically the result of excessive tensile and shear stresses produced during board flexure and thermal cycling. Flexible termination technology inhibits the transfer of board stress to the rigid ceramic body, therefore mitigating flex cracks which can result in low IR or short circuit failures.

Although this technology does not eliminate the potential for mechanical damage that may propagate during extreme environmental and handling conditions, it does provide superior flex performance over standard termination systems. FT-CAP complements the KEMET Open Mode, Floating Electrode (FE-CAP), Floating Electrode with Flexible Termination (FF-CAP) and KEMET Power Solutions

(KPS) product lines by providing a complete portfolio of flex mitigation solutions.

Combined with the stability of an X7R dielectric and designed to accommodate all capacitance requirements, these flex-robust devices are RoHS-compliant, offer up to 5 mm of flex-bend capability and exhibit a predictable change in capacitance with respect to time and voltage. Capacitance change with reference to ambient temperature is limited to $\pm 15\%$ from -55° C to $+125^{\circ}$ C.

In addition to commercial grade, automotive grade devices are available which meet the demanding Automotive Electronics Council's AEC-Q200 qualification requirements.



Ordering Information

С	1206	X	106	K	4	R	Α	С	TU
Ceramic	Case Size (L" x W")	Specification/ Series	Capacitance Code (pF)	Capacitance Tolerance	Rated Voltage (VDC)	Dielectric	Failure Rate/ Design	Termination Finish ¹	Packaging/Grade (C-Spec) ²
	0603 0805 1206 1210 1808 1812 1825 2220 2225	X = Flexible termination	Two significant digits and number of zeros	J = ±5% K = ±10% M = ±20%	9 = 6.3 8 = 10 4 = 16 3 = 25 5 = 50 1 = 100 2 = 200 A = 250	R = X7R	A = N/A	C = 100% Matte Sn L = SnPb (5% Pb minimum)	See "Packaging C-Spec Ordering Options Table"

¹ Additional termination finish options may be available. Contact KEMET for details.



Packaging C-Spec Ordering Options Table

Packaging Type ¹	Packaging/Grade Ordering Code (C-Spec)
Bulk Bag/Unmarked	Not required (Blank)
7" Reel/Unmarked	TU
13" Reel/Unmarked	7411 (EIA 0603 and smaller case sizes) 7210 (EIA 0805 and larger case sizes)
7" Reel/Marked	TM
13" Reel/Marked	7040 (EIA 0603) 7215 (EIA 0805 and larger case sizes)
7" Reel/Unmarked/2 mm pitch²	7081
13" Reel/Unmarked/2 mm pitch ²	7082

¹ Default packaging is "Bulk Bag." An ordering code C-Spec is not required for "Bulk Bag" packaging.

Benefits

- -55°C to +125°C operating temperature range
- Superior flex performance (up to 5 mm)
- · High capacitance flex mitigation
- · Lead (Pb)-free, RoHS and REACH compliant
- EIA 0603, 0805, 1206, 1210, 1808, 1812, 1825, 2220, and 2225 case sizes
- DC voltage ratings of 6.3 V, 10 V, 16 V, 25 V, 50 V, 100 V, 200 V, and 250 V
- Capacitance offerings ranging from 180 pF to 22 μF
- Available capacitance tolerances of ±5%, ±10%, and ±20%
- · Automotive (AEC-Q200) grade available
- Non-polar device, minimizing installation concerns
- 100% pure matte tin-plated termination finish allowing for excellent solderability
- SnPb termination finish option available upon request (5% Pb minimum)

Applications


Typical applications include circuits with a direct battery or power source connection, critical and safety relevant circuits without (integrated) current limitation and any application that is subject to high levels of board flexure or temperature cycling. Examples include raw power input side filtering (power plane/bus), high current applications (automobile battery line) and circuits that cannot be fused to open. Markets include consumer, medical, industrial (power supply), automotive, aerospace and telecom.

¹ The terms "Marked" and "Unmarked" pertain to laser marking option of capacitors. All packaging options labeled as "Unmarked" will contain capacitors that have not been laser marked. Please contact KEMET if you require a laser marked option. For more information see "Capacitor Marking."

² The 2 mm pitch option allows for double the packaging quantity of capacitors on a given reel size. This option is limited to EIA 0603 (1608 metric) case size devices. For more information regarding 2 mm pitch option see "Tape & Reel Packaging Information."



Dimensions - Millimeters (Inches)



EIA Size Code	Metric Size Code	L Length	W Width	T Thickness	B Bandwidth	S Separation Minimum	Mounting Technique
06031	1608	1.60 (0.063) ±0.17 (0.007)	0.80 (0.032) ±0.15 (0.006)		0.45 (0.018) ±0.15 (0.006)	0.58 (0.023)	Caldarwaya
0805²	2012	2.00 (0.079) ±0.30 (0.012)	1.25 (0.049) ±0.30 (0.012)		0.50 (0.02) ±0.25 (0.010)	0.75 (0.030)	Solder wave or Solder reflow
1206	3216	3.30 (0.130) ±0.40 (0.016)	1.60 (0.063) ±0.35 (0.013)		0.60 (0.024) ±0.25 (0.010)		Solder reliow
1210	3225	3.30 (0.130) ±0.40 (0.016)	2.60 (0.102) ±0.30 (0.012)		0.60 (0.024) ±0.25 (0.010)		
1808	4520	4.70 (0.185) ±0.50 (0.020)	2.00 (0.079) ±0.20 (0.008)	See Table 2 for Thickness	0.70 (0.028) ±0.35 (0.014)		
1812	4532	4.50 (0.178) ±0.40 (0.016)	3.20 (0.126) ±0.30 (0.012)		0.70 (0.028) ±0.35 (0.014)	N/A	Solder reflow
1825	4564	4.60 (0.181) ±0.40 (0.016)	6.40 (0.252) ±0.40 (0.016)	-	0.70 (0.028) ±0.35 (0.014)		only
2220	5650	5.90 (0.232) ±0.75 (0.030)	5.00 (0.197) ±0.40 (0.016)		0.70 (0.028) ±0.35 (0.014)		
2225	5664	5.90 (0.232) ±0.75 (0.030)	6.40 (0.248) ±0.40 (0.016)		0.70 (0.028) ±0.35 (0.014)		

 $^{^{1}}$ For capacitance values ≥ 0.56 μF add 0.03 (0.001) to length tolerance dimension.

 $^{^{2}}$ For capacitance values 1.0 μF or ≥ 2.7 μF add 0.05 (0.002) to length tolerance dimension.



Qualification/Certification

Commercial grade products are subject to internal qualification. Details regarding test methods and conditions are referenced in Table 4, Performance & Reliability.

Environmental Compliance

Lead (Pb)-free, RoHS, and REACH compliant without exemptions (excluding SnPb termination finish option.)

Electrical Parameters/Characteristics

Item	Parameters/Characteristics
Operating Temperature Range	-55°C to +125°C
Capacitance Change with Reference to +25°C and 0 VDC Applied (TCC)	±15%
¹ Aging Rate (Maximum % Capacitance Loss/Decade Hour)	3.0%
² Dielectric Withstanding Voltage (DWV)	250% of rated voltage (5 ±1 seconds and charge/discharge not exceeding 50 mA)
³ Dissipation Factor (DF) Maximum Limit at 25°C	See Dissipation Factor Limit table
⁴ Insulation Resistance (IR) Minimum Limit at 25°C	See Insulation Resistance Limit table (Rated voltage applied for 120 ±5 seconds at 25°C)

¹ Regarding Aging Rate: Capacitance measurements (including tolerance) are indexed to a referee time of 1,000 hours.

Note: When measuring capacitance it is important to ensure the set voltage level is held constant. The HP4284 and Agilent E4980 have a feature known as Automatic Level Control (ALC). The ALC feature should be switched to "ON."

²DWV is the voltage a capacitor can withstand (survive) for a short period of time. It exceeds the nominal and continuous working voltage of the capacitor.

³ Capacitance and dissipation factor (DF) measured under the following conditions:

¹ kHz ± 50 Hz and 1.0 ± 0.2 V_{rms} if capacitance $\leq 10 \mu F$

¹²⁰ Hz ±10 Hz and 0.5 ±0.1 V_{rms} if capacitance > 10 μF

⁴ To obtain IR limit, divide $M\Omega$ - μ F value by the capacitance and compare to $G\Omega$ limit. Select the lower of the two limits.



Post Environmental Limits

High	Temperature	Life, Biased	Humidity, Mo	oisture Resis	tance
EIA Case Size	Rated DC Voltage	Capacitance	Dissipation Factor (Maximum %)	Capacitance Shift	Insulation Resistance
	< 16		7.5		
06031	16/25	< 1.0 µF	5.0		
00031	> 25		3.0		
	All	≥ 1.0 µF	20.0		
	< 16	< 4.7 μF	7.5		
	< 10	≥ 4.7 µF	20.0		
0805²	16	< 4.7 μF	5.0		
0805-	10	≥ 4.7 µF	20.0		
	25	All	5.0		
	> 25	All	3.0	±20%	10% of Initial limit
	< 16	All	7.5		
1206³	16/25	All	5.0		
	> 25	All	3.0		
	< 16	All	7.5		
1210	16/25	All	5.0		
	> 25	All	3.0		
	< 16	All	7.5		
1808 - 2225	16/25	All	5.0		
	> 25	All	3.0		

¹ For Capacitance values 0.22uF (16 and 25 Volts) DF is 7.5%.

 $^{^2}$ For Capacitance values 2.2 μ F (6.3, 10, and 16 Volts) and 4.7 μ F (25 Volts) DF is 20%.

 $^{^3}$ For Capacitance values 4.7 and 10 μ F (All Voltages) and 2.2 μ F (25 and 50 Volts) DF is 20%.



Insulation Resistance Limit Table

EIA Case Size	Rated DC Voltage	1,000 megohm microfarads or 100 GΩ	500 megohm microfarads or 10 GΩ	100 megohm microfarads or 10 GΩ
0402	ALL	< 0.012 µF	≥ 0.012 µF	N/A
0603	≤ 200 V	< 0.047 µF	≥ 0.047 µf < 0.47 µf	≥ 0.47 µf
0003	250 V	N/A	N/A	ALL
0805	≤ 200 V	< 0.15 μF	≥ 0.15 µF < 2.2 µf	≥ 2.2 µf
0805	250 V	< .027 μF	N/A	≥ .027 µF
1206	≤ 200 V	< 0.47 µF	≥ 0.47 µF < 2.2 µf	≥ 2.2 µf
1200	250 V	< 0.12 µF	N/A	≥ 0.12 µF
1210	≤ 200 V	< 0.39 µF	≥ 0.39 µF < 10 µf	≥ 10 µf
1210	250 V	< 0.27 μF	N/A	≥ 0.27 µF
1808	ALL	ALL	N/A	N/A
1812	ALL	< 2.2 μF	≥ 2.2 µF	N/A
1825	ALL	ALL	N/A	N/A
2220	ALL	< 10 μF	≥ 10 µF	N/A
2225	ALL	ALL	N/A	N/A

Dissipation Factor (DF) Limit Table

EIA Case Size	Rated DC Voltage	Capacitance	Dissipation Factor (Maximum %)
	< 16		5.0
0603¹	16/25	< 1.0 µF	3.5
0003	> 25		2.5
	All	≥ 1.0 µF	10.0
	< 16	< 4.7 µF	5.0
	× 10	≥ 4.7 µF	10.0
08052	16	< 4.7 μF	3.5
0005	10	≥ 4.7 µF	10.0
	25	All	3.5
	> 25	All	2.5
	< 16	All	5.0
1206³	16/25	All	3.5
	> 25	All	2.5
	< 16	All	5.0
1210	16/25	All	3.5
	> 25	All	2.5
	< 16	All	5.0
1808 - 2225	16/25	All	3.5
	> 25	All	2.5

¹ For Capacitance values 0.22uF (16 and 25 Volts) DF is 5%.

 $^{^2}$ For Capacitance values 2.2 μ F (6.3, 10, and 16 Volts) and 4.7 μ F (25 Volts) DF is 10%.

 $^{^3}$ For Capacitance values 4.7 and 10 μ F (All Voltages) and 2.2 μ F (25 and 50 Volts) DF is 10%.



Table 1A - Capacitance Range/Selection Waterfall (0603 - 1210 Case Sizes)

			e Si erie				(C 06	03	X					(:08	052	X					(C12	062	X					(C12	210	X		
Cap	Cap	Volt	age C	ode	9	8	4	3	5	1	2	Α	9	8	4	3	5	1	2	Α	9	8	4	3	5	1	2	Α	9	8	4	3	5	1	2	Α
Oup	Code		d Vol		w.	10	16	25	20	100	200	250	w.	9	16	25	20	100	200	250	w.	9	16	25	20	100	200	20	6.3	2	16	25	20	100	200	250
			(VDC)		ف	_	_	7					ف ا								ف ا							7	<u> </u>				L.	=	7	2
		Cap	Tolera	ance								Avail		-, -		<u> </u>		_			s – S	See '	Table	2 f	or Cl	hip 1	hicl	knes	s Di	men	sion	s				
180 pF	181	J	K	М	CJ	CJ	CJ	CJ	CJ	CJ	CJ		DR																							
220 pF	221	J	K	М	CJ	CJ	CJ	CJ	CJ	CJ	CJ		DR																							
270 pF	271	J	K	М	CJ	CJ	CJ	CJ	CJ	CJ	CJ		DR																							
330 pF	331	J	K	М	CJ	CJ	CJ	CJ	CJ	CJ	CJ		DR																							
390 pF	391	J	K	М	CJ	CJ	CJ	CJ	CJ	CJ	CJ		DR																							
470 pF	471	J	K	М	CJ	CJ	CJ	CJ	CJ	CJ	CJ		DR	EQ	EQ	EQ	EQ	EQ				l														
560 pF	561	J	K	М	CJ	CJ	CJ	CJ	CJ	CJ	CJ		DR																							
680 pF	681	J	K	M	CJ	CJ	CJ	CJ	CJ	CJ	CJ		DR	l																						
820 pF	821	J	K	M	CJ	CJ	CJ	CJ	CJ	CJ	CJ	۵.	DR																							
1,000 pF	102	J	K	M	CJ	CJ	CJ	CJ	CJ	CJ	CJ	CJ	DR	EQ	EQ	EQ	EQ	EQ	EQ	EQ	EQ															
1,200 pF	122	J	K	M	CJ	CJ	CJ	CJ	CJ	CJ	CJ	CJ	DR	EQ	EQ	EQ	EQ	EQ	EQ	EQ	EQ															
1,500 pF	152	J	K	M	CJ	CJ	CJ	CJ	CJ	CJ	CJ	CJ	DR	EQ	EQ	EQ	EQ	EQ	EQ	EQ	EQ															
1,800 pF	182	J	K	M	CJ	CJ	CJ	CJ	CJ	CJ	CJ	CJ	DR	EQ	EQ	EQ	EQ	EQ	EQ	EQ	EQ	 	ENI	ENI	ENI	ENI	ENI	ENI	-NI							
2,200 pF	222	J	K	M	CJ	CJ	CJ	CJ	CJ	CJ	CJ	CJ	DR	EQ	EQ	EQ	EQ	EQ	EQ	EQ	EQ	FN	FN	FN	FN	FN	FN		FN							
2,700 pF	272	J	K	M	CJ	CJ	CJ	CJ	CJ	CJ	CJ	CJ	DR	EQ	EQ	EQ	EQ	EQ	EQ	EQ	EQ	FN	FN	FN	FN	FN	FN	FN	FN							
3,300 pF	332	J	K	M	CJ	CJ	CJ	CJ	CJ	CJ	CJ	CJ	DR	EQ	EQ	EQ	EQ	EQ	EQ	EQ	EQ	FN FN	FN													
3,900 pF 4,700 pF	392 472	J	K	M	CJ	CJ	CJ	CJ	CJ	CJ	CJ	CJ	DR DR	DR	DR	DR DR	DR	DR	DR	DR	EQ EQ	EQ	EQ EQ	EQ	EQ	EQ	EQ	EQ	FN	FN	FN	FN	FN	FN	FN	FN FN
1 ' ' 1		J	K	M	CJ	CJ	CJ	CJ	CJ	CJ	CJ	CJ	DR	DR	DR		DR	DR	DR	DR		EQ		EQ	EQ	EQ	EQ	EQ	FN	FN FN	FN	FN	FN	FN	FN	FN
5,600 pF	562	J	K K	M	Cl	CJ	CJ	CJ	CJ	CJ	CJ	CJ	!	DR	EQ EQ	EQ EQ	EQ	EQ	EQ EQ	EQ	EQ	EQ E0			FN	FN	FN	FN	FN FN							
6,800 pF 8,200 pF	682 822	J	K	M	CJ	CJ	CJ	CJ	CJ	CJ	CJ	CJ	DR DR	EQ	EQ	EQ	EQ	EQ	EQ	EQ	EQ	FN	FN	FN	FN	FN	FN	FN	FN FN							
10,000 pF		J		M									DR			DR	DR				EQ	EQ	EQ	EQ EQ		EQ	EQ EQ	_		FN				FN		FN
	103	J	K K	M	CJ	CJ	CJ	CJ	CJ	CJ	CJ	CJ	DR	DR DR	DR DR	DR	DR	DR	DR	DR DR					EQ	EQ		EQ	FN FN	FN	FN	FN	FN FN	FN	FN	FN
12,000 pF 15,000 pF	123 153	J	K	M	CJ	CJ	CJ	CJ	CJ	CJ			DR	DR	DR	DR DR	DR	DR DD	DR DR	DR	EQ EQ	EQ EQ	EQ EQ	EQ EQ	EQ EQ	EQ EO	EQ EQ	EQ EQ	FN	FN	FN FN	FN FN	FN	FN FN	FN FN	FN
18,000 pF	183	J	K	M	CJ	CJ	CJ	CJ	CJ	CJ			DR	DR	DR	DR	DR	DD	DR	DR	EQ	EQ	EQ	EQ	EQ	EQ EO	EQ	EQ	FN	FN	FN	FN	FN	FN	FN	FN
22,000 pF	223	J	K	M	CJ	CJ	CJ	CJ	CJ	CJ			DR	DR	DR	DR	DR	DD	DR	DR	EQ	EQ	EQ	EQ	EQ	EQ	EQ	EQ	FN	FN	FN	FN	FN	FN	FN	FN
27,000 pF	273	J	K	M	CJ	CJ	CJ	CJ	CJ	CJ			DR	DR	DR	DR	DR	DD	DS	DG	EQ	EQ	EQ	EQ	EQ	EQ	EQ	EQ	FN	FN	FN	FN	FN	FN	FN	FN
33,000 pF	333	J	K	M	CJ	CJ	CJ	CJ	CJ	CJ			DR	DR	DR	DR	DR	DD	DS	DG	EQ	EQ	EQ	EQ	EQ	EQ	EQ	EQ	FN	FN	FN	FN	FN	FN	FN	FN
39,000 pF	393	J	K	M	CJ	CJ	CJ	CJ	CJ	CJ			DR	DR	DR	DR	DR	DD	DS	DG	EQ	EQ	EQ	EQ	EQ	ER	EQ	EO	FN	FN	FN	FN	FN	FN	FN	FN
47,000 pF	473	J	K	M	CJ	CJ	CJ	CJ	CJ	CJ			DR	DR	DR	DR	DR		DG	DG	EQ	EQ	EQ	EQ	EQ	ER	ES	ES	FN	FN	FN	FN	FN	FN	FQ	FQ
.7,000 μι	7,5	Rate	d Vol	_	m					_		-	<u>ه</u>								3	Ė		i i	T .	_	_		-							_
	Сар	(VDC)		•	6.3	10	16	25	20	100	200	250	6.3	9	16	25	20	100	200	250	6.3	9	91	25	20	100	200	250	6.3	2	91	25	20	100	200	250
Cap	Code	Volt	age C	ode	9	8	4	3	5	1	2	A	9	8	4	3	5	1	2	A	9 8 4 3 5			1	2	Α	9	8	4	3	5	1	2	A		
	353		se Si Series					C06	03X							C08	05X				C1206X								C12	10X						



Table 1A - Capacitance Range/Selection Waterfall (0603 - 1210 Case Sizes) cont.

			e Si erie				(CO 6	03	X					(208	05	X					(C12	06)	((C12	102	K		
Cap	Cap	Volt	age C	ode	9	8	4	3	5	1	2	A	9	8	4	3	5	1	2	Α	9	8	4	3	5	1	2	Α	9	8	4	3	5	1	2	A
33.6	Code		d Vol		6.3	10	16	25	20	100	200	250	6.3	2	16	25	20	100	200	250	6.3	10	16	25	20	100	200	250	6.3	2	16	25	20	100	200	250
			Toler				<u> </u>		F		uct A		ı labil	ity a	nd C	hip	Thic				: - S	ee 1	Γable	2 f	or Cl	nip T	<u> </u>		s Di	nen	sion	s				
56,000 pF	563	J	K	М	CJ	CJ	CJ	CJ	CJ				DD	DD	DD	DD	DD	DS	_	DG	EQ	EQ	EQ	EQ	EQ	EQ	ES		FN	FN	FN	FN	FN	FN	FQ	FQ
68,000 pF	683	J	K	М	CJ	CJ	CJ	CJ	CJ				DD	DD	DD	DD	DD	DS	DG	DG	EQ	EQ	EQ	EQ	EQ	EQ	ES	ES	FN	FN	FN	FN	FN	FN	FQ	FQ
82,000 pF	823	J	K	М	CJ	CJ	CJ	CJ	CJ				DD	DD	DD	DD	DD	DS			EQ	EQ	EQ	EQ	EQ	EQ	ES	ES	FN	FN	FN	FN	FN	FQ	FA	FA
0.10 µF	104	J	K	М	CJ	CJ	CJ	CJ	CJ				DR	DR	DR	DR	DR	DS			EQ	EQ	EQ	EQ	EQ	EQ	EM	EM	FN	FN	FN	FN	FN	FX	FZ	FZ
0.12 µF	124	J	K	М	CJ	CJ	CJ	CJ	CJ				DR	DR	DR	DR	DD	DG			ER	ER	ER	ER	ER	ER	EU	EM	FN	FN	FN	FN	FN	FX	FU	FU
0.15 μF	154	J	K	М	CJ	CJ	CJ	CJ	CJ				DR	DR	DR	DR	DD	DG			ER	ER	ER	ER	ER	ER	EU	EH	FQ	FQ	FQ	FQ	FQ	FX	FM	FM
0.18 µF	184	J	K	М	CJ	CJ	CJ	CJ					DR	DR	DR	DR	DG	DG			ER	ER	ER	ER	ER	ER	EM	EM	FQ	FQ	FQ	FQ	FQ	FX	FK	FK
0.22 µF	224	J	K	М	CJ	CJ	CJ	CJ					DR	DR	DR	DR	DG	DG			ER	ER	ER	ER	ER	ER	EH	EH	FQ	FQ	FQ	FQ	FQ	FX	FK	FK
0.27 µF	274	J	K	М	CJ	CJ	CJ						DD	DD	DD	DD	DD				EQ	EQ	EQ	EQ	ER	EM			FQ	FQ	FQ	FQ	FQ	FX	FP	FP
0.33 µF	334	J	K	М	CJ	CJ	CJ						DG	DG	DG	DG	DD				EQ	EQ	EQ	EQ	ER	EU			FX	FX	FX	FX	FX	FX	FM	FM
0.39 µF	394	J	K	М	CJ	CJ	CJ						DG	DG	DG	DG	DS				EQ	EQ	EQ	EQ	ER	EU			FX	FX	FX	FX	FX	FX	FK	FK
0.47 µF	474	J	K	М	CJ	CJ	CJ						DG	DG	DG	DG	DS				ER	ER	ER	ER	ER	EU			FX	FX	FX	FX	FX	FX	FS	FS
0.56 μF	564	J	K	М									DD	DD	DD	DG	DH				ES	ES	ES	ES	ER	ЕМ			FX	FX	FX	FX	FX	FA		
0.68 µF	684	J	K	М									DD	DD	DD	DG	DH				ET	ET	ET	ET	ES	ЕМ			FX	FX	FX	FX	FX	FZ		
0.82 µF	824	J	K	М									DD	DD	DD	DG					EF	EF	EF	EF	ES	EU			FA	FA	FA	FA	FA	FL		
1.0 μF	105	J	K	М	CJ	CJ	CJ						DD	DD	DD	DG					EF	EF	EF	EU	ES	EU			FU	FU	FU	FU	FU	FM		
1.2 µF	125	J	К	М									DS	DS	DS						ES	ES	ES	EU	EH				FU	FU	FU	FU	FZ	FH		
1.5 µF	155	J	K	М	i								DG	DG	DG						EF	EF	EF	EU	EH				FU	FU	FU	FU	FZ	FM		
1.8 µF	185	J	K	М	i								DG	DG	DG						ES	ES	ES	EF	EH				FU	FU	FU	FU	FZ	FJ		
2.2 µF	225	J	K	М	i								DG	DG	DG						EA	EA	EA	EH	EH				FJ	FJ	FJ	FJ	FZ	FK		
2.7 µF	275	J	K	М																	EN	EN	EN	EH					FE	FE	FE	FZ	FU			
3.3 µF	335	Ĵ	K	М									i								ES	ES	ES	EH					FA	FA	FA	FM	FM			
3.9 µF	395	J	K	М																	EF	EF	EF	EH					FZ	FZ	FZ	FZ	FK			
4.7 μF	475	J	K	М									DH	DH	DH	DH					EA	EA	EA	EA	EA				FQ	F0	F0	FZ	FS			
5.6 μF	565	J	K	M										J.1	5.1	511					EH	EH	EH						FA	FA		FU	'			
6.8 µF	685	J	K	M																	EH	EH	EH						FZ	FZ	FZ	FM				
8.2 µF	825	J	K	M									l								EH	EH	EH						FU	FU	FU	FK				
10 μF	106	J	K	M									ПН	DH							EA	EA	EA	EA					FS	FS	FS	FS				
22 μF	226	J.	K	M									"									-~	-	-~					FS	FS	' '	' '				
μ·		Rate	d Vol			6.3 10 16 16 50 50 200 250				<u> </u>		٠,0			0	0	0			,0			-	0	0	_		٠,0			0	0	-			
			(VDC)	•	9	10	16	25	20	9	20	250	6.3	2	16	25	20	100	200	250	6.3	2	16	25	20	100	200	250	6.3	2	16	25	20	100	200	250
Cap	Cap Code	Volt	age C	ode	9	8	4	3	5	1	2	A	9	8	4	3	5	1	2	A	A 9 8 4 3 5 1 2 A			Α	9	8	4	3	5	1	2	Α				
	Joue		se Si Serie					C06	03X							C08	05X				C1206X								C12	10X						



Table 1B - Capacitance Range/Selection Waterfall (1808 - 2225 Case Sizes)

			e Si erie			C18	08X			С	1812	X			C18	25X			С	2220	X			C22	25X	
Сар	Cap	Volt	age C	ode	5	1	2	Α	3	5	1	2	Α	5	1	2	Α	3	5	1	2	Α	5	1	2	Α
Oup	Code		d Vol		20	9	200	250	25	20	001	200	250	20	901	200	250	25	20	100	200	250	20	100	200	250
			Tolera				, ,		ıct Av	ailabi	itv an			kness	Codes			e 2 foi	r Chip	Thick	l		sions			_ ``
4,700 pF	472	J	K	М	LD	LD	LD				,								- III							
5,600 pF	562	J	K	М	LD	LD	LD																			
6,800 pF	682	J	K	М	LD	LD	LD		GB	GB	GB	GB	GB													
8,200 pF	822	J	K	M	LD	LD	LD		GB	GB	GB	GB	GB										ļ			
10,000 pF	103	J	K	М	LD	LD	LD		GB	GB	GB	GB	GB													
12,000 pF	123	J	K	М	LD	LD	LD		GB	GB	GB	GB	GB										ŀ			
15,000 pF	153	J	K	M	LD LD	LD LD	LD LD		GB	GB	GB	GB GB	GB										ŀ			
18,000 pF 22,000 pF	183 223	J	K K	M	LD	LD	LD		GB GB	GB GB	GB GB	GB	GB GB	НВ	НВ	НВ	НВ						ŀ			
27,000 pF	273	J	K	M	LD	LD			GB	GB	GB	GB	GB	НВ	НВ	НВ	НВ						ŀ			
33,000 pF	333	J	K	M	LD	LD			GB	GB	GB	GB	GB	НВ	НВ	НВ	НВ									
39,000 pF	393	Ĵ	K	M	LD	LD			GB	GB	GB	GB	GB	НВ	НВ	НВ	НВ									
47,000 pF	473	Ĵ	K	М	LD	LD			GB	GB	GB	GB	GB	НВ	НВ	НВ	НВ									
56,000 pF	563	J	K	М	LD	LD			GB	GB	GB	GB	GB	НВ	НВ	НВ	НВ						İ			
68,000 pF	683	J	K	М	LD				GB	GB	GB	GB	GB	НВ	НВ	НВ	НВ									
82,000 pF	823	J	K	М	LD				GB	GB	GB	GB	GB	НВ	НВ	НВ	НВ	JC	JC	JC	JC	JC				
0.10 μF	104	J	K	M	LD				GB	GB	GB	GB	GB	НВ	НВ	НВ	НВ	JC	JC	JC	JC	JC	KC	KC	KC	KC
0.12 µF	124	J	K	М	LD				GB	GB	GB	GB	GB	НВ	HB	HB	HB	JC	JC	JC	JC	JC	KC	KC	KC	KC
0.15 μF	154	J	K	M	LD				GB	GB	GB	GE	GE	НВ	НВ	HB	HB	JC	JC	JC	JC	JC	KC	KC	KC	KC
0.18 μF	184	J	K	М	LD				GB	GB	GB	GF	GG	НВ	НВ	НВ	HB	JC	JC	JC	JC	JC	KC	KC	KC	KC
0.22 µF	224	J	K	M					GB	GB	GB	GG	GG	НВ	НВ	НВ	НВ	JC	JC	JC	JC	JC	KC	KC	KC	KC
0.27 μF	274	J	K	M					GB	GB	GG	GG	GG	НВ	НВ	НВ	НВ	JC	JC	JC	JC	JC	KB	KC	KC	KC
0.33 μF	334	J	K	M					GB GB	GB GB	GG GG	GG GG	GG	НВ	HB HB	HB	HB HD	JC	JC	JC	JC	JC	KB KB	KC KC	KC KC	KC
0.39 μF 0.47 μF	394 474	J	K K	M M					GB	GB	GG	GJ	GG GJ	HB HB	НВ	HD HD	HD	JC JC	JC	JC	JC	JC	KB	KC	KD	KC KD
0.47 μF 0.56 μF	564	J	K	M					GC	GC	GG	GJ	GJ	НВ	HD	HD	HD	JC	JC	JC	JD	JD	KB	KC	KD	KD
0.68 μF	684	J	K	M					GC	GC	GG			НВ	HD	HD	HD	JC	JC	JD	JD	JD	KB	KC	KD	KD
0.82 μF	824	Ĵ	K	М					GE	GE	GG			НВ	HF	HF	HF	JC	JC	JF	JF	JF	KB	KC	KE	KE
1.0 µF	105	Ĵ	K	М					GE	GE	GG			НВ	HF	HF	HF	JC	JC	JF	JF	JF	KB	KD	KE	KE
1.2 µF	125	Ĵ	K	М					GB	GB	GB			НВ				JC	JC				KB	KE	KE	KE
1.5 µF	155	J	K	М					GC	GC	GC			НС				JC	JC				KC			
1.8 μF	185	J	K	М					GE	GE	GE			HD				JD	JD				KD			
2.2 µF	225	J	K	М					GG	GG	GG			HF				JF	JF				KD			
2.7 μF	275	J	K	М					GJ	GJ	GJ															
3.3 μF	335	J	K	М					GL	GL	GL															
4.7 μF	475	J	K	M					GK	GK								ا					1			
10 μF	106	J	K	M					GK									JF	J0							
15 µF	156	J	K K	M														J0	J0							
22 μF	226	J Rate		M	_			-			_	-	•	_				J0	_	-		-	 _ 		-	-
	Con	Rated Voltage (VDC)		20	100	200	250	25	20	100	200	250	20	100	200	250	25	20	190	200	250	20	100	200	250	
Сар	Cap Code	<u> </u>	age C		5	1	2	A	3	5	1	2	A	5	1	2	Α	3	5	1	2	Α	5	1	2	Α
			se Siz Series			C18	08X				1812	K			C18	25X				2220	x			C22	25X	



Table 2A - Chip Thickness/Tape & Reel Packaging Quantities

Thickness	Case	Thickness ±	Paper Q	uantity ¹	Plastic (Quantity
Code	Size ¹	Range (mm)	7" Reel	13" Reel	7" Reel	13" Reel
CJ	0603	0.80 ±0.15*	4,000	15,000	0	0
DR	0805	0.78 ±0.20	0	0	4,000	10,000
DD	0805	0.90 ±0.10	0	0	4,000	10,000
DS DG	0805 0805	1.00 ±0.20 1.25 ±0.15	0 0	0 0	2,500 2,500	10,000 10,000
DH	0805	1.25 ±0.15	0	0	2,500	10,000
EQ	1206	0.78 ±0.20	4,000	10,000	4,000	10,000
ER	1206	0.90 ±0.20	0	0	4,000	10,000
EN	1206	0.95 ±0.10	0	0	4,000	10,000
ES	1206	1.00 ±0.20	0	0	2,500	10,000
ET	1206	1.10 ±0.20	0	0	2,500	10,000
EF	1206	1.20 ±0.15	0	0	2,500	10,000
EM	1206	1.25 ±0.15	0	0	2,500	10,000
EH	1206	1.60 ±0.20	0	0	2,000	8,000
EU	1206	1.60 ±0.25	0	0	2,000	8,000
EA FN	1206 1210	1.60 ±0.35 0.78 ±0.20	0 0	0 0	2,000 4,000	8,000 10,000
FQ FQ	1210	0.76 ±0.20 0.90 ±0.20	0	0	4,000	10,000
FX	1210	0.95 ±0.20	0	0	4,000	10,000
FE	1210	1.00 ±0.10	Ö	Ö	2,500	10,000
FA	1210	1.10 ±0.15	0	0	2,500	10,000
FZ	1210	1.25 ±0.20	0	0	2,500	10,000
FL	1210	1.40 ±0.15	0	0	2,000	8,000
FH	1210	1.55 ±0.15	0	0	2,000	8,000
FU	1210	1.55 ±0.20	0	0	2,000	8,000
FP	1210	1.60 ±0.20	0	0	2,000	8,000
FM	1210	1.70 ±0.20	0	0	2,000	8,000
FJ FK	1210 1210	1.85 ±0.20 2.10 ±0.20	0 0	0 0	2,000 2,000	8,000 8,000
FS	1210	2.50 ±0.20	0	0	1,000	4,000
LD	1808	0.90 ±0.10	Ö	0	2,500	10,000
GB	1812	1.00 ±0.10	0	0	1,000	4,000
GC	1812	1.10 ±0.10	0	0	1,000	4,000
GE	1812	1.30 ±0.10	0	0	1,000	4,000
GF	1812	1.50 ±0.10	0	0	1,000	4,000
GG	1812	1.55 ±0.10	0	0	1,000	4,000
GK	1812	1.60 ±0.20	0	0	1,000	4,000
GJ GL	1812 1812	1.70 ±0.15 1.90 ±0.20	0 0	0 0	1,000 500	4,000
HB	1812	1.90 ±0.20 1.10 ±0.15	0	0	1,000	2,000 4,000
HC	1825	1.10 ±0.15	0	0	1,000	4,000
HD	1825	1.30 ±0.15	Ö	Ö	1,000	4,000
HF	1825	1.50 ±0.15	0	0	1,000	4,000
JC	2220	1.10 ±0.15	0	0	1,000	4,000
JD	2220	1.30 ±0.15	0	0	1,000	4,000
JF	2220	1.50 ±0.15	0	0	1,000	4,000
J0	2220	2.40 ±0.15	0	0	500	2,000
KB	2225	1.00 ±0.15	0	0	1,000	4,000
KC KD	2225 2225	1.10 ±0.15 1.30 ±0.15	0 0	0 0	1,000 1,000	4,000 4,000
KE	2225	1.40 ±0.15	0	0	1,000	4,000
		1	7" Reel	13" Reel	7" Reel	13" Reel
Thickness Code	Case Size ¹	Thickness ± Range (mm)				
Joue	3125	yc (mm)	Paper Q	udiilily .	Plastic (Quantity

Package quantity based on finished chip thickness specifications.

¹ If ordering using the 2 mm Tape & Reel pitch option, the packaging quantity outlined in the table above will be doubled. This option is limited to EIA 0603 (1608 metric) case size devices. For more information regarding 2 mm pitch option see "Tape & Reel Packaging Information."



Table 2B - Bulk Packaging Quantities

Dookse	ving Type	Loose P	ackaging
Раска	jing Type	Bulk Bag	(default)
Packagi	ng C-Spec ¹	N,	/A ²
Cas	e Size	Packaging Quantities (pieces/unit packaging)
EIA (in)	Metric (mm)	Minimum	Maximum
0402	1005		
0603	1608		
0805	2012		50,000
1206	3216		
1210	3225	1	
1808	4520	ľ	
1812	4532		
1825	4564		20,000
2220	5650		
2225	5664		

¹ The "Packaging C-Spec" is a 4 to 8 digit code which identifies the packaging type and/or product grade. When ordering, the proper code must be included in the 15th through 22nd character positions of the ordering code. See "Ordering Information" section of this document for further details. Commercial grade product ordered without a packaging C-Spec will default to our standard "Bulk Bag" packaging. Contact KEMET if you require a bulk bag packaging option for automotive grade products.

² A packaging C-Spec (see note 1 above) is not required for "Bulk Bag" packaging (excluding anti-static Bulk Bag and automotive grade products.) The 15th through 22nd character positions of the ordering code should be left blank. All products ordered without a packaging C-Spec will default to our standard "Bulk Bag" packaging.




Table 3 - Chip Capacitor Land Pattern Design Recommendations per IPC-7351

EIA Size Code	Metric Size Code	Density Level A: Maximum (Most) Land Protrusion (mm)				Density Level B: Median (Nominal) Land Protrusion (mm)				Density Level C: Minimum (Least) Land Protrusion (mm)						
Code	Code	С	Y	X	V1	V2	С	Y	X	V1	V2	С	Y	X	V1	V2
0603	1608	0.85	1.25	1.10	4.00	2.10	0.75	1.05	1.00	3.10	1.50	0.65	0.85	0.90	2.40	1.20
0805	2012	0.99	1.44	1.66	4.47	2.71	0.89	1.24	1.56	3.57	2.11	0.79	1.04	1.46	2.42	1.81
1206	3216	1.59	1.62	2.06	5.85	3.06	1.49	1.42	1.96	4.95	2.46	1.39	1.22	1.86	4.25	2.16
1210	3225	1.59	1.62	3.01	5.90	4.01	1.49	1.42	2.91	4.95	3.41	1.39	1.22	2.81	4.25	3.11
1808	4520	2.30	1.75	2.30	7.40	3.30	2.20	1.55	2.20	6.50	2.70	2.10	1.35	2.10	5.80	2.40
1812	4532	2.10	1.80	3.60	7.00	4.60	2.00	1.60	3.50	6.10	4.00	1.90	1.40	3.40	5.40	3.70
1825	4564	2.15	1.80	6.90	7.10	7.90	2.05	1.60	6.80	6.20	7.30	1.95	1.40	6.70	5.50	7.00
2220	5650	2.85	2.10	5.50	8.80	6.50	2.75	1.90	5.40	7.90	5.90	2.65	1.70	5.30	7.20	5.60
2225	5664	2.85	2.10	6.90	8.80	7.90	2.75	1.90	6.80	7.90	7.30	2.65	1.70	6.70	7.20	7.00

Density Level A: For low-density product applications. Recommended for wave solder applications and provides a wider process window for reflow solder processes. KEMET only recommends wave soldering of EIA 0603, 0805, and 1206 case sizes.

Density Level B: For products with a moderate level of component density. Provides a robust solder attachment condition for reflow solder processes. **Density Level C:** For high component density product applications. Before adapting the minimum land pattern variations, the user should perform qualification testing based on the conditions outlined in IPC Standard 7351 (IPC-7351).

Image below based on Density Level B for an EIA 1210 case size.





Soldering Process


Recommended Soldering Technique:

- Solder wave or solder reflow for EIA case sizes 0603, 0805 and 1206
- · All other EIA case sizes are limited to solder reflow only

Recommended Reflow Soldering Profile:

The KEMET families of surface mount multilayer ceramic capacitors (SMD MLCCs) are compatible with wave (single or dual), convection, IR or vapor phase reflow techniques. Preheating of these components is recommended to avoid extreme thermal stress. The KEMET recommended profile conditions for convection and IR reflow reflect the profile conditions of the IPC/ J-STD-020 standard for moisture sensitivity testing. These devices can safely withstand a maximum of three reflow passes at these conditions.

Profile Feature	Termination Finish			
Trome readure	SnPb	100% Matte Sn		
Preheat/Soak				
Temperature Minimum (T _{Smin})	100°C	150°C		
Temperature Maximum (T _{Smax})	150°C	200°C		
Time (t_s) from T_{smin} to T_{smax}	60 - 120 seconds	60 - 120 seconds		
Ramp-Up Rate (T _L to T _P)	3°C/second maximum	3°C/second maximum		
Liquidous Temperature (T_L)	183°C	217°C		
Time Above Liquidous (t _L)	60 - 150 seconds	60 - 150 seconds		
Peak Temperature (T _P)	235°C	260°C		
Time Within 5°C of Maximum Peak Temperature (t _p)	20 seconds maximum	30 seconds maximum		
Ramp-Down Rate $(T_p \text{ to } T_L)$	6°C/second maximum	6°C/second maximum		
Time 25°C to Peak Temperature	6 minutes maximum	8 minutes maximum		








Table 4 - Performance & Reliability: Test Methods and Conditions


Stress	Reference	Test or Inspection Method				
Terminal Strength	JIS-C-6429	Appendix 1, Note: Force of 1.8 kg for 60 seconds.				
Board Flex	JIS-C-6429	Appendix 2, Note: Standard termination system – 2.0 mm (minimum) for all except 3 mm for COG. Flexible termination system – 3.0 mm (minimum).				
		Magnification 50 X, conditions:				
Solderability	J-STD-002	a) Method B, 4 hours at 155°C, dry heat at 235°C				
Solderability	J-31D-002	b) Method B, category 3 at 215°C				
		c) Method D, category 3 at 260°C				
Temperature Cycling	JESD22 Method JA-104	1,000 cycles (-55°C to +125°C). Measurement at 24 hours ±4 hours after test conclusion.				
Biased Humidity	MIL-STD-202	Load humidity: 1,000 hours 85°C/85% RH and rated voltage. Add 100 K ohm resistor. Measurement at 24 hours ±4 hours after test conclusion.				
blased Hullilaity	Method 103	Low volt humidity: 1,000 hours 85°C/85% RH and 1.5 V. Add 100 K ohm resistor. Measurement at 24 hours ±4 hours after test conclusion.				
Moisture Resistance	MIL-STD-202 Method 106	t = 24 hours/cycle. Steps 7a and 7b not required. Measurement at 24 hours ±4 hours after test conclusion.				
Thermal Shock	MIL-STD-202 Method 107	-55°C/+125°C. Note: Number of cycles required – 300. Maximum transfer time – 20 seconds. Dwell time – 15 minutes. Air – air.				
High Temperature Life	MIL-STD-202 Method 108/EIA-198	1,000 hours at 125°C (85°C for X5R, Z5U and Y5V) with 2 X rated voltage applied.				
Storage Life	MIL-STD-202 Method 108	150°C, 0 VDC for 1,000 hours.				
Vibration	MIL-STD-202 Method 204	5 g's for 20 minutes, 12 cycles each of 3 orientations. Note: Use 8" X 5" PCB 0.031" thick 7 secure points on one long side and 2 secure points at corners of opposite sides. Parts mounted within 2" from any secure point. Test from 10 – 2,000 Hz				
Mechanical Shock	MIL-STD-202 Method 213	Figure 1 of Method 213, Condition F.				
Resistance to Solvents	MIL-STD-202 Method 215	Add aqueous wash chemical, OKEM Clean or equivalent.				

Storage & Handling

Ceramic chip capacitors should be stored in normal working environments. While the chips themselves are quite robust in other environments, solderability will be degraded by exposure to high temperatures, high humidity, corrosive atmospheres, and long term storage. In addition, packaging materials will be degraded by high temperature – reels may soften or warp and tape peel force may increase. KEMET recommends that maximum storage temperature not exceed 40°C and maximum storage humidity not exceed 70% relative humidity. Temperature fluctuations should be minimized to avoid condensation on the parts and atmospheres should be free of chlorine and sulfur bearing compounds. For optimized solderability chip stock should be used promptly, preferably within 1.5 years of receipt.



Construction





Capacitor Marking (Optional)

These surface mount multilayer ceramic capacitors are normally supplied unmarked. If required, they can be marked as an extra cost option. Marking is available on most KEMET devices, but must be requested using the correct ordering code identifier(s). If this option is requested, two sides of the ceramic body will be laser marked with a "K" to identify KEMET, followed by two characters (per EIA–198 - see table below) to identify the capacitance value. EIA 0603 case size devices are limited to the "K" character only.

Laser marking option is <u>not</u> available on:

- · COG, ultra stable X8R and Y5V dielectric devices.
- EIA 0402 case size devices.
- EIA 0603 case size devices with flexible termination option.
- KPS commercial and automotive grade stacked devices
- X7R dielectric products in capacitance values outlined below.

EIA Case Size	Metric Size Code	Capacitance
0603	1608	≤ 170 pF
0805	2012	≤ 150 pF
1206	3216	≤ 910 pF
1210	3225	≤ 2,000 pF
1808	4520	≤ 3,900 pF
1812	4532	≤ 6,700 pF
1825	4564	≤ 0.018 µF
2220	5650	≤ 0.027 µF
2225	5664	≤ 0.033 µF

Marking appears in legible contrast. Illustrated below is an example of an MLCC with laser marking of "KA8", which designates a KEMET device with rated capacitance of 100 μ F. Orientation of marking is vendor optional.





Capacitor Marking (Optional) cont.

Capacitance (pF) For Various Alpha/Numeral Identifiers													
Alpha						Numera	ıl						
Alpha Character	9	0	1	2	3	4	5	6	7	8			
Cilaracter	Capacitance (pF)												
Α	0.10	1.0	10	100	1,000	10,000	100,000	1,000,000	10,000,000	100,000,000			
В	0.11	1.1	11	110	1,100	11,000	110,000	1,100,000	11,000,000	110,000,000			
С	0.12	1.2	12	120	1,200	12,000	120,000	1,200,000	12,000,000	120,000,000			
D	0.13	1.3	13	130	1,300	13,000	130,000	1,300,000	13,000,000	130,000,000			
Е	0.15	1.5	15	150	1,500	15,000	150,000	1,500,000	15,000,000	150,000,000			
F	0.16	1.6	16	160	1,600	16,000	160,000	1,600,000	16,000,000	160,000,000			
G	0.18	1.8	18	180	1,800	18,000	180,000	1,800,000	18,000,000	180,000,000			
Н	0.20	2.0	20	200	2,000	20,000	200,000	2,000,000	20,000,000	200,000,000			
J	0.22	2.2	22	220	2,200	22,000	220,000	2,200,000	22,000,000	220,000,000			
K	0.24	2.4	24	240	2,400	24,000	240,000	2,400,000	24,000,000	240,000,000			
L	0.27	2.7	27	270	2,700	27,000	270,000	2,700,000	27,000,000	270,000,000			
М	0.30	3.0	30	300	3,000	30,000	300,000	3,000,000	30,000,000	300,000,000			
N	0.33	3.3	33	330	3,300	33,000	330,000	3,300,000	33,000,000	330,000,000			
Р	0.36	3.6	36	360	3,600	36,000	360,000	3,600,000	36,000,000	360,000,000			
Q	0.39	3.9	39	390	3,900	39,000	390,000	3,900,000	39,000,000	390,000,000			
R	0.43	4.3	43	430	4,300	43,000	430,000	4,300,000	43,000,000	430,000,000			
S	0.47	4.7	47	470	4,700	47,000	470,000	4,700,000	47,000,000	470,000,000			
T	0.51	5.1	51	510	5,100	51,000	510,000	5,100,000	51,000,000	510,000,000			
U	0.56	5.6	56	560	5,600	56,000	560,000	5,600,000	56,000,000	560,000,000			
V	0.62	6.2	62	620	6,200	62,000	620,000	6,200,000	62,000,000	620,000,000			
W	0.68	6.8	68	680	6,800	68,000	680,000	6,800,000	68,000,000	680,000,000			
Х	0.75	7.5	75	750	7,500	75,000	750,000	7,500,000	75,000,000	750,000,000			
Υ	0.82	8.2	82	820	8,200	82,000	820,000	8,200,000	82,000,000	820,000,000			
Z	0.91	9.1	91	910	9,100	91,000	910,000	9,100,000	91,000,000	910,000,000			
а	0.25	2.5	25	250	2,500	25,000	250,000	2,500,000	25,000,000	250,000,000			
b	0.35	3.5	35	350	3,500	35,000	350,000	3,500,000	35,000,000	350,000,000			
d	0.40	4.0	40	400	4,000	40,000	400,000	4,000,000	40,000,000	400,000,000			
е	0.45	4.5	45	450	4,500	45,000	450,000	4,500,000	45,000,000	450,000,000			
f	0.50	5.0	50	500	5,000	50,000	500,000	5,000,000	50,000,000	500,000,000			
m	0.60	6.0	60	600	6,000	60,000	600,000	6,000,000	60,000,000	600,000,000			
n	0.70	7.0	70	700	7,000	70,000	700,000	7,000,000	70,000,000	700,000,000			
t	0.80	8.0	80	800	8,000	80,000	800,000	8,000,000	80,000,000	800,000,000			
у	0.90	9.0	90	900	9,000	90,000	900,000	9,000,000	90,000,000	900,000,000			



Tape & Reel Packaging Information

KEMET offers multilayer ceramic chip capacitors packaged in 8, 12 and 16 mm tape on 7" and 13" reels in accordance with EIA Standard 481. This packaging system is compatible with all tape-fed automatic pick and place systems. See Table 2 for details on reeling quantities for commercial chips.




Table 5 - Carrier Tape Configuration, Embossed Plastic & Punched Paper (mm)

	Tape	Tape Embossed Plastic		Punched Paper		
EIA Case Size	Size	7" Reel	13" Reel	7" Reel	13" Reel	
	(W)*	Pitch	(P ₁)*	Pitch	(P ₁)*	
01005 - 0402	8			2	2	
0603	8			2/4	2/4	
0805	8	4	4	4	4	
1206 - 1210	8	4	4	4	4	
1805 - 1808	12	4	4			
≥ 1812	12	8	8			
KPS 1210	12	8	8			
KPS 1812 and 2220	16	12	12			
Array 0612	8	4	4			

^{*}Refer to Figures 1 and 2 for W and P_1 carrier tape reference locations.

New 2 mm Pitch Reel Options*	•
------------------------------	---

	Packaging Ordering Code (C-Spec)	Packaging Type/Options
•	C-3190	Automotive grade 7" reel unmarked
	C-3191	Automotive grade 13" reel unmarked
	C-7081	Commercial grade 7" reel unmarked
	C-7082	Commercial grade 13" reel unmarked

^{* 2} mm pitch reel only available for 0603 EIA case size. 2 mm pitch reel for 0805 EIA case size under development.

Benefits of Changing from 4 mm to 2 mm Pitching Spacing

- Lower placement costs.
- Double the parts on each reel results in fewer reel changes and increased efficiency.
- Fewer reels result in lower packaging, shipping and storage costs, reducing waste.

^{*}Refer to Tables 6 and 7 for tolerance specifications.



Figure 1 – Embossed (Plastic) Carrier Tape Dimensions




Table 6 – Embossed (Plastic) Carrier Tape Dimensions

Metric will govern

	Constant Dimensions — Millimeters (Inches)										
Tape Size	D ₀	D ₁ Minimum Note 1	E ₁	P ₀	P ₂	R Reference Note 2	S ₁ Minimum Note 3	T Maximum	T ₁ Maximum		
8 mm		1.0 (0.039)				25.0 (0.984)					
12 mm	1.5 +0.10/-0.0 (0.059 +0.004/-0.0)	1.0	1.75 ±0.10 (0.069 ±0.004)	4.0 ±0.10 (0.157 ±0.004)	2.0 ±0.05 (0.079 ±0.002)	30	0.600 (0.024)	0.600 (0.024)	0.100 (0.004)		
16 mm		(0.059)				(1.181)					
	Variable Dimensions — Millimeters (Inches)										
Tape Size	Pitch	B ₁ Maximum Note 4	${\sf E_2^{}}$ Minimum	F	P ₁	T ₂ Maximum	W Maximum	A ₀ ,B ₀	& K ₀		
8 mm	Single (4 mm)	4.35 (0.171)	6.25 (0.246)	3.5 ±0.05 (0.138 ±0.002)	4.0 ±0.10 (0.157 ±0.004)	2.5 (0.098)	8.3 (0.327)				
12 mm	Single (4 mm) and double (8 mm)	8.2 (0.323)	10.25 (0.404)	5.5 ±0.05 (0.217 ±0.002)	8.0 ±0.10 (0.315 ±0.004)	4.6 (0.181)	12.3 (0.484)	Not	e 5		
16 mm	Triple (12 mm)	12.1 (0.476)	14.25 (0.561)	7.5 ±0.05 (0.138 ±0.002)	12.0 ±0.10 (0.157 ±0.004)	4.6 (0.181)	16.3 (0.642)				

- 1. The embossment hole location shall be measured from the sprocket hole controlling the location of the embossment. Dimensions of the embossment location and the hole location shall be applied independently of each other.
- 2. The tape with or without components shall pass around R without damage (see Figure 6.)
- 3. If $S_1 < 1.0$ mm, there may not be enough area for a cover tape to be properly applied (see EIA Standard 481, paragraph 4.3, section b.)
- 4. B, dimension is a reference dimension for tape feeder clearance only.
- 5. The cavity defined by A_{α} , B_{α} and K_{α} shall surround the component with sufficient clearance that:
 - (a) the component does not protrude above the top surface of the carrier tape.
 - (b) the component can be removed from the cavity in a vertical direction without mechanical restriction, after the top cover tape has been removed.
 - (c) rotation of the component is limited to 20° maximum for 8 and 12 mm tapes and 10° maximum for 16 mm tapes (see Figure 3.)
 - (d) lateral movement of the component is restricted to 0.5 mm maximum for 8 and 12 mm wide tape and to 1.0 mm maximum for 16 mm tape (see Figure 4.)
 - (e) for KPS product, A_0 and B_0 are measured on a plane 0.3 mm above the bottom of the pocket.
 - (f) see addendum in EIA Standard 481 for standards relating to more precise taping requirements.



Figure 2 - Punched (Paper) Carrier Tape Dimensions




Table 7 - Punched (Paper) Carrier Tape Dimensions

Metric will govern

	Constant Dimensions — Millimeters (Inches)											
Tape Size	D ₀	E ₁	P ₀	P ₂	T ₁ Maximum	G Minimum	R Reference Note 2					
8 mm	1.5 +0.10 -0.0 (0.059 +0.004 -0.0)	1.75 ±0.10 (0.069 ±0.004)	4.0 ±0.10 (0.157 ±0.004)	2.0 ±0.05 (0.079 ±0.002)	0.10 (0.004) maximum	0.75 (0.030)	25 (0.984)					
	Variable Dimensions — Millimeters (Inches)											
Tape Size	Pitch	E2 Minimum	F	P ₁	T Maximum	W Maximum	A_0B_0					
8 mm	Half (2 mm)	6.25	3.5 ±0.05	2.0 ±0.05 (0.079 ±0.002)	1.1	8.3 (0.327)	Note 1					
8 mm	Single (4 mm)	(0.246)	(0.138 ±0.002)	4.0 ±0.10 (0.157 ±0.004)	(0.098)	8.3 (0.327)	NOTE I					

- 1. The cavity defined by A_{n} , B_{n} and T shall surround the component with sufficient clearance that:
 - a) the component does not protrude beyond either surface of the carrier tape.
 - b) the component can be removed from the cavity in a vertical direction without mechanical restriction, after the top cover tape has been removed.
 - c) rotation of the component is limited to 20° maximum (see Figure 3.)
 - d) lateral movement of the component is restricted to 0.5 mm maximum (see Figure 4.)
 - e) see addendum in EIA Standard 481 for standards relating to more precise taping requirements.
- 2. The tape with or without components shall pass around R without damage (see Figure 6.)



Packaging Information Performance Notes


- 1. Cover Tape Break Force: 1.0 kg minimum.
- 2. Cover Tape Peel Strength: The total peel strength of the cover tape from the carrier tape shall be:

Tape Width	Peel Strength
8 mm	0.1 to 1.0 newton (10 to 100 gf)
12 and 16 mm	0.1 to 1.3 newton (10 to 130 gf)

The direction of the pull shall be opposite the direction of the carrier tape travel. The pull angle of the carrier tape shall be 165° to 180° from the plane of the carrier tape. During peeling, the carrier and/or cover tape shall be pulled at a velocity of 300 ±10 mm/minute.

3. Labeling: Bar code labeling (standard or custom) shall be on the side of the reel opposite the sprocket holes. *Refer to EIA Standards 556 and 624*.

Figure 3 – Maximum Component Rotation






Figure 4 - Maximum Lateral Movement




Figure 5 - Bending Radius







Figure 6 - Reel Dimensions



Note: Drive spokes optional; if used, dimensions B and D shall apply.

Table 8 - Reel Dimensions

Metric will govern

	Constant Dimensions — Millimeters (Inches)											
Tape Size	A	B Minimum	С	D Minimum								
8 mm	178 ±0.20											
12 mm	(7.008 ±0.008) or	1.5 (0.059)	13.0 +0.5/-0.2 (0.521 +0.02/-0.008)	20.2 (0.795)								
16 mm	330 ±0.20 (13.000 ±0.008)	(***)	(
	Variable Dimensions — Millimeters (Inches)											
Tape Size	N Minimum	W_1	W ₂ Maximum	W ₃								
8 mm		8.4 +1.5/-0.0 (0.331 +0.059/-0.0)	14.4 (0.567)									
12 mm	50 (1.969)	12.4 +2.0/-0.0 (0.488 +0.078/-0.0)	18.4 (0.724)	Shall accommodate tape width without interference								
16 mm		16.4 +2.0/-0.0 (0.646 +0.078/-0.0)	22.4 (0.882)									



Figure 7 - Tape Leader & Trailer Dimensions





Figure 8 - Maximum Camber





KEMET Electronics Corporation Sales Offices

For a complete list of our global sales offices, please visit www.kemet.com/sales.

Disclaimer

All product specifications, statements, information and data (collectively, the "Information") in this datasheet are subject to change. The customer is responsible for checking and verifying the extent to which the Information contained in this publication is applicable to an order at the time the order is placed. All Information given herein is believed to be accurate and reliable, but it is presented without guarantee, warranty, or responsibility of any kind, expressed or implied.

Statements of suitability for certain applications are based on KEMET Electronics Corporation's ("KEMET") knowledge of typical operating conditions for such applications, but are not intended to constitute – and KEMET specifically disclaims – any warranty concerning suitability for a specific customer application or use. The Information is intended for use only by customers who have the requisite experience and capability to determine the correct products for their application. Any technical advice inferred from this Information or otherwise provided by KEMET with reference to the use of KEMET's products is given gratis, and KEMET assumes no obligation or liability for the advice given or results obtained.

Although KEMET designs and manufactures its products to the most stringent quality and safety standards, given the current state of the art, isolated component failures may still occur. Accordingly, customer applications which require a high degree of reliability or safety should employ suitable designs or other safeguards (such as installation of protective circuitry or redundancies) in order to ensure that the failure of an electrical component does not result in a risk of personal injury or property damage.

Although all product-related warnings, cautions and notes must be observed, the customer should not assume that all safety measures are indicted or that other measures may not be required.

Mouser Electronics

Authorized Distributor

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

KEMET:

```
C1206X104K5RAC C1206X474K1RACTU C1206X106K8RACTU C1210X106K3RACTU C1206X104K5RACTU
C0805X103K2RACTU C1206X104K2RACTU C1206X473J5RACTU C0603X152K1RACTU C0603X152K5RACTU
C0603X153K5RACTU C0603X221K1RACTU C0603X221K5RACTU C0603X222K1RACTU C0603X331K1RACTU
C0603X331K5RACTU C0603X332K5RACTU C0603X333K5RACTU C0603X471K1RACTU C0603X472K1RACTU
C0603X681K5RACTU C0805X104K5RACTU C0805X153K1RACTU C0805X223K2RACTU C0805X333K5RACTU
C0805X472K2RACTU C0805X473K1RACTU C1206X473K2RACTU C1210X224K1RACTU C1206X225K5RACTU
C0805X334K5RACTU C1210X226K8RACTU C1808X103K2RACTU C1808X104K5RACTU C1808X273K1RACTU
C1812X103K5RACTU C1812X105M5RACTU C1812X223K1RACTU C1812X224K2RACTU C1812X474K2RACTU
C1825X105K2RACTU C1825X684K2RACTU C2220X105K2RACTU C2220X156K5RACTU C2225X105K2RACTU
C2225X125K2RACTU C0805X103K1RAC3124 C0603X273K5RACTU C1210X474K1RACTU C1206X475M3RACTU
 C1206X475K3RACTU C1210X335K5RACTU C0603X222K2RACTU C0603X472K2RACTU C0805X474M9RALTU
C0805X561J1RAL7210 C0805X561J1RALTU C0805X561J2RAL7210 C0805X561J2RALTU C0805X561J3RAL7210
 C0805X561J3RALTU C0805X561J4RAL7210 C0805X561J4RALTU C0805X561J5RAL7210 C0805X561J5RALTU
C0805X561J8RAL7210 C0805X561J8RALTU C0805X561J9RAL7210 C0805X561J9RALTU C0805X561K1RAL7210
 C0805X561K1RALTU C0805X561K2RAL7210 C0805X561K2RALTU C0805X561K3RAL7210
C0805X561K3RALTU C0805X561K4RAL7210 C0805X561K4RALTU C0805X561K5RAL7210 C0805X561K5RALTU
 C0805X561K8RAL7210 C0805X561K8RALTU C0805X561K9RAL7210 C0805X561K9RALTU
C0805X561M1RAL7210 C0805X561M1RALTU C0805X561M2RAL7210 C0805X561M2RALTU
C0805X561M3RAL7210 C0805X561M3RALTU C0805X561M4RAL7210 C0805X561M4RALTU
C0805X561M5RAL7210 C0805X561M5RALTU C0805X561M8RAL7210 C0805X561M8RALTU
C0805X561M9RAL7210 C0805X561M9RALTU C0805X562J1RAL7210 C0805X562J1RALTU
C0805X562J2RAL7210
```