

Name of Company

: AKIJ ISPAT LIMITED : BAUSIA, GAZARIA, MUNSHIGONJ

Address To : MATERIALS LABORATRORY

Sample ID AKIJ ISPAT B5000DWR 12MM

ID /	Nominal diameter(d)		Actual Unit Weight	Gauge Length	Gauge length after fracture(Lu)		EMF	Yield load
	mm	mm	kg/m	mm	mm	%	%	kN
NO.1	12.00	12.02	0.89	200.000	228.00	14.00	6.05	59.34

Name	Yield strength(Re)	Maximum force(Fm)	Tensile strength(Rm)	Rupture load	TS/YS Ratio
ID \	MPa	kN	MPa	kN	
NO.1	523.22	76.3	673	56.34	1.2855

