MAGNUM STEEL INDUSTRIES LTD



Measure Date Time		Method Name		Type Corr Sample Name						
11/16/2023 10:22:1	AM Fe-10-F Magnui									
Sample Name		Heat No	Operator Name	Grade TMT						
AKIJ ISPAT LIMITED	Bat	h AK-117.B C-3								
Meas.	С	Si	Mn	Р	S	Cr	Мо	Ni	Al	Со
	%	%	%	%	%	%	%	%	%	%
<x></x>	0.251	0.0521	0.229	0.0312	0.0239	0.146	0.0173	0.0595	0.233	0.0055
Meas.	Cu	Nb	Ti	V	W	Pb	Sn	As	Zr	Bi
	%	%	%	%	%	%	%	%	%	%
<x></x>	0.116	<0.00100	<0.00020	0.0040	<0.0050	<0.00100	0.0166	0.0131	<0.00100	<0.00100
Meas.	Ca	Ce	Sb	Se	Те	Та	В	Zn	La	Fe
	%	%	%	%	%	%	%	%	%	%
<x></x>	0.00013	<0.00100	0.0092	0.0022	0.0156	0.0171	0.00100	>0.0270	<0.00030	98.7
Meas.	Ceq									
	%									
<x></x>	0.334									