

Specification data sheet

Page: 1/2

BASF Specification data sheet

Date / Revised: 2025/11/25

Product: **Laropal® 855 S**

Version: 1.0

(30861609/SPE_GEN_P/EN)

Date of print 26.11.2025

1. Substance/preparation and company identification

Laropal® 855 S

BASF SE

Global Business Unit Resins and Additives

67056 Ludwigshafen, Germany

E-mail address: ede-qm@basf.com

2. Characterization

polycondensate, resin

dissolved in: Solvent naphtha (petroleum), light arom.

3. Specified tests

Property	Test method (parameter)	Value
Viscosity, dynamic	DIN EN ISO 3219 (23 °C, 25 1/s)	100 - 500 mPa.s
Color number	DIN EN ISO 6271	<= 100
Non-volatile content	DIN EN ISO 3251 (30 min, 140 °C)	53.5 - 56.5 %(m)

4. Handling and Storage

Advice on safe handling:

See SDS section 7 - Handling and storage.

Vertical lines in the left hand margin indicate an amendment from the previous version.

BASF Specification data sheet

Date / Revised: 2025/11/25

Product: **Laropal® 855 S**

Version: 1.0

(30861609/SPE_GEN_P/EN)

Date of print 26.11.2025

The Specified Parameters listed in section 3 represent the contractual quality at the time of the transfer of risk. The data are controlled at regular intervals as part of our quality assurance program. BASF MAKES NO WARRANTY OF ANY KIND, EITHER EXPRESS OR IMPLIED, BY FACT OR LAW, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.

This product specification was issued automatically and is not signed.