

Starvis® S 5514 F

High performance water swellable polymer for construction materials

Characteristics / Chemistry

Starvis® S 5514 F is a powder based on a high-molecular weight synthetic copolymer.

Starvis® S 5514 F is a water swellable polymer acting as a water reservoir at constant water content. It influences the water balance and therefore related green and solid properties of dry mortars.

The use of **Starvis® S 5514 F** offers advantages related to

- ➔ improved workability profile / reduced stickyness
- ➔ prolonged open time
- ➔ increased sag resistance
- ➔ optimized pore design / reduced shrinkage
- ➔ reduced water absorption / increased frost resistance
- ➔ increased efficiency
- ➔ optimization of basic additives

Field of Application

Starvis® S 5514 F is especially suitable for modification and improvement of rheological properties of sophisticated dry mortar applications.

Starvis® S 5514 F is particularly recommended if water management or pore design are of significant interest, e. g. during hot climate conditions or to improve specific hardened mortar properties in, e.g.:

- ➔ EIFS mortars (Exterior Insulation Finishing Systems)
- ➔ plasters and renders
- ➔ cementitious tile adhesives and joint fillers
- ➔ repair mortars
- ➔ masonry mortars

Technical Data

Physical shape	powder
Appearance	characteristic, white to slightly yellowish
Drying loss, [%]	max. 10
Bulk density, [kg/m³]	500 to 700
Dosage recommendation, [%] in relation to weight of dry material mix depending on recipe and application	0.30 to 0.50

Further Technical Data

Packaging	25 kg paper bag 625 kg big bag
Storage	to be stored in its unopened original packaging, store dry below 40 °C and protect from excessive heat
Shelf life	1 year

Safety notes:

Comprehensive instructions are given in the corresponding Material Safety Data Sheets which are available on request.

This information and all further technical advice are based on our current knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether expressed or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of goods. Performance and suitability of the product described herein have to be verified by testing, which has to be carried out only by qualified experts in the sole responsibility of the customer. Reference to trade names used by other companies is neither a recommendation nor an implementation that similar products could not be used. Customer is obliged to keep the disclosed samples and any related information under strict confidence and shall neither analyze such samples nor disclose them to third parties. In addition our general terms and conditions for sale are valid.

Issue: October 2019

This technical note is valid until replaced by a new issue.